



Brazilian Agro-industrial Wastes as Potential Textile and Other Raw Materials: a Sustainable Approach

Mylena Uhlig Siqueira¹ · Barbara Contin¹ · Palloma Renny Beserra Fernandes¹ · Raysa Ruschel-Soares¹ · Philipe Uhlig Siqueira² · Julia Baruque-Ramos¹

Received: 18 June 2021 / Revised: 8 December 2021 / Accepted: 13 December 2021
© The Author(s), under exclusive licence to Springer Nature Singapore Pte Ltd. 2022

Abstract

The Brazilian agro-industrial chain generates about 291 million/tons/year of wastes, which, if inadequately destined, could originate social and environmental risks. There is a growing need for the use of alternative raw materials to replace that originated from fossil resources in the Brazilian industry. Renewable materials play an important role on the sustainability of ecosystems and materials' circularity. The issue has acquired importance in light of recent bio-based agro-fiber development potential applications. Considering sustainability guidelines, this study aimed to analyze the main Brazilian agro-industrial waste crops (temporary and permanent) as important sources of natural fibers and other raw materials. A systematic review of the literature (SRL) about Brazilian researches, based on concepts of industrial ecology, and the creation of a bibliometric analysis network were carried out. The agricultural biomass related to the main crops presents characteristics making them suitable to be applied for textiles, as natural fibers and polymers, in biosorbents for industrial effluents, and cellulose obtention and reinforcement material in composites. Thus, scientific investment in researches on materials and technology development are necessary to provide applications that could meet current and future demands and expand the scope of new materials for sustainability.

Keywords Brazilian · Agro-industrial wastes · Textile industry · Natural fibers · Sustainability

Introduction

In Brazil, agribusiness plays an important role in the production, processing, and transformation of food. According to the Brazilian Institute of Geography and Statistics (IBGE 2021), the crop of agricultural production forecasts a record 2.5% in 2021, and to meet food needs in 2050, it requires a 60% increase in the planted area, and in the consumption of water in the region amid water crises (Biase 2017). The abundance is the result of increased activity in the modern

agricultural sector, which produces 291.1 million/ton. of residues in its largest crops (Schneider et al. 2012). However, this system presents unexplored economic opportunities, pressuring conservation of resources, polluting and degrading natural ecosystems, causing environmental risks and contamination to society (Biase 2017; Ellen MacArthur Foundation 2017).

The need for renewable manufactured products is a major challenge for the Brazilian industry dependent on petrochemical resources. For Dungani et al. (2015), agricultural waste is the most abundant form of natural fiber. The use, processing, and characterization of agro-industrial wastes are a great opportunity to generate value and develop by-products and co-products (Berté 2009; Dahiya et al. 2020; Embrapa 2018; Shahid-ul-Islam et al. 2013).

Renewable resources are aimed at the sustainability of ecosystems and for maintaining healthy and sustaining the textile industry. There is great interest in sustainability by industry professionals, including in materials with competitive mechanical properties, lightness, and biodegradability of low-cost natural fibers to replace petroleum-based fibers

This article is part of the Topical Collection on *Natural Fibers: Materials of the Future*

✉ Mylena Uhlig Siqueira
mylena.uhlig@gmail.com

¹ School of Arts, Sciences and Humanities, University of Sao Paulo, Av. Arlindo Bettio, 1000, Sao Paulo, SP 03828-000, Brazil

² Department of Environmental Engineering, Federal University of Espirito Santo, Av. Fernando Ferrari, 514, Vitoria, ES 29075-910, Brazil

in composites (Alarcon et al. 2021; Atiqah et al. 2020; Hoque et al. 2021; Izwan et al. 2021). Indeed, markets for products based on the agro-fiber present great potential for application in absorbents, technical textiles, geotextiles, filters, biocomposites, and other automotive and construction sectors (Shishoo 2007). Research efforts have been alternatives to different levels of control and management (Chan et al. 2021; Onu & Mbohwa 2021d).

The high volumetric rate of agro-industrial residue in combination with increased environmental awareness makes research into appropriate textile technologies and treatments a priority (Madhav et al. 2018). In this way, this study aimed to analyze the main Brazilian agro-industrial waste crops (temporary and permanent) as important sources of natural fibers and other raw materials.

Research Methods

The methodology was based on a bibliographic survey and analysis by systematic literature review (RSL) followed by bibliometrics. The focus, based on industrial ecology concepts (Giannetti and Almeida 2006; Lifset and Graedel 2015), examined researches on the use of agro-wastes for the development of sustainable textile materials. The results were compared with data from the Brazilian Ministries of Agriculture and Environment and related associations. To index a descriptive exploratory bibliometric analysis of the data with greater precision to the object of study, it was built a network from the grouping of bibliographic sources in the Scopus platform (from December 2020 to January 2021 that encompass the years from 2021 to 2006) and transcribed by Software VOSviewer (*Universiteit Leiden*). To generate the database, the searches performed used the variation of the terms “agro-industrial,” “agro,” “waste,” “fiber,” “textile,” “fashion,” and “bio-based” limited to Brazil. When diagramming the network, 3,296 significant expressions were identified, out of the 305 articles selected, of which 2,496 meet the correlation requirement. The same database was used to develop a diagram focusing on the highest incidence of materials citation by classification and types, crops, formats, conversion technology, and end-of-use researches. Crops were divided following the Food and Agriculture Organization of the United Nations (FAO) food classification (FAO 2021b).

The next items discussed respectively the following: (i) structural analysis of the textile industry from the perspective of the progress of synthetic materials, consumption patterns, and interaction of the value chain with the agricultural industrial segment; (ii) the dynamics of sustainability as a guideline and fundamentals for restructuring cycles of agricultural residues; (iii) the Brazilian scenario of productive insertion (marked by the data analysis network); (iv)

materials and related applications in Brazilian development researches.

Results and Discussion

Textile and Agricultural Sector Challenges

The textile and agricultural industries share challenges within the current Brazilian economic system, concerning global demand consumption, land use, greenhouse gas emissions, pollution, effluent generation, generation and disposal of waste, and recycling (Circular Systems 2020).

According to the Brazilian Association of Artificial and Synthetic Fiber Producers (ABRAFAS), the Brazilian petrochemical-textile complex operates on a large scale and is responsible for productivity above 380 thousand tons/year, between synthetic and artificial fibers and multifilaments (ABRAFAS 2020). Brazil is currently the 5th largest textile industry in the world and the 4th in the clothing segment. In 2019, textile production reached an average of 2.04 million tons, which represents a turnover of near US\$ 36.5 billion from the entire chain, investments of about US\$ 730 million, creating about 1.5 million direct jobs and 8 million indirect jobs, of which 75% are female labor, the 2nd largest employer in the manufacturing industry, the most complete in the West, from fiber production to retail (ABIT 2020; Cavalcanti and Dos Santos 2021; Filletti and Boldrin 2020), with estimated expansion of 11.5% from 2017 to 2022 in apparel retail (Mariano 2018) growth of 10.4% in apparel production in volume, reaching 5.5 billion pieces (IEMI 2021).

The rise in consumption and use of synthetic fibers represents a major change in the country’s textile chain, which until then remained largely with the production of cotton and natural fibers (Zeferino 2019), in contrast to the exponential growth of 42.7% synthetic textile fibers over the period 2010–2017, while natural fibers did not show significant growth worldwide (Cavalcanti and Dos Santos 2021) (Fig. 1).

In reason to the expansion of activities in the clothing textile industry to meet the growing demand in the clothing supply chain, there is a significant and abusive increase in the use of inputs such as energy, water, and soil (Barbosa et al. 2016).

In the textile sector, with the growing and large consumption demand of natural textile fibers, the production and market of synthetic fibers found a great space for expansion due to their characteristics of low cost, strength, shine, and, mainly, the absence of large agricultural spaces, a special type of climate and intensive work (Lobo et al. 2014).

Onu and Mbohwa (2021a) support the argument that the continuous application of petroleum derivatives involves




Fig. 1 Consumption of natural, artificial, and synthetic fibers and filaments in Brazil, 2013–2018. Source: adapted from ABIT (2018)

high cost, intensive use of energy, and insecurity, while the diversity of agricultural residues is the basis for replacing the use of non-biodegradable synthetic materials.

Agriculture and food processing plants represent point and diffuse sources of agricultural waste that are difficult to control (Hanson 2014). The deficiencies of the agricultural system attract the interest of effective management, which consider the inadequate disposal of material in landfills and the distribution of space, facing the challenges of greenhouse gases and the toxic runoff of water in useful fertile land (Gomiero 2018; Onu & Mbohwa 2021a; Warner 1980; Yusuf et al. 2019). In addition to discarded nutritional and economic values, environmental, social, and cultural values are wasted. Soil, water, energy, land, logistics, and labor are heavily used up in the service of wasted food production (Biase 2017; Saath and Fachinello 2018; dos Santos et al. 2020). The deterioration of these systems imposes a time limit, and their regenerative properties are slow and cannot be boosted healthily. For Kapoor et al. (2016), since the generation of waste and by-products are consequences of all industrial sectors, just like their inadequate disposal, the study of recovery and reuse of these by-products must be disseminated.

The current degradation reveals an inadequate technology, as industrial progress must be more concerned with increasing its efficiency more than production, and the consumption scale assumes limitations to the carrying capacity (Goodland 1995). In the case of agro-industrial residues, due to their abundance, renewability, and use, they are economically and environmentally advantageous for their low density, low CO₂ emission, and biodegradability characteristics, when compared to thermoplastic polymer composites. The technology applied for conversion of agricultural biomass in products is not being realized in scale-up due to competitiveness with synthetic products (Dungani et al. 2015; Prithivirajan et al. 2015; Zeferino 2019).




Fig. 2 Planted area or destined for harvesting (green line) and harvested area (blue line) from temporary and permanent crops. Source: adapted from IBGE—Municipal Agricultural Production (PAM 2021)

Goodland (1995) emphasizes that human's dependence on agriculture will always exist, so land and other renewable sources are essential. This reflects the concerns of the Malthusian theory, addressed by Lambin (2012), that the finite stock of land and its inadequate distribution are insufficient to meet growing demand, causing a decline in welfare. Based on the work of Malthus, Moran (2011) argues that, since demographic pressure has brought about a rapid agricultural technological innovation, resulting in extensive and harmful agriculture, one should expect from its expansion to increase the level of deforestation as well. In global studies, about 12% of the global surface is used for cultivation; it is estimated that 15% of the global surface of land without ice could be converted to agricultural land, and more than 40% of the available lands were used (Foley 2005; Rockström et al. 2009).

The 2017 Agricultural Census recorded an area of 351.3 million hectares (41.3% of the national territory). The area occupied with crops, 63.5 million hectares, represents 7.5% of the territory with annual, semi-perennial, and perennial agriculture (grains, horticulture, fruit, and forestry) (Embrapa 2018; Ministério da Agricultura 2019a, 2019b). Patterson (2012) highlights that population growth of advanced per capita consumption, rising temperatures, world food, clean water, and fuel supplies are at constant risk, putting pressure on declining amounts of farmland and mineral and mineral reserves and fresh water (Patterson 2012). Salleh et al. (2021) raises the issue that natural fiber production is expected to decline due to the need for more land for food production. Fibrous material is cultivated in agriculture (animals and plants) (Tobler-Rohr 2011).

The search for more land is a threat to afforestation and increases the impacts of the climate crisis (Campbell et al. 2018; Onu and Mbohwa 2021c). Brazil faces a growth curve in planted area and harvested area in all temporary and permanent crops grown in the country (Fig. 2):

Waste from these activities is an example of an expensive and inevitable result of human activity that poses a threat to the environment, while the decrease in the supply of raw materials is also a cause for concern (Dungani et al. 2015; Sundarraj and Ranganathan 2018). The threat linked to agricultural exploration activities and the production of materials attracts the attention of both industries, in an attempt to balance habitats, protect the ecosystem, and dispose of useful land in reversing the loss of biodiversity (Macaulay 2007; Onu and Mbohwa 2021c, e).

Specific analyses reveal that the increase in temperature in Brazil can cause the reduction of suitable regions for cultivation (Bolfe et al. 2018). The protection until then economic extend to biological safety and plant biodiversity (Teixeira et al. 2015). The future of agriculture, therefore, must encompass sustainable agricultural systems, understood as the management and conservation of the natural resource base and the orientation of technological changes to ensure the achievement and satisfaction of the human needs of the present and future generations (do Bezerra and da Veiga 2000; Bolfe et al. 2018; FAO 2021c; Pinazza and Araujo 1993; Soglio and Kubo 2016; Vieira and Vieira 2019).

Recent reports by Laudes Foundations reveal that turning innovations to the responsible use of agro-waste to generate raw materials based on cellulose textiles would not require increasing cultivated land or increasing the volume of crops. Studies show that there is sufficient residue for fiber relocation and emphasize the importance of collaborative interventions in textile and agri-food systems to enable scaling of materials (Laudes Foundation 2021).

The Agro-industrial Wastes Issue

The issue of food loss and waste (FLW) is highlighted in regional, national, and international political agendas, still on the rise in Brazil (FAO 2021a; Henz and Porpino 2017; Teuber and Jensen 2020). The Committee on World Food Security (CFS) highlights the importance of FLW in the search for more sustainable and equitable food systems and societies (FAO 2015).

The dumping of agricultural waste is one of the great eminent challenges that are highly expensive, harmful to soil contamination, greenhouse gas emissions (GHG), toxic to local waters, damage to land, and compromise environmental safety and quality of life and regional food (Onu and Mbohwa 2021c; Wilts et al. 2020). According to the 2021 Food Waste Index, 931 million tons of food was wasted, and 20% of the volume belongs to Latin America, where 55% are fruits and vegetables; however, there is no consistent information on each developing country (FAO 2016; United Nations Environment Programme 2021).

The definitions of food loss and waste take different approaches. The loss of food considers the decrease in the

quality or quantity of food resulting from suppliers along the harvest/slaughter/capture supply chain that is not used as feed or seed, whereas food waste is related to a decrease in the quantity or quality of food from service providers and consumers (FAO 2018; SOFA/FAO 2019, 2020).

Waste is liquid or solid materials that are generated from agricultural activities, direct consumption, or industrialization, and are not useful to the process, which assumes concepts such as reduction, reuse, and recycling (Loehr 1974; Nguyen and Schnitzer 2008; Onu and Mbohwa 2021d). Some of the influencing factors are topography, precipitation, cover crop, season, and location, and even the chemicals, cultivation practices, and fertilizers used, which make impact assessments and measurements difficult (Hanson 2014).

In large volumes, the residues are in the form of straw, stems, bark, wood, and forest residues, and commonly occupy land in the form of disposal by burning, which allows the start of fires and the proliferation of diseases. Residues and by-products are rich in lignocellulosic materials that can be recovered through chemical, physical, and biotechnological treatments (Bigdeloo et al. 2021; Dietrich et al. 2016; Scarlat et al. 2010).

Five segments classify the types of FLW, namely the following: (i) agricultural production (mechanical damage and harvesting operations); (ii) post-harvest handling and storage (spill and degradation); (iii) processing (industrial and domestic); (iv) distribution (market and retail systems); and (v) consumption (household) (FAO 2011). Considerations involve FL as unintentional reduction of food available for human consumption as a result of inefficiency in the production and supply chain, and FW to the intentional disposal of food items, particularly by retailers and consumers (CEDES 2018). Groups can also be divided into food losses (during processing); unavoidable (perish during the consumption stage, e.g., husks and pits); and avoidable (suitable for food, but wasted in the period of human consumption) (Ahmad et al. 2021) (Table 1).

About 45% of fruit and vegetable biomass is wasted during agriculture, post-harvest, processing, distribution, and consumption. Residues such as fruits and vegetables can be considered valuable raw materials, as they are produced in large quantities all over the world (Dietrich et al. 2016).

Losses and waste are classified into four categories along the supply chain: (i) primary and post-harvest production; (ii) processing and manufacturing; (iii) wholesale, food retail, service, and distribution; and (iv) consumption or household waste (WRAP 2009). For Six et al. (2016), biomass recovery can be divided into groups of direct use (unchanged), material recovery (biochemical extraction, conversion of biomass and useful products), and energy recovery (biogas/energy content). Developing countries,

Table 1 Definitions for food losses/waste in supply chain

Food loss	Waste of food		
	Production	Processing	Consumption
Loss occurs during and shortly after the harvest	Postharvest and storage Loss occurs during handling, drying, local/regional transport, and storage	Processing The loss occurs during processing and local or industrial treatment and packaging	Distribution, Retail The waste occurs during the market and retail systems Consumption The waste occurs at household and consumption levels

Source: adapted from Ruviano et al. (2020)

such as Brazil, face a higher rate of waste in the primary stages (FAO 2020; Henz and Porpino 2017; Júnior 2020).

There is insufficient world data on the edible fraction of food waste (UNEP 2021), although fruit processing residues, as parts of the entire food waste processing sector, such as bagasse (peel, seed, and pulp), bark, seeds, and stems can be considered unavoidable residues (Kavitha et al. 2020; Kosseva 2020b, 2020a). Currently, the methods used in FW organizations are animal feed, mainly composed of organic fertilizer, anaerobic use, carbonization, and landfill; no method has been supported for the ecologically correct use of FW. Therefore, FW can be used in the production of biocomposites using sustainable FW management methods (Blakeney 2019). For Dai et al. (2018), lignocellulosic biomass resources do not affect the food supply chain.

Brazil follows a waste management structure similar to developed countries (Nascimento et al. 2015). The Brazilian Solid Waste Plan (PNRS), law n. 2305/2010, valid since 2010, prioritizes non-generation, reduction, reuse, recycling, waste treatment, and, finally, the final disposal of waste. In theory, all the possibilities of recovering available and economically viable technologies were considered (BRASIL 2010; Henz and Porpino 2017; Nascimento et al. 2015).

Efforts are aimed at reducing the amount of waste according to the stipulated hierarchy, a large amount of unavoidable waste remains being generated. Therefore, agricultural innovation should apply sustainability at different levels and structures. Sustainable agriculture can facilitate technological integration and facilitate the production and processing of food as fiber and green resources, as greater knowledge of processes becomes presuppositions for significant advances (Onu and Mbohwa 2021e, 2021a; Shahid-ul-Islam et al. 2013).

Taking into account the growing scarcity of ecosystem services, the question would be how to reallocate the structure between the raw materials needed for production and survival. Otherwise, allocation strategies must be judged for their sustainability, fairness, and efficiency (Farley 2010).

Agro-industrial Waste and Industrial Ecology for Materials Circularity

Sustainability has multifaceted concepts (Salleh et al. 2021). The Science of Sustainability affirms the need to be able to integrate such a range of temporal scales (Becker 2014). Sustainable development is defined as “meeting the needs of the present without compromising the ability of future generations to meet their own needs” (Keeble 1988). The Brundtland report also highlights an interest in three main pillars: (i) environmental preservation; (ii) social equity; and (iii) economic growth (Akiyode et al. 2017). In 2015, the Sustainable Development Goals (SDGs) were re-adopted to address climate change and environmental protection,

divided into 17 goals that address social and economic issues. These are directly linked to sustainable industry, infrastructure, clean energy, and responsible consumption and production, which relate to the efficient use of natural resources and reduction of waste (Ishak et al. 2021). The promoted actions by World Summit on Sustainable Development in 2000 reveal that resource management and distribution are approaches to controlling global depletion in ecosystem conservation (Onu and Mbohwa 2021b). Regarding the 2030 Agenda with a focus on food and agriculture transformation, the 2nd key principle for sustainability is “protecting and enhancing natural resources,” which includes “improving soil health and restoring the land; protect water and manage scarcity; conserve biodiversity and protect ecosystem functions; reduce losses and encourage reuse and recycling and promote sustainable consumption” (FAO 2018, p.18). Onu and Mbohwa (2021d) highlight that all Sustainable Development Goals (SDG) centers contribute resources to these biodiversification opportunities.

The life cycle of textile products is one of the shortest due to the logic of the fashion industry (Lopes et al. 2021). The linear model of the textile industry causes restrictions in the supply of products and high costs and environmental risks (Gardetti 2018; Senthil Kumar and Femina Carolin 2018). Industrial systems follow the context of open flow, that is, the use of materials and energy that generate non-usable waste. The current situation does not yet cover the closing of the cycle efficiently (Coste-Maniere et al. 2018). Biofibers are among the most researched and demanded materials in the twenty-first century (Nishino 2017). Studies reveal that mentions of sustainability have increased. For two-thirds of respondents, sustainability has become a priority in combating climate change after COVID-19 (Arici and Lehmann 2020; Lehmann et al. 2019; Wong et al. 2021). For Textile Exchange Institution (2019), the textile industry acts primarily in 14 of the 17 UN SDGs (Textile Exchange 2019).

Industrial ecology definitions comprise similar attributes and different emphases (Clift and Druckman 2015). Among these, El-haggar (2007a, b, c, d) highlights, in short, a systemic and balanced view of the interactions between industrial and ecological systems, based on the study of flows and transformations of materials and energies, as an ideal model for the management of natural resources and waste industrial. Cooperation between industrial processes and environmental sustainability (El-Haggar 2007c, d). Authors talk about industrial ecology integrating the circular economy in search of eco-efficiency.

Ayres (2002) exemplifies the field of Industrial Ecology as an enhancer, which can highlight the importance of efficient biogeochemical cycles through concepts, metaphors, applications, and analyses, comprising technological knowledge and environmentally informed processes for this purpose. The author identifies that the study of material flows as

raw materials has a great contribution to the development of types of efficiency and cycling of materials already produced by natural ecosystems (Ayres 2002). Ayres (2002) exemplifies the field of Industrial Ecology as an enhancer, which can highlight the importance of efficient biogeochemical cycles through concepts, metaphors, applications, and analyses, including technological knowledge and environmentally informed processes for this purpose. The author confirmed that the study of material flows as raw materials has a great contribution to the development of types of efficiency and cycling of materials already produced by natural ecosystems (Giannetti and Almeida 2006).

Thus, adding value to agro-waste by converting it into useful products is currently one of the main areas of basic laboratory research, and will soon reach an economic potential that can collaborate with green technologies (Kapoor et al. 2016).

Efforts are aimed at reducing the amount of waste according to the stipulated hierarchy, a large amount of unavoidable waste remains being generated. Therefore, agricultural innovation should apply sustainability at different levels and structures. Sustainable agriculture can facilitate technological integration and facilitate the production and processing of food as fiber and green resources, as greater knowledge of processes becomes presuppositions for significant advances (Barker and McLemore 2005; Onu and Mbohwa 2021e, 2021a; Shahid-ul-Islam et al. 2013).

Taking into account the growing scarcity of ecosystem services, the question would be how to reallocate the structure between the raw materials needed for production and survival. Otherwise, allocation strategies must be judged for their sustainability, fairness, and efficiency (Farley 2010). Regarding the 2030 Agenda with a focus on food and agriculture transformation, the 2nd key principle for sustainability is “protecting and enhancing natural resources”, which includes “improving soil health and restoring the land; protect water and manage scarcity; conserve biodiversity and protect ecosystem functions; reduce losses and encourage reuse and recycling and promote sustainable consumption” (FAO 2018, p.18). Onu and Mbohwa (2021d) highlight that all Sustainable Development Goals (SDG) centers contribute resources to these biodiversification opportunities. Target 12.3 addresses the issue of food waste and loss, which contributes not only to SDG 12, but also SDGs SDG 2 (“Zero hunger and sustainable agriculture”), 6 (“Drinking water and sanitation”), 13 (“Action against global climate change”), 14 (“Life in the water”), and 15 (“Terrestrial life”) (Filho et al. 2021).

For Barket (2005), the difficulty in finding new sources of raw material while the safe disposal of waste is scarce, makes hierarchy and the total use of waste a necessity. Minimization is a priority in the hierarchy of waste management strategies, rather than treating the end of the tube; however,

there is no economic incentive and technology available, turning the importance of waste recovery as opportunities for sustainability (Herrero et al. 2020; Sillanpää and Ncibi 2019c).

The LCA methodology can define the main impact areas, assess potential environmental threats, make environmental decisions, and ensure the labeling and ecological certification of textiles (Eryuruk 2015). For Laudes Foundation (2021), conscious sourcing decisions contribute to help farmers, agricultural communities, and the textile industry to achieve greater sustainability, ensuring a possible balance of resources and people (Laudes Foundation 2021).

By-products from the food industry can be seen as waste or resources when recovery technologies are implemented (Herrero et al. 2020). However, the reprocessing of organic matter does not include the recovery of energy used in the recycling process (Wiesmeth 2021). For this, the concepts of circularity become restricted when focused only on waste management (Sillanpää and Ncibi 2019b, 2019a, c). Therefore, sustainable development represents a shared commitment to stable economic growth in the satisfactory and available management of resources. The allocation of these resources can be solidly directed to ensure new supplies (El-Haggar 2007a; Vivien 2011).

Brazilian Biomass Scenario

According to the Confederation of Agriculture and Livestock of Brazil (CNA), agribusiness is recognized as a great vector of expansion and Brazilian economic growth (CNA 2020). The agricultural productive harvest forecasts a record increase of 2.5% for Brazil in 2021 (IBGE 2021). Its abundance is the result of increased activity in the modern agricultural sector, which annually wastes 1.3 billion tons of food along the production chain (FAO 2013; Zaro 2018). Agroindustry accounts for approximately 5.9% of the Brazilian gross domestic product (GDP), promoting integration with the economy (EMBRAPA 2020; Torrezan et al. 2017).

The “Panorama of Solid Waste in Brazil 2020” by the Brazilian Association of Public Cleaning and Special Waste Companies (ABRELPE) highlights that organic matter comprises 45.3% of the total solid waste generated in 2020, approximately 170 kg discarded per person/year, and it is estimated that this waste will increase 50% by the year 2050 (ABRELPE 2020). In contrast, this report reveals that the total amount of waste generation and final destination remain inadequate, growing respectively 19% and 16%, even after the implementation of the Brazilian PNRS in 2010, which institutes the plan for integrated management, responsibility, and economic instrumentation applicable to solid waste (ABRELPE 2020; de Campos and Goulart 2017; Freiria 2011).

Table 2 Data about the main Brazilian temporary crops

Temporary crops	Waste, million/ton	Residual factor
Soybeans (grain)	41,862,129	73%
Corn (grain)	29,432,678	58% (straw and cob)
Sugar cane	201,418,487	30%
Beans (grain)	1,847,984	53%
Rice (paddy)	2,530,355	20%
Wheat (grain)	3,033,315	60%
Cassava	23,786,281	-

Sources: adapted from ABIB (2011), Matos (2005), Schneider et al. (2012), and Silva et al. (2007)

Table 3 Data about the main Brazilian permanent crops

Permanent crops	Waste, million/ton	Residual factor
Coffee (beans)	1.220.029	45-55% (husks and straw)
Cocoa (beans)	83.025	38%
Banana (bunches)	99.640	50% (husks and stalks)
Orange	8.825.276	50%
Coconut	405.009	60%
Cashew nuts	80.484	73%
Grapes	300.459	40%

Sources: adapted from ABIB (2011), Mello (2006), Rezzadori and Benedetti (2009), Silva et al. (2009), and Vale (2007)

Biomass was defined as “any material, excluding fossil fuel, which was a living organism that could be used as fuel directly or after a conversion process” (ASTM 1995). According to EMBRAPA, Brazil is responsible for 140 gigatons of agro-industrial residues, in which there are different types of biomasses of heterogeneous chemical composition from different physical states, such as oily biomass, saccharide biomass, and starchy and lignocellulosic biomass, which is more abundant (Júnior 2020). Worldwide, the main crops responsible for agricultural residues are rice, wheat, cotton, and corn (El-Haggar 2007b).

Therefore, the report by the Institute of Applied Economic Research (IPEA) of Organic Waste (2012) was based on 7 temporary crops (Table 2) and 7 permanent crops (Table 3), which are the greatest representation ones in Brazil. Among the permanent crops, the following were selected: coffee (beans), cocoa (almonds), bananas (bunch), oranges, coconuts, cashew nuts, and grapes. For the temporary crops, in turn, the following were selected: soy (in grain), corn (in grain), sugar cane, beans (in grain), rice (in husk), wheat (in grain), and cassava. It highlights that these 14 largest crops in the country produce a total of 291.1 million tons of waste per year (Schneider et al. 2012).

According Table 2, only soybean crops correspond to 49% of the planted area in Brazil, producing about 2,700

strength at 425 in the document, while the term “textile fibers” has 12 occurrences and 384 total links, and “textile,” has only 273 links to the name, and 8 co-occurrences, showing a small impact on the Brazilian textile industrial scenario in scaling materials.

The Brazilian Agroindustry Profile Report of the Institute for Applied Economic Research (IPEA) states that the inventories of existing products, material flows, and the functioning of circuits are still some of the challenges found in its main structure (IPEA 2013), although, according Organic Waste Report, wastes from the country’s main crops present distributive potential and Brazilian legal support for reverse logistics projects (Schneider et al. 2012).

The Application of Agro-industrial Wastes in Textile and Other By-products in Brazil

The water content, pathogenic potential, and biological instability make the disposal of waste difficult to control, directing it generally to animal feed (Dietrich et al. 2016). In the same way, the administration of large residues leads agrarian communities to opt for low-cost and low-effort options, such as burning to clear the scums for the next harvests (Textile Horizons International 1993). The content of organic matter prioritizes its application on 4 main fronts: (i) animal fodder; (ii) briquetting; (iii) biogas; and (iv) composting; moreover, there is a surplus input for exploration in other industrial applications (El-Haggag 2007b). One of the main difficulties in the converting process of biomass into products is the transport and storage protocol, in addition to the knowledge of the operational techniques that should be applied (Onu and Mbohwa 2021b). For Laudes Foundation (2021), the domestic uses such as forage, animal bedding, mulch, and compost use a small part of the waste. Among the benefits of using waste materials are the protection and

maintenance of natural resources, protection of human health, and reduction in resource extraction (Ahmad et al. 2021).


The world’s largest production crops such as sugarcane, corn, rice, and wheat are in discussion as food and fuel commodities as well as due to their important source of hemicellulose and lignocellulose for industrial manufacture. Waste treatment and disposal are only part of agricultural waste management systems (Loehr 1974). For Shishoo (2007) and Yu (2009), agricultural-based fibers should present special quality criteria as follows: strengthening potential (strength), stiffness, wear resistance, brittleness, moisture-related properties (aging, dimensional stability, swelling), heat stability, purity, resistance to microorganisms, non-odor, resistance to chemicals, etc.

The use of solid potential fibers, lack resilience and have low elasticity and elongation potential, being mixed with other sources of natural fibers can have better performance (Laudes Foundation 2021; Salleh et al. 2021). Some textile innovations such as Orange Fiber, Green Whisper, AltMat (Fig. 4), and Agralooop, in collaboration with Fashion For Good, enable alternatives through bio-based products, processes, and technologies in the production of fibers from pineapple, hemp, banana stem, fruit residues citrus, and food crops for textile and clothing manufacturing (FFG 2021; Laudes Foundation 2021).

Sharma et al. (2016) highlight that fruit and vegetable wastes mainly contain soluble materials and fibers, but they are the most commonly discarded in landfills and rot in industrial and retail establishments. Vegetables, cereals, roots and tubers, and fruits are the most promising resources for value-added production (Galanakis 2012).

The adaptation of fibers to consumption needs, in order to be employed in conventional technologies and applications, has increased tremendously their market potential

Fig. 4 AltMat representation processes. Source: AltMat (2021)



(Narasimhan et al. 2016). Depending on the extraction methods, fibers can be prepared in various forms, such as long continuous fibers, processed fibers, short-staple fibers, and powdered microfibers or nanometric fibers. The most common source of natural fiber reinforcement extraction is from stems (bast fibers), while leaves are the least reported in previous studies (Izwan et al. 2021). Worldwide, residues such as corn husks, rice, sorghum stalk and leaves, banana leaves, pineapple leaves, and others have been studied to develop new cellulose fibers with similar mechanical properties as those of common textile fibers (Reddy and Yang 2005, 2009). Companies that embrace the concept of circularity of materials claim that banana crops, pineapple leaves, rice straws, and sugarcane husks together can provide more than 250 million tons of fiber per year, meeting 2.5 times the world demand for fibers (Biomimicry 2020).

In Brazilian scenario, agribusiness has gained great notoriety in the context of studies and political-economic-institutional focus (ABRA 2013). There is a movement of research in the country in order to create viable alternatives for the relocation of waste. According the Brazilian Agricultural Research Corporation (EMBRAPA), the industrial processing of agricultural biomass from waste can be distributed in the generation of materials (polymers, resins, and fibers), energy, food and animal feed, chemical inputs (biofertilizers, surfactants, esters, acids organic), and biofuels (ethanol, biodiesel, and biogas) (Júnior 2020).

Soy straw, in particular, is an abundant and renewable form of biomass with enormous potential as a cheap and sustainable source. According to Martelli-Tosi et al. (2017), soy is a very significant agricultural commodity (Martelli-Tosi et al. 2017). However, its application in by-products


is mainly used for rural energy, animal feed, and disposal in the field (Liu et al. 2015). Araújo et al. (2019), evaluating parameters, which consider the chemical composition, growth rate, and disposition, state that soy straw is the most suitable residue to be used as raw material for the production of cellulosic-based materials, followed by sugarcane leaf, corn husk, sugarcane straw, and bagasse, revealing that the main crops in the country are the most suitable residually.

Mustafa et al. (2021) highlights that agropolymers from agricultural residues such as starch and cellulose derivatives can be efficiently regulated by natural or chemical mechanisms for the development of green materials, highlighting the use of biofibers in structural performance as a significant reinforcement. Currently, natural fiber reinforcement composites are used in advancing technologies due to their low density, light weight and good mechanical strength, and ecological characteristics (Ahmad et al. 2021; Benyus 1997) (Fig. 5).

For Ahmad et al. (2021), the advantages of using natural fiber in thermoplastic composites are as follows: (i) biodegradability; (ii) lower greenhouse gas emissions; (iii) availability in variety and format; (iv) job creation in rural areas; (v) non-linear economic development; (vi) efficient and (vii) economical energy consumption. The growing interest in technical lignins, by-products of cellulose, as a polymeric material is also due to their large-scale availability and biodegradability. These can play different roles in promoting and regulating adhesives, fillers, and reinforcing agents in engineering, replacing synthetic fixed terms (Lapsa et al. 2000).

The economic and technological advantages of lignocellulosic fibers can increase the durability and also

Fig. 5 Economic beneficial factors to the conversion of agro-industrial waste into textile raw material. Source: partially adapted from Circular Systems (2020), Dungani et al. (2015), Gomiero (2018), Laudes Foundation (2021), Onu and Mbohwa (2021a, b), Sundarraj and Ranganathan (2018), Teixeira et al. (2015), Wilts et al. (2020), and Yusuf et al. (2019) and partially authors



recyclability of incorporated products, leading to sustainable development (Mustafa et al. 2021). Fibers based on agricultural residues are promising innovations and can meet dual objectives, in the solution to the search for alternatives in the fashion industry and, in parallel, a path for millions of farmers who burn their agricultural residues and generate dangerous levels of emissions (LOUDES FOUNDATION 2021) (Fig. 5).

Scientific Literature Database Diagram on Agro-industrial Materials' Researches


The same network database was used to develop a diagram focusing on the highest incidence of materials citations by classification and types, crops, formats, conversion technology, and end-of-use researches (Fig. 6).

Sugarcane is the largest incidence term from studies in the analyzed database (Fig. 6). Brazil tightly generates bioenergy and bioethanol from sugarcane. Studies show the growing and improvements in these processes, employing bagasse, straw, and fibers from the residual material (Aguilar et al. 2021; Alarcon et al. 2021; Barbosa et al. 2020; Canilha et al. 2012; Giese et al. 2012; Soares et al. 2020). In bagasse format, sugarcane presents a greater diversity of

technology conversions for applicability for final use of cellulose nanocrystals (Fig. 6) (Bilatto et al. 2020; de Oliveira Júnior et al. 2020; Leão et al. 2017, 2020; Oliveira et al. 2016; Pereira and Arantes 2018, 2020). Figure 6 also highlights studies in which the plant works as a matrix for other textile fibers such as sisal for new biodegradable composites (de Castro et al. 2021; Satyanarayana et al. 2009); fibers are commonly used for reinforcement in composites (Cardoso et al. 2017; De Lemos et al. 2017; Dos Santos et al. 2018; Ferreira et al. 2019; Mulinari et al. 2012); production of multifunctional biocatalysts (Bilal et al. 2020; Silveira et al. 2014a, b); enzymes such as peroxidase (Queiroz et al. 2018), amylase (Orlandelli et al. 2017), cellulase (Do Nascimento and Coelho 2011), hemicellulase (Camassola & Dillon 2007), and xylanase (L. A. Oliveira et al. 2006); and dye adsorption (Cunha et al. 2018; B. C. S. Ferreira et al. 2015; Giusto et al. 2017; Meili et al. 2019; Piffer et al. 2020). In addition, Costa et al. (2015) highlight the use of sugarcane as a material suitable for textile application and the development of bioproducts.

Soybean, the main cultivated area in Brazil, presents husks and straw in its main format (Fig. 6): functioning like a chemical adsorbent (de Souza et al. 2021); bioenergy (De Pretto et al. 2018); biomaterials (Rosa et al. 2015); and

Fig. 6 Scientific literature database diagram focusing on the highest incidence of agro-industrial materials citations by classification and types, crops, formats, conversion technology, and end-of-use researches. Source: partially adapted from Onu and Mbohwa (2021b) and partially authors



cellulose (Souza et al. 2020), in particular, nanofibrillated cellulose (Debiagi et al. 2020; Flauzino Neto et al. 2013; Martelli-Tosi et al. 2016). One of the highlights is its potential for composites and films (Martelli-Tosi et al. 2017).

Cassava presents its main formats in husks, stems, and leaves for the following: the generation of bioenergy (Cruz et al. 2021); a substrate for composites (de Lima et al. 2020); a generator of cellulose nanocrystals (Czaikoski et al. 2020; Travalini et al. 2018); biosorbent (de Oliveira et al. 2019a, b); and enzyme production (Oliveira et al. 2006) (Fig. 6).

In the cereals group, corn presents the main format as a cob and stem. Its main applications are as follows: adsorption material (Campos et al. 2020); to obtain cellulose (Araújo et al. 2020; Ditzel et al. 2017; Longaresi et al. 2019; Souza and Quadri 2014); biocatalysts (Bilal et al. 2020); green composites (Ramos et al. 2019); reinforcement polymers (Coiado et al. 2017; Silvério et al. 2013); and enzyme producer (Grigorevski-Lima et al. 2009; Orlandelli et al. 2017). Rice, on the other hand, is presented in the form of husks and husk bran from the cultivation. Its main applications are the following: to obtain cellulose nanocrystals (Hafemann et al. 2020); enzymes (Gautério et al. 2020); adsorption of violet dyes in textile industry (Ribeiro et al. 2017); and biodegradable composites (Pereira et al. 2015). Wheat term appears less frequently, but it presents unique bran format for applications: in enzyme production (Cama-sola and Dillon 2007; Do Nascimento and Coelho 2011; Grigorevski-Lima et al. 2009; Orlandelli et al. 2017) and composites (Pereira et al. 2015) (Fig. 6).

The fruit group contains also the citrus fruits. The study by Alarcon et al. (2021) mentions coconut and banana as references to textile fibers and their application to composites and polymeric films. The fermented banana pseudostem and coconut fiber are potential producers of lipase and cellulase (Ferreira da Silva et al. 2019) and nano crystallized cellulose (Pereira et al. 2014). Coconut husk fibers, which represent a large amount of material mass, present applicability as follows: biosorbent for textile dyes (Carvalho Costa et al. 2020; de Oliveira et al. 2018b, a; Merci et al. 2019; Lopes et al. 2020), and bioenergy and cellulosic ethanol (Gonçalves et al. 2014, 2019). The applicability with this fiber involves crafts (Nunes et al. 2020), green composites (Lomelí-Ramírez et al. 2018), and copolymers (Rosa et al. 2009), in particular, for the removal of chromium from tannery effluents (Cunha et al. 2018). Orange term presents the greatest intensity of studies with the pomace, for the generation of nanofibers (Miranda et al. 2019), nanocellulose (Mariño et al. 2018, 2016), and adsorbent of dyes (Nascimento et al. 2014). The grape appears with its research in the stalk, in the development of polymeric composites (Borsoi et al. 2020; Taurino et al. 2020), and removal of blue and brown textile dyes (Benvenuti et al. 2020; Oliveira et al. 2018b, a). Pineapple has great potential for studies in

the textile sector. Applications such as cellulose fibers and nanofibers from their residual crowns have been increasingly developed (Pereira et al. 2021; Prado et al. 2020; Prado and Spinacé 2019), and the use of fibers from the sheets for reinforcement mechanics in polymer composites (de Azêvedo et al. 2021; Leão et al. 2015; Sena Neto et al. 2015). Leao et al. (2010) highlighted the textile fibers from their sheets as the future of industrial applications (Fig. 6).

Sawdust from eucalyptus wood provides a biosorbent for removing textile dyes such as methylene blue (Cemin et al. 2021), and its pulp, cellulose nanofibrils (Camani et al. 2020; Demuner et al. 2020; Siqueira et al. 2019) (Fig. 6).

Other fruits, not shown in the diagram, stand out, such as apple, khaki, avocado, and pomegranate for the removal of dyes (Bazzo et al. 2016; Bonetto et al. 2021; Silveira et al. 2014a, b); the seeds of açai in the adsorption and obtaining of fibers and application in composites (de Oliveira et al. 2019a, b; Wataya et al. 2016, 2015; Zavarize 2021); cashew and acerola for bionanocomposites (Duarte et al. 2015; Vieira Amorim et al. 2021); cocoa husks for cellulose nanofiber (Souza et al. 2019); and papaya and mango for the generation of enzymes for the textile industry (Okino-Delgado et al. 2018). The cereal group also presents incidence of moreover materials, such as oat husks for the generation of nanofibrillated cellulose (Debiagi et al. 2021). Tubers such as sweet potato also demonstrate to have composite potential (Pereira et al. 2017). The group of nuts, which are not identified in the diagram, contains pecan nutshells for biosorption of cationic dyes (Georgin et al. 2018; Pang et al. 2019). Peanut husks stand out from the oleaginous grain in dye adsorption research (Nascimento et al. 2014; Villar da Gama et al. 2018). Coffee beans, which are not very evident, act as reinforcing recycled polymers (Coiado et al. 2017).

According to all analyzed studies, the technology conversions are diverse: preliminary analysis of the chemical, physical, and morphological structure is the most used in materials, added to thermal, rheological, and mechanical ones; alkaline treatment in synergy with spectroscopy, ultrasound, bleaching, hydrothermal, and chemical/acid treatment; extraction and characterization, on the other hand, appear as chemical sequential and moderate; kinetic analysis in examples with pseudo-first and second-order models, pyrolysis, and combustion; solid-state fermentation was mentioned the most, but the data includes submerged fermentation with hydrolysis; the biorefinery includes a set of general analyses that are not in-depth in the present study (Fig. 6).

Conclusion

Efficient management, based on sustainable criteria, of agro-industry wastes, requires urgent programs to evaluate methods and new possibilities in the short and long term. The

development of appropriate technologies for these processes reduces the sector's negative impacts and increases its eco-efficiency, generating ecological benefits on several fronts, from land use and waste, as well as greater management of the extraction of non-renewable resources.

All reported results contributed to a preliminary understanding of the potential use of agro-industrial waste in the generation of industrial textile products in agreement with other industries. The employment of fibers from residual agricultural biomass is a cheap, accessible, and widely available alternative, constituting a model for adding economic value to the agro-industrial chains of the Brazilian main crops.

The analysis of the scientific literature database reveals that research on the recovery and relocation of agro-industrial materials in the textile industry still shows incipient advances in Brazil. The main areas identified address materials such as dye biosorbents from industrial effluents and reinforcement material in composites. In general, researches on natural fibers represent further advances in sugarcane, coconut, banana, and pineapple, which are already employed as fibers in these studies. Materials such as açai, rice, wheat, and corn are highlighted for obtaining the raw fiber of the material, especially for reinforcing composites. Furthermore, all other agro-industrial materials are investigated to obtain cellulose nanofibers.

Sugarcane has a higher incidence in the analyzed studies, presenting a greater diversity of formats and implemented technologies compared to other materials. Despite the largest area of productive land being devoted to soy in Brazil, the waste is devoted only to absorbents, biomaterials, and cellulose nanofibers. Fibers are commonly used as reinforcement in composites, biodegradable composites, and film production. Due to preliminary studies and material knowledge, there is little scalability of materials for the market and industry at the moment, but great potential for product development due to analyzed properties. The studies that highlight the transfer of technology to the Brazilian textile industry involve materials such as sugar cane, corn, rice, coconut, banana, pineapple, and acai seeds in the production of fibers and application in green composites. Those fibers stand out due to their intense abundance of residues, and their physicochemical properties of high quality, low cost, and biodegradability. The industrial applicability of fibers in Brazil is small, almost null in the textile sector, while availability is growing.

The researches directed to the textile industry present a larger incidence focused on treating effluents than applied to new materials, constituting scientific opportunities. Thus, scientific investment in researches on materials and technology development are necessary to provide applications that could meet current and future demands and expand the scope of new materials for sustainability.

Acknowledgements The authors gratefully acknowledge CAPES (Coordination for the Improvement of Higher Education Personnel of Brazilian Education Ministry).

Author Contribution The authors MUS, BC, PRBF, RRS, PUS, and JBR carried out documentation process and design of the study. Material preparation, data collection and analysis were performed by MUS, BC, PRBF, and RRS. The manuscript was written by MUS, while BC, PRBF, RRS, PUS, and JBR reviewed critically all versions of the manuscript. Supervision was performed by JBR. All authors MUS, BC, PRBF, RRS, PUS, and JBR read and approved the final manuscript.

Availability of Data and Materials All data generated or analyzed during this study are included in this published article, more information is available with the corresponding author on reasonable request.

Declarations

Competing Interests The authors declare no competing interests.

References

- ABIB (2011) Inventário residual Brasil. ASSOCIAÇÃO BRASILEIRA DE INDÚSTRIAS DA BIOMASSA. <http://pt.calameo.com/accounts/200968>
- ABIT (2018) Brazil: Industrial Consumption of Fibers and Filaments - 1970 to 2018. 1, 1. http://api.ning.com/files/72uT8VTpQjXD1dZ55VhITN*NeVUYMfsPv15Iy01dxMos7ejNSxfDuhGmkTrOBqzKbcZgnoWQjrWXH0hC0pKmGxBoWmT8Ki2MGSf67qG-e9Q_/Publicacao_ABIT_Publicacao_ABIT_Consumo_industrial_de_fibras_e_filamentos_2009_11.xls
- ABIT (2020) Perfil do Setor. <https://www.abit.org.br/cont/perfil-do-setor>
- ABRA (2013) Agronegócio e Realidade Agrária no Brasil. Revista Da Associação Brasileira de Reforma Agrária – ABRA, 96
- ABRAFAS (2020) Indústrias e Fibras. <http://www.abrafas.org.br/site/abrafas/industrias-e-fibras>
- ABRELPE (2020) Panorama dos Resíduos Sólidos no Brasil 2020. Associação Brasileira de Empresas de Limpeza Pública e Resíduos Especiais - ABRELPE, 51. <https://abrelpe.org.br/panorama-2020/>
- Aguiar A, Milessi TS, Mulinari DR, Lopes MS, da Costa SM, Candido RG (2021) Sugarcane straw as a potential second generation feedstock for biorefinery and white biotechnology applications. *Biomass Bioenerg* 144. <https://doi.org/10.1016/j.biombioe.2020.105896>
- Ahmad I, Ahmad MD, Abdullah N (2021) Composites leading to a clean and green future. *Des Sustain*. <https://doi.org/10.1016/b978-0-12-819482-9.00014-9>
- Akiyode O, Tumushabe A, Hadijah K, Peter O (2017) Climate change, food security and environmental security : a conflict inclination assessment of Karamoja region of Uganda. *Int J Sci World* 5(2):172. <https://doi.org/10.14419/ijsw.v5i2.8458>
- Alarcon RT, Lamb KJ, Bannach G, North M (2021) Opportunities for the use of Brazilian biomass to produce renewable chemicals and materials. *Chemsuschem* 14(1):169–188. <https://doi.org/10.1002/cssc.202001726>
- AltMat (2021) AltMat Materials. <https://altmat.in/alt-materials/>
- Araújo D, Castro MCR, Figueiredo A, Vilarinho M, Machado A (2020) Green synthesis of cellulose acetate from corn: physicochemical properties and assessment of environmental impacts. *J Clean Prod* 260. <https://doi.org/10.1016/j.jclepro.2020.120865>

- Araújo DJC, Machado AV, Vilarinho MCLG (2019) Availability and suitability of agroindustrial residues as feedstock for cellulose-based materials: Brazil case study. *Waste Biomass Valoriz* 10(10):2863–2878. <https://doi.org/10.1007/s12649-018-0291-0>
- Arici G, Lehmann M (2020) CEO Agenda 2020: Covid-19 edition. *Ceo Agenda 2020*, 14. <https://www.globalfashionagenda.com/publications-and-policy/ceo-agenda-covid-19-edition/>
- ASTM (1995) Standard Technology Relating to Biotechnology ASTM International. Westconshohocken, PA, Standard E. www.astm.org
- Atiqah A, Chandrasekar M, Senthil Muthu Kumar T, Senthilkumar K, Ansari MNM (2020) Characterization and interface of natural and synthetic hybrid composites. In *Encyclopedia of Renewable and Sustainable Materials*, pp 389–400. Elsevier. <https://doi.org/10.1016/B978-0-12-803581-8.10805-7>
- Ayres RU (2002) A handbook of industrial ecology
- Barbosa PP, Moraes KK, Longo MT, Rodrigues GJ (2016) Análise Do Impacto Ambiental De Fibras Têxteis Naturais, Sintéticas E Artificiais. http://www.abepro.org.br/biblioteca/TN_STP_236_373_30246.pdf
- Barbosa KL, Silva JDS, Dos Santos TV, Malta VRDS, Dos Santos-Rocha MSR, Almeida RMRG (2020) Pre-treatment of steam explosion, chemical and morphological characterization of sugarcane bagasse used for 2G ethanol production | Pré-tratamento de explosão a vapor, caracterização química e morfológica do bagaço da cana-de-açúcar usado para produção de. *Rev Virtual Quim* 12(1): 63–74. <https://doi.org/10.21577/1984-6835.2020007>
- Barker JM, McLemore VT (2005) Sustainable development and industrial minerals. *Min Eng* 57(12):48–52. <https://doi.org/10.1016/B978-0-12-373623-9.50005-8>
- Bazzo A, Adebayo MA, Dias SLP, Lima EC, Vagheti JCP, de Oliveira ER, Leite AJB, Pavan FA (2016) Avocado seed powder: characterization and its application for crystal violet dye removal from aqueous solutions. *Desalin Water Treat* 57(34):15873–15888. <https://doi.org/10.1080/19443994.2015.1074621>
- Becker P (2014) Introducing the book. *Sustain Sci* 1–6. <https://doi.org/10.1016/b978-0-444-62709-4.00001-4>
- Benvenuti J, GiraldiFisch A, Zimnoch Dos Santos JH, Gutterres M (2020) Hybrid sol–gel silica adsorbent material based on grape stalk applied to cationic dye removal. *Environ Progress Sustain Energy* 39(4). <https://doi.org/10.1002/ep.13398>
- Benyus JB (1997) *Biomimética : Inocavao Inspirada pela Natureza*. Cultrix
- Berté R (2009) *Gestão socioambiental no Brasil* (Ibpx (ed.))
- Biase CAF (2017) Desperdício de alimentos. *Convenção ABRAS*, 1–29
- Bigdeloo M, Teymourian T, Kowsari E, Ramakrishna S, Ehsani A (2021) Sustainability and circular economy of food wastes: waste reduction strategies, higher recycling methods, and improved valorization. *Mater Circ Econ* 3(1):3. <https://doi.org/10.1007/s42824-021-00017-3>
- Bilal M, Wang Z, Cui J, Ferreira LFR, Bharagava RN, Iqbal HMN (2020) Environmental impact of lignocellulosic wastes and their effective exploitation as smart carriers – a drive towards greener and eco-friendlier biocatalytic systems. *Sci Total Environ* 722. <https://doi.org/10.1016/j.scitotenv.2020.137903>
- Bilatto S, Marconcini JM, Mattoso LHC, Farinas CS (2020) Lignocellulose nanocrystals from sugarcane straw. *Ind Crops Prod* 157. <https://doi.org/10.1016/j.indcrop.2020.112938>
- Biomimicry (2020) Food Waste. <https://biomimicry.org/biomimicry-examples/#foodwaste>
- Blakeney M (2019) Food loss and food waste: causes and solutions *Food Loss Food Waste Causes Sol* <https://doi.org/10.4337/9781788975391>
- Bolfe ÉL, Campos SK, Júnior MAGP, Contini E, de Rodrigues RAR, Santana CAM (2018) *Futuro da Agricultura Brasileira*. Embrapa, 212. <https://www.embrapa.br/visao/trajetoria-da-agricultura-brasileira>
- Bonetto LR, Crespo JS, Guégan R, Esteves VI, Giovanela M (2021) Removal of methylene blue from aqueous solutions using a solid residue of the apple juice industry: full factorial design, equilibrium, thermodynamics and kinetics aspects. *J Mol Struct* 1224. <https://doi.org/10.1016/j.molstruc.2020.129296>
- Borsoi C, Dahlem Júnior MA, Beltrami LVR, Hansen B, Zattera AJ, Catto AL (2020) Effects of alkaline treatment and kinetic analysis of agroindustrial residues from grape stalks and yerba mate fibers. *J Therm Anal Calorim* 139(5):3275–3286. <https://doi.org/10.1007/s10973-019-08666-y>
- BRASIL (2010) Política Nacional de Resíduos Sólidos. http://www.planalto.gov.br/ccivil_03/_ato2007-2010/2010/lei/112305.htm
- Camani PH, Anholon BF, Toder RR, Rosa DS (2020) Microwave-assisted pretreatment of eucalyptus waste to obtain cellulose fibers. *Cellulose* 27(7):3591–3609. <https://doi.org/10.1007/s10570-020-03019-7>
- Camassola M, Dillon AJP (2007) Production of cellulases and hemicellulases by *Penicillium echinulatum* grown on pretreated sugar cane bagasse and wheat bran in solid-state fermentation. *J Appl Microbiol* 103(6):2196–2204. <https://doi.org/10.1111/j.1365-2672.2007.03458.x>
- Campbell BM, Hansen J, Rioux J, Stirling CM, Twomlow S, Wollenberg E (2018) Urgent action to combat climate change and its impacts (SDG 13): transforming agriculture and food systems. *Curr Opin Environ Sustain* 34:13–20. <https://doi.org/10.1016/j.cosust.2018.06.005>
- Campos NF, Guedes GAJC, Oliveira LPS, Gama BMV, Sales DCS, Rodriguez-Díaz JM, Barbosa CMBM, Duarte MMBM (2020) Competitive adsorption between Cu²⁺ and Ni²⁺ on corn cob activated carbon and the difference of thermal effects on mono and bicomponent systems. *J Environ Chem Eng* 8(5). <https://doi.org/10.1016/j.jece.2020.104232>
- Canilha L, Chandel AK, SuzanedossantosMilessi T, Antunes FAF, Luiz Da Costa Freitas W, Das Graças Almeida Felipe M, Da Silva SS (2012) Bioconversion of sugarcane biomass into ethanol: an overview about composition, pretreatment methods, detoxification of hydrolysates, enzymatic saccharification, and ethanol fermentation. *J Biomed Biotechnol*. <https://doi.org/10.1155/2012/989572>
- Cardoso ECL, Scagliusi SR, Lugo AB (2017) The effect of gamma radiation on biodegradability of natural fiber/PP-HMSPP foams: a study of thermal stability and biodegradability. In *Handbook of composites from renewable materials*, vols. 1–8. <https://doi.org/10.1002/9781119441632.ch75>
- Carvalho Costa AWM, Guerhardt F, Ribeiro Júnior SER, Cânovas G, Vanale RM, de Freitas Coelho D, Ehrhardt DD, Rosa JM, BasileTambourgi E, Curvelo Santana JC, Curvelo Santana JC, de Souza RR (2020) Biosorption of Cr(VI) using coconut fibers from agro-industrial waste magnetized using magnetite nanoparticles. *Environ Technol (UK)*. <https://doi.org/10.1080/0959330.2020.1752812>
- Cavalcanti AM, Dos Santos GF (2021) A INDÚSTRIA TÊXTIL NO BRASIL: uma análise da importância da competitividade frente ao contexto mundial. *Exacta*. <https://doi.org/10.5585/exactaep.2021.17784>
- CEDES (2018) Estratégias para redução de perdas e desperdício de alimentos. *Perdas e Desperdício de Alimentos: Estratégias Para Redução*. *Cadernos de Trabalhos e Debates* 3:33–52. <http://bd.camara.gov.br/bd/handle/bdcamara/36779#>
- Cemin A, Ferrarini F, Poletto M, Bonetto LR, Bortoluz J, Lemée L, Guégan R, Esteves VI, Giovanela M (2021) Characterization and use of a lignin sample extracted from *Eucalyptus grandis* sawdust for the removal of methylene blue dye. *Int J Biol Macromol* 170:375–389. <https://doi.org/10.1016/j.jbiomac.2020.12.155>

- Chan JX, Wong JF, Hassan A, Zakaria Z (2021) Bioplastics from agricultural waste. In: Biopolymers and biocomposites from agrowaste for packaging applications. Elsevier Ltd. <https://doi.org/10.1016/b978-0-12-819953-4.00005-7>
- Circular Systems (2020) Agraloop. <https://circularsystems.com/agraloop>
- Clift R, Druckman A (2015) Taking stock of industrial ecology Taking stock of industrial ecology <https://doi.org/10.1007/978-3-319-20571-7>
- CNA (2020) PIB do agronegócio tem expansão de 6,75% em 2020. <https://www.cnabrazil.org.br/noticias/pib-do-agronegocio-tem-expansao-de-6-75-em-2020>
- Coiado RDS, Lazo GD, Oliveira RR, Rodrigues RCLB, Moura EAB (2017) Polymer blend based on recycled polyethylene and ethylene vinyl acetate copolymers reinforced with natural fibers from agricultural wastes. In: Minerals, metals and materials series: Vol. Part F7. https://doi.org/10.1007/978-3-319-51382-9_76
- Costa SM, Aguiar A, Luz SM, Pessoa A, Costa SA (2015) Sugarcane straw and its cellulosic fraction as raw materials for obtainment of textile fibers and other bioproducts. In: Polysaccharides: Bioactivity and Biotechnology. https://doi.org/10.1007/978-3-319-16298-0_53
- Coste-Maniere I, Croizet K, Sette E, Fanien A, Guezguez H, Lafforgue H (2018) Circular economy: a necessary (r)evolution. In: Circular economy in textiles and apparel: processing, manufacturing, and design. Elsevier Ltd. <https://doi.org/10.1016/B978-0-08-102630-4.00006-6>
- Cruz G, Rodrigues ALP, da Silva DF, Gomes WC (2021) Physical–chemical characterization and thermal behavior of cassava harvest waste for application in thermochemical processes. *J Therm Anal Calorim* 143(5):3611–3622. <https://doi.org/10.1007/s10973-020-09330-6>
- Cunha GC, Silva IAA, Alves JR, Oliveira RVM, Menezes THS, Romão LPC (2018) Magnetic hybrids synthesized from agroindustrial byproducts for highly efficient removal of total chromium from tannery effluent and catalytic reduction of 4-nitrophenol. *Cellulose* 25(12):7409–7422. <https://doi.org/10.1007/s10570-018-2046-2>
- Czaikoski A, da Cunha RL, Menegalli FC (2020) Rheological behavior of cellulose nanofibers from cassava peel obtained by combination of chemical and physical processes. *Carbohydr Polym* 248. <https://doi.org/10.1016/j.carbpol.2020.116744>
- Dahiya S, Katakojwala R, Ramakrishna S, Mohan SV (2020) Biobased products and life cycle assessment in the context of circular economy and sustainability. *Mater Circ Econ* 2(1):7. <https://doi.org/10.1007/s42824-020-00007-x>
- Dai L, Liu R, Si C (2018) A novel functional lignin-based filler for pyrolysis and feedstock recycling of poly(lactide). *Green Chem* 20(8):1777–1783. <https://doi.org/10.1039/C7GC03863A>
- de Azêvedo LC, Rovani S, Santos JJ, Dias DB, Nascimento SS, Oliveira FF, Silva LGA, Fungaro DA (2021) Study of renewable silica powder influence in the preparation of bioplastics from corn and potato starch. *J Polym Environ* 29(3):707–720. <https://doi.org/10.1007/s10924-020-01911-8>
- de Campos A, Goulart VDG (2017) Logística Reversa Integrada. Erica de Castro BD, Fotouhi M, Vieira LMG, de Faria PE, Campos Rubio JC (2021) Mechanical behaviour of a green composite from biopolymers reinforced with sisal fibres. *J Polym Environ* 29(2):429–440. <https://doi.org/10.1007/s10924-020-01875-9>
- de Filho CHMS, Cunha EP, Queiroz HM, Vieira J, Pinto MM (2021) Perdas e Desperdício de Alimentos. *Agro Global*
- de Filleti JP, Boldrin R (2020) A indústria têxtil no Brasil: um modelo econométrico analisando a hipótese de desindustrialização setorial. *Econ Soc* 29(3):861–890. <https://doi.org/10.1590/1982-3533.2020v29n3art08>
- De Lemos AL, Mauss CJ, Santana RMC (2017) Characterization of natural fibers: wood, sugarcane and babassu for use in biocomposites. *Cell Chem Technol* 51(7–8):711–718
- de Oliveira FM, Coelho LM, de Melo EI (2018) Evaluation of the adsorption process using green coconut mesocarp for removal of methylene blue dye | Avaliação de processo adsorptivo utilizando mesocarpio de coco verde para remoção do corante azul de metileno. *Rev Mater* 23(4). <https://doi.org/10.1590/s1517-707620180004.0557>
- de Lima GG, Schoenherr ZCP, Magalhães WLE, Tavares LBB, Helm CV (2020) Enzymatic activities and analysis of a mycelium-based composite formation using peach palm (*Bactris gasipaes*) residues on *Lentinula edodes*. *Bioresour Bioprocess* 7(1). <https://doi.org/10.1186/s40643-020-00346-2>
- de Oliveira AVB, Rizzato TM, Barros BCB, Favaro SL, Caetano W, Hioka N, Batistela VR (2019a) Physicochemical modifications of sugarcane and cassava agro-industrial wastes for applications as biosorbents. *Bioresour Technol Rep* 7. <https://doi.org/10.1016/j.biteb.2019.100294>
- de Oliveira DNPS, Claro PIC, de Freitas RR, Martins MA, Souza TM, da S. e Silva BM, Mendes LM, Bufalino L (2019) Enhancement of the Amazonian Açaí waste fibers through variations of alkali pretreatment parameters. *Chem Biodivers* 16(9). <https://doi.org/10.1002/cbdv.201900275>
- de Oliveira Júnior SD, Asevedo EA, de Araújo JS, Brito PB, de Santos Cruz Costa CL, de Macedo GR, de Santos ES (2020) Enzymatic extract of *Aspergillus fumigatus* CCT 7873 for hydrolysis of sugarcane bagasse and generation of cellulose nanocrystals (CNC). *Biomass Convers Biorefin*. <https://doi.org/10.1007/s13399-020-01020-5>
- De Pretto C, Giordano RLC, Tardioli PW, Costa CBB (2018) Possibilities for producing energy, fuels, and chemicals from soybean: a biorefinery concept. *Waste Biomass Valoriz* 9(10):1703–1730. <https://doi.org/10.1007/s12649-017-9956-3>
- de Souza RM, Quesada HB, Cusioli LF, Fagundes-Klen MR, Bergamasco R (2021) Adsorption of non-steroidal anti-inflammatory drug (NSAID) by agro-industrial by-product with chemical and thermal modification: adsorption studies and mechanism. *Ind Crops Prod* 161. <https://doi.org/10.1016/j.indcrop.2020.113200>
- Debiagi F, Faria-Tischer PCS, Mali S (2020) Nanofibrillated cellulose obtained from soybean hull using simple and eco-friendly processes based on reactive extrusion. *Cellulose* 27(4):1975–1988. <https://doi.org/10.1007/s10570-019-02893-0>
- Debiagi F, Faria-Tischer PCS, Mali S (2021) A green approach based on reactive extrusion to produce nanofibrillated cellulose from oat hull. *Waste Biomass Valoriz* 12(2):1051–1060. <https://doi.org/10.1007/s12649-020-01025-1>
- Demuner IF, Colodette JL, Gomes FJB, De Oliveira RC (2020) Study of LCNF and CNF from pine and eucalyptus pulps. *Nord Pulp Pap Res J* 35(4):670–684. <https://doi.org/10.1515/npprj-2019-0075>
- Dietrich, T., Del Carmen Villaran Velasco, M., Echeverría, P. J., Pop, B., & Rusu, A. (2016). Crop and plant biomass as valuable material for BBB. Alternatives for valorization of green wastes. In *Biotransformation of agricultural waste and by-products: the food, feed, fibre, fuel (4F) economy*. Elsevier Inc. <https://doi.org/10.1016/B978-0-12-803622-8.00001-X>
- Ditzel FI, Prestes E, Carvalho BM, Demiate IM, Pinheiro LA (2017) Nanocrystalline cellulose extracted from pine wood and corncob. *Carbohydr Polym* 157:1577–1585. <https://doi.org/10.1016/j.carbpol.2016.11.036>
- do Bezerra MCL, da Veiga JE (2000) Agricultura Sustentavel. Ministerio do Meio Ambiente e Instituto Brasileiro do Meio Ambiente e dos Recursos Naturais Renovaveis
- Do Nascimento RP, Coelho RRR (2011) Cellulases: from production to biotechnological applications. In: Cellulase: types and action, mechanism and uses

- Dos Santos BH, De Souza Do Prado K, Jacinto AA, Da Silva Spinacé MA (2018) Influence of sugarcane bagasse fiber size on biodegradable composites of thermoplastic starch. *J Renew Mater* 6(2):176–182. <https://doi.org/10.7569/JRM.2018.634101>
- dos Santos KL, Panizzon J, Cenci MM, Grabowski G, Jahno VD (2020) Perdas e desperdícios de alimentos: reflexões sobre o atual cenário brasileiro. *Braz J Food Technol* 23. <https://doi.org/10.1590/1981-6723.13419>
- Duarte EB, das Chagas BS, Andrade FK, Brígida AIS, Borges MF, Muniz CR, Souza Filho MSM, Morais JPS, Feitosa JPA, Rosa MF (2015) Production of hydroxyapatite–bacterial cellulose nanocomposites from agroindustrial wastes. *Cellulose* 22(5):3177–3187. <https://doi.org/10.1007/s10570-015-0734-8>
- Dungani R, Karina MS, Sulaeman A, Hermawan D, Hadiyane A (2015) Agricultural waste fibers towards sustainability and advanced utilization: a review. *Asian J Plant Sci* 15(1–2):42–55. <https://doi.org/10.3923/ajps.2016.42.55>
- El-Haggar SM (2007a) Current practice and future sustainability. *Sustain Ind Des Waste Manag* 1–19. <https://doi.org/10.1016/b978-012373623-9/50003-4>
- El-Haggar SM (2007b) Sustainability of agricultural and rural waste management. *Sustain Ind Des Waste Manag* 223–260. <https://doi.org/10.1016/b978-012373623-9/50009-5>
- El-Haggar SM (2007c) Sustainability of industrial waste management. *Sustain Ind Des Waste Manag* 307–369. <https://doi.org/10.1016/b978-012373623-9/50012-5>
- El-Haggar SM (2007d) Sustainability of municipal solid waste management. *Sustain Ind Des Waste Manag* 149–196. <https://doi.org/10.1016/b978-012373623-9/50007-1>
- Ellen MacArthur Foundation (2017) A new textiles economy: redesigning fashion's future. Ellen MacArthur Foundation, 1–150. https://www.ellenmacarthurfoundation.org/assets/downloads/publications/A-New-Textiles-Economy_Full-Report_Updated_1-12-17.pdf <https://www.ellenmacarthurfoundation.org/publications/a-new-textiles-economy-redesigning-fashions-future>
- Embrapa (2018) Visão 2030 - o futuro da agricultura brasileira. Embrapa, 212. <http://www.embrapa.br/futuro>
- EMBRAPA (2020) Resultados e impactos positivos da pesquisa agropecuária na economia, no meio ambiente e na mesa do brasileiro. <https://www.embrapa.br/grandes-contribuicoes-para-a-agricultura-brasileira/agroindustria>
- Eryuruk SH (2015) Life cycle assessment method for environmental impact evaluation and certification systems for textiles and clothing. In: *Handbook of Life Cycle Assessment (LCA) of Textiles and Clothing*. Elsevier Ltd. <https://doi.org/10.1016/B978-0-08-100169-1.00007-1>
- FAO (2011) Global food losses and food waste – extent, causes and prevention
- FAO (2013) Food wastage footprint impacts on natural resources. <http://www.fao.org/3/i3347e/i3347e.pdf>
- FAO (2015) SAVE FOOD: Global Initiative on Food Loss and Waste Reduction. <http://www.fao.org/save-food/news-and-multimedia/news/news-details/en/c/288692/>
- FAO (2016) Food losses and waste: In Latin America and the Caribbean
- FAO (2018) Transforming food and agriculture to achieve the SDGs -TECHNICAL REFERENCE DOCUMENT. <http://www.fao.org/3/I9900EN/i9900en.pdf>
- FAO (2020) Final evaluation of “Strengthening national policy and knowledge framework in support of sustainable management of Brazil’s forest resources”
- FAO (2021a) Food loss and waste (FLW). <http://www.fao.org/platform-food-loss-waste/flw-data/en/>
- FAO (2021b) Organização das Nações Unidas para a Alimentação e a Agricultura. FAOSTAT. <http://www.fao.org/faostat/en/#data/QD>
- FAO (2021c) Sustainable Food and Agriculture. <http://www.fao.org/agriculture-consumer-protection-department/en/>
- Farley J (2010) Conservation through the economics lens. *Environ Manag* 45(1):26–38
- Ferreira BCS, Teodoro FS, Mageste AB, Gil LF, de Freitas RP, Gurgel LVA (2015) Application of a new carboxylate-functionalized sugarcane bagasse for adsorptive removal of crystal violet from aqueous solution: kinetic, equilibrium and thermodynamic studies. *Ind Crops Prod* 65(1):521–534. <https://doi.org/10.1016/j.indcrop.2014.10.020>
- Ferreira da Silva I, Rodrigues da Luz JM, Oliveira SF, Humberto de Queiroz J, Megumi Kasuya MC (2019) High-yield cellulase and LiP production after SSF of agricultural wastes by *Pleurotus ostreatus* using different surfactants. *Biocatal Agric Biotechnol* 22. <https://doi.org/10.1016/j.bcab.2019.101428>
- Ferreira FV, Trindade GN, Lona LMF, Bernardes JS, Gouveia RF (2019) LDPE-based composites reinforced with surface modified cellulose fibres: 3D morphological and morphometrical analyses to understand the improved mechanical performance. *Eur Polym J* 117:105–113. <https://doi.org/10.1016/j.eurpolymj.2019.05.005>
- FFG (2021) FASHION FOR GOOD - Partners. <https://fashionforgood.com>
- Flauzino Neto WP, Silvério HA, Dantas NO, Pasquini D (2013) Extraction and characterization of cellulose nanocrystals from agro-industrial residue - Soy hulls. *Ind Crops Prod* 42(1):480–488. <https://doi.org/10.1016/j.indcrop.2012.06.041>
- Foley JA (2005) Global consequences of land use. *Science* 309(5734):570–574. <https://doi.org/10.1126/science.1111772>
- Freiria RC (2011) Direito, Gestão e Políticas Públicas Ambientais. SENAC SP
- Galanakis CM (2012) Recovery of high added-value components from food wastes: conventional, emerging technologies and commercialized applications. *Trends Food Sci Technol* 26(2):68–87. <https://doi.org/10.1016/j.tifs.2012.03.003>
- Gardetti MA (2018) Introduction and the concept of circular economy. In: *Circular economy in textiles and apparel: processing, manufacturing, and design*. Elsevier Ltd. <https://doi.org/10.1016/B978-0-08-102630-4.00001-7>
- Gautério GV, da Silva LGG, Hübner T, da Rosa Ribeiro T, Kalil SJ (2020) Maximization of xylanase production by *Aureobasidium pullulans* using a by-product of rice grain milling as xylan source. *Biocatal Agric Biotechnol* 23. <https://doi.org/10.1016/j.bcab.2020.101511>
- Georgin J, Marques BS, Peres EC, Allasia D, Dotto GL (2018) Biosorption of cationic dyes by Pará chestnut husk (*Bertholletia excelsa*). *Water Sci Technol* 77(6):1612–1621. <https://doi.org/10.2166/wst.2018.041>
- Giannetti BF, Almeida CM (2006) *Ecologia Industrial: Conceitos, Ferramentas e Aplicações* (Editora Blucher (ed.))
- Giese EC, Chandel AK, dos Santos Oliveira I, da Silva SS (2012) Prospects for the bioethanol production from sugarcane feedstock: focus on Brazil. In: *Sugarcane: Production, Cultivation and Uses*
- Giusto LAR, Pissetti FL, Castro TS, Magalhães F (2017) Preparation of activated carbon from sugarcane bagasse soot and methylene blue adsorption. *Water Air Soil Pollut* 228(7). <https://doi.org/10.1007/s11270-017-3422-5>
- Gomiero T (2018) Agriculture and degrowth: state of the art and assessment of organic and biotech-based agriculture from a degrowth perspective. *J Clean Prod* 197:1823–1839. <https://doi.org/10.1016/j.jclepro.2017.03.237>
- Gonçalves FA, Ruiz HA, Nogueira CDC, Santos ESD, Teixeira JA, De Macedo GR (2014) Comparison of delignified coconuts waste and cactus for fuel-ethanol production by the simultaneous and semi-simultaneous saccharification and fermentation strategies. *Fuel* 131:66–76. <https://doi.org/10.1016/j.fuel.2014.04.021>

- Gonçalves FA, Ruiz HA, dos Santos ES, Teixeira JA, de Macedo GR (2019) Valorization, comparison and characterization of coconuts waste and cactus in a biorefinery context using $\text{NaClO}_2\text{-C}_2\text{H}_4\text{O}_2$ and sequential $\text{NaClO}_2\text{-C}_2\text{H}_4\text{O}_2$ /autohydrolysis pretreatment. *Waste Biomass Valoriz* 2249–2262. <https://doi.org/10.1007/s12649-018-0229-6>
- Goodland R (1995) The concept of environmental sustainability. *Annu Rev Ecol Syst* 26:1–24. <http://www.jstor.org/stable/2097196>
- Grigorevski-Lima AL, Da Vinha FNM, Souza DT, Bispo ASR, Bon EPS, Coelho RRR, Nascimento RP (2009) *Aspergillus fumigatus* thermophilic and acidophilic endoglucanases. *Appl Biochem Biotechnol* 155(1–3):321–329. <https://doi.org/10.1007/s12010-008-8482-y>
- Hafemann E, Battisti R, Bresolin D, Marangoni C, Machado RAF (2020) Enhancing chlorine-free purification routes of rice husk biomass waste to obtain cellulose nanocrystals. *Waste Biomass Valoriz* 11(12):6595–6611. <https://doi.org/10.1007/s12649-020-00937-2>
- Hanson K (2014) Environmental impact. *Cut Tool Eng* 66(6):62–68. <https://doi.org/10.1016/B978-0-12-455250-0.50008-6>
- Henz GP, Porpino G (2017) Food losses and waste: how Brazil is facing this global challenge? *Hortic Bras* 35(4):472–482. <https://doi.org/10.1590/s0102-053620170402>
- Herrero M, Laca A, Laca A, Díaz M (2020) Application of life cycle assessment to food industry wastes. *Food Ind Wastes* 331–353. <https://doi.org/10.1016/b978-0-12-817121-9.00015-2>
- Hoque ME, Chuan YL, Meng PM (2021) Agro-based green biocomposites for packaging applications. In: *Biopolymers and biocomposites from agro-waste for packaging applications*. Elsevier Ltd. <https://doi.org/10.1016/b978-0-12-819953-4.00008-2>
- IBGE (2021) IBGE prevê safra recorde de 260,5 milhões de toneladas para 2021. <https://agenciadenoticias.ibge.gov.br/agencia-sala-de-imprensa/2013-agencia-de-noticias/releases/29889-ibge-preve-safra-recorde-de-260-5-milhoes-de-toneladas-para-2021>
- IEMI (2021) Estimativas para a produção de vestuário | Abril 2021. <https://www.iemi.com.br/estimativas-para-a-producao-de-vestuario/>
- IPEA (2013) O Perfil da Agroindústria Rural no Brasil. Relatório de Pesquisa Do Instituto de Pesquisa Econômica Aplicada 1(3): 86. http://www.ipea.gov.br/agencia/images/stories/PDFs/relatoriopesquisa/130319_relatorio_perfil_agroindustria.pdf
- Ishak NM, Mansor MR, Ab Ghani AF (2021) Conceptual design development and selection of green product. In: *Design for sustainability*. INC. <https://doi.org/10.1016/b978-0-12-819482-9.00012-5>
- Izwan SM, Sapuan SM, Zuhri MYM, Mohamed AR, Ilyas RA (2021) A comprehensive review of natural fiber reinforced polymer biocomposites and their applications. In: *Design for sustainability*. INC. <https://doi.org/10.1016/b978-0-12-819482-9.00019-8>
- Júnior SV (2020) Aproveitamento de resíduos agroindustriais - Uma abordagem sustentável. Embrapa Agroenergia
- Kapoor M, Panwar D, Kaira GS (2016) Bioprocesses for enzyme production using agro-industrial wastes. In: *Agro-industrial wastes as feedstock for enzyme production*. Elsevier, pp 61–93. <https://doi.org/10.1016/B978-0-12-802392-1.00003-4>
- Kavitha S, Yukesh Kannah R, Kumar G, Gunasekaran M, Rajesh Banu J (2020) Introduction: sources and characterization of food waste and food industry wastes. In: *Food Waste to Valuable Resources* (Issue July 2014). INC. <https://doi.org/10.1016/b978-0-12-818353-3.00001-8>
- Keeble BR (1988) The Brundtland report: 'Our common future.' *Med War* 4(1):17–25. <https://doi.org/10.1080/07488008808408783>
- Kosseva MR (2020a) Sources, characteristics, treatment, and analyses of animal-based food wastes. In: *Food industry wastes*. INC. <https://doi.org/10.1016/b978-0-12-817121-9.00004-8>
- Kosseva MR (2020b) Sources, characteristics and treatment of plant-based food waste. In: *Food industry wastes*. INC. <https://doi.org/10.1016/b978-0-12-817121-9.00003-6>
- Lambin EF (2012) Global land availability: Malthus versus Ricardo. *Glob Food Sec* 1(2):83–87
- Lapsa V, Betkers T, Shulga G (2000) Composite materials from pulp and papermaking wastes. In: *Cellulosic pulps, fibres and materials*. Woodhead Publishing Ltd. <https://doi.org/10.1533/9781845698546.297>
- Laudes Foundation (2021) Spinning future threads-the potential of agricultural residues as textile fibre feedstock
- Leão AL, Cherian BM, Narine S, Souza SF, Sain M, Thomas S (2015) The use of pineapple leaf fibers (PALFs) as reinforcements in composites. *Biofiber Reinforcements in Composite Materials*. <https://doi.org/10.1533/9781782421276.2.211>
- Leao AL, Souza SF, Cherian BM, Frollini E, Thomas S, Pothan LA, Kottaisamy M (2010) Agro-based biocomposites for industrial applications. *Mol Cryst Liq Cryst* 522:18/[318]-27/[327]. <https://doi.org/10.1080/15421401003719852>
- Leão RM, Jesus LCC, Bertuoli PT, Zattera AJ, Maia JMLL, del Menezzi CHS, Amico SC, da Luz SM (2020) Production and characterization of cellulose nanocrystals/ acrylonitrile butadiene styrene nanocomposites. *J Compos Mater* 54(27):4207–4214. <https://doi.org/10.1177/0021998320927773>
- Leão RM, Miléo PC, Maia JMLL, Luz SM (2017) Environmental and technical feasibility of cellulose nanocrystal manufacturing from sugarcane bagasse. *Carbohydr Polym* 175:518–529. <https://doi.org/10.1016/j.carbpol.2017.07.087>
- Lehmann M, Arici G, Martinez-pardo C (2019) Pulse of the fashion - 2019 Update. *Global Fashion Agenda & Boston Consulting Group & Sustainable Apparel Coalition*. <http://media-publications.bcg.com/france/Pulse-of-the-Fashion-Industry2019.pdf>
- Lifset R, Graedel TE (2015) Industrial ecology: goals and definitions. *A handbook of industrial ecology*. <https://doi.org/10.4337/9781843765479.00009>
- Liu Z, Cao Y, Wang Z, Ren H, Amidon TE, Lai Y (2015) The utilization of soybean straw. I. Fiber morphology and chemical characteristics. *BioResources* 10(2). <https://doi.org/10.15376/biores.10.2.2266-2280>
- Lobo RN, Limeira TNP, Marques RN (2014) *Fundamentos da Tecnologia Têxtil: Da concepção da fibra ao processo de estamparia*. (1ª ed.). Erica
- Loehr RC (1974) Waste characteristics. *Agric Waste Manag* 100–126. <https://doi.org/10.1016/b978-0-12-455250-0.50009-8>
- Lomeli-Ramírez MG, Anda RR, Satyanarayana KG, Bolzon de Muniz GI, Iwakiri S (2018) Comparative study of the characteristics of green and brown coconut fibers for the development of green composites. *BioResources* 13(1): 1637–1660. <https://doi.org/10.15376/biores.13.1.1637-1660>
- Longaresi RH, de Menezes AJ, Pereira-da-Silva MA, Baron D, Mathias SL (2019) The maize stem as a potential source of cellulose nanocrystal: cellulose characterization from its phenological growth stage dependence. *Ind Crops Prod* 133:232–240. <https://doi.org/10.1016/j.indcrop.2019.02.046>
- Lopes LS, Vieira N, da Luz RJM, Silva SMDC, Cardoso WS, Kasuya MMC (2020) Production of fungal enzymes in Macaúba coconut and enzymatic degradation of textile dye. *Biocatal Agric Biotechnol* 26. <https://doi.org/10.1016/j.cbab.2020.101651>
- Lopes, T. J., Rosa, G. R., da Silva, L. S., Scheeren, C. W., Antelo, F. S., & Martins, M. L. (2021). Identification, characterization and quality management of natural textile fibres. In: *Fundamentals of natural fibres and textiles*. LTD. <https://doi.org/10.1016/b978-0-12-821483-1.00008-5>
- LSPA/IBGE (2021) Levantamento Sistemático da Produção Agrícola Abril 2021. <https://www.ibge.gov.br/estatisticas/economicas/agricultura-e-pecuaria/9201-levantamento-sistema>

- [matico-da-producao-agricola.html?edicao=30703&t=resutados](https://doi.org/10.1016/j.matcir.2022.100000)
- Macaulay SK (2007) Use of waste as raw materials: efficient recycling techniques. In *Ecotextiles: the Way Forward for Sustainable Development in Textiles* Woodhead Publishing Limited. <https://doi.org/10.1533/9781845693039.1.33>
- Madhav S, Ahamad A, Singh P, Mishra PK (2018) A review of textile industry: wet processing, environmental impacts, and effluent treatment methods. *Environ Qual Manag* 27(3):31–41. <https://doi.org/10.1002/tqem.21538>
- Mariano M (2018) Abit e IEMI apresentam balanço da cadeia têxtil e vestuário. *Textilia*. http://www.textilia.net/materias/ler/textil/mercado/abit_e_iemi_apresentam_balanco_da_cadeia_textil_e_vestuario
- Mariño MA, Rezende CC, Tasic L (2016) A multistep mild process for preparation of nanocellulose from orange bagasse. *European Biomass Conference and Exhibition Proceedings, 2016(24thEU-BCE)*, 1025–1031
- Mariño MA, Rezende CA, Tasic L (2018) A multistep mild process for preparation of nanocellulose from orange bagasse. *Cellulose* 25(10):5739–5750. <https://doi.org/10.1007/s10570-018-1977-y>
- Martelli-Tosi M, Assis OBG, Silva NC, Esposto BS, Martins MA, Tapia-Blácido DR (2017) Chemical treatment and characterization of soybean straw and soybean protein isolate/straw composite films. *Carbohydr Polym* 157:512–520. <https://doi.org/10.1016/j.carbpol.2016.10.013>
- Martelli-Tosi M, Torricillas MDS, Martins MA, Assis OBG, Tapia-Blácido DR (2016) Using commercial enzymes to produce cellulose nanofibers from soybean straw. *J Nanomater* 2016. <https://doi.org/10.1155/2016/8106814>
- Matos AT (2005) Curso sobre tratamento de resíduos agroindustriais. <http://www.ebah.com.br/content/ABAAAAYNoAL/tratamento-residuos-agroindustriais>
- Meili L, Lins PVS, Costa MT, Almeida RL, Abud AKS, Soletti JI, Dotto GL, Tanabe EH, Sellaoui L, Carvalho SHV, Carvalho SHV, Erto A (2019) Adsorption of methylene blue on agroindustrial wastes: experimental investigation and phenomenological modelling. *Prog Biophys Mol Biol* 141:60–71. <https://doi.org/10.1016/j.pbiomolbio.2018.07.011>
- Mello LMR (2006) Produção e comercialização de uvas e vinhos – Panorama 2005. Embrapa
- Merci A, Rezende MI, Constantino LV, Doi SMO (2019) Evaluation of different factors in the removal of remazol brilliant blue from aqueous solutions by adsorption in sugarcane and green coconut fibers | Avaliação de diferentes fatores na remoção de remazol brilliant blue de soluções aquosas por adsorção em. *Rev Mater* 24(3). <https://doi.org/10.1590/S1517-707620190003.0752>
- Ministério da Agricultura, P. e A. (2019a) Projeções de Longo Prazo. In: Mapa. <http://www.agricultura.gov.br/assuntos/politica-agricola/todas-publicacoes-de-politica-agricola/projecoes-do-agronegocio/projecoes-do-agronegocio-2018-2019-2028-2029/view>
- Ministério da Agricultura, P. e A. (2019b) Projeções do Agronegócio: Brasil 2018/19 a 2028/29 projeções de longo prazo. In: Ministério da Agricultura, Pecuária e Abastecimento. <http://www.agricultura.gov.br/assuntos/politica-agricola/todas-publicacoes-de-politica-agricola/projecoes-do-agronegocio/projecoes-do-agronegocio-2018-2019-2028-2029/view>
- Miranda KWE, Mattoso LHC, Bresolin JD, Hubinger SZ, Medeiros ES, de Oliveira JE (2019) Polystyrene bioactive nanofibers using orange oil as an ecofriendly solvent. *J Appl Polym Sci* 136(15). <https://doi.org/10.1002/app.47337>
- Moran EF (2011) Meio ambiente e ciências sociais: interações homem-ambiente e sustentabilidade. Editora SENAC
- Mulinari DR, Capri MR, Maia TF (2012) Use of the sugarcane bagasse in thermoplastics and thermosetting composites. In: *Sugarcane: Production, Cultivation and Uses*
- Mustafa Z, Chang SY, Fadzullah SHSM, Osman AF, Ibrahim I (2021) Degradable composites: processes and applications. *Des Sustain*. <https://doi.org/10.1016/b978-0-12-819482-9.00017-4>
- Narasimhan S, Srikanth BS, Poltronieri P (2016) Plants by-products and fibers' industrial exploitation. In: *Biotransformation of agricultural waste and by-products: the food, feed, fibre, fuel (4F) economy*. Elsevier Inc. <https://doi.org/10.1016/B978-0-12-803622-8.00003-3>
- Nascimento GED, Duarte MMB, Campos NF, Rocha ORSD, Silva VLD (2014) Adsorption of azo dyes using peanut hull and orange peel: A comparative study. *Environ Technol (UK)* 35(11):1436–1453. <https://doi.org/10.1080/09593330.2013.870234>
- Nascimento VF, Sobral AC, De Andrade PR, Ometto JPHB (2015) Evolução e desafios no gerenciamento dos resíduos sólidos urbanos no Brasil. *Ambient Agua* 10(4). <https://doi.org/10.4136/ambi-agua.1635>
- Nguyen NU, Schnitzer H (2008) Waste management towards zero emissions approach in the fruit juice processing industry. 1st WSEAS Int Conf Environ Geol Sci Eng 91–97
- Nishino T (2017) Cellulose fiber/nanofiber from natural sources including waste-based sources. In *Green Composites: Waste and Nature-Based Materials for a Sustainable Future: Second Edition*. Elsevier Ltd. <https://doi.org/10.1016/B978-0-08-100783-9.00010-1>
- Nunes LA, Silva MLS, Gerber JZ, Kalid RDA (2020) Waste green coconut shells: diagnosis of the disposal and applications for use in other products. *J Clean Prod* 255. <https://doi.org/10.1016/j.jclepro.2020.120169>
- Okino-Delgado CH, Prado DZ, Fleuri LF (2018) Brazilian fruit processing, wastes as a source of lipase and other biotechnological products: a review. *Anais Acad Bras Cienc* 90(3):2927–2943. <https://doi.org/10.1590/0001-3765201820180095>
- Oliveira LA, Porto ALF, Tambourgi EB (2006) Production of xylanase and protease by *Penicillium janthinellum* CRC 87M–115 from different agricultural wastes. *Biores Technol* 97(6):862–867. <https://doi.org/10.1016/j.biortech.2005.04.017>
- Oliveira APD, Módenes AN, Bragião ME, Hinterholz CL, Trigueros DEG, de O. Bezerra, I. G. (2018b) Use of grape pomace as a biosorbent for the removal of the Brown KROM KGT dye. *Bioreour Technol Rep* 2:92–99. <https://doi.org/10.1016/j.biteb.2018.05.001>
- Oliveira FBD, Bras J, Pimenta MTB, Curvelo AADS, Belgacem MN (2016) Production of cellulose nanocrystals from sugarcane bagasse fibers and pith. *Ind Crops Prod* 93:48–57. <https://doi.org/10.1016/j.indcrop.2016.04.064>
- Onu P, Mbohwa C (2021a) Economics and risk assessment of new technologies in agrowaste diversity. *Agric Waste Divers Sustain Issues* 171–181. <https://doi.org/10.1016/b978-0-323-85402-3.00004-8>
- Onu P, Mbohwa C (2021b) Sustainable agricultural waste diversity: advances in green energy and materials production. *Agric Waste Divers Sustain Issues* 55–73. <https://doi.org/10.1016/b978-0-323-85402-3.00008-5>
- Onu P, Mbohwa C (2021c) Sustainable agrowaste diversity versus sustainable development goals. *Agric Waste Divers Sustain Issues* 2017:75–96. <https://doi.org/10.1016/b978-0-323-85402-3.00012-7>
- Onu P, Mbohwa C (2021d) Waste management and the prospect of biodegradable wastes from agricultural processes. *Agric Waste Divers Sustain Issues* 1–20. <https://doi.org/10.1016/b978-0-323-85402-3.00006-1>
- Onu P, Mbohwa C (2021e) Which way forward: agricultural waste management and the fourth industrial revolution appraisal. *Agric Waste Divers Sustain Issues* 155–170. <https://doi.org/10.1016/b978-0-323-85402-3.00010-3>

- Orlandelli RC, Santos MS, Polonio JC, de Azevedo JL, Pamphile JA (2017) Use of agro-industrial wastes as substrates for α -amylase production by endophytic fungi isolated from *Piper hispidum* Sw | Uso de resíduos agroindustriais para a produção de α -amilase por fungos endofíticos isolados de *Piper hispidum* Sw. *Acta Sci Technol* 39(3):255–261. <https://doi.org/10.4025/actascitechnol.v39i3.30067>
- PAM-Produção Agrícola Municipal (2021) Área plantada ou destinada à colheita e área colhida. BGE. <https://sidra.ibge.gov.br/tabela/5457#resultado>
- Pang X, Sellaoui L, Franco D, Dotto GL, Georgin J, Bajahzar A, Belmabrouk H, Ben Lamine A, Bonilla-Petriciolet A, Li Z (2019) Adsorption of crystal violet on biomasses from pecan nutshell, para chestnut husk, araucaria bark and palm cactus: experimental study and theoretical modeling via monolayer and double layer statistical physics models. *Chem Eng J* 378. <https://doi.org/10.1016/j.cej.2019.122101>
- Patterson P (2012) The impact of environmental regulation on future textile products and processes The global textile and clothing industry: technological advances and future challenges Woodhead Publishing Limited <https://doi.org/10.1533/9780857095626.29>
- Pereira ALS, Nascimento DMD, Souza Filho MDSM, Morais JPS, Vasconcelos NF, Feitosa JPA, Brígida AIS, Rosa MDF (2014) Improvement of polyvinyl alcohol properties by adding nanocrystalline cellulose isolated from banana pseudostems. *Carbohydr Polym* 112:165–172. <https://doi.org/10.1016/j.carbpol.2014.05.090>
- Pereira B, Arantes V (2018) Nanocelluloses from sugarcane biomass. In: *Advances in sugarcane biorefinery: technologies, commercialization, policy issues and paradigm shift for bioethanol and by-products*. <https://doi.org/10.1016/B978-0-12-804534-3.00009-4>
- Pereira B, Arantes V (2020) Production of cellulose nanocrystals integrated into a biochemical sugar platform process via enzymatic hydrolysis at high solid loading. *Ind Crops Prod* 152. <https://doi.org/10.1016/j.indcrop.2020.112377>
- Pereira PHF, De Freitas Rosa M, Cioffi MOH, De Carvalho Benini KCC, Milanese AC, Voorwald HJC, Mulinari DR (2015) Vegetal fibers in polymeric composites: a review. *Polimeros* 25(1):9–22. <https://doi.org/10.1590/0104-1428.1722>
- Pereira CR, Resende JTV, Guerra EP, Lima VA, Martins MD, Knob A (2017) Enzymatic conversion of sweet potato granular starch into fermentable sugars: Feasibility of sweet potato peel as alternative substrate for α -amylase production. *Biocatal Agric Biotechnol* 11:231–238. <https://doi.org/10.1016/j.bcab.2017.07.011>
- Pereira PHF, Ornaghi HL, Arantes V, Cioffi MOH (2021) Effect of chemical treatment of pineapple crown fiber in the production, chemical composition, crystalline structure, thermal stability and thermal degradation kinetic properties of cellulosic materials. *Carbohydr Res* 499. <https://doi.org/10.1016/j.carres.2020.108227>
- Piffer HH, Veit MT, Juchen PT, da Cunha Gonçalves G, Palácio SM, Zanette JC (2020) Sugarcane bagasse biomass applied to the adsorption of reactive blue bb dye. *Environ Eng Manag J* 19(7):1017–1023
- Pinazza LA, de Araujo NB (1993) *Agricultura na virada do século XX*. Globo
- Prado KS, Spinacé MAS (2019) Isolation and characterization of cellulose nanocrystals from pineapple crown waste and their potential uses. *Int J Biol Macromol* 122:410–416. <https://doi.org/10.1016/j.ijbiomac.2018.10.187>
- Prado KS, Jacinto AA, Spinacé MAS (2020) Cellulose nanostructures extracted from pineapple fibres. *Green Energy Technol*. https://doi.org/10.1007/978-981-15-1416-6_10
- Prithivirajan R, Jayabal S, Bharathiraja G (2015) Bio-based composites from waste agricultural residues: mechanical and morphological properties. *Cellul Chem Technol* 49:65–68
- Queiroz MLB, Da Conceição KC, Melo MN, Sánchez OC, Alvarez HM, Soares CMF, Fricks AT (2018) Immobilization of horseradish peroxidase on sugarcane bagasse | IMOBILIZAÇÃO DE PEROXIDASE DE RAIZ FORTE EM BAGAÇO DE CANA-DE-AÇÚCAR. *Quim Nova* 41(9): 1019–1024. <https://doi.org/10.21577/0100-4042.20170279>
- Ramos RRF, Siqueira DD, Wellen RMR, Leite IF, Glenn GM, Medeiros ES (2019) Development of green composites based on polypropylene and corncob agricultural residue. *J Polym Environ* 27(8):1677–1685. <https://doi.org/10.1007/s10924-019-01462-7>
- Reddy N, Yang Y (2005) Structure and properties of high quality natural cellulose fibers from cornstalks. *Polymer* 46(15):5494–5500. <https://doi.org/10.1016/j.polymer.2005.04.073>
- Reddy N, Yang Y (2009) Natural cellulose fibers from soybean straw. *Bioresour Technol* 100(14):3593–3598. <https://doi.org/10.1016/j.biortech.2008.09.063>
- Rezzadori K, Benedetti S (2009) Proposições para valorização de resíduos do processamento do suco de laranja. UFSC
- Ribeiro GAC, Silva DSA, Dos Santos CC, Vieira AP, Bezerra CWB, Tanaka AA, Santana SAA (2017) Removal of Remazol brilliant violet textile dye by adsorption using rice hulls. *Polimeros* 27(1):16–26. <https://doi.org/10.1590/0104-1428.2386>
- Rockström J, Steffen W, Noone K, Persson Å, Chapin FS III, Lambin E, Lenton TM, Scheffer M, Folke C, Schellnhuber H, Nykvist B, De Wit CA, Hughes T, van der Leeuw S, Rodhe H, Sörlin S, Snyder PK, Costanza R, Svedin U, Falke M, J. F. (2009) Planetary boundaries: exploring the safe operating space for humanity. *Ecology and Society* 14(2):32 ((online))
- Rosa MF, Chiou B-S, Medeiros ES, Wood DF, Williams TG, Mattoso LHC, Orts WJ, Imam SH (2009) Effect of fiber treatments on tensile and thermal properties of starch/ethylene vinyl alcohol copolymers/coir biocomposites. *Bioresour Technol* 100(21):5196–5202. <https://doi.org/10.1016/j.biortech.2009.03.085>
- Rosa JR, da Silva ISV, de Lima CSM, Pasquini D (2015) Production of polyols and new biphasic mono-component materials from soy hulls by oxypropylation. *Ind Crops Prod* 72:152–158. <https://doi.org/10.1016/j.indcrop.2014.12.044>
- Ruviaro, C. F., Borges, A., Farinha, M., Bernardo, L. M., Morais, H. B., Leis, C. M., & Domingues, C. F. (2020). Food losses and wastes in Brazil: a systematic review. *Desenvolvimento Socioeconômico Em Debate*, 6(1), 78. <https://doi.org/10.18616/rdsd.v6i1.5878>
- Saath KCO, Fachinello AL (2018) Crescimento da demanda mundial de alimentos e restrições do fator terra no Brasil. *Rev Econ Sociol Rural* 56(2):195–212. <https://doi.org/10.1590/1234-56781806-94790560201>
- Salleh KM, Armir NAZ, Mazlan NSN, Wang C, Zakaria S (2021) Cellulose and its derivatives in textiles: primitive application to current trend. In *Fundamentals of Natural Fibres and Textiles*. LTD. <https://doi.org/10.1016/b978-0-12-821483-1.00014-0>
- Satyanarayana KG, Arizaga GGC, Wypych F (2009) Biodegradable composites based on lignocellulosic fibers-an overview. *Progress Polym Sci (Oxford)* 34(9):982–1021. <https://doi.org/10.1016/j.progpolymsci.2008.12.002>
- Scarlat N, Martinov M, Dallemand JF (2010) Assessment of the availability of agricultural crop residues in the European Union: potential and limitations for bioenergy use. *Waste Manag* 30:1889–1897
- Schneider VE, Peresin D, Trentin AC, Bortolin TA, Sambuichi RHR (2012) Diagnóstico dos Resíduos Orgânicos do Setor Agroindustrial e Agroindústrias Associadas. Instituto de Pesquisa Econômica Aplicada – IPEA, 134

- Sena Neto AR, Araujo MAM, Barboza RMP, Fonseca AS, Tonoli GHD, Souza FVD, Mattoso LHC, Marconcini JM (2015) Comparative study of 12 pineapple leaf fiber varieties for use as mechanical reinforcement in polymer composites. *Ind Crops Prod* 64:68–78. <https://doi.org/10.1016/j.indcrop.2014.10.042>
- Senthil Kumar P, Femina Carolin C (2018) Future for circular economy. In: *Circular economy in textiles and apparel: processing, manufacturing, and design*. Elsevier Ltd. <https://doi.org/10.1016/B978-0-08-102630-4.00010-8>
- Shahid-ul-Islam, Shahid M, Mohammad F (2013) Perspectives for natural product based agents derived from industrial plants in textile applications – a review. *J Clean Prod* 57:2–18. <https://doi.org/10.1016/j.jclepro.2013.06.004>
- Sharma R, Oberoi HS, Dhillon GS (2016) Fruit and vegetable processing waste: renewable feed stocks for enzyme production. In: *Agro-industrial wastes as feedstock for enzyme production: apply and exploit the emerging and valuable use options of waste biomass* Elsevier Inc. <https://doi.org/10.1016/B978-0-12-802392-1.00002-2>
- Shishoo R (2007) The use of renewable resource based materials for technical textiles applications Ecotextiles: the way forward for sustainable development in textile Woodhead Publishing Limited <https://doi.org/10.1533/9781845693039.3.109>
- Sillanpää M, Ncibi C (2019a) Circular economy and sustainable development. In the *Circular Economy*. <https://doi.org/10.1016/b978-0-12-815267-6.00006-2>
- Sillanpää M, Ncibi C (2019b) Circular economy in action. In the *Circular Economy*. <https://doi.org/10.1016/b978-0-12-815267-6.00004-9>
- Sillanpää M, Ncibi C (2019c) Getting hold of the circular economy concept. In the *Circular Economy*. <https://doi.org/10.1016/b978-0-12-815267-6.00001-3>
- Silva VLMM, Gomes WC, Alsina O (2007) Utilização do bagaço de cana de açúcar como biomassa adsorvente na adsorção de poluentes orgânicos. *Revista Eletrônica De Materiais e Processos* 2:27–32
- Silva T et al (2009) Banana – Fonte de energia. FÓRUM NACIONAL DE INICIAÇÃO CIENTÍFICA NO ENSINO MÉDIO E TÉCNICO
- Silveira MB, Pavan FA, Gelos NF, Lima EC, Dias SLP (2014a) Punica granatum shell preparation, characterization, and use for crystal violet removal from aqueous solution. *Clean - Soil Air Water* 42(7):939–946. <https://doi.org/10.1002/clen.201100722>
- Silveira MHL, De Siqueira FG, Rau M, Silva LD, Moreira LRDS, Ferreira-Filho EX, Andreus J (2014b) Hydrolysis of sugarcane bagasse with enzyme preparations from *Acrophialophora nainiana* grown on different carbon sources. *Biocatal Biotransform* 32(1):53–63. <https://doi.org/10.3109/10242422.2013.872634>
- Silvério HA, Flauzino Neto WP, Dantas NO, Pasquini D (2013) Extraction and characterization of cellulose nanocrystals from corncob for application as reinforcing agent in nanocomposites. *Ind Crops Prod* 44:427–436. <https://doi.org/10.1016/j.indcrop.2012.10.014>
- Siqueira GA, Dias IKR, Arantes V (2019) Exploring the action of endoglucanases on bleached eucalyptus kraft pulp as potential catalyst for isolation of cellulose nanocrystals. *Int J Biol Macromol* 133:1249–1259. <https://doi.org/10.1016/j.ijbiomac.2019.04.162>
- Six L, Velghe F, Verstichel S, De Meester S (2016) Sustainability considerations on the valorization of organic waste. In: *Biotransformation of agricultural waste and by-products: the food, feed, fibre, fuel (4F) economy*. Elsevier Inc. <https://doi.org/10.1016/B978-0-12-803622-8.00011-2>
- Soares LDS, Maia AAD, Moris VAS, De Paiva JMF (2020) Study of the effects of the addition of coffee grounds and sugarcane fibers on thermal and mechanical properties of briquettes. *J Nat Fibers* 17(10):1430–1438. <https://doi.org/10.1080/15440478.2019.1578325>
- SOFA/FAO (2019) Moving forward on food loss and waste reduction. <https://creativecommons.org/licenses/by-nc-sa/3.0/igo.%0A>
- SOFA/FAO (2020) Overcoming water challenges in agriculture. FAO
- Soglio FD, Kubo RR (2016) Desenvolvimento, agricultura e sustentabilidade. UFRGS
- Souza VC, Quadri MGN (2014) Preparation and properties of cellulose nanocrystals derived from corn cobs: application as a reinforcing material for “green nanocomposite” films. *J Biobased Mater Bioenergy* 8(5):495–505. <https://doi.org/10.1166/jbmb.2014.1465>
- Souza LO, Lessa OA, Dias MC, Tonoli GHD, Rezende DVB, Martins MA, Neves ICO, de Resende JV, Carvalho EEN, de Barros Vilas Boas EV, de Oliveira JR, Franco M (2019) Study of morphological properties and rheological parameters of cellulose nanofibrils of cocoa shell (*Theobroma cacao* L.). *Carbohydr Polym* 214:152–158. <https://doi.org/10.1016/j.carbpol.2019.03.037>
- Souza EF, Furtado MR, Carvalho CWP, Freitas-Silva O, Gottschalk LMF (2020) Production and characterization of Gluconacetobacter xylinus bacterial cellulose using cashew apple juice and soybean molasses. *Int J Biol Macromol* 146:285–289. <https://doi.org/10.1016/j.ijbiomac.2019.12.180>
- Sundarraaj AA, Ranganathan TV (2018) A review on cellulose and its utilization from agro-industrial waste. *Drug Inven Today* 10(2018b):89–94
- Taurino R, De Bortoli LS, Schabbach ML, Bondioli F (2020) Development of glass-stalks-unsaturated polyester hybrid composites. *Compos Commun* 22. <https://doi.org/10.1016/j.coco.2020.100428>
- Teixeira EM, Tsuzuki N, Fernandes AC, Martins RM (2015) Produção Agroindustrial: noções de processos, tecnologias de fabricação de alimentos de origem animal e vegetal e gestão industrial (1st ed.). Erica
- Teuber R, Jensen JD (2020) Definitions, measurement, and drivers of food loss and waste. *Food Ind Wastes* 3–18. <https://doi.org/10.1016/b978-0-12-817121-9.00001-2>
- Textile Exchange (2019) Corporate fiber & materials benchmark
- Textile Horizons International (1993) Cleaner production. *Textile Horiz Int* 13. <https://doi.org/10.1201/b13145-7>
- Tobler-Rohr MI (2011) The supply chain of textiles. *Handbook of Sustainable Textile Production* 45–149. <https://doi.org/10.1533/9780857092861.45>
- Torrezan R, Cascelli SMF, Diniz JD de AS (2017) Agroindústria familiar: aspectos a serem considerados na sua implantação. <http://ainfo.cnptia.embrapa.br/digital/bitstream/item/165331/1/ABC-AGR-FAMILIAR-Agroindustria-familiar-aspectos-a-serem-considerados-na-sua-implantacao-ed-01-2017.pdf>
- Travalini AP, Prestes E, Pinheiro LA, Demiate IM (2018) Extraction and characterization of nanocrystalline cellulose from cassava bagasse. *J Polym Environ* 26(2):789–797. <https://doi.org/10.1007/s10924-017-0983-8>
- United Nations Environment Programme (2021) Food Waste Index
- Vale AT et al (2007) Caracterização energética e rendimento da carbonização de resíduos de grãos de café e de madeira. *Lavras: UFLA*, 416–420
- Vieira Amorim F, José Ribeiro Padilha R, Maria Vinhas G, Ramos Luiz M, Costa de Souza N, Medeiros Bastos de Almeida Y (2021) Development of hydrophobic polyurethane/castor oil biocomposites with agroindustrial residues for sorption of oils and organic solvents. *J Colloid Interface Sci* 581:442–454. <https://doi.org/10.1016/j.jcis.2020.07.091>
- Vieira JER, Vieira ACP (2019) Diagnóstico e desafios da Agricultura Brasileira
- Villar da Gama BM, Elisandra do Nascimento G, Silva Sales DC, Rodríguez-Díaz JM, Bezerra de Menezes Barbosa CM, Menezes Bezerra Duarte MM (2018) Mono and binary component

- adsorption of phenol and cadmium using adsorbent derived from peanut shells. *J Clean Prod* 201:219–228. <https://doi.org/10.1016/j.jclepro.2018.07.291>
- Vivien, F.-D. (2011). *Economia e Ecologia*. SENAC SP.
- Warner F (1980) Current constraints. *EFCE Publ Ser (Eur Fed Chem Eng)* 14:3–15. <https://doi.org/10.1016/b978-0-12-455250-0.50006-2>
- Wataya CH, Lima RA, Oliveira RR, Moura EAB (2016) Mechanical, morphological and thermal properties of AÇAÍ fibers reinforced biodegradable polymer composites. In: *Characterization of Minerals, Metals, and Materials 2015*. https://doi.org/10.1007/978-3-319-48191-3_33
- Wataya CH, Lima RA, Oliveira RR, Moura EAB (2015) Mechanical, morphological and thermal properties of Açaí fibers reinforced biodegradable polymer composites. *TMS Annual Meeting, 2015-Janua(January)*, 265–272. <https://doi.org/10.1002/978119093404.ch33>
- Wiesmeth H (2021) The economics of the waste hierarchy. *Implement Circ Econ Sustain Dev* 213–225. <https://doi.org/10.1016/b978-0-12-821798-6.00018-1>
- Wilts H, Schinkel J, Koop C (2020) Effectiveness and efficiency of food-waste prevention policies, circular economy, and food industry. In: *Food Industry Wastes. INC*. <https://doi.org/10.1016/b978-0-12-817121-9.00002-4>
- Wong C, Parviainen J, Xue AS, Beddari E, Ramanathan M, Birch E, Rota C, Ji CR, Tuft N, Shen X (2021) *Fashion Sustainability Report 2021*
- WRAP (2009) Household food and drink waste in the UK. report prepared by WRAP (Issue November)
- Yu J (2009) Production of green bioplastics from agri-food chain residues and co-products. *Handbook of waste management and co-product recovery in food processing* 2:515–536. <https://doi.org/10.1533/9781845697051.4.515>
- Yusuf AA, Peter O, Hassan AS, Tunji LA, Oyagbola IA, Mustafa MM, Yusuf DA (2019) Municipality solid waste management system for Mukono District, Uganda. *Procedia Manuf* 35:613–622. <https://doi.org/10.1016/j.promfg.2019.06.003>
- Zaro M (2018) Desperdício de alimentos : velhos hábitos , novos desafios. In: *Desperdício de Alimentos, Velhos Hábitos, Novos Desafios*
- Zavarize DG (2021) Insights on preparation and characteristics of KOH-doped carbons derived from an abundant agroindustrial waste in Brazil: Amazon açaí berry seeds. *Bioresour Technol Rep* 13. <https://doi.org/10.1016/j.biteb.2020.100611>
- Zeferino M (2019) *Mais Algodão no Mercado Brasileiro*. Secretaria de Agricultura e Abastecimento-Instituto de Economia Agrícola (IEA). <http://www.iea.agricultura.sp.gov.br/out/LerTexto.php?codTexto=14573>

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.