



## Data Article

# Dataset on ten-years monitoring of MSWI bottom ashes in six MSWI plants in the Canton of Zürich, Switzerland



Andreas Glauser<sup>a,\*</sup>, Leo S. Morf<sup>b</sup>, Gisela Weibel<sup>a,c</sup>,  
Urs Eggenberger<sup>a</sup>

<sup>a</sup> Institut für Geologie, Universität Bern, Switzerland

<sup>b</sup> Baudirektion Kanton Zürich, Amt für Abfall, Wasser, Energie und Luft, Zürich, Switzerland

<sup>c</sup> Zentrum für nachhaltige Abfall- und Ressourcennutzung ZAR, Hinwil, Switzerland

## ARTICLE INFO

*Article history:*

Received 10 August 2020

Accepted 27 August 2020

Available online 4 September 2020

*Keywords:*

Municipal solid waste incineration

Bottom ash

Monitoring

Chemical analysis

Batch leaching test

## ABSTRACT

The dataset presented in this article is the supplementary data for the research article “Ten-years monitoring of MSWI bottom ashes with focus on TOC development and leaching behaviour” (<https://doi.org/10.1016/j.wasman.2020.07.038>) by Glauser et al. (2020) [1]. From 2008–2018 bottom ashes have been monitored in six MSWI plants in the Canton of Zürich with regular sampling campaigns and analysis of important species defined in the Swiss Waste Legislation [2]. Both the size of the dataset and the long period of consistent and representative monitoring are unique for Switzerland. Relevant aspects of the monitoring data are discussed and interpreted in the above mentioned research article and complemented by simple emission forecast modelling. While only selected species were discussed in the research article, this data article covers all the monitoring data. The focus of the monitoring was laid on carbon-species with the analysis of total carbon (TC), total organic carbon (TOC), total inorganic carbon (TIC), degradable organic carbon (OC) and elemental carbon (EC). Total contents of nitrogen (N), sulphur (S), phosphorus (P), selected heavy metals (As, Cd, Cr, Cu, Ni, Pb, Sb and Zn) and loss on ignition (LOI) complete the solid chem-

DOI of original article: [10.1016/j.wasman.2020.07.038](https://doi.org/10.1016/j.wasman.2020.07.038)

\* Corresponding author.

E-mail address: [andreas.glauser@geo.unibe.ch](mailto:andreas.glauser@geo.unibe.ch) (A. Glauser).

<https://doi.org/10.1016/j.dib.2020.106261>

2352-3409/© 2020 The Author(s). Published by Elsevier Inc. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>)

ical analysis. In addition, particulate ferrous (Fe) and non-ferrous (NF) metals and unburnt material were determined manually. Batch eluate tests according to Swiss Waste Legislation [3] were performed and analysed for dissolved organic carbon (DOC), ammonium ( $\text{NH}_4^+$ ), nitrite ( $\text{NO}_2^-$ ), fluoride ( $\text{F}^-$ ), sulphite ( $\text{SO}_3^{2-}$ ), sulphide ( $\text{S}_2^-$ ), chromate Cr(IV) and the heavy metals Cu (aq) and Zn (aq) and Cr(IV). In addition, data on the biochemical oxygen demand (BOD) and the physical parameters pH and electrical conductivity complete the eluate analysis.

© 2020 The Author(s). Published by Elsevier Inc.

This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>)

## Specifications Table

Subject	Waste Management and Disposal
Specific subject area	MSWI bottom ash, representative sampling, chemical analysis, batch eluate tests
Type of data	Table
How data were acquired	Solid chemical analysis: <ul style="list-style-type: none"> <li>• Cr, Cu, Ni, P, Pb and Zn with ICP-OES (ISO 11885, 2007) [4]</li> <li>• As, Cd and Sb with ICP-MS (EN ISO 17294-2, 2016) [5]</li> <li>• TC, TOC, TIC, N and S with CHNS-analysis (EN 15936, 2012) [6]</li> <li>• OC and EC with temperature-dependent combustion of carbon (DIN 19539, 2016) [7]</li> <li>• Loss on ignition (LOI) at 550°C for 2 h in muffle furnace</li> <li>• Fe- and NE-metal content and unburnt material by manual magnetic and optical separation</li> </ul>
	Analysis of eluate behaviour: <ul style="list-style-type: none"> <li>• Cr(IV), Cu (aq) and Zn (aq) with ICP-MS (EN ISO 17294-2, 2016) [5]</li> <li>• DOC with thermal oxidation (EN 1484, 1997) [8]</li> <li>• <math>\text{NH}_4^+</math> and <math>\text{NO}_2^-</math> with photometry (DIN 38406-5, 1983) [9]</li> <li>• <math>\text{SO}_3^{2-}</math> and <math>\text{S}_2^-</math> with polarography (Metrohm Appl. 99/1)</li> <li>• <math>\text{F}^-</math> with ion-sensitive electrode in water samples and digestions (DIN 38405-1, 1985 and ISO 10304-1, 2007) [10, 11]</li> <li>• BOD 5 days respirometric measurement (Oxitop-system)</li> <li>• Electrical conductivity (El. Cond) with a 5-ring conductivity measuring cell (<math>c = 1.0 \text{ cm}^{-1}</math>)</li> <li>• pH with an Aquatorde plus</li> </ul>
Data format	Raw
Parameters for data collection	Bottom ash was sampled regularly for monthly periods in six MSWI plants. Subsequently the monthly composite samples were homogenised, and crushed in order to reduce the amount of material and to acquire the grain size needed for analysis.
Description of data collection	For solid chemical analysis, bottom ash was dried at 105°C, crushed to <1 mm and milled to <0.1 mm. Total digestion was performed for analysis with ICP-OES and MS. For CHNS-analysis, the material <0.1 mm was combusted. Batch elute tests were performed on bottom ash in its original condition, crushed to <5 mm. The test consists of two parts, each with a liquid to solid (L/S) ratio of 10 and a duration of 24 h. One part (Test 1) is performed with $\text{CO}_2$ -saturated water for the analysis of heavy metals. The other part (Test 2) is performed with deionised water, for the analysis of all other constituents (incl. Cr(IV)).

(continued on next page)

---

Data source location	MSWI Plants A-F, Canton of Zürich, Switzerland
Data accessibility	Data are accessible with the article
Related research article	Glauser et al. (2020), Ten-years monitoring of MSWI bottom ashes with focus on TOC development and leaching behaviour, Waste Management ( <a href="https://doi.org/10.1016/j.wasman.2020.07.038">https://doi.org/10.1016/j.wasman.2020.07.038</a> ) [1]

---

## Value of the Data

- The data derive from a systematic and representative monitoring over ten years of bottom ashes identically applied in six Swiss MSWI plants. The extent of the dataset and the systematic of sampling are unique for bottom ash.
- Beneficiaries of these data include researchers, authorities, MSWI plant operators and others involved in waste management.
- The data is of value for the ongoing political discussion in Switzerland regarding legislation of bottom ash quality requirements. The dataset further serves as a basis for comparison with other bottom ashes worldwide and helps to estimate potential for bottom ash quality improvements.
- Thanks to the long sampling period at six different MSWI plants temporal trends and correlations between parameters can be derived from these data. In addition, the data serve as a basis for further studies such as the investigation of long-term behaviour using geochemical modelling.

## 1. Data Description

In Switzerland, bottom ash has to be deposited on landfills due to elevated total contents of pollutants, such as heavy metals and TOC. With the periodic measurements presented in this dataset, the Canton of Zürich monitors the development of bottom ash quality of all six MSWI plants. For technical details of the concerning MSWI plants in the Canton of Zürich refer to [1].

The results of the monitoring of each plant are presented in Table 1–6 as well as in a supplementary excel file and are structured as follows:

- Results of the solid chemical analysis
- Results of the batch eluate tests

The results are listed in Table 1–6, in the following order: Table 1: Plant A, Table 2: Plant B, Table 3: Plant C, Table 4: Plant D, Table 5: Plant E, Table 6: Plant F. Parameters that have not been analysed in one of the measurement campaigns are indicated with “not sampled” (n.s.).

## 2. Experimental Design, Materials, and Methods

Sampling campaigns were performed from 2008–2018 generally on a four month interval at all six MSWI plants with identical sampling procedure. During selected months, at least 20 sub-samples of ~12 kg of untreated bottom ash have been sampled on working days over all furnace lines. Samples were collected on the conveyor belt directly after wet or dry discharge and stored in an air-tight container. At the end of the month, this composite sample has been homogenised and split into two representative samples of ~12 kg. One composite-sample was retained, while the other was split in two parts, which were used for (1) solid chemical analysis and (2) batch eluate tests. The preparation of the material for these two purposes was performed differently: (1) the material was dried at 105°C and subsequently crushed to a grain size <1 mm, while metals and unburnt material were manually separated. In an additional step the material was milled to <0.1 mm using a planetary ball mills. (2) The material was sieved at 5 mm in its

**Table 1**  
Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant A in the Canton of Zürich, Switzerland.

		Plant A														
Parameter	Unit	Jan 2008	June 2008	Dec 2008	Mar 2010	June 2010	Nov 2010	Feb 2011	June 2011	Sept 2011	Jan 2012	May 2012	Oct 2012	Mar 2013	Oct 2013	Dec 2013
<b>Solid chemical analysis</b>																
Dry substance (105°C)	wt.-%	98.5	99.9	99.9	99.9	99.9	n.s.	n.s.	n.s.	n.s.	99.9	n.s.	n.s.	100	100	99.8
LOI (550°C)	wt.-%	n.s.	100	99.8	99.9	99.0	n.s.	n.s.	n.s.	n.s.	99.8	n.s.	n.s.	99.4	99.5	99.2
Fe-Metals	wt.-%	n.s.	n.s.	n.s.	4.48	2.75	n.s.	n.s.	n.s.	n.s.	5.85	n.s.	n.s.	3.07	3.65	6.95
NF-Metals	wt.-%	n.s.	n.s.	n.s.	4.42	2.70	n.s.	n.s.	n.s.	n.s.	3.49	n.s.	n.s.	2.85	2.62	2.71
Unburnt material	wt.-%	n.s.	n.s.	n.s.	0.92	0.10	n.s.	n.s.	n.s.	n.s.	0.050	n.s.	n.s.	0.050	0.050	0.169
TIC	wt.-%	0.775	0.900	n.s.	0.932	0.720	n.s.	n.s.	n.s.	n.s.	0.650	n.s.	n.s.	0.685	0.517	0.890
TOC	wt.-%	0.357	0.260	0.528	0.328	0.269	n.s.	n.s.	n.s.	n.s.	0.387	n.s.	n.s.	0.685	0.443	0.405
OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.104	n.s.	n.s.	0.177	0.186	0.179
TiC	wt.-%	n.s.	n.s.	n.s.	0.654	0.367	n.s.	n.s.	n.s.	n.s.	0.298	n.s.	n.s.	0.199	0.370	0.475
N	wt.-%	0.083	0.145	0.065	0.568	0.116	n.s.	n.s.	n.s.	n.s.	0.010	n.s.	n.s.	0.013	0.013	0.013
P	wt.-%	1.22	1.38	0.989	1.51	0.632	n.s.	n.s.	n.s.	n.s.	0.951	n.s.	n.s.	0.769	0.496	1.006
S	wt.-%	9.884	11.998	9.263	8.912	8.951	n.s.	n.s.	n.s.	n.s.	8.495	n.s.	n.s.	12.968	9.921	9.103
As	mg/kg	n.s.	n.s.	30.4	30.9	27.7	n.s.	n.s.	n.s.	n.s.	24.2	n.s.	n.s.	22.9	26.3	29.5
Cd	mg/kg	5.91	3.76	5.65	5.36	8.98	n.s.	n.s.	n.s.	n.s.	7.08	n.s.	n.s.	3.74	4.07	4.34
Cr	mg/kg	n.s.	n.s.	n.s.	839	843	n.s.	n.s.	n.s.	n.s.	1317	n.s.	n.s.	592	817	768
Cu	mg/kg	6375	7048	6764	9854	11927	n.s.	n.s.	n.s.	n.s.	10730	n.s.	n.s.	7900	8674	7156
Ni	mg/kg	338	260	347	377	589	n.s.	n.s.	n.s.	n.s.	661	n.s.	n.s.	366	432	388
Pb	mg/kg	1502	4615	1413	1706	2125	n.s.	n.s.	n.s.	n.s.	1854	n.s.	n.s.	1210	1135	1491
Sb	mg/kg	n.s.	n.s.	269	179	321	n.s.	n.s.	n.s.	n.s.	272	n.s.	n.s.	104	173	137
Zn	mg/kg	4796	4528	4159	4507	6800	n.s.	n.s.	n.s.	n.s.	7118	n.s.	n.s.	4318	5143	6092
El. Cond	µS/cm	n.s.	n.s.	5870	n.s.	6738	n.s.	n.s.	n.s.	n.s.	9705	n.s.	n.s.	8956	10595	8935
pH (Test 1)	-	n.s.	n.s.	n.s.	n.s.	6.65	n.s.	n.s.	n.s.	n.s.	6.95	n.s.	n.s.	6.64	6.78	6.60
pH (Test 2)	-	n.s.	12.2	n.s.	n.s.	11.8	n.s.	n.s.	n.s.	n.s.	12.5	n.s.	n.s.	12.5	12.6	12.5
Dry substance (p. 0.1 µm)	mg/l	n.s.	n.s.	n.s.	n.s.	2914	n.s.	n.s.	n.s.	n.s.	3057	n.s.	n.s.	3261	3408	3343
<b>Batch eluate test</b>																
DOC	mg/l	n.s.	3.18	0.275	n.s.	0.24	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	7.72	6.37	14.5
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	n.s.	2.07	2.46	n.s.	3.91	n.s.	n.s.	n.s.	n.s.	3.89	n.s.	n.s.	3.27	1.77	1.43
Ammonium-N	mg N/l	n.s.	n.s.	n.s.	n.s.	3.04	n.s.	n.s.	n.s.	n.s.	3.03	n.s.	n.s.	2.54	1.38	1.12
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	n.s.	0.031	0.091	n.s.	0.041	n.s.	n.s.	n.s.	n.s.	0.068	n.s.	n.s.	0.031	0.033	0.032
Fluoride (F <sup>-</sup> )	mg/l	n.s.	n.s.	n.s.	n.s.	1.95	n.s.	n.s.	n.s.	n.s.	1.65	n.s.	n.s.	0.760	1.19	0.690
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	n.s.	n.s.	n.s.	n.s.	0.220	n.s.	n.s.	n.s.	n.s.	1.40	n.s.	n.s.	0.010	0.010	0.013
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	n.s.	n.s.	n.s.	n.s.	3.24	n.s.	n.s.	n.s.	n.s.	2.82	n.s.	n.s.	3.14	2.06	0.660
Cr(VI)	mg/l	n.s.	n.s.	0.075	n.s.	0.041	n.s.	n.s.	n.s.	n.s.	0.186	n.s.	n.s.	0.184	0.139	0.102
Cu	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.558	0.321	0.163	n.s.	0.601	n.s.	0.864
Cu (aq + CO <sub>2</sub> )	mg/l	0.002	0.002	0.002	n.s.	0.004	n.s.	n.s.	n.s.	n.s.	0.003	n.s.	n.s.	n.s.	0.012	n.s.
Zn (aq + CO <sub>2</sub> )	mg/l	2.02	1.55	n.s.	n.s.	2.91	n.s.	n.s.	n.s.	n.s.	4.64	n.s.	n.s.	0.670	2.36	2.43
BOD 5 days	mg O <sub>2</sub> /l	n.s.	n.s.	n.s.	n.s.	11.0	n.s.	n.s.	n.s.	n.s.	9.43	n.s.	n.s.	8.00	3.20	14.1
<b>Solid chemical analysis</b>																
Dry substance (105°C)	wt.-%	99.8	100	100	100	n.s.	99.7	100	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
LOI (550°C)	wt.-%	99.2	98.5	99.6	98.8	n.s.	100	99.4	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Fe-Metals	wt.-%	5.58	4.28	7.04	6.04	n.s.	7.29	6.16	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
NF-Metals	wt.-%	2.71	2.68	3.18	2.76	n.s.	3.00	3.31	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Unburnt material	wt.-%	0.204	0.950	0.990	0.090	n.s.	0.950	0.050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
TIC	wt.-%	0.803	0.582	0.785	0.734	n.s.	0.694	0.904	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
TOC	wt.-%	0.425	0.475	0.288	0.352	n.s.	0.371	0.468	0.340	n.s.	n.s.	n.s.	0.340	0.225	n.s.	0.225
OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
TiC	wt.-%	0.378	0.127	0.470	0.410	n.s.	0.290	0.480	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
N	wt.-%	0.023	0.023	0.016	0.049	n.s.	0.019	0.026	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
S	wt.-%	0.786	0.754	0.687	0.710	n.s.	0.616	0.677	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
P	mg/kg	8563	9716	10810	12340	n.s.	5007	5162	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
As	mg/kg	25.4	20.3	23.4	25.4	n.s.	25.3	27.9	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cd	mg/kg	4.08	7.68	2.60	3.93	n.s.	4.68	3.83	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cr	mg/kg	934	792	908	765	n.s.	979	905	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cu	mg/kg	7300	8953	8815	7881	n.s.	7116	10108	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Ni	mg/kg	522	439	489	556	n.s.	508	462	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Pb	mg/kg	1682	1153	1539	1481	n.s.	1190	1509	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Sb	mg/kg	203	174	171	158	n.s.	162	166	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Zn	mg/kg	5293	6018	5345	5028	n.s.	5394	5262	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
El. Cond	µS/cm	9647	5345	4707	8918	n.s.	4669	4943	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
pH (Test 1)	-	6.75	6.68	6.72	6.79	n.s.	6.60	6.65	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
pH (Test 2)	-	12.6	12.3	12.1	12.2	n.s.	11.9	11.9	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Dry substance (p. 0.1 µm)	mg/l	3076	1804	1725	3077	n.s.	2004	2107	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
<b>Batch eluate test</b>																
DOC	mg/l	9.42	2.74	5.64	11.0	n.s.	5.20	4.26	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	3.84	2.34	3.03	4.05	n.s.	1.83	2.77	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Ammonium-N	mg N/l	2.98	1.81	2.36	3.62	n.s.	1.44	2.15	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.040	0.021	0.044	0.061	n.s.	0.044	0.032	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Fluoride (F <sup>-</sup> )	mg/l	0.810	1.09	0.660	0.790	n.s.	0.820	0.860	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.010	0.010	0.010	0.010	n.s.	0.010	0.010	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	6.19	0.400	0.670	5.37	n.s.	0.250	1.00	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cr(VI)	mg/l	0.213	0.143	0.114	0.142	n.s.	0.171	0.343	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cu (aq)	mg/l	0.214	0.252	0.171	0.114	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cu (aq + CO <sub>2</sub> )	mg/l	0.002	0.002	0.002	0.002	n.s.	0.002	0.002	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Zn (aq + CO <sub>2</sub> )	mg/l	1.26	1.20	1.09	1.21	n.s.	n.s.	1.67	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
BOD 5 days	mg O <sub>2</sub> /l	3.65	1.47	17.0	14.3	n.s.	n.s.	3.25	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.

n.s. = not sampled

original condition, while particles >5 mm were crushed and metals and unburnt material were manually separated. Subsequently the crushed bottom ash was mixed with the material portion <5 mm.

Analysis of the bottom ash was based on the criteria of the Swiss Waste Ordinance according to certified procedures [12]. Only TOC, being the parameter of main interest, was monitored during the entire period from 2008–2018. The other C-constituents, N, S, P, heavy metals (As, Cd, Cr, Cu, Ni, Pb, Sb and Zn) and the eluate composition were only measured in the period 2008–2015, OC and EC only from 2011–2013.

For solid chemical analysis test portions of 0.5 g bottom ash <0.1 mm were digested with a mixture of 3 ml hydrochloric acid, 8 ml nitric acid and 3 ml hydrofluoric acid. Free hydrofluoric

**Table 2**

Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant B in the Canton of Zürich, Switzerland.

		Plant B																
Parameter	Unit	Jan 2008	July 2009	Dec 2009	Mar 2010	June 2010	Dec 2010	Mar 2011	June 2011	Sept 2011	Jan 2012	May 2012	Oct 2012	Mar 2013	July 2013	Nov 2013		
Solid chemical analysis	Dry substance (105°C)	wt.-%	80.0	80.9	79.3	79.4	78.3	79.5	76.7	78.4	75.9	76.6	79.9	74.8	78.0	80.0	79.9	
	LOI (550°C)	wt.-%	97.0	96.8	97.6	96.8	97.1	97.8	97.3	96.2	96.8	96.9	96.1	97.2	96.1	97.0	96.0	
	Fe-Metals	wt.-%	3.79	9.41	4.26	5.09	3.75	3.24	2.33	2.09	3.30	4.77	2.80	1.51	1.37	4.44	4.33	
	NF-Metals	wt.-%	3.12	3.11	3.73	3.28	2.97	3.48	3.30	3.09	3.97	3.26	3.64	2.13	2.45	3.09	3.40	
	Unburnt material	wt.-%	0.270	0.105	0.035	0.116	0.030	0.015	0.050	0.050	0.050	0.050	0.050	0.050	0.050	0.200	0.135	
	TIC	wt.-%	2.20	1.74	1.68	1.70	1.53	1.53	1.55	1.50	1.51	1.53	1.30	1.72	1.57	1.47	1.66	
	TOC	wt.-%	1.49	1.05	1.06	1.01	0.725	0.835	0.810	0.945	0.720	0.810	0.690	0.930	1.03	0.825	0.890	
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.345	0.445	0.360	0.440	0.606	0.361	0.462	
	TiC	wt.-%	n.s.	0.608	0.540	0.685	0.615	0.695	0.735	0.645	0.790	0.270	0.605	0.780	0.635	0.645	0.785	
	N	wt.-%	0.125	0.073	0.085	0.100	0.055	0.065	0.065	0.045	0.070	0.065	0.010	0.045	0.020	0.015	0.060	
	S	wt.-%	1.05	0.719	0.995	0.789	0.720	0.990	0.545	0.490	0.430	0.840	0.220	0.799	0.775	0.799	0.290	
	P	mg/kg	n.s.	13025	11900	19950	13450	10140	11230	8050	13950	14000	12200	14200	11800	11900	12600	
	Batch eluate test	As	mg/kg	n.s.	n.s.	30.0	39.1	26.5	30.6	30.4	24.8	23.7	24.6	30.3	30.0	22.4	20.9	28.8
		Cd	mg/kg	6.01	7.21	27.1	36.0	5.34	5.33	4.21	6.81	3.39	3.82	4.02	4.30	4.95	3.60	28.5
Cr		mg/kg	872	790	887	1046	617	697	441	539	555	521	495	455	568	428	572	
Cu		mg/kg	11050	5385	6400	7335	5735	6405	5910	5750	5090	4975	7455	5020	7130	4505	4240	
Ni		mg/kg	440	312	580	435	342	377	211	291	243	264	445	250	338	376	281	
Pb		mg/kg	1735	1950	1545	1965	848	1995	1655	1000	1480	878	2170	2530	1700	1005	1160	
Sb		mg/kg	n.s.	n.s.	324	324	176	179	139	180	147	155	133	114	163	112	111	
Zn		mg/kg	8655	5963	5440	5130	4215	4625	3845	4130	4100	4190	4245	4515	3975	3060	3340	
El. Cond		µS/cm	2740	4543	8705	8360	7495	9500	9115	4925	6915	7275	7245	4900	6900	8270	7440	
pH (Test 1)		-	n.s.	6.84	6.98	6.69	7.09	7.27	7.20	7.47	7.29	7.16	6.87	7.45	6.91	7.04	6.71	
pH (Test 2)		-	n.s.	12.2	13.0	12.5	12.4	12.4	12.4	12.1	12.4	12.5	12.4	12.6	12.3	12.1	12.5	
Dry substance (n 0.1 l)		mg/l	1087	1610	2770	2870	2400	3195	2910	1955	2195	2315	2205	3080	2125	2915	2485	
DOC		mg/l	42.2	32.8	32.0	36.5	77.0	77.0	64.5	57.0	64.5	57.0	82.5	95.0	72.5	69.0	71.0	
Batch eluate test		Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	3.37	2.23	5.05	5.69	9.95	9.91	6.38	6.73	5.18	11.6	6.80	8.90	6.78	4.41	4.47
	Ammonium-N	mg N/l	n.s.	1.73	3.93	4.42	7.70	3.04	4.96	5.24	4.03	8.96	5.29	6.85	5.28	3.43	4.25	
	Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.044	0.102	0.089	0.138	0.091	0.039	0.047	0.031	0.050	0.171	0.046	0.072	0.180	0.039	0.045	
	Fluoride (F <sup>-</sup> )	mg/l	4.45	0.425	1.55	0.550	0.800	0.750	1.25	0.600	0.450	0.450	0.400	0.550	0.500	0.500	0.450	
	Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.100	0.140	0.200	0.100	0.550	0.100	0.100	1.00	0.500	1.00	0.010	0.010	0.010	0.010	0.100	
	Sulfate (SO <sub>4</sub> <sup>2-</sup> )	mg/l	1.30	1.05	2.15	0.750	0.300	1.50	0.100	0.300	0.550	0.300	0.100	0.100	0.100	0.100	0.100	
	Cr (IV)	mg/l	0.007	0.022	0.031	0.036	0.040	0.028	0.031	0.003	0.008	0.013	0.046	0.038	0.012	0.032	0.006	
	Cu (aq)	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	1.51	2.79	2.17	1.45	1.93	
	Cu (aq + CO <sub>2</sub> )	mg/l	1.22	0.841	1.03	1.48	1.37	1.23	0.986	0.915	0.871	1.55	1.17	1.65	1.76	1.09	1.21	
	Zn (aq + CO <sub>2</sub> )	mg/l	6.77	5.30	3.03	2.14	3.05	3.41	1.47	1.56	1.89	2.88	3.61	1.74	1.76	1.73	1.51	
	BOD 5 days	mg O <sub>2</sub> /l	n.s.	n.s.	55.5	67.0	88.0	44.0	76.0	77.0	64.5	88.5	57.0	89.5	93.5	70.0	77.5	

n.s. = not sampled

acid was bound with boric acid and the mixture subsequently heated in three steps to 175°C using a high-pressure microwave system. In this total digest Cr, Cu, Ni, P, Pb and Zn were determined by inductively coupled plasma optical emission spectroscopy (ICP-OES) (ISO 11885, 2007) [4] using a Thermo Fisher Scientific iCap 7400 Duo Full MFC (Dual View). The heavy metals As, Cd and Sb were determined by inductively coupled plasma mass spectroscopy (ICP-MS) (EN ISO 17294-2, 2016) [5] using a Agilent Technologies 7900. Total contents of C, N and S were determined using a EuroEA3000 CHNS-analyser by Hekatech with the software Callidus according to EN 15936, 2012 [6]. The composition of C was additionally characterised by TOC and TIC with the same method as used for TC. Further, applying another method based on temperature-dependent combustion of carbon (DIN 19539, 2016) [7] using a Primacs SCN-100 analyser, the

**Table 3**  
Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant C in the Canton of Zürich, Switzerland.

		Plant C															
Parameter	Unit	Jan 2008	June 2009	Dec 2009	Apr 2010	June 2010	Nov 2011	Jan 2011	May 2011	Sept 2011	Jan 2012	May 2012	Sept 2012	Jan 2013	May 2013	Sept 2013	
<b>Solid chemical analysis</b>																	
Dry substance (105°C)	wt.-%	79.0	75.2	71.8	78.2	80.0	80.0	83.0	87.8	74.7	77.5	84.7	75.5	73.4	72.9	76.4	
LOI (550°C)	wt.-%	96.4	96.3	97.2	96.7	97.8	98.3	96.2	98.4	97.0	97.7	97.8	95.4	96.2	97.3	96.1	
Fe-Metals	wt.-%	11.8	6.27	8.76	2.64	1.75	3.35	5.53	2.64	2.40	3.37	2.13	1.49	3.17	3.38	2.72	
NF-Metals	wt.-%	2.44	2.38	4.05	2.85	2.26	2.87	2.68	2.77	3.29	3.70	2.34	1.78	3.34	5.29	4.14	
Unburnt material	wt.-%	0.360	0.200	0.020	0.040	0.040	0.050	0.050	0.060	0.150	0.050	0.050	0.050	0.050	0.160	0.480	
TIC	wt.-%	2.20	1.83	2.34	1.94	1.69	1.74	1.61	1.06	1.68	1.72	1.22	1.88	1.58	1.65	2.44	
TOC	wt.-%	1.05	1.03	1.44	1.34	0.990	0.920	0.980	0.500	0.820	1.12	0.730	1.08	1.36	1.13	1.61	
OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.080	0.180	0.390	0.160	0.310	0.415	0.272	0.741	
TiC	wt.-%	n.s.	0.805	0.900	0.600	0.970	0.050	0.630	0.560	0.860	0.600	0.490	0.800	0.330	0.500	0.830	
N	wt.-%	0.100	0.055	0.080	0.120	0.030	0.750	0.060	0.010	0.030	0.090	0.010	0.010	0.010	0.010	0.050	
S	wt.-%	2.00	1.25	1.54	1.70	0.950	1.00	0.870	0.720	0.830	0.890	0.910	0.820	0.900	0.980	0.960	
P	wt.-%	4.705	3.960	4.410	3.990	2.630	3.960	4.130	3.180	3.640	3.580	3.950	3.270	3.130	2.960		
As	mg/kg	n.s.	n.s.	27.9	26.2	15.4	20.6	19.3	16.7	18.3	32.3	17.0	23.5	31.4	23.1	116	
Cd	mg/kg	7.00	5.44	2.52	4.23	6.91	2.34	2.37	2.10	7.01	4.36	7.39	2.63	2.79	4.41	6.01	
Cr	mg/kg	581	590	565	803	522	462	377	724	639	495	537	494	1040	475	559	
Cu	mg/kg	5010	3055	1810	3380	2930	5000	3530	5830	3810	3640	3820	4240	4080	3880	4530	
Ni	mg/kg	195	143	161	331	169	142	171	252	217	197	179	260	381	158	235	
Pb	mg/kg	1225	2080	1050	1690	1880	1250	1380	1940	2210	1430	952	1380	1850	584	1130	
Sb	mg/kg	n.s.	n.s.	142	141	142	85.6	94.3	185	100	102	89.3	89.5	147	107	140	
Zn	mg/kg	3045	3005	1920	3330	2620	3110	2760	4210	3490	3200	2850	2990	3830	2260	2940	
El. Cond	µS/cm	5300	7530	12000	8960	9360	9850	8950	7940	8930	9310	8990	8990	8760	9000	9120	
pH (Test 1)	-	n.s.	6.86	6.91	6.77	6.87	7.40	7.25	7.39	7.15	7.42	6.40	7.04	6.80	6.92	6.89	
pH (Test 2)	-	n.s.	12.4	13.1	12.3	12.0	12.4	12.5	12.4	12.3	12.4	12.3	12.2	12.5	12.6	12.5	
Dry substance (n.0.1 l)	mg/l	2035	1975	3790	2290	3190	3290	2870	2410	2550	3090	2910	2730	2760	2620	3000	
DOC	mg/l	220	150	170	170	140	83.0	87.0	93.0	144.0	103.0	24.0	65.0	65.0	53.0		
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	1.51	0.815	2.60	5.20	1.51	3.87	2.98	1.04	4.83	5.83	1.61	7.24	11.5	4.08	3.38	
Ammonium-N	mg N/l	1.17	0.630	2.02	4.04	1.17	3.01	2.31	0.810	3.76	4.53	1.25	5.63	8.96	3.17	2.63	
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.078	0.197	0.190	0.081	0.047	0.087	0.071	0.017	0.243	0.263	0.117	0.059	0.069	0.053	0.090	
Fluoride (F <sup>-</sup> )	mg/l	4.05	0.450	1.00	0.700	0.700	0.800	1.00	2.30	0.600	0.900	0.600	0.800	0.700	0.600	0.800	
Sulfate (S <sub>2</sub> O <sub>4</sub> <sup>2-</sup> )	mg/l	0.060	0.050	0.200	0.010	0.010	0.010	0.010	0.200	0.500	0.010	2.00	0.010	0.010	0.010	0.010	
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	0.450	0.850	2.20	0.100	0.600	4.40	0.400	0.700	0.100	0.100	0.200	0.100	0.100	0.400	0.500	
Cr(VI)	mg/l	0.012	0.006	n.s.	0.003	0.010	0.030	0.021	0.009	0.016	0.032	0.009	0.003	0.010	0.027	0.019	
Cu (aq)	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.550	1.32	1.99	1.30	0.960	
Cu (aq + CO <sub>2</sub> )	mg/l	0.363	0.573	0.002	0.801	0.725	0.010	0.643	0.372	0.986	1.46	0.702	1.36	1.58	0.899	1.02	
Zn (aq + CO <sub>2</sub> )	mg/l	9.27	3.05	1.73	3.41	1.29	1.72	2.06	2.37	1.89	3.35	1.12	1.57	3.84	1.24	3.81	
BOD 5 days	mg O <sub>2</sub> /l	n.s.	n.s.	12.0	72.0	46.0	86.0	85.0	11.0	69.0	86.0	31.0	69.0	58.0	58.0	78.0	
<b>Batch eluate test</b>																	
Parameter	Unit	Jan 2014	May 2014	Sept 2014	Jan 2015	May 2015	Sept 2015	Dec 2015	June 2016	Feb 2017	May 2017	Sept 2017	Jan 2018	May 2018	Oct 2018		
<b>Solid chemical analysis</b>																	
Dry substance (105°C)	wt.-%	75.7	82.3	79.6	76.7	82.2	80.3	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
LOI (550°C)	wt.-%	96.2	96.8	96.2	96.0	95.8	95.8	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Fe-Metals	wt.-%	2.53	4.54	3.47	3.41	2.09	5.00	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
NF-Metals	wt.-%	3.63	2.70	3.06	2.97	2.84	2.86	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Unburnt material	wt.-%	0.520	0.950	0.220	0.210	0.050	0.050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
TIC	wt.-%	1.43	1.26	1.99	1.84	1.28	1.57	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
TOC	wt.-%	0.830	0.750	1.27	1.07	0.630	0.850	n.s.	0.760	1.26	0.750	1.10	0.850	0.600	0.900		
OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
TiC	wt.-%	0.500	0.530	0.700	0.800	0.700	0.700	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
N	wt.-%	0.050	0.020	0.030	0.030	0.030	0.050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
S	wt.-%	0.780	0.760	1.03	0.630	0.850	0.720	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
P	mg/kg	3990	3470	3020	4110	3650	3280	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
As	mg/kg	24.7	27.8	42.0	22.9	18.6	28.2	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cd	mg/kg	4.81	5.10	3.21	11.0	6.86	3.11	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cr	mg/kg	661	495	481	572	339	560	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cu	mg/kg	5700	6230	4670	4280	4720	4860	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Ni	mg/kg	274	224	255	225	283	251	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Pb	mg/kg	1580	4790	1260	1940	1250	1510	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Sb	mg/kg	132	122	104	135	142	98.2	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Zn	mg/kg	3370	3490	3220	3740	3390	3050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
El. Cond	µS/cm	9150	9310	9220	9510	9490	8970	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
pH (Test 1)	-	6.73	6.49	6.78	6.90	6.58	6.79	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
pH (Test 2)	-	12.5	12.5	12.5	12.4	12.3	12.4	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Dry substance (n.0.1 l)	mg/l	2780	2760	3020	2090	2940	2970	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
DOC	mg/l	55.0	29.0	38.0	62.0	25.0	24.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	3.81	2.33	2.04	3.70	1.34	2.21	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Ammonium-N	mg N/l	2.96	1.81	1.59	2.88	1.04	1.72	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.078	0.026	0.038	0.101	0.040	0.055	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Fluoride (F <sup>-</sup> )	mg/l	0.600	0.500	0.600	0.900	0.800	0.800	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Sulfate (S <sub>2</sub> O <sub>4</sub> <sup>2-</sup> )	mg/l	0.010	0.010	0.010	0.010	0.010	0.010	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	0.100	0.300	8.00	0.100	0.200	0.100	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cr(VI)	mg/l	0.027	0.048	0.022	0.029	0.020	0.021	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cu (aq)	mg/l	1.01	0.646	0.912	1.27	0.722	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cu (aq + CO <sub>2</sub> )	mg/l	0.949	0.529	0.735	0.821	0.700	0.698	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Zn (aq + CO <sub>2</sub> )	mg/l	6.01	2.44	1.69	3.00	2.03	3.12	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
BOD 5 days	mg O <sub>2</sub> /l	21.0	22.0	41.0	80.0	25.0	36.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		

n.s. = not sampled

differentiation of TOC into degradable organic carbon (TOC400 or OC) and residual oxidisable carbon or elemental carbon (ROC or EC) was achieved. The TIC900, which is released from 4

**Table 4**

Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant D in the Canton of Zürich, Switzerland.

		Plant D																
Parameter	Unit	Feb 2008	Jan 2009	Dec 2009	Apr 2010	June 2010	Oct 2010	Feb 2011	July 2011	Oct 2011	Sept 2012	Dec 2012	Dec 2012	Mar 2013	May 2013	Sept 2013		
Solid chemical analysis	Dry substance (105°C)	wt.-%	83.0	76.0	63.5	78.8	79.0	79.5	75.0	77.6	69.9	82.0	77.8	81.0	76.5	79.4	81.7	
	LOI (550°C)	wt.-%	97.6	98.1	98.1	98.9	98.9	96.3	98.5	99.2	97.5	98.0	98.2	98.3	98.6	97.4	97.8	
	Fe-Metals	wt.-%	3.52	0.520	0.630	0.860	0.550	0.470	0.490	0.500	0.640	0.560	0.560	0.350	0.880	0.390	4.30	
	NF-Metals	wt.-%	0.10	0.890	1.42	1.52	1.63	0.870	0.850	1.40	1.23	1.28	1.22	0.820	0.980	0.970	2.12	
	Unburnt material	wt.-%	0.030	n.s.	0.030	0.010	n.s.	0.010	0.050	0.050	0.050	0.050	0.050	0.050	0.050	0.050	0.050	
	TIC	wt.-%	1.50	1.75	1.45	1.40	1.53	1.40	1.65	1.51	1.55	1.35	1.50	1.42	1.26	1.54	1.75	
	TOC	wt.-%	0.690	1.15	0.800	0.840	0.840	0.730	0.920	0.720	0.890	0.560	0.750	0.620	0.810	1.23	0.570	
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.120	0.120	0.220	0.040	0.144	0.183	0.714	
	TiC	wt.-%	n.s.	0.600	0.640	0.580	0.740	0.770	0.680	0.790	0.670	0.790	0.850	0.660	0.530	0.520	0.700	
	N	wt.-%	0.095	0.045	0.060	0.040	0.010	0.020	0.060	0.010	0.020	0.010	0.010	0.010	0.010	0.010	0.020	
	S	wt.-%	1.50	0.700	0.530	0.090	1.20	0.990	1.38	1.42	0.790	1.08	2.15	1.94	2.29	1.70	1.01	
	P	mg/kg	n.s.	4345	4160	4350	4170	4370	7900	4340	3320	3930	2970	2840	2740	2540	2310	
	Solid chemical analysis	As	mg/kg	n.s.	n.s.	18.2	22.9	17.1	20.4	27.2	16.2	19.3	19.9	19.9	18.6	19.7	16.2	20.4
		Cd	mg/kg	8.80	4.77	8.67	9.60	6.73	7.55	3.58	7.75	5.41	5.13	5.45	4.75	33.6	6.04	5.10
Cr		mg/kg	1350	742	756	563	658	627	1770	619	556	506	496	543	698	380	587	
Cu		mg/kg	8470	2560	3510	4790	2760	8180	13400	2900	2970	3060	5310	6230	5980	5860	6910	
Ni		mg/kg	481	227	260	339	321	351	1290	218	208	259	228	286	317	212	256	
Pb		mg/kg	4050	1775	1490	2220	1790	1450	1660	1050	991	1490	2090	1320	1360	1630	1350	
Sb		mg/kg	n.s.	n.s.	259	226	327	187	269	162	387	187	142	143	157	127	146	
Zn		mg/kg	4925	3495	5630	4490	3490	4420	7600	4360	3530	3590	4310	4240	5770	4130	3730	
Batch eluate test		El. Cond	µS/cm	6285	8105	7750	10900	10700	8710	10300	10100	9450	9760	11300	10900	11100	13100	10700
		pH (Test 1)	-	n.s.	6.61	6.95	6.41	6.99	7.04	7.25	8.24	7.01	6.66	6.84	6.73	6.70	6.50	6.51
		pH (Test 2)	-	n.s.	12.5	13.0	12.3	12.5	12.4	12.5	12.6	12.4	12.4	12.5	12.6	12.5	12.4	12.6
		Dry substance (n 0.1 l)	mg/l	2180	2100	2950	3960	4230	2150	2350	3730	2540	3320	4420	4350	4790	6320	3900
		DOC	mg/l	10.5	16.5	16.0	17.1	25.0	4.90	34.0	11.0	20.0	15.0	42.0	12.0	23.0	40.0	28.0
		Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	1.12	1.70	2.72	2.54	2.50	3.79	4.11	3.20	3.44	3.01	2.50	1.80	1.30	3.14	3.37
	Ammonium-N	mg N/l	n.s.	1.32	2.12	1.98	1.94	2.95	3.19	2.49	2.68	2.34	1.94	1.40	1.01	2.44	2.62	
	Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.076	0.234	0.156	0.248	0.048	0.017	0.054	0.031	0.037	0.041	0.053	0.019	0.023	0.037	0.057	
	Fluoride (F <sup>-</sup> )	mg/l	0.750	0.900	1.40	0.60	0.900	1.00	1.20	0.900	1.00	1.40	1.50	1.00	1.60	1.20	1.00	
	Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.010	0.200	0.200	0.010	0.100	0.010	0.100	0.500	1.00	0.010	0.010	0.010	0.010	0.010	0.010	
	Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	1.55	1.25	0.400	0.500	4.10	0.100	0.800	0.900	0.500	0.800	1.00	2.20	1.90	0.600	1.00	
	Cr(IV)	mg/l	0.040	0.007	0.005	0.011	0.032	0.030	0.037	0.037	0.066	0.021	0.031	0.033	0.031	0.035	0.030	
	Cu (aq)	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.495	1.38	0.771	1.18	1.01	
	Cu (aq + CO <sub>2</sub> )	mg/l	0.274	0.269	0.349	0.499	0.420	0.226	0.460	0.365	0.477	0.402	0.884	1.50	0.989	0.906	0.927	
Zn (aq + CO <sub>2</sub> )	mg/l	8.92	2.81	4.04	3.21	1.32	1.51	5.65	3.43	1.99	3.58	3.96	2.44	6.45	2.91	3.31		
BOD 5 days	mg O <sub>2</sub> /l	n.s.	n.s.	20.0	13.0	38.0	9.90	42.0	14.0	15.0	19.0	38.0	12.0	30.0	51.0	30.0		

n.s. = not sampled

mm in its original condition with deionised water for the determination of DOC, NH<sub>4</sub><sup>+</sup>, NO<sub>2</sub><sup>-</sup>, F<sup>-</sup>, SO<sub>3</sub><sup>2-</sup>, S<sub>2</sub><sup>-</sup>, Cr(IV) and Cu (aq). Saturation with CO<sub>2</sub> is achieved by continuous injection of ~50 mL CO<sub>2</sub>/min through a glass tube into the elution vessel. The analyses of Cr(IV), Cu (aq), Cu (aq + CO<sub>2</sub>) and Zn (aq + CO<sub>2</sub>) was performed by liquid chromatography (LC) coupled with ICP-MS using a Agilent Technologies 7900 (EN ISO 17294-2, 2016) [5]. DOC was determined by thermal oxidation using a Shimadzu 5000 (EN 1484, 1997) [8], NH<sub>4</sub><sup>+</sup> and NO<sub>2</sub><sup>-</sup> photometric with an Aquakem 250 (DIN 38406-5, 1983) [9]. Sulphite and sulphide were measured by polarography using a Metrohm 884 Professional VA according to Methrom Appl. 99/1 and F<sup>-</sup> with an ion-sensitive electrode in water samples and digestions (DIN 38405-1, 1985; ISO 10304-1,

**Table 5**  
Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant E in the Canton of Zürich, Switzerland.

		Plant E																
Parameter	Unit	Jan 2008	June 2009	Dec 2009	Apr 2010	May 2010	Aug 2010	Jan 2011	May 2011	Sept 2011	Jan 2012	May 2012	Oct 2012	Jan 2013	May 2013	Sept 2013		
Solid chemical analysis	Dry substance (105°C)	wt.-%	74.1	74.1	74.0	75.3	63.6	74.6	73.5	75.6	59.9	74.4	75.4	75.3	74.4	72.8	73.2	
	LOI (550°C)	wt.-%	96.4	96.3	97.2	97.7	97.6	97.3	97.2	98.0	97.0	97.2	96.1	97.9	97.5	96.1	97.1	
	Fe-Metals	wt.-%	4.03	4.38	2.34	1.72	2.71	1.32	1.35	1.77	1.88	2.23	2.63	1.76	2.37	2.40	2.93	
	NF-Metals	wt.-%	2.41	3.70	3.65	4.11	4.05	3.44	3.12	3.30	3.33	3.93	2.84	2.54	3.78	2.92	3.33	
	Unburnt material	wt.-%	0.055	0.050	0.050	0.050	0.010	0.010	0.010	0.050	0.050	0.050	0.050	0.050	0.050	0.050	0.050	
	TIC	wt.-%	2.01	2.21	1.88	1.44	1.50	1.16	1.03	1.34	1.74	1.72	1.62	1.56	1.52	1.70	1.70	
	TOC	wt.-%	1.04	1.06	0.950	0.850	0.540	0.440	0.825	0.560	0.945	0.520	0.735	0.640	0.755	0.820	0.850	
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.105	0.130	0.125	0.110	0.230	0.511	0.459	
	TiC	wt.-%	1.09	1.07	0.740	0.590	0.845	0.720	0.800	0.770	0.795	0.765	0.885	0.715	0.760	0.880	0.845	
	N	wt.-%	0.055	0.070	0.050	0.010	0.020	0.020	0.030	0.010	0.010	0.010	0.015	0.045	0.010	0.010	0.015	
	S	wt.-%	1.03	1.10	0.750	0.510	0.110	0.600	0.915	0.495	0.275	0.595	0.775	0.590	0.915	0.930	0.655	
	P	mg/kg	13.900	12.600	11.200	13.950	11.020	10.005	10.775	9.760	10.375	11.900	10.360	9.310	9.270	10.375	9.860	
	Batch release test	As	mg/kg	n.s.	n.s.	24.3	29.4	26.1	29.1	24.3	23.7	24.7	24.0	20.9	24.4	21.5	18.5	22.4
Cd		mg/kg	9.33	8.99	7.91	7.45	5.59	6.19	6.82	20.1	12.9	16.3	14.0	7.55	12.9	7.42	14.7	
Cr		mg/kg	833	804	572	623	483	562	693	547	479	642	532	483	467	497	509	
Cu		mg/kg	4.310	4.560	5020	4.600	8410	6.580	6.425	7.555	3725	5730	6.650	9475	5.600	5.750	7.580	
Ni		mg/kg	321	327	374	218	302	242	210	282	298	358	280	269	244	182	288	
Pb		mg/kg	2075	2.260	1.860	1.925	2.065	1.590	2.115	2.365	1.175	2.350	2.825	2.070	3.200	2.170	2.075	
Sb		mg/kg	n.s.	n.s.	409	209	338	195	265	421	231	238	176	474	202	208	230	
Zn		mg/kg	4.370	4.410	4.130	4.970	5.060	4.505	5.710	5.575	4.815	5.300	6.500	5.920	5.655	5.505	5.210	
El. Cond		µS/cm	5.515	5.335	9040	8.190	7635	8.615	8.100	8.190	7855	8400	8.225	8.715	9.570	9.155	8.245	
pH (Test 1)		-	7.06	7.13	6.93	6.66	6.94	6.89	7.22	7.05	7.23	7.00	6.52	6.57	6.96	6.87	6.77	
pH (Test 2)		-	12.3	12.3	13.0	12.2	12.5	12.1	12.5	12.4	12.4	12.4	12.4	12.5	12.5	12.6	12.6	
Dry substance (n 0.1 l)		mg/l	1.880	1.855	2.760	2.290	2.165	2.275	2.455	2.325	2.485	2.530	2.160	2.340	3.015	2.935	2.345	
DOC		mg/l	4.145	10.3	6.990	7.715	4.400	7.355	4.445	8.50	7.330	6.505	6.75	13.3	17.3	7.20		
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg N/l	0.540	0.575	1.34	1.25	1.16	1.03	1.21	0.700	1.75	1.19	1.07	0.760	1.02	0.585			
Ammonium-N	mg N/l	0.400	0.460	1.04	0.970	0.900	0.800	0.935	0.540	1.36	0.915	0.845	0.830	0.590	0.790	0.455		
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.081	0.099	0.112	0.096	0.030	0.026	0.021	0.022	0.021	0.030	0.101	0.035	0.108	0.025	0.017		
Fluoride (F <sup>-</sup> )	mg/l	0.750	0.850	0.800	0.700	1.55	1.00	0.250	0.800	0.600	0.750	1.00	0.700	0.700	0.800	0.750		
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.110	0.110	0.200	0.010	0.010	0.010	0.010	0.010	0.350	0.500	n.s.	0.010	0.010	0.010	0.010		
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	0.700	0.600	0.500	0.700	0.350	1.40	0.700	0.250	0.450	0.350	13.6	0.500	1.20	2.45	0.650		
Cr(VI)	mg/l	0.011	0.013	0.024	0.011	0.007	0.008	0.008	0.008	0.007	0.035	0.005	0.014	0.010	0.027	0.008		
Cu (aq)	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.208	0.443	0.652	0.336	0.354		
Cu (aq + CO <sub>2</sub> )	mg/l	0.071	0.117	0.210	0.034	0.112	0.376	0.139	0.231	0.330	0.349	0.359	0.214	0.039	0.025	0.260		
Zn (aq + CO <sub>2</sub> )	mg/l	2.82	2.40	3.03	1.25	2.53	4.16	1.47	2.59	1.78	3.33	4.04	2.32	2.01	1.32	2.02		
BOD 5 days	mg O <sub>2</sub> /l	5.30	3.65	10.0	5.80	5.75	3.35	5.20	4.45	10.9	7.15	7.05	5.35	16.5	21.0	3.85		
Parameter		Unit	Jan 2014	May 2014	Aug 2014	Jan 2015	July 2015	Dec 2015	Jan 2016	June 2016	Feb 2017	July 2017	Oct 2017	Feb 2018	July 2018	Oct 2018		
Solid chemical analysis	Dry substance (105°C)	wt.-%	72.6	73.3	73.0	72.6	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	LOI (550°C)	wt.-%	95.8	95.6	97.3	96.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	Fe-Metals	wt.-%	2.41	1.89	1.67	2.06	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	NF-Metals	wt.-%	3.27	3.83	2.98	3.62	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	Unburnt material	wt.-%	0.050	0.050	0.050	0.050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	TIC	wt.-%	1.74	1.76	1.85	1.32	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	TOC	wt.-%	0.945	0.835	0.940	1.02	n.s.	n.s.	0.310	0.300	0.030	0.200	0.300	0.200	0.100	0.100		
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	TiC	wt.-%	0.795	0.920	0.900	0.800	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	N	wt.-%	0.015	0.045	0.025	0.025	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	S	wt.-%	0.925	0.795	0.740	0.615	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	P	mg/kg	10.975	9.815	7.555	11.230	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
	As	mg/kg	17.8	20.2	19.2	19.5	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.		
Cd	mg/kg	12.2	7.32	5.77	6.86	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Cr	mg/kg	391	513	471	445	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Cu	mg/kg	6.375	5.475	5.440	5.855	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Ni	mg/kg	193	300	188	218	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Pb	mg/kg	1.840	3.165	1.790	3.295	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Sb	mg/kg	134	145	115	117	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Zn	mg/kg	5.695	5.440	5.310	5.735	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
El. Cond	µS/cm	9.200	8.630	8.975	8.715	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
pH (Test 1)	-	6.58	6.71	6.77	6.86	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
pH (Test 2)	-	12.6	12.5	12.5	12.3	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Dry substance (n 0.1 l)	mg/l	2.940	2.545	2.895	2.375	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
DOC	mg/l	17.0	8.70	13.5	11.1	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	1.53	1.37	1.19	1.31	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Ammonium-N	mg N/l	1.19	1.07	0.930	1.01	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.037	0.028	0.017	0.021	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Fluoride (F <sup>-</sup> )	mg/l	0.550	0.550	0.550	0.600	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.010	0.010	0.010	0.010	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	0.850	0.750	1.05	0.400	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Cr(VI)	mg/l	0.005	0.008	0.011	0.007	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Cu (aq)	mg/l	n.s.	0.480	0.320	0.357	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Cu (aq + CO <sub>2</sub> )	mg/l	0.247	0.190	0.505	0.141	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
Zn (aq + CO <sub>2</sub> )	mg/l	2.82	2.36	2.29	2.31	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			
BOD 5 days	mg O <sub>2</sub> /l	19.0	10.5	14.6	10.5	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.			

n.s. = not sampled

2007) [10,11]. Finally, the biochemical oxygen demand (BOD) of five days has been measured respirometric using an Oxitop-system.

The physical parameters pH and electrical conductivity were measured with a pH electrode (Aquatrode plus, Metrohm 6.0257.600) and a 5-ring conductivity measuring cell with cell constant  $c = 1.0 \text{ cm}^{-1}$  (Metrohm 6.0915.130), both with integrated Pt1000 temperature sensor.



**Table 6**

Dataset on ten-years monitoring of MSWI bottom ashes in MSWI Plant F in the Canton of Zürich, Switzerland.

		Plant F																
Parameter	Unit	Jan 2008	July 2009	Dec 2009	Mar 2010	June 2010	Dec 2010	Mar 2011	June 2011	Nov 2011	Jan 2012	May 2012	Oct 2012	Mar 2013	July 2013	Nov 2013		
Solid chemical analysis	Dry substance (105°C)	wt.-%	n.s.	83.7	82.8	85.7	80.0	83.0	82.8	83.3	82.6	81.8	83.6	84.7	83.9	85.9	80.3	
	LOI (550°C)	wt.-%	n.s.	97.1	98.8	98.2	98.9	97.3	98.4	97.9	98.5	97.6	97.4	98.5	97.3	98.2	96.5	
	Fe-Metals	wt.-%	n.s.	7.77	4.15	3.01	1.54	2.21	1.80	2.80	3.50	2.93	3.35	1.50	1.75	1.58	2.58	
	NF-Metals	wt.-%	n.s.	2.82	3.41	4.43	2.91	2.62	2.67	1.69	3.14	2.19	2.20	1.78	2.05	1.43	2.71	
	Unburnt material	wt.-%	n.s.	0.19	0.20	0.23	0.10	0.10	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	
	TiC	wt.-%	n.s.	1.67	1.59	1.13	1.45	1.54	1.54	1.54	1.54	1.54	1.54	1.54	1.54	1.54	1.76	
	TOC	wt.-%	n.s.	0.855	0.630	0.520	0.650	0.760	0.950	0.890	0.870	0.905	0.705	0.620	0.910	1.04	1.08	
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	0.100	0.220	0.190	0.285	0.682	0.518	0.703
	TiC	wt.-%	n.s.	0.715	0.520	0.560	0.480	0.690	0.620	0.480	0.760	0.695	0.740	0.575	0.520	0.460	0.680	
	N	wt.-%	n.s.	0.045	0.050	0.100	0.040	0.030	0.040	0.030	0.030	0.050	0.180	0.100	0.010	0.010	0.010	0.030
	S	wt.-%	n.s.	0.750	0.430	0.550	0.570	1.21	1.18	0.990	1.11	1.05	1.19	1.09	1.15	1.02	0.980	
	P	mg/kg	n.s.	8335	11600	9970	3720	7900	6290	7850	6400	6560	6620	7300	7260	9170	8060	
	As	mg/kg	n.s.	n.s.	17.3	35.7	32.3	16.7	22.8	18.4	21.3	27.6	21.2	16.7	25.0	31.2	24.4	
	Cd	mg/kg	n.s.	4.94	4.14	6.56	2.94	2.96	8.56	5.81	4.97	16.8	6.51	8.31	6.07	5.65	8.08	
Cr	mg/kg	n.s.	684	632	578	470	714	891	635	821	738	1660	936	1220	861	931		
Cu	mg/kg	n.s.	4320	5190	6190	3840	8200	6560	5770	4110	6810	6770	7690	11800	6460	7220		
Ni	mg/kg	n.s.	315	262	249	139	365	442	753	418	386	1030	507	637	501	633		
Pb	mg/kg	n.s.	1975	1700	1990	1260	1040	6330	1520	1450	713	1590	1120	1850	1160	2480		
Sb	mg/kg	n.s.	n.s.	197	173	82.8	137	324	121	122	159	155	140	125	123	154		
Zn	mg/kg	n.s.	4000	3710	4720	2770	4750	4980	3790	5050	5160	5340	5310	6770	5160	5710		
El. Cond	µS/cm	n.s.	4263	8780	8370	9120	10200	9150	8850	9390	9000	9220	9380	8790	8930	9770		
pH (Test 1)	-	n.s.	6.75	6.89	6.71	7.08	7.31	7.06	7.30	7.10	7.08	6.57	6.86	6.82	6.86	6.87		
pH (Test 2)	-	n.s.	12.2	13.0	12.5	12.4	12.4	12.4	12.3	12.4	12.5	12.2	12.5	12.5	12.2	12.5		
Dry substance (n 0.1 l)	mg/l	n.s.	1955	2380	2380	3060	2740	3920	3960	3790	3570	3790	3760	3350	3410	3340		
DOC	mg/l	n.s.	25.8	20.0	18.0	25.0	36.0	25.0	28.0	22.0	33.0	17.0	34.0	40.0	28.0	53.0		
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	n.s.	1.44	1.22	1.90	1.69	1.41	1.73	0.930	1.69	3.44	1.39	2.42	12.13	1.48	3.32		
Ammonium-N	mg NI	n.s.	0.12	0.950	1.40	1.31	1.09	1.35	0.020	1.31	2.67	1.08	1.88	3.21	1.15	2.58		
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	n.s.	0.074	0.134	0.212	0.016	0.021	0.045	0.031	0.068	0.136	0.019	0.039	0.043	0.022	0.071		
Fluoride (F <sup>-</sup> )	mg/l	n.s.	0.250	0.300	0.400	0.400	0.500	2.40	0.800	0.900	0.700	0.800	1.00	0.900	2.00	1.40		
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	n.s.	0.100	0.200	0.010	0.100	0.010	0.010	1.00	1.00	1.00	0.910	0.010	0.010	0.010	0.010		
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	n.s.	1.45	1.00	2.30	1.00	6.00	0.100	2.30	3.00	1.80	2.30	1.10	1.50	1.70	2.10		
Cr(IV)	mg/l	n.s.	0.008	0.020	0.007	0.009	0.018	0.006	0.018	0.027	0.041	0.030	0.028	0.041	0.025	0.078		
Cu (aq)	mg/l	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	1.63	1.56	n.s.		
Cu (aq + CO <sub>2</sub> )	mg/l	n.s.	0.650	0.511	0.682	0.783	1.51	1.05	0.849	1.01	0.884	0.809	1.37	0.999	0.929	0.520		
Zn (aq + CO <sub>2</sub> )	mg/l	n.s.	2.04	2.31	2.54	1.42	2.55	3.96	4.45	3.24	4.03	5.12	6.60	14.9	3.75	5.31		
BOD 5 days	mg O <sub>2</sub> /l	n.s.	n.s.	n.s.	21.0	20.0	32.0	33.0	26.0	36.0	26.0	39.0	15.0	33.0	15.0	49.0		

  

Parameter	Unit	May 2014	July 2014	Dec 2014	Jan 2015	July 2015	Dec 2015	Jan 2016	June 2016	Jan 2017	May 2017	Sept 2017	July 2018	Oct 2018	Dec 2018
Solid chemical analysis	Dry substance (105°C)	wt.-%	85.7	87.0	71.5	81.7	84.7	82.9	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	LOI (550°C)	wt.-%	97.2	97.5	97.7	96.7	96.4	96.7	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	Fe-Metals	wt.-%	4.60	6.15	4.43	4.45	6.30	3.71	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	NF-Metals	wt.-%	2.85	3.22	3.51	3.03	3.30	2.66	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	Unburnt material	wt.-%	0.050	0.050	0.060	0.050	0.060	0.150	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	TiC	wt.-%	1.61	1.20	1.16	1.41	1.44	1.58	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	TOC	wt.-%	1.13	0.810	0.830	1.06	1.13	0.970	n.s.	0.780	0.500	0.900	0.700	0.600	0.500
	OC	wt.-%	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	TiC	wt.-%	0.480	0.400	0.300	0.400	0.300	0.600	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	N	wt.-%	0.010	0.010	0.030	0.040	0.130	0.050	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	S	wt.-%	0.680	0.790	1.05	0.900	0.670	1.06	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	P	mg/kg	7620	8280	8330	9410	8210	7880	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	As	mg/kg	10.5	39.6	23.7	32.1	28.0	22.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
	Cd	mg/kg	4.86	26.5	11.5	9.52	5.78	4.23	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.
Cr	mg/kg	604	882	959	947	1110	1120	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Cu	mg/kg	3480	5020	8590	7260	6670	4430	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Ni	mg/kg	382	543	495	589	757	552	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Pb	mg/kg	1090	1390	1300	1200	1920	1310	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Sb	mg/kg	103	135	141	177	198	119	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Zn	mg/kg	4120	4610	5820	4740	6090	4390	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
El. Cond	µS/cm	9530	7430	9750	7300	7630	9220	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
pH (Test 1)	-	6.95	6.57	6.64	6.86	6.78	6.90	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
pH (Test 2)	-	12.6	12.4	12.5	12.3	12.2	12.4	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Dry substance (n 0.1 l)	mg/l	3650	2980	4180	2840	2580	3580	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
DOC	mg/l	29.0	20.0	30.0	38.0	45.0	32.0	56.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Ammonium (NH <sub>4</sub> <sup>+</sup> )	mg/l	1.95	1.71	3.02	4.39	1.62	2.86	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Ammonium-N	mg NI	1.51	1.33	2.35	3.42	1.26	2.22	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Nitrite (NO <sub>2</sub> <sup>-</sup> )	mg/l	0.026	0.052	0.038	0.032	0.021	0.011	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Fluoride (F <sup>-</sup> )	mg/l	1.00	0.800	0.800	0.800	0.700	0.900	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Sulfide (S <sub>2</sub> <sup>-</sup> )	mg/l	0.010	0.010	0.010	0.010	0.300	0.010	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Sulfite (SO <sub>3</sub> <sup>2-</sup> )	mg/l	1.60	1.60	4.40	3.00	1.40	0.700	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Cr(IV)	mg/l	0.030	0.028	0.033	0.023	0.016	0.028	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Cu (aq)	mg/l	0.890	0.395	2.02	n.s.	1.21	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Cu (aq + CO <sub>2</sub> )	mg/l	0.890	0.584	1.60	1.28	0.739	0.866	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
Zn (aq + CO <sub>2</sub> )	mg/l	5.90	6.20	6.37	3.39	3.39	2.28	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	
BOD 5 days	mg O <sub>2</sub> /l	29.0	32.0	54.0	44.0	47.0	66.0	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	n.s.	

n.s. = not sampled

**Acknowledgments**

We thank the MSWI plants of the Canton of Zürich who agreed to provide the data presented in this article.

**Supplementary materials**

Supplementary material associated with this article can be found, in the online version, at doi:10.1016/j.dib.2020.106261.

## References

- [1] A. Glauser, L.S. Morf, G. Weibel, U. Eggenberger, Ten-years monitoring of MSWI bottom ashes with focus on TOC development and leaching behaviour, *Waste Manage. (Oxford)* (2020).
- [2] Swiss Confederation, Ordinance on the Avoidance and the Disposal of Waste, 2016.
- [3] Federal Office for the Environment, Messmethoden im Abfall- und Altlastenbereich: Umwelt-Vollzug Nr. 1715, 2017.
- [4] ISO 11885, Water quality – Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES), *Int. Organ. Stand.* (2007).
- [5] EN ISO 17294-2, Water quality - Application of inductively coupled plasma mass spectrometry (ICP-MS) - Part 2: Determination of selected elements including uranium isotopes, *Eur. Comm. for Stand.* (2016).
- [6] EN 15936, Sludge, treated biowaste, soil and waste - Determination of total organic carbon (TOC) by dry combustion, *Eur. Comm. Stand.* (2012).
- [7] DIN 19539, Untersuchung von Feststoffen – Temperaturabhängige Differenzierung des Gesamtkohlenstoffs (TOC400, ROC, TIC900), *Deutsches Institut für Normung* (2016).
- [8] EN 1484, Water analysis - Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC), *Eur. Comm. Stand.* (1997).
- [9] DIN 38406-5, Deutsche Einheitsverfahren zur Wasser-, Abwasser- und Schlammuntersuchung; Kationen (Gruppe E); Bestimmung des Ammonium-Stickstoffs (E 5), *Deutsches Institut für Normung* (1983).
- [10] DIN 38405-1, Deutsche Einheitsverfahren zur Wasser-, Abwasser- und Schlammuntersuchung; Anionen (Gruppe D); Bestimmung der Chlorid-Ionen (D 1), *Deutsches Institut für Normung* (1985).
- [11] ISO 10304-1, Water quality – Determination of dissolved anions by liquid chromatography of ions – Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate, *Int. Organ. Stand.* (2007).
- [12] A.G. Bachema, Dienstleistungsverzeichnis 17/19, 2017.