

Research Article

The Effect of Multiple Autoclave Sterilization on the Cyclic Fatigue of Three Heat-Treated Nickel-Titanium Rotary Files: EdgeFile X7, Vortex Blue, and TRUShape

Reham Sharroufna ¹ and Mohammed Mashyakhly ²

¹Private Dental Practice, Riyadh, Saudi Arabia

²Department of Restorative Dental Sciences, College of Dentistry, Jazan University, Jazan, Saudi Arabia

Correspondence should be addressed to Mohammed Mashyakhly; dr.mashyakhly@gmail.com

Received 30 August 2020; Revised 21 November 2020; Accepted 6 December 2020; Published 14 December 2020

Academic Editor: GuoXin Ni

Copyright © 2020 Reham Sharroufna and Mohammed Mashyakhly. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Objective. The purpose of this study was to evaluate the effect of repeated autoclave sterilization on the cyclic fatigue resistance of heat-treated NiTi rotary endodontic instruments. **Materials and Methods.** Three NiTi rotary endodontic instruments (EdgeFile X7, EFX7 0.30/0.4; Vortex Blue, VB 0.30/0.4; and TRUShape, TS 0.30/0.6) were selected. Each group ($n = 24$ each) was divided into 2 subgroups ($n = 12$ each): sterilized instruments and nonsterilized instruments. The sterilized instruments were subjected to 10 cycles of autoclave sterilization. Twelve instruments from each different subgroups were tested for cyclic fatigue resistance, and the number of cycles to failure (NCF) was calculated. Means and standard deviations were calculated for each group, and data were statistically analyzed using the SPSS program ($P < 0.05$). **Results.** Sterilized and nonsterilized EFX7 files showed the highest NCF compared with other file subgroups. Comparing the results between sterilized and nonsterilized instruments for each type of files, there was a statistically significant difference ($P < 0.05$) only between sterilized and nonsterilized EFX7 files (1198 versus 755 NCF). The other instruments did not show significant differences ($P > 0.05$) in the mean NCF as a result of sterilization cycles (VB, 606 versus 568 NCF; TS, 487 versus 442 NCF). **Conclusion.** Repeated cycles of autoclave sterilization increased the NCF of the new heat-treated files, with EFX7 showing statistically significant superior results compared with other files tested.

1. Introduction

Chemomechanical cleaning and shaping is the most critical step of root canal treatment (RCT) [1–4]. This important step, with the help of nickel-titanium (NiTi) rotary endodontic files, becomes faster and more predictable; however, there is an uneventful risk of instrument separation, and it is a well-reported challenge in endodontic literature [5–8]. Despite the outstanding properties of recent NiTi instruments, they still can be separated due to cyclic or flexural fatigue [9–13]. Cyclic fatigue is reported to occur as a result of repeated bending of the instruments in curved canals that lead to deformation and stress within the instruments, which end up with fracture due to complete tension-compression cycles [14]. Manufacturers developed thermomechanical processing by adjusting the transformation temperatures of

the NiTi alloys to improve the fatigue resistance to overcome instrument fracture [15]. Thermal treatment of NiTi alloy has shown favorable effects on mechanical and physical properties of NiTi files [16]. In clinical practice settings, NiTi rotary files might be used many times, and the repeated sterilization process by autoclave is necessary to prevent cross-contamination [17, 18]. A 2020 systematic review and meta-analysis study found that autoclave was the most effective method to sterilize endodontic instruments [19].

Many studies had investigated the sterilization using autoclave effects on the physical properties of NiTi rotary files and reported contrasting results. Some showed that repeated sterilization badly affects the files and cause fractures [20–24]. While other studies reported that repeated cycles of heat sterilization did not cause the failure of NiTi files [25, 26]. Plotino et al. [27] showed that repeated

sterilization only significantly increases the cyclic fatigue resistance of one file (K3XF) out of four groups that were tested, where their properties were not influenced. Also, Zhao et al. [18] observed an extension of the cyclic fatigue life of HyFlex CM and K3XF compared with three other tested groups. A recent review [19] showed that hot sterilization by autoclave generally did not alter the physical and mechanical properties of most NiTi endodontic files. Studies seem to be inconsistent and showed different results in different types of NiTi endodontic rotary files. Many heat-treated NiTi endodontic files are found in the market with a variety of metallurgic properties. Vortex Blue (VB; Dentsply Tulsa, Tulsa, OK, the USA) is a NiTi rotary instrument manufactured by a proprietary thermomechanical process to improve fatigue resistance, cutting efficiency, flexibility, and canal centering capability [28]. It has been reported that Vortex Blue has a significant cyclic fatigue resistance compared with similar sizes of NiTi files that are made of M-wire [29]. EdgeFile X7 instruments (Edge Endo; Albuquerque, New Mexico, United States) is a NiTi file which has a constant taper, manufactured by a process called "FireWire™," which potentially increases the flexibility and resistance to fatigue and reduces the shape memory effect inherent of NiTi instruments [30]. A recent study [31] showed that EdgeFile instruments have higher fatigue resistance than VB files. TRUShape (TS; Dentsply Tulsa Dental Specialties, Tulsa, OK) is a novel heat-treated NiTi file where the heat treatment is applied after flutes are ground into blanks; it is characterized by an S-curve and a taper of 0.06 in the apical 2 mm. TS file has recently been introduced in the market and not well studied [32].

The aim of this study, therefore, was to evaluate the effect of multiple autoclave sterilization on the cyclic fatigue of three types of thermally treated NiTi files (Vortex Blue, EdgeFile X7, and TRUShape). The null hypothesis is that no significant difference could be found between the three types of heat-treated NiTi endodontic files in terms of cyclic fatigue after multiple autoclave sterilization.

2. Materials and Methods

Three types of NiTi rotary endodontic heat-treated instruments were selected: EdgeFile X7 (EFX7 group) 0.30 mm tip diameter and 0.4 taper (EdgeEndo, Albuquerque, NM, USA), Vortex Blue (VB group) 0.30 mm tip diameter and 0.4 taper (Dentsply Tulsa, Tulsa, OK, the USA), and TRUshape (TS group) 0.30 mm tip diameter and 0.6 taper (Dentsply Tulsa, Tulsa, OK, the USA). All files had the same length of 25 mm. Twenty-four instruments from each type were collected (total = 72 files). Each group was then divided into 2 subgroups ($n = 12$ each), sterilized (S) and nonsterilized (NS) instruments. The sterilized instruments were subjected to autoclave sterilization (10 cycles) at a temperature of 134°C for 35 minutes for each cycle (time included 20 minutes for sterilization and 15 minutes for drying).

For testing, a previously described methodology was followed [27]. In brief, the device consisted of mobile plastic support connected to the mainframe of the device. This plastic support was used to hold the handpiece and metal block

containing the artificial canals. Each instrument was tested in a simulated root canal with a 60° angle of curvature and 5 mm radius of curvature. The center of the curvature was located 5 mm from the tip of the file, and the curved segment of the canal measured about 5 mm in length.

A contra-angle (6:1) handpiece (Sirona, Bensheim, Germany) powered by a torque-controlled electric motor (E3; Dentsply Tulsa, Tulsa, OK) was used to rotate the instruments at a constant speed of 300 rpm until their fracture occurred. The number of cycles to failure (NCF) was calculated by multiplying the time to fracture by the speed of the handpiece. The data of NCF were analyzed using one-way analysis of variance (ANOVA) and Tukey's post hoc tests. The level of significance was set at $P < 0.05$ for all tests.

3. Results

As shown in Table 1, higher values of NCF were noticed in sterilized groups compared to nonsterilized groups with the highest value 1198.76 ± 255.56 for the EFX7(S) group and lowest value 442.22 ± 80.92 for the TS(NS) group. There was a highly statistically significant difference ($P < 0.001$) between sterilized and nonsterilized EFX7 instruments. However, no differences were found between sterilized and nonsterilized Vortex Blue as well as True Shape instruments ($P > 0.05$). Generally (regardless of sterilized or not), the EFX7 group had the highest cyclic fatigue resistance followed by the VB group and the TS group.

Based on Tukey's post hoc test (Table 2) for multiple comparisons, there were significant differences ($P < 0.001$) between the EFX7(S) group and all other groups. Also, there were significant differences between the EFX7(NS) group and TS(S) and TS(NS) groups. However, no significant differences were found between all other instrument groups ($P > 0.05$).

4. Discussion

Dental practitioners usually use NiTi endodontic files repeatedly for practical and economic reasons, which are accompanied by many cycles of autoclave sterilization [18]. Manufacturers promote a single use of NiTi files for fracture safety; however, we chose to perform our study doing 10 cycles by autoclave as other previous studies [27, 33] to assess the effect of repeated sterilization trying to mimic a clinical use. The superior properties of NiTi alloy are highly dependent on the thermomechanical processing of the manufactured product [34], and additional heat of the instrument by autoclave sterilization may increase its mechanical and physical properties as suggested by Yahata et al. [16]. Up to our best knowledge, there are no available studies in the literature evaluating the cyclic fatigue resistance of VB, EFX7, and TS instruments after repeated cycles of autoclave sterilization. So, in this in vitro study, we investigated the effect of repeated cycles of autoclave sterilization on cyclic fatigue of new heat-treated files that are commercially available in the market. Although lab testing has some limitations, the results could be of practical value [35].

TABLE 1: Mean \pm SD and mean differences between sterilized and nonsterilized instruments.

Type	N	Mean \pm SD	Mean difference	95% CI of difference		P
				Lower	Upper	
EdgeFile X7						
Sterilized	12	1198.8 \pm 255.6	443.0	246.9	639.0	P < 0.001
Nonsterilized	12	755.8 \pm 175.4				
Vortex Blue						
Sterilized	12	606.1 \pm 145.1	37.4	-158.7	233.5	0.993
Nonsterilized	12	568.7 \pm 174.6				
TRUShape						
Sterilized	12	487.8 \pm 80.7	45.5	-150.6	241.6	0.983
Nonsterilized	12	442.2 \pm 80.9				

Significance level at P < 0.05.

TABLE 2: Tukey’s post hoc test for multiple comparisons between different groups.

Type		Mean difference	95% confidence interval		P
			Lower	Upper	
EdgeFile (S)	Vortex Blue (NS)	630.0	433.9	826.1	<0.001
	Vortex Blue (S)	592.6	396.5	788.7	<0.001
	TRUShape (NS)	756.5	560.5	952.6	<0.001
	TRUShape (S)	711.0	514.9	907.1	<0.001
EdgeFile (NS)	Vortex Blue (NS)	187.1	-9.0	383.2	0.070
	Vortex Blue (S)	149.7	-46.4	345.8	0.234
	TRUShape (NS)	313.6	117.5	509.7	<0.001
	TRUShape (S)	268.1	72.0	464.1	0.002
Vortex Blue (S)	TRUShape (NS)	163.9	-32.2	360.0	0.153
	TRUShape (S)	118.4	-77.7	314.5	0.491
Vortex Blue (NS)	TRUShape (NS)	126.5	-69.6	322.6	0.415
	TRUShape (S)	81.0	-115.1	277.1	0.829

Significance level at P < 0.05.

The results of the current investigation did not support the null hypothesis as the number of cyclic to fracture was higher in sterilized compared with unsterilized endodontic files. Interestingly, the main finding is that sterilized NiTi instrument groups had more cyclic fatigue resistance compared with nonsterilized ones, with only EFX7 showing a highly statistically significant difference. In addition, VB files performed better than the TS ones in both sterilized and nonsterilized groups. The results of NS groups are consistent with a previous observation, where EdgeFile instruments had higher fatigue resistance compared with VB files when subjected to different temperature settings [31]. In another study, however, EFX7 did not show superior cyclic fatigue resistance and was similar to HyFlex and MTwo but significantly lower than the ProDesign logic NiTi instrument for the same file size [36]. In regard to TS and VB files, a study showed no significant difference between TS and VB at 20°C, but when the temperature rose to body temperature, VB showed higher cyclic fatigue resistance than TS [37]. Also, other studies reported that TS files had less fatigue resistance compared with other files tested [38, 39].

Many studies evaluated the effect of sterilization on mechanical properties and performance of NiTi endodontic instruments with contradicting results [40–52]. Repeated cycles of sterilization of ProFile instrument [25] and Light-Speed instruments [41] did not increase their resistance to cyclic fatigue, while in a more recent study [42], ProFile NiTi showed higher NCF when exposed to autoclave sterilization. These studies have been done on traditional NiTi endodontic files, whereas only a few ones investigated the influence of a repeated cycle of autoclave sterilization on cyclic fatigues of new heat-treated NiTi instruments [18, 27, 33, 53]. Our results showed clearly that the repeated cycle of autoclave sterilization improved the mechanical properties of the tested files where more NCF is needed. This finding is in agreement with Zhao et al.’s study [18], where autoclave sterilization increased the cyclic fatigue of HyFlex CM and K3XF, which are made of thermally treated alloy. Also, Plotino et al. [27] tested K3 XF files, produced with an innovative heat-treated NiTi alloy, and showed a statistically significant increase in the CNF after 10 cycles of autoclave sterilization. In contrast, another study [33] found that repeated

sterilization did not significantly affect 3 of the 4 groups of NiTi instruments tested (GTX 20.04, GTX 20.06, Twisted File 25.04). However, another study [53] evaluated (PTU, K3X, TFA, and EDM) NiTi files and reported that sterilization did not influence the cyclic fatigue significantly.

Our study showed generally that all files tested (regardless of sterilized or not) showed higher cyclic fatigue resistance with the EFX7 group having the highest NCF followed by the VB group and the TS group. It seems that the new generation of heat-treated NiTi files tends to have better metallurgic properties, and the repeated heat of sterilization improved their resistance to cyclic fatigue. In addition, interestingly, the EFX7 nonsterilized group showed significantly higher CFR than all other file subgroups (VB and TS), and that may be related to the “WireFire™” technology used and its special design. More studies are highly recommended in a body temperature simulation to mimic the clinical situation for more reliable results which is one of the main limitations of our study.

5. Conclusion

Within the limitations of this in vitro study, it can be concluded that repeated cycles of autoclave sterilization increased the NCF of the new heat-treated files tested, with EFX7 made by FireWire™ technology showing statistically significant superior results.

Data Availability

Data are available upon request from the corresponding author.

Conflicts of Interest

The authors declare that they have no conflicts of interest.

References

- [1] H. Schilder, “Cleaning and shaping the root canal,” *Dental Clinics of North America*, vol. 18, no. 2, pp. 269–296, 1974.
- [2] L. Buchanan, “Cleaning and shaping the root canal systems,” in *Pathways of the Pulp*, Mosby-Yearbook, St Louis, 5th edition, 1991.
- [3] O. Peters, P. M. H. Dummer, and M. Hu, “Mechanical preparation of root canals: shaping goals, techniques and means,” *Endodontic Topics*, vol. 10, pp. 30–76, 2005.
- [4] A. Bystrom and G. Sundqvist, “Bacteriologic evaluation of the efficacy of mechanical root canal instrumentation in endodontic therapy,” *Scandinavian Journal of Dental Research*, vol. 89, no. 4, pp. 321–328, 1981.
- [5] F. C. Arens, M. M. Hoen, H. R. Steiman, and G. C. J. Dietz, “Evaluation of single-use rotary nickel-titanium instruments,” *Journal of Endodontia*, vol. 29, no. 10, pp. 664–666, 2003.
- [6] O. A. Peters, “Current challenges and concepts in the preparation of root canal systems: a review,” *Journal of Endodontia*, vol. 30, no. 8, pp. 559–567, 2004.
- [7] K. I. Knowles, N. B. Hammond, S. G. Biggs, and J. L. Ibarrola, “Incidence of instrument separation using LightSpeed rotary instruments,” *Journal of Endodontia*, vol. 32, no. 1, pp. 14–16, 2006.
- [8] M. K. Iqbal, M. R. Kohli, and J. S. Kim, “A retrospective clinical study of incidence of root canal instrument separation in an endodontics graduate program: a PennEndo database study,” *Journal of Endodontia*, vol. 32, no. 11, pp. 1048–1052, 2006.
- [9] G. G. J. Kitchens, F. R. Liewehr, and P. C. Moon, “The effect of operational speed on the fracture of nickel-titanium rotary instruments,” *Journal of Endodontia*, vol. 33, no. 1, pp. 52–54, 2007.
- [10] J.-Y. Kim, G. S.-P. Cheung, S.-H. Park, D.-C. Ko, J.-W. Kim, and H.-C. Kim, “Effect from cyclic fatigue of nickel-titanium rotary files on torsional resistance,” *Journal of Endodontia*, vol. 38, no. 4, pp. 527–530, 2012.
- [11] Y. Gao, V. Shotton, K. Wilkinson, G. Phillips, and W. Johnson, “Effects of raw material and rotational speed on the cyclic fatigue of ProFile vortex rotary instruments,” *Journal of Endodontia*, vol. 36, no. 7, pp. 1205–1209, 2010.
- [12] P. Parashos, I. Gordon, and H. H. Messer, “Factors influencing defects of rotary nickel-titanium endodontic instruments after clinical use,” *Journal of Endodontia*, vol. 30, no. 10, pp. 722–725, 2004.
- [13] C. Champa, V. Divya, A. Sreirekha, R. Karale, A. Shetty, and P. Sadashiva, “An analysis of cyclic fatigue resistance of reciprocating instruments in different canal curvatures after immersion in sodium hypochlorite and autoclaving: an in vitro study,” *Journal of Conservative Dentistry*, vol. 20, no. 3, pp. 194–198, 2017.
- [14] G. Zelada, P. Varela, B. Martin, J. G. Bahillo, F. Magan, and S. Ahn, “The effect of rotational speed and the curvature of root canals on the breakage of rotary endodontic instruments,” *Journal of Endodontia*, vol. 28, no. 7, pp. 540–542, 2002.
- [15] U. K. Bulem, A. D. Kececi, and H. E. Guldaz, “Experimental evaluation of cyclic fatigue resistance of four different nickel-titanium instruments after immersion in sodium hypochlorite and/or sterilization,” *Journal of Applied Oral Science*, vol. 21, no. 6, pp. 505–510, 2013.
- [16] Y. Yahata, T. Yoneyama, Y. Hayashi, A. Ebihara, H. Doi, and T. Hanawa, “Effect of heat treatment on transformation temperatures and bending properties of nickel-titanium endodontic instruments,” *International Endodontic Journal*, vol. 42, no. 7, pp. 621–626, 2009.
- [17] G. Spagnuolo, G. Ametrano, V. D’Anto et al., “Effect of autoclaving on the surfaces of TiN-coated and conventional nickel-titanium rotary instruments,” *International Endodontic Journal*, vol. 45, no. 12, pp. 1148–1155, 2012.
- [18] D. Zhao, Y. Shen, B. Peng, and M. Haapasalo, “Effect of autoclave sterilization on the cyclic fatigue resistance of thermally treated nickel-titanium instruments,” *International Endodontic Journal*, vol. 49, no. 10, pp. 990–995, 2016.
- [19] M. Dioguardi, D. Sovereto, G. Illuzzi et al., “Management of instrument sterilization workflow in endodontics: a systematic review and meta-analysis,” *International Journal of Dentistry*, vol. 2020, Article ID 5824369, 20 pages, 2020.
- [20] C. Eggert, O. Peters, and F. Barbakow, “Wear of nickel-titanium lightspeed instruments evaluated by scanning electron microscopy,” *Journal of Endodontia*, vol. 25, no. 7, pp. 494–497, 1999.
- [21] E. Rapisarda, A. Bonaccorso, T. R. Tripi, G. G. Condorelli, and L. Torrisi, “Wear of nickel-titanium endodontic instruments evaluated by scanning electron microscopy: effect of

- ion implantation," *Journal of Endodontia*, vol. 27, no. 9, pp. 588–592, 2001.
- [22] E. Schafer, "Effect of sterilization on the cutting efficiency of PVD-coated nickel-titanium endodontic instruments," *International Endodontic Journal*, vol. 35, no. 10, pp. 867–872, 2002.
- [23] S. B. Alapati, W. A. Brantley, T. A. Svec, J. M. Powers, J. M. Nusstein, and G. S. Daehn, "SEM observations of nickel-titanium rotary endodontic instruments that fractured during clinical use," *Journal of Endodontia*, vol. 31, no. 1, pp. 40–43, 2005.
- [24] C. R. A. Valois, L. P. Silva, and R. B. Azevedo, "Multiple autoclave cycles affect the surface of rotary nickel-titanium files: an atomic force microscopy study," *Journal of Endodontia*, vol. 34, no. 7, pp. 859–862, 2008.
- [25] J. Silvaggio and M. L. Hicks, "Effect of heat sterilization on the torsional properties of rotary nickel-titanium endodontic files," *Journal of Endodontia*, vol. 23, no. 12, pp. 731–734, 1997.
- [26] M. Khabiri, M. Ebrahimi, and M. R. Saei, "The effect of autoclave sterilization on resistance to cyclic fatigue of Hero endodontic file #642 (6%) at two artificial curvature," *Journal of Dentistry*, vol. 18, no. 4, pp. 277–281, 2017.
- [27] G. Plotino, A. Costanzo, N. M. Grande, R. Petrovic, L. Testarelli, and G. Gambarini, "Experimental evaluation on the influence of autoclave sterilization on the cyclic fatigue of new nickel-titanium rotary instruments," *Journal of Endodontia*, vol. 38, no. 2, pp. 222–225, 2012.
- [28] Y. Gao, J. L. Gutmann, K. Wilkinson, R. Maxwell, and D. Ammon, "Evaluation of the impact of raw materials on the fatigue and mechanical properties of ProFile vortex rotary instruments," *Journal of Endodontia*, vol. 38, no. 3, pp. 398–401, 2012.
- [29] G. Plotino, N. M. Grande, E. Cotti, L. Testarelli, and G. Gambarini, "Blue treatment enhances cyclic fatigue resistance of vortex nickel-titanium rotary files," *Journal of Endodontia*, vol. 40, no. 9, pp. 1451–1453, 2014.
- [30] EdgeEndo, *EdgeFile X7 Directions for Use*, 2015, <https://edgeendo.com/wp-content/uploads/2015/08/DFU-EdgeFile-x7.pdf>.
- [31] A. Dosanjh, S. Paurazas, and M. Askar, "The effect of temperature on cyclic fatigue of nickel-titanium rotary endodontic instruments," *Journal of Endodontia*, vol. 43, no. 5, pp. 823–826, 2017.
- [32] D. Ammon, V. Shotton, Y. Gao, and R. Maxwell, *Endodontic Instruments and Methods of Manufacturing Thereof*, 2014, US Patent Application 8916009 B2.
- [33] P. B. Hilfer, B. E. Bergeron, M. J. Mayerchak, H. W. Roberts, and B. G. Jeansonne, "Multiple autoclave cycle effects on cyclic fatigue of nickel-titanium rotary files produced by new manufacturing methods," *Journal of Endodontia*, vol. 37, no. 1, pp. 72–74, 2011.
- [34] S. Zinelis, M. Darabara, T. Takase, K. Ogane, and G. D. Papadimitriou, "The effect of thermal treatment on the resistance of nickel-titanium rotary files in cyclic fatigue," *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontics*, vol. 103, no. 6, pp. 843–847, 2007.
- [35] G. Plotino, N. M. Grande, M. Cordaro, L. Testarelli, and G. Gambarini, "A review of cyclic fatigue testing of nickel-titanium rotary instruments," *Journal of Endodontia*, vol. 35, no. 11, pp. 1469–1476, 2009.
- [36] M. Tanomaru-Filho, C. Galletti Espir, A. Carolina Vencao, N. Macedo-Serrano, J. Camilo-Pinto, and J. Guerreiro-Tanomaru, "Cyclic fatigue resistance of heat-treated nickel-titanium instruments," *Iranian endodontic journal*, vol. 13, no. 3, pp. 312–317, 2018.
- [37] R. A. de Vasconcelos, S. Murphy, C. A. T. Carvalho, R. G. Govindjee, S. Govindjee, and O. A. Peters, "Evidence for reduced fatigue resistance of contemporary rotary instruments exposed to body temperature," *Journal of Endodontia*, vol. 42, no. 5, pp. 782–787, 2016.
- [38] E. J. N. L. Silva, V. T. L. Vieira, F. G. Belladonna et al., "Cyclic and torsional fatigue resistance of XP-endo shaper and TRUShape instruments," *Journal of Endodontia*, vol. 44, no. 1, pp. 168–172, 2018.
- [39] M. E. Kaval, I. D. Capar, H. Ertas, and B. H. Sen, "Comparative evaluation of cyclic fatigue resistance of four different nickel-titanium rotary files with different cross-sectional designs and alloy properties," *Clinical Oral Investigations*, vol. 21, no. 5, pp. 1527–1530, 2017.
- [40] C. M. Larsen, I. Watanabe, G. N. Glickman, and J. He, "Cyclic fatigue analysis of a new generation of nickel titanium rotary instruments," *Journal of Endodontia*, vol. 35, no. 3, pp. 401–403, 2009.
- [41] S. B. Mize, D. J. Clement, J. P. Pruett, and D. L. J. Carnes, "Effect of sterilization on cyclic fatigue of rotary nickel-titanium endodontic instruments," *Journal of Endodontia*, vol. 24, no. 12, pp. 843–847, 1998.
- [42] A. C. D. Viana, B. M. Gonzalez, V. T. L. Buono, and M. G. A. Bahia, "Influence of sterilization on mechanical properties and fatigue resistance of nickel-titanium rotary endodontic instruments," *International Endodontic Journal*, vol. 39, no. 9, pp. 709–715, 2006.
- [43] T. R. Tripi, A. Bonaccorso, and G. G. Condorelli, "Cyclic fatigue of different nickel-titanium endodontic rotary instruments," *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontics*, vol. 102, no. 4, pp. e106–e114, 2006.
- [44] G. Gambarini, "Cyclic fatigue of nickel-titanium rotary instruments after clinical use with low-and high-torque endodontic motors," *Journal of Endodontia*, vol. 27, no. 12, pp. 772–774, 2001.
- [45] M. G. A. Bahia, R. C. Martins, B. M. Gonzalez, and V. T. L. Buono, "Physical and mechanical characterization and the influence of cyclic loading on the behaviour of nickel-titanium wires employed in the manufacture of rotary endodontic instruments," *International Endodontic Journal*, vol. 38, no. 11, pp. 795–801, 2005.
- [46] H. P. Lopes, E. J. L. Moreira, C. N. Elias, R. A. de Almeida, and M. S. Neves, "Cyclic fatigue of protaper instruments," *Journal of Endodontia*, vol. 33, no. 1, pp. 55–57, 2007.
- [47] C. Aydin, U. Inan, and Y. M. Tunca, "Comparison of cyclic fatigue resistance of used and new RaCe instruments," *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontics*, vol. 109, no. 3, pp. e131–e134, 2010.
- [48] D. Fife, G. Gambarini, and L. Britto Lr, "Cyclic fatigue testing of ProTaper NiTi rotary instruments after clinical use," *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontics*, vol. 97, no. 2, pp. 251–256, 2004.
- [49] G. Gambarini, "Cyclic fatigue of ProFile rotary instruments after prolonged clinical use," *International Endodontic Journal*, vol. 34, no. 5, pp. 386–389, 2001.

- [50] A. S. Nair, M. Tilakchand, and B. D. Naik, "The effect of multiple autoclave cycles on the surface of rotary nickel-titanium endodontic files: an in vitro atomic force microscopy investigation," *Journal of Conservative Dentistry*, vol. 18, no. 3, pp. 218–222, 2015.
- [51] J. A. Duque, C. M. Bramante, M. A. H. Duarte, M. P. Alcalde, E. J. N. L. Silva, and R. R. Vivan, "Cyclic fatigue resistance of nickel-titanium reciprocating instruments after simulated clinical use," *Journal of Endodontics*, vol. 46, no. 11, pp. 1771–1775, 2020.
- [52] S. T. Seago, B. E. Bergeron, T. C. Kirkpatrick et al., "Effect of repeated simulated clinical use and sterilization on the cutting efficiency and flexibility of Hyflex CM nickel-titanium rotary files," *Journal of Endodontia*, vol. 41, no. 5, pp. 725–728, 2015.
- [53] W. Kim, S. Oh, G.-J. Ryu et al., "Effect of autoclave sterilization on cyclic fatigue and torsional fracture resistance of NiTi rotary instruments," *Odontology*, vol. 108, no. 2, pp. 194–201, 2020.