

Cite this: *RSC Adv.*, 2019, 9, 23744

Rational design of MgF₂ catalysts with long-term stability for the dehydrofluorination of 1,1-difluoroethane (HFC-152a)†

Haodong Tang,^{*a} Mingming Dang,^b Yuzhen Li,^a Lichun Li,^{id}^{*b} Wenfeng Han,^a Zongjian Liu,^b Ying Li^{id}^a and Xiaonian Li^a

In this study, three different approaches, *i.e.* the sol–gel method, precipitation method and hard-template method, were applied to synthesize MgF₂ catalysts with improved stability towards the dehydrofluorination of hydrofluorocarbons (HFCs); the *in situ* XRD technique was employed to investigate the relationship between the calcination temperature and the crystallite size of precursors to determine optimal calcination temperature for the preparation of the MgF₂ catalysts. Moreover, the physicochemical properties of MgF₂ catalysts were examined *via* BET, XRD, EDS and TPD of NH₃ and compared. Undoubtedly, the application of different methods had a significant influence on the surface properties and catalytic performances of MgF₂ catalysts. The surface areas of the catalysts prepared by the precipitation method, sol–gel method and template method were 120, 215 and 304 m² g⁻¹, respectively, upon calcination at 200 °C. However, the surface area of the MgF₂ catalysts decreased significantly when the calcination temperatures of 300 and 350 °C were applied. The catalytic performance of these catalysts was evaluated *via* the dehydrofluorination of 1,1-difluoroethane (HFC-152a). The MgF₂ catalyst prepared by the precipitation method showed the lowest catalytic activity among all the MgF₂ catalysts. When the calcination temperature was above 300 °C, the MgF₂ catalysts prepared *via* the template method demonstrated the highest catalytic conversion rate with catalytic activity following the order: MgF₂-T (template method) > MgF₂-S (sol–gel method) > MgF₂-P (precipitation method). The conversion rate generally agreed with the total amount of acid on the surface of the catalysts, which was measured by the NH₃-TPD technique. The MgF₂-T catalysts were further examined for the dehydrofluorination of HFC-152a for 600 hours, and a conversion rate greater than 45% was maintained, demonstrating superior long-term stability of these catalysts.

Received 6th June 2019

Accepted 11th July 2019

DOI: 10.1039/c9ra04250d

rsc.li/rsc-advances

1 Introduction

Polyvinyl fluoride (PVF) is a widely used polymeric material because of its outstanding resistance to weathering, chemically inert nature, suitable mechanical strength, low permeability and light transmittance.^{1,2} PVF has been commonly applied in packaging, glazing and electrical applications; the production of vinyl fluoride (VF) is rather important as it is the raw chemical material for the synthesis of PVF. The dehydrofluorination of 1,1-difluoroethane (HFC-152a) is the most broadly used chemical process for the production of VF. The dehydrofluorination of hydrofluorocarbons (HFCs) is generally accepted to be thermodynamically and kinetically hindered.^{3,4} Hence, it is essential to employ highly effective catalysts to accelerate the reaction

rate and improve the yield of the target product. Currently, the commonly used catalysts for the dehydrofluorination of hydrofluorocarbons (HFCs) are Lewis acid catalysts including chromia^{5–7} and alumina^{5,8}-based catalysts. However, the chromia and alumina-based catalysts often suffer from short lifetime as they get deactivated from coking on the strong Lewis acid offered by the catalysts. Zhu *et al.* have reported the application of porous alumina (Al₂O₃) as a catalyst for the dehydrofluorination of 1,1,1,2-tetrafluoroethane and demonstrated that strong Lewis acid sites are responsible for the deactivation of catalysts due to coke formation.⁸ As reported by Luo *et al.*,⁶ the catalytic dehydrofluorination of 1,1,1,3,3-pentafluoropropane was investigated using Cr₂O₃ as a catalyst. The results showed that the conversion rate of the Cr₂O₃ catalyst significantly decreased from 68% to 23% after a 10 hour test, and the addition of NiO benefited the stability of the catalyst. Due to its high strength, the Lewis acid certainly acts as an active site and offers high conversion rate; however, it also increases the chances of catalyst deactivation.

On the other hand, magnesium fluoride (MgF₂) nanoparticles have been widely applied as supporting materials and

^aInstitute of Industrial Catalysis, Zhejiang University of Technology, Hangzhou, 310014, PR China. E-mail: tanghd@zjut.edu.cn; lichunli@zjut.edu.cn

^bCollege of Chemical Engineering, Zhejiang University of Technology, Hangzhou, 310014, PR China

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c9ra04250d



heterogeneous catalysts because they contain medium-strength Lewis acids, which are less likely to get deactivated due to coking;^{5,9–11} MgF_2 typically exists in the rutile form where each Mg^{2+} ion is surrounded by six F^- ions and each F^- ion is surrounded by three Mg^{2+} ions.^{12,13} A typical MgF_2 crystal does not contain any acid property and exists in the form of a neutral solid. Therefore, the manipulation of the synthesis method offers an intelligent way to modify the surface property and create a surface disordered MgF_2 material to produce medium-strength Lewis acid sites on the surface. This can be explained by the Tanabe model where the surface acidity of MgF_2 is generated from the excessive positive charge caused by the coordinated unsaturated Mg^{2+} ions on the surface;¹⁴ the generation of high surface area is often accompanied by the production of large amount of acid sites;¹⁵ therefore, significant research efforts have been focused on the synthesis of high-surface area MgF_2 (HS- MgF_2).^{16–23} Kemnitz *et al.*¹⁷ have successfully synthesized amorphous nano-sized MgF_2 with the high surface area of $150\text{--}350\text{ m}^2\text{ g}^{-1}$ *via* a non-aqueous fluoro-lytic sol-gel method. The results of the analysis of temperature-programmed desorption of ammonia (NH_3 -TPD) showed that the strong acid sites disappeared when the catalysts were pre-treated at $300\text{ }^\circ\text{C}$, and above this temperature, the structure of HS- MgF_2 would probably be affected. The microemulsion route was also applied as another effective method to synthesise HS- MgF_2 .^{22,23} Saberi *et al.*¹³ have prepared HS- MgF_2 with the surface area of $190\text{ m}^2\text{ g}^{-1}$ and the average crystallite size of $9\text{--}11\text{ nm}$ *via* the microemulsion route. However, it was challenging to remove the microemulsion agent.

Despite all these promising efforts towards the synthesis of HS- MgF_2 , to date, the MgF_2 catalysts still suffer from deactivation caused by the aggrandizement of particle size at evaluated temperatures. The main purposes of this study were to rationally design and manufacture the surface properties of MgF_2 as they govern the catalytic performance of the catalyst. In this study, three different synthesis methods, *i.e.* the precipitation method, aqueous sol-gel method and hard template method, were attempted to synthesize MgF_2 . The *in situ* XRD technique was first applied to examine the effect of calcination temperature on the MgF_2 size. Moreover, three calcination temperatures, *i.e.* 200 , 300 and $350\text{ }^\circ\text{C}$, were selected and used in each synthesis method to further evaluate the influence of calcination temperature on catalyst properties. The nine MgF_2 samples prepared using three synthesis methods and three calcination temperatures were examined *via* Brunauer–Emmett–Teller (BET), X-ray powder diffraction (XRD) and NH_3 -TPD techniques to reveal the surface properties of these samples. The dehydrofluorination of 1,1-difluoroethane (HFC-152a) was employed as a probe reaction to test the catalytic performance of the MgF_2 catalysts. The surface acidic property was further employed to rationalize the catalytic performance of the MgF_2 catalysts.

2 Materials and methods

Chemicals

$\text{Mg}(\text{AC})_2$ (AR grade, Sinopharm Chemical Reagent Co., Ltd), NH_4F (AR grade, Sinopharm Chemical Reagent Co., Ltd), SP-15

(Hangzhou Wanjing Chemical Reagent Co., Ltd), and HF (40 wt%, Quzhou Juhua Reagents Co., Ltd.) were used as obtained without further purification. 1,1-Difluoroethane (HFC-152a, 99.0%) was purchased from Zhejiang Juhua Group Company.

Preparation of catalysts

Precipitation method. The prepared $\text{Mg}(\text{AC})_2$ solution was mixed with the NH_4F solution under rigorous stirring for 1 hour to ensure complete precipitation. The molar ratio of $\text{F} : \text{Mg}$ was controlled to be $2 : 1$. The resulting gel solution was aged for 3 hours before filtration for three times. The generated residue was dried in an oven for 12 hours at $100\text{ }^\circ\text{C}$. The dry paste was then calcined for 4 hours at 200 , 300 and $350\text{ }^\circ\text{C}$ under an air atmosphere. The obtained product was labelled as $\text{MgF}_2\text{-P}$.

Sol-gel method. Mg turnings were added to excess amount of anhydrous methanol to form magnesium methoxide slurry under rigorous stirring. The obtained mixture was then fluorinated by adding a certain amount ($\text{F}/\text{Mg} = 2 : 1$) of 40 wt% HF solution followed by stirring for 1 hour until a clear gel was formed. The resulting gel mixture was subjected to aging for 3 hours at room temperature and then dried overnight under vacuum at $70\text{ }^\circ\text{C}$. The dried samples were calcined for 4 hours at 200 , 300 and $350\text{ }^\circ\text{C}$. The obtained product was labelled as $\text{MgF}_2\text{-S}$.

Template method. SP-15 (SiO_2) was first soaked in the $\text{Mg}(\text{AC})_2$ solution before the addition of the NH_4F solution to ensure the fluorination process. Rigorous stirring was applied for one hour to produce a gel solution. The gel solution was aged for three hours before filtration. The residue was then dried at $100\text{ }^\circ\text{C}$ for 12 hours and calcined for 4 hours at 200 , 300 and $350\text{ }^\circ\text{C}$ under an air atmosphere. The calcined product was transferred into a 40 wt% HF solution to remove the SP-15 template. The obtained product was labelled as $\text{MgF}_2\text{-T}$.

Characterisation

The surface area of the catalysts was examined using N_2 gas sorption *via* the Micromeritics ASAP 2000 instrument at $-196\text{ }^\circ\text{C}$. The samples were degassed at $120\text{ }^\circ\text{C}$ for 6 hours before each measurement. The surface area was evaluated by the Brunauer–Emmett–Teller (BET) method using the adsorption data. Pore size distributions were obtained from the adsorption branches *via* a nonlocal density functional theory (NLDFT) method. The pore volume was approximated at the relative pressure P/P_0 of 0.99.

X-ray powder diffraction (XRD) characterization was conducted using the X'pert PRO diffractometer with $\text{Cu K}\alpha$ radiation (40 kV and 100 mA) in the range of $10^\circ \leq 2\theta \leq 80^\circ$. The as-prepared MgF_2 catalysts were evaluated before and after the dehydrofluorination reaction of HFC-152 using the XRD technique.

The *in situ* XRD characterization was performed using the same instrument under the same conditions with temperature ranging from 25 to $400\text{ }^\circ\text{C}$, which was controlled *via* a thermocouple in the presence of a H_2 atmosphere. The MgF_2 samples prepared by the precipitation, sol-gel, and template methods

before calcination were examined *via* the *in situ* XRD technique at temperatures between 25 and 400 °C.

The temperature-programmed desorption of ammonia (NH₃-TPD) was used to reveal the distribution and strength of the acid sites on the catalysts. The MgF₂ sample (about 0.15 g) was first degassed by heating at 300 °C for 30 minutes under an argon atmosphere. After being gently cooled down to room temperature, the catalyst was exposed to a gas mixture containing 10% of NH₃ and 90% of He for 30 minutes. The TPD program was started (10 °C min⁻¹ up to 850 °C) after the excess amount of NH₃ was flushed out under N₂ at 100 °C. The amount of desorbed NH₃ was continuously monitored *via* online mass spectrometry.

Energy dispersive spectrometry (EDS) analysis was performed using the HITACHI 7700 microscope at the accelerating voltage of 100 kV.

Catalytic performance

The MgF₂ catalysts were applied for the dehydrofluorination of HFC-152 to evaluate the catalytic performance of the catalysts prepared using different synthesis methods and calcination temperatures. The dehydrofluorination reaction of HFC-152 is shown in eqn (1).



In a typical experiment, about 2.0 mL of the catalyst was packed in the Nickel-iron-chromium alloy tube flow reactor with the flowing mixed gases of HFC-152 (~25 mL min⁻¹) and N₂ (20 mL min⁻¹). The reaction was performed at 200, 300 and 350 °C under atmospheric conditions. The component of the gas phase was monitored by a gas chromatography instrument (GC16900) equipped with the TCD analyzer.

3 Results and discussion

In situ XRD

Fig. 1 shows the *in situ* XRD patterns of the pre-calcined MgF₂-S, MgF₂-T, and MgF₂-P catalysts obtained under a H₂ atmosphere with temperature ranging from 25 to 450 °C. The distinct advantage of the *in situ* XRD measurement is that it eliminates the multiple XRD measurements of the MgF₂ samples calcined at different temperatures, which are time and effort consuming; herein, the MgF₂ samples examined *via* the *in situ* XRD measurements are not exactly the same as the actual catalysts as they have typically undergone a calcination process at a certain temperature for 4 hours under a N₂ atmosphere. The purpose of the *in situ* XRD measurements was to rationalize the relationship between the calcination temperature and the size of the MgF₂ crystallite to confirm that temperature played an important role in the crystallite size and select optimal temperature for the synthesis of the MgF₂ catalysts.

The different planes of the MgF₂ crystallite with corresponding diffraction peaks are shown in Fig. 1(a)–(c). This validated that all the preparation methods could successfully produce MgF₂ catalysts.

It is also clear that with the increasing temperature, all the diffraction peaks become sharp at full-width-at-half maxima;




Fig. 1 *In situ* XRD patterns of the MgF₂ catalysts MgF₂-P (a), MgF₂-S (b), and MgF₂-T (c) catalysts at calcination temperatures varying from 25 to 450 °C.

this indicates the growth of MgF₂ crystallites. To further investigate the effect of temperature on crystallite size, the Scherrer equation was employed to calculate the average crystallite size of MgF₂ based on the diffraction peak at 40.12° representing the (111) plane of the MgF₂ crystallite in the *in situ* XRD patterns shown in Fig. 1. The average MgF₂ crystal size as a function of temperature is plotted in Fig. 2.

As can be concluded from Fig. 2, there is no significant change in the average crystal size of MgF₂ when the treatment temperature is below 300 °C, whereas the crystal size increases significantly when the temperature increases up to 300 °C and above. Therefore, it can be concluded that the crystal size is very sensitive to the treatment temperature; this is of significant use for the rational optimization of the calcination temperature during the synthesis of the MgF₂ catalysts. Hence, three calcination temperatures were selected and used for the preparation of MgF₂ catalysts: 200, 300 and 350 °C. In addition, the crystal




Fig. 2 Average crystal size of MgF_2 crystallites of the catalysts prepared *via* three different methods as a function of atmospheric temperature calculated from the diffraction peak at 40.12° representing the (111) plane of the MgF_2 crystallite.

size generally followed the trend $\text{MgF}_2\text{-T} > \text{MgF}_2\text{-P} > \text{MgF}_2\text{-S}$ at all temperatures.

Characterization of the MgF_2 catalysts

The MgF_2 catalysts synthesized *via* different methods using three different calcination temperatures certainly exhibited different surface properties including surface area, pore structure, crystal size as well as surface acid properties. The N_2 adsorption/desorption isotherms together with the pore size distribution for the nine MgF_2 samples are shown in Fig. 3.

All the MgF_2 catalysts synthesized using different methods and calcination temperatures belong to the type IV isotherm




Fig. 3 N_2 adsorption/desorption isotherms (a) together with the pore size distribution (b) for samples: $\text{MgF}_2\text{-P-200}^\circ\text{C}$, $\text{MgF}_2\text{-P-300}^\circ\text{C}$, $\text{MgF}_2\text{-P-350}^\circ\text{C}$, $\text{MgF}_2\text{-S-200}^\circ\text{C}$, $\text{MgF}_2\text{-S-300}^\circ\text{C}$, $\text{MgF}_2\text{-S-350}^\circ\text{C}$, $\text{MgF}_2\text{-T-200}^\circ\text{C}$, $\text{MgF}_2\text{-T-300}^\circ\text{C}$ and $\text{MgF}_2\text{-T-350}^\circ\text{C}$.

and H1 hysteresis loop, indicating the existence of a mesoporous structure. All the MgF_2 samples possess inter-particle voids with an exception of $\text{MgF}_2\text{-S-200}^\circ\text{C}$ that possesses an intra-particle mesoporous property. The surface area and the average pore size of all the catalysts are listed in Table 1. The surface area generally decreased with an increase in calcination temperature for all three different preparation methods. When the calcination temperature was 200°C , high-surface area MgF_2 (HS-MgF_2) catalysts were successfully prepared with the surface area following the trend: $\text{MgF}_2\text{-T}$ ($304\text{ m}^2\text{ g}^{-1}$) $>$ $\text{MgF}_2\text{-S}$ ($215\text{ m}^2\text{ g}^{-1}$) $>$ $\text{MgF}_2\text{-P}$ ($120\text{ m}^2\text{ g}^{-1}$). With an increase in calcination temperature, the surface area decreased dramatically in all cases. For example, the surface area of the MgF_2 catalysts prepared using the hard template method decreased from $304\text{ m}^2\text{ g}^{-1}$ to $24\text{ m}^2\text{ g}^{-1}$ when the calcination temperature was increased from 200 to 350°C . This observation shows a good agreement with the open literature that calcination at high temperatures causes a decrease in the surface area of MgF_2 .¹⁷ The average pore size of all the MgF_2 catalysts is mainly in the range from 5 to 33 nm, indicating the mesoporous nature of all catalysts. Moreover, the MgF_2 crystallite size increases notably with an increase in the calcination temperature; this agrees well with the *in situ* XRD results. This verifies the application of the *in situ* XRD technique for the intelligent selection of catalysts calcination temperature.

NH_3 -TPD analysis

The temperature-programmed desorption of ammonia (NH_3 -TPD) was employed to reveal the surface acidic properties of the MgF_2 catalysts. In general, the NH_3 desorption peak is a measure of the strength of the acid sites in the catalyst, whereas the area of the desorption peak is an indication of the amount of acid. The NH_3 -TPD results of the $\text{MgF}_2\text{-S}$, $\text{MgF}_2\text{-T}$, and $\text{MgF}_2\text{-P}$ catalysts calcined at 200°C (a), 300°C (b) and 350°C (c) are shown in Fig. 4.

To distinguish between the medium and high-strength acid sites in the catalysts, the desorption of NH_3 at a temperature less than 350°C is attributed to the presence of medium-strength acid sites, whereas the desorption of NH_3 at a temperature greater than 350°C is ascribed to the presence of high-

Table 1 Surface area and crystal size of the MgF_2 catalysts

Catalyst	Surface area ^a ($\text{m}^2\text{ g}^{-1}$)	Pore size ^a (nm)	Crystal size ^b (nm)	
$\text{MgF}_2\text{-P}$	200°C	120	30	82
	300°C	63	18	142
	350°C	20	12	226
$\text{MgF}_2\text{-T}$	200°C	304	19	163
	300°C	97	28	191
	350°C	24	18	217
$\text{MgF}_2\text{-S}$	200°C	215	5	67
	300°C	46	33	91
	350°C	22	10	196

^a Calculated from the nitrogen physical desorption isotherm.

^b Calculated from the XRD results employing the Debye-Scherrer equation.




Fig. 4 NH_3 -TPD results of MgF_2 -S, MgF_2 -T, and MgF_2 -P catalysts calcined at 200 °C (a), 300 °C (b) and 350 °C (c).

strength acid sites on the catalysts. The amount of acid desorbed at 350 °C for the MgF_2 -P-200 °C sample was normalized to 1. Following this, the amount of the medium, strong and total amount of acid sites on the surface of the MgF_2 catalysts was calculated, and the results are presented in Table 2.

Note that the total amount of acid decreases when the calcination temperature increases from 300 to 350 °C; this confirms the conclusion reported by Kemnitz *et al.*¹⁷ that the acidity of MgF_2 gradually diminishes upon heating; however, for the MgF_2 samples prepared by the precipitation method, the amount of acid does not change significantly with only minor changes in the NH_3 desorption temperature. For the MgF_2 -P

catalysts, the NH_3 desorption peaks appeared at ~ 350 °C upon calcination at 200 °C, whereas the NH_3 desorption peaks appeared at ~ 450 °C upon calcination at 300 and 350 °C. MgF_2 -P exhibited lowest amount of acid because it did not have enough surface defects to provide acid sites; moreover, the relatively stable structure of MgF_2 -P with low surface defects did not experience a significant change at different calcination temperatures, which contributed to the relatively uniform amount of acid at different calcination temperatures. It can also be observed from Table 2 that the lowest total amount of acid can be observed on the surface of MgF_2 prepared *via* the precipitation method. The total amount of acid follows the order: MgF_2 -S > MgF_2 -T > MgF_2 -P at 200 and 300 °C and MgF_2 -T > MgF_2 -S > MgF_2 -P at 350 °C.

Catalytic reactivity

The MgF_2 catalysts synthesized *via* three different approaches at three calcination temperatures were applied for the production of VF *via* the dehydrofluorination of HFC-152a.

The temperature employed for the dehydrofluorination of HFC-152a was kept the same as the calcination temperature of the catalyst. The dehydrofluorination reaction of CF_2HCH_3 (HFC-152a) in this study exhibited almost 100% selectivity towards the target product $\text{CH}_2=\text{CHF}$ under the reaction conditions applied herein with the MgF_2 catalysts. This observation agrees well with the results reported in the open literature where the reaction of CH_2FCF_3 (ref. 8) and HFC-152a (ref. 7) over Lewis acid catalysts shows almost 100% selectivity towards the dehydrofluorination product. As can be observed from Fig. 5, the conversion rate generally increases with the increasing temperature, which agrees well with literature.⁷ The conversion rate was between 8% and 20% at 200 °C, between 35% and 55% at 300 °C, and between 55% and 85% at 350 °C. The conversion rate at 350 °C was comparable to that obtained using chromia-based catalysts (Cr_2O_3) in the dehydrofluorination of HFC-152a in our previous study.⁷

MgF_2 prepared *via* the precipitation method showed the lowest conversion rate at all three temperatures. At 200 °C, the conversion rate follows the order: MgF_2 -S > MgF_2 -T > MgF_2 -P. This agrees well with the trend of the total amount of acid on the surface of the catalysts as surface acids contribute to the active sites for the dehydrofluorination reaction. For the reaction temperature above 300 °C, MgF_2 prepared *via* the hard template method demonstrates the best conversion rate with all the conversion rates following the order: MgF_2 -T > MgF_2 -S > MgF_2 -P. Note that the conversion rate obtained using the MgF_2 catalysts synthesized using the hard template method outperformed that obtained using the MgF_2 catalysts synthesized

Table 2 Amount of medium, high strength and total acid on the MgF_2 catalysts

	MgF_2 -P			MgF_2 -T			MgF_2 -S		
	200 °C	300 °C	350 °C	200 °C	300 °C	350 °C	200 °C	300 °C	350 °C
Med.	0.0	0.0	0.0	1.2	4.2	1.4	4.8	1.4	1.0
Str.	1.1	1.1	1.0	1.8	4.3	1.1	0.0	2.6	2.8
Total	1.1	1.1	1.0	3.0	8.5	2.4	4.8	4.0	3.8

using the sol-gel method when the calcination temperature was greater than 300 °C. For the conversion rate at 300 °C, the order matches with the amount of acid on the surface of the MgF_2 catalysts prepared by different preparation methods. It can also be observed in Fig. 5(b) that the MgF_2 -T catalyst demonstrates the best stability with no obvious decrease in the conversion rate after 25 hours of reaction. However, with same time span, there is somehow a slight decrease in the conversion rate in the case of both MgF_2 -S and MgF_2 -P catalysts. In other words, MgF_2 -T demonstrates the best stability among all three catalysts at 300 °C.

For the catalytic performance at 350 °C, as shown in Fig. 5(c), the MgF_2 -T catalyst exhibits the best conversion rate and stability among all three MgF_2 catalysts. However, as shown in Table 2, there is more relative amount of acid on the surface of the MgF_2 -S catalyst than that on the MgF_2 -T catalyst; this is not exactly consistent with the overall conversion rate shown in




Fig. 5 Conversion rate as a function of time on stream for three MgF_2 catalysts, including MgF_2 -S, MgF_2 -T, and MgF_2 -P at 200 °C (a), 300 °C (b) and 350 °C (c).

Fig. 5(c). This discrepancy is likely due to the fact that the MgF_2 -S catalyst deactivates very quickly when exposed to high temperatures. The conversion rates of the MgF_2 -T catalyst in the initial three hours were determined and are shown in Fig. S1, ESI,† demonstrating its intense deactivation rate with a decrease in the conversion rate from ~81.8% to 77.5% in the initial 2.5 hours; after reaction for ~30 hours, the conversion rate upon the MgF_2 -T catalyst still remains at ~80%, which is only about 5% less than the initial conversion rate. Note that this catalytic performance is comparable to that obtained using the chromia-based Lewis acid catalysts reported in open literature.⁷ However, the conversion rate of both MgF_2 -S and MgF_2 -P catalysts declined substantially to about 57% during the reaction within same time span. To further investigate the reason for the deactivation of the MgF_2 catalysts, XRD and EDS techniques were employed to measure the crystal size and surface carbon content of the MgF_2 -T, MgF_2 -S, and MgF_2 -P catalysts before and after reaction for ~30 hours at 350 °C. The results are listed in Table 3. As can be observed from Table 3, there are no major changes between the surface carbon contents of the as-prepared and post-reaction MgF_2 catalysts. Thus, coking can be excluded from the main reasons accounting for the deactivation of the MgF_2 -S and MgF_2 -P catalysts. On the other hand, the crystal size of the MgF_2 synthesised *via* the sol-gel method and precipitation method increased significantly from below 10 nm to ~20 nm. This is consistent with the *in situ* XRD results stating that the size of the MgF_2 crystal increases drastically with the increasing temperature. This is probably the main reason why the MgF_2 -S and MgF_2 -P catalysts easily deactivate than MgF_2 -T at high temperatures.

Stability performance

The MgF_2 -T-300 °C catalysts were further examined for about 600 hours for the dehydrofluorination reaction of HFC-152a to test the stability and lifetime of the catalysts, which are shown in Fig. 6(a). The conversion rate of the MgF_2 -S catalyst shows good stability as it remains greater than 45% at the reaction time of 600 hours. To the best of our knowledge, the longest reaction time reported in the open literature is 100 hours using Cr_2O_3 -based catalysts.⁷ The MgF_2 catalysts reported in this study have certainly demonstrated superior stability as catalysts for the dehydrofluorination of HFCs.

The XRD patterns were obtained for the MgF_2 -T-300 °C catalyst before and after the 600 hour test to evaluate the

Table 3 Crystal size and surface carbon content of the MgF_2 -T, MgF_2 -S, and MgF_2 -P catalysts before and after reaction at 350 °C

Catalysts		Crystal size nm ^a	Surface carbon ^b %
MgF_2 -T-350 °C	Fresh	16	3.88
	Post-reaction	21	3.45
MgF_2 -S-350 °C	Fresh	6	4.07
	Post-reaction	19	4.36
MgF_2 -P-350 °C	Fresh	8	2.91
	Post-reaction	22	3.64

^a Calculated from the XRD results employing the Debye-Scherrer equation. ^b From the EDS measurements.




Fig. 6 (a) Conversion rate of the $\text{MgF}_2\text{-T}$ catalyst as a function of reaction time at 300 °C and (b) XRD patterns of the $\text{MgF}_2\text{-T}$ catalyst before and after the reaction.

changes in the crystal size of the catalyst, as shown in Fig. 6(b). As can be observed in Fig. 6(b), there are no significant changes in the diffraction peaks before and after the reaction with only a minor increase in the intensity of the peaks. The crystal size in the (111) plane of MgF_2 was calculated applying the Scherrer equation. The crystal size increased from ~ 19.1 nm to ~ 22.9 nm after the 600 hour test. This minor increase in the crystal size is probably the reason why the MgF_2 catalysts prepared *via* the template method demonstrate superior long-term stability throughout the 600 hour test at 300 °C. In addition, the surface carbon content of the $\text{MgF}_2\text{-T}$ catalyst after the 600 hour reaction was examined *via* the EDS technique. The surface carbon content of the $\text{MgF}_2\text{-T}$ catalyst after the 600 h reaction was revealed to be 4.74%, demonstrating only minor changes from the initial carbon content before reaction (3.88%). This indicates that the $\text{MgF}_2\text{-T}$ catalyst has high resistance towards coking when applied as a catalyst for the dehydrofluorination of HFC-152a at 350 °C.

4 Conclusions

To manipulate the surface property and rationally design the catalytic performance of MgF_2 catalysts, three synthesis methods were used and compared in the current study. The *in situ* XRD results showed that the crystal size increased dramatically when the calcination temperature was greater than 300 °C. Moreover, three temperatures, *i.e.* 200 °C, 300 °C and 350 °C, were investigated to further evaluate the effect of calcination temperature on the surface properties of the catalysts. At

the calcination temperature of 200 °C, high-surface area MgF_2 catalysts were generated *via* all preparation methods, whereas at a calcination temperature greater than 200 °C, the surface area decreased significantly; this agreed well with the *in situ* XRD results. The catalytic performance of the catalysts followed the order: $\text{MgF}_2\text{-S} > \text{MgF}_2\text{-T} > \text{MgF}_2\text{-P}$ at 200 °C, whereas it was $\text{MgF}_2\text{-T} > \text{MgF}_2\text{-S} > \text{MgF}_2\text{-P}$ at 300 and 350 °C. The order of the catalytic performance generally agreed with the total amount of acid measured by the $\text{NH}_3\text{-TPD}$ technique. Among the MgF_2 catalysts prepared *via* different methods, the MgF_2 catalysts synthesized *via* the hard template method demonstrated best stability for the dehydrofluorination of HFC-152a. Moreover, the $\text{MgF}_2\text{-T-300 °C}$ catalyst was successfully applied for the dehydrofluorination of HFC-152a for 600 hours, and the conversion rate remained greater than 45%, showing the superior long-term stability of this catalyst.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors acknowledge the financial support received from the Zhejiang Natural Science Foundation, LY19B060009.

References

- 1 J. K. Murthy, U. Groß, S. Rüdiger, E. Ünveren and E. Kemnitz, *J. Fluorine Chem.*, 2004, **125**, 937–949.
- 2 S. Ebnesajjad and L. G. Snow, Poly(vinyl fluoride), in *Encyclopedia of Chemical Technology*, ed. J. I. Kroschwitz, Wiley, New York, 4th edn, 1994, vol. 11, pp. 683–694.
- 3 A. W. Baker, D. Bonniface, T. M. Klapötke, I. Nicol, J. D. Scott, W. D. S. Scott, R. R. Spence, M. J. Watson, G. Webb and J. M. Winfield, *J. Fluorine Chem.*, 2000, **102**, 279–284.
- 4 A. Kohne and E. Kemnitz, *J. Fluorine Chem.*, 1995, **75**, 103–110.
- 5 G.-L. Li, H. Nishiguchi, T. Ishihara, Y. Moro-oka and Y. Takita, *Appl. Catal., B*, 1998, **16**, 309–317.
- 6 J.-W. Luo, J.-D. Song, W.-Z. Jia, Z.-Y. Pu, J.-Q. Lu and M.-F. Luo, *Appl. Surf. Sci.*, 2018, **433**, 904–913.
- 7 W. Han, X. Li, H. Tang, Z. Wang, M. Xi, Y. Li and H. Liu, *J. Nanoparticle Res.*, 2015, **17**, 365.
- 8 W. Jia, W. Qian, X. Lang, H. Chao, G. Zhao, J. Li and Z. Zhu, *Catal. Lett.*, 2015, **145**, 654–661.
- 9 M. Wojciechowska, J. Bartoszewicz and J. Goslar, *ChemInform*, 1995, **26**, 2207–2211.
- 10 A. Malinowski, W. Juszczyk, J. Pielaszek, M. Bonarowska, Z. Karpiński and M. Wojciechowska, *Chem. Commun.*, 1999, **8**, 685–686.
- 11 M. Wojciechowska, M. Pietrowski, S. Lomnicki and B. Czajka, *Catal. Lett.*, 1997, **46**, 63–69.
- 12 W. H. Baur and A. A. Khan, *Acta Crystallogr., Sect. B: Struct. Crystallogr. Cryst. Chem.*, 2010, **27**, 2133–2139.
- 13 A. Saberi, Z. Negahdari, S. Bouazza and M. Willert-Porada, *J. Fluorine Chem.*, 2010, **131**, 1353–1355.

- 14 E. Kemnitz, Y. Zhu and B. Adamczyk, *J. Fluorine Chem.*, 2002, **114**, 163–170.
- 15 E. Kemnitz and S. Rüdiger, *High Surface Area Metal Fluorides as Catalysts*, 2010.
- 16 I. Agirrezabal-Telleria, F. Hemmann, C. Jäger, P. L. Arias and E. Kemnitz, *J. Catal.*, 2013, **305**, 81–91.
- 17 J. Krishna Murthy, U. Groß, S. Rüdiger, E. Kemnitz and J. M. Winfield, *J. Solid State Chem.*, 2006, **179**, 739–746.
- 18 I. Agirrezabal-Telleria, Y. Guo, F. Hemmann, P. L. Arias and E. Kemnitz, *Catal. Sci. Technol.*, 2014, **4**, 1357–1368.
- 19 A. B. D. Nandiyanto, O. Takashi and O. Kikuo, *ACS Appl. Mater. Interfaces*, 2014, **6**, 4418–4427.
- 20 M. Chen, J. M. Jin, S. D. Lin, Y. Li, W. C. Liu, L. Guo, L. Li and X. N. Li, *J. Fluorine Chem.*, 2013, **150**, 46–52.
- 21 J. Noack, K. Teinz, C. Schaumberg, C. Fritz, S. Rüdiger and E. Kemnitz, *J. Mater. Chem.*, 2010, **21**, 334–338.
- 22 M. Pietrowski, M. Zieliński and M. Wojciechowska, *Pol. J. Chem. Technol.*, 2014, **16**, 63–68.
- 23 A. Saberi, Z. Negahdari, S. Bouazza and M. Willert-Porada, *J. Fluorine Chem.*, 2010, **131**, 1353–1355.