

ORIGINAL ARTICLE

Open Access



Substrate stereoselectivity of poly(Asp) hydrolase-1 capable of cleaving β -amide bonds as revealed by investigation of enzymatic hydrolysis of stereoisomeric β -tri(Asp)s

Tomohiro Hiraishi^{1,2*}, Hideki Abe² and Mizuo Maeda¹

Abstract

We previously reported that poly(Asp) hydrolase-1 (PahZ1_{KP-2}) from *Pedobacter* sp. KP-2 selectively, but not completely, cleaved the amide bonds between β -Asp units in thermally synthesized poly(Asp) (tPAA). In the present study, the enzymatic hydrolysis of stereoisomeric β -tri(Asp)s by PahZ1_{KP-2} was investigated to clarify the substrate stereoselectivity of PahZ1_{KP-2} in the hydrolysis of tPAA. The results suggest the following structural features of PahZ1_{KP-2} at its substrate binding site: (1) the active site contains four subsites (2, 1, -1, and -2), three of which need to be occupied by Asp units for cleavage to occur; (2) for the hydrolysis to proceed, subsite 1 should be occupied by an L-Asp unit, whereas the other three subsites may accept both L- and D-Asp units; (3) for the two central subsites between which cleavage occurs, the (L-Asp)-(D-Asp) sequence is the most favorable for cleavage.

Keywords: Poly(Asp) (PAA), PAA hydrolase-1, *Pedobacter* sp. KP-2, β -Tri(Asp)s, Stereoselectivity

Introduction

β -Peptides, in which monomer units are connected at the β -position, fold into a conformationally ordered state in solution to exert their unique properties and potentially show their enzymatic and metabolic stabilities, which are consistent with the advantages of α -peptides such as interactions with proteins, DNA/RNA, and cell membranes (Seebach et al. 2004; Seebach and Gardiner 2008). Accordingly, β -peptides have recently attracted a wide variety of interests as functional materials.

Poly(Asp) (PAA) is a bio-based, biocompatible, biodegradable, and water-soluble polymer that shows high polyanionic properties because of its high content of carboxyl groups relative to its molecular weight (Freeman et al. 1996; Kim et al. 1996; Tang and Wheeler 2001; Joentgen et al. 2003; Thombre and Sarwade 2005). Methods of synthesizing PAA have been studied, particularly

the thermal synthesis of PAA (Kim et al. 1996; Ross et al. 2001; Joentgen et al. 2003; Thombre and Sarwade 2005). Thermally synthesized PAA (tPAA) is chemically prepared on a large scale from L-Asp, resulting in low production cost compared with the microbial synthesis of polymers such as poly(malate) and poly(glutamate). From earlier structural analyses, β -Asp units account for 70% of the total composition in tPAA, indicating that tPAA is composed of a high proportion of β -peptides. The analyses also showed that tPAA contains equivalent moles of D- and L-Asp units and branching and cross-linking as unnatural structures in addition to β -Asp units (Pivcova et al. 1981, 1982; Wolk et al. 1994; Matsubara et al. 1998; Nakato et al. 1998).

Owing to the unique structural and functional characteristics of tPAA, tPAA can be used as an environmentally benign material for dispersing agents and scale inhibitors. In addition to its application as a homopolymer, tPAA derivatives, including block copolymers with poly(ethylene glycol) and hydrogel cross-linked via diamine, have attracted attention owing to their potential applications in the medical and industrial fields as drug delivery systems

*Correspondence: thiraish@riken.jp

¹ Bioengineering Laboratory, RIKEN, 2-1 Hirosawa, Wako, Saitama 351-0198, Japan

Full list of author information is available at the end of the article

and superabsorbent materials (Thombre and Sarwade 2005; Osada et al. 2009). Accordingly, it is considered that tPAA biodegradability should be carefully taken into consideration in its applications for practical use.

Generally, unnatural structures in polymer materials affect the biodegradability of the materials because polymer biodegradation is caused by naturally occurring microorganisms and secreted polymer-degrading enzymes that basically recognize naturally occurring polymer structures and their analogs. Thus, tPAA biodegradation by isolated microorganisms or purified enzymes should be examined in order to elucidate its reaction mechanism. To this end, we have isolated tPAA-degrading bacteria and enzymes from the natural environment and investigated their tPAA degradation behavior (Tabata et al. 1999, 2000, 2001; Hiraishi et al. 2003a, b, 2004, 2009; Hiraishi and Maeda 2011). We previously isolated two tPAA-degrading bacteria, *Sphingomonas* sp. KT-1 and *Pedobacter* sp. KP-2, from river water and purified two types of enzyme that may participate in tPAA biodegradation. Recently, we have characterized PAA hydrolase-1 (PahZ1_{KP-2}) from *Pedobacter* sp. KP-2 and examined its tPAA-degrading behavior. Nuclear magnetic resonance (NMR) analysis suggests that the enzyme selectively, but not completely, cleaves the amide bonds between β -Asp units in tPAA. As stated before, as the tPAA molecule contains equivalent numbers of D- and L-Asp units, unnaturally occurring sequences (D-D, D-L, L-D) formed by these units in addition to the L-L sequence may be responsible for the incomplete hydrolysis of the β - β amide bonds in tPAA by PahZ1_{KP-2}. In addition, we demonstrated the enzymatic polymerization of diethyl L-Asp to obtain β -poly(Asp) (β -PAA) by taking advantage of the substrate recognition by PahZ1_{KP-2}. The synthesized β -PAA had a relatively low molecular weight in the range of 750–2,500 (MALDI-TOF MS analysis) and the reaction needs a relatively large amount of PahZ1_{KP-2} (Hiraishi et al. 2011). This low activity of PahZ1_{KP-2} is also probably attributed to its substrate stereoselectivity. In the present study, to clarify the substrate stereoselectivity of PahZ1_{KP-2}, we conducted the enzymatic hydrolysis of β -tri(Asp)s having well-defined sequences of D- and L-Asp units using PahZ1_{KP-2} and examined the substrate-binding site of the enzyme.

Materials and methods

Materials, bacterial strains, culture conditions, plasmid, and genetic procedures

The β -tri(Asp)s with all possible combinations of L- and D-Asp units were designed, and the synthetic tri(Asp)s and di(Asp)s were purchased from Medical & Biological Laboratories. All of the other chemicals used were of biochemical grade or the highest purity, and were used

without further purification. *Escherichia coli* JM109 (Takara) and BL21(DE3) (Novagen) were used as the cloning and expression hosts, respectively. *E. coli* was grown in Luria–Bertani (LB) broth (1% Bacto trypton, 0.5% Bacto yeast extract, and 0.5% NaCl, pH 7.0) containing 100 μ g/mL ampicillin. pET-15b (Novagen) was used as the expression vector for His-tagged PahZ1_{KP-2}. All of the DNA-modifying enzymes for genetic engineering were purchased from Takara and Toyobo. The enzymes were used in accordance with the supplier's instructions. Gene manipulations were performed in accordance with standard procedures (Sambrook and Russell 2001).

Expression and purification of PahZ1_{KP-2}

PahZ1_{KP-2} was expressed using the recombinant *E. coli* BL21(DE3) harboring pPAA1KP-2, in which the enzyme was designed as a His-tagged fusion protein, as was reported in our previous work (Hiraishi et al. 2009). PahZ1_{KP-2} was purified from the soluble fraction of the recombinant *E. coli* with a cOmplete His-Tag Purification Column (Roche Applied Science). After the sample solution was applied, the column was washed with buffer A (50 mM NaH₂PO₄, 300 mM NaCl, pH 8.0). The enzyme was eluted with buffer B (50 mM NaH₂PO₄, 300 mM NaCl, and 150 mM imidazole, pH 7.4). The enzyme fractions were collected, concentrated, and exchanged with 10 mM phosphate buffer (pH 7.0). The purity and concentration of the purified PahZ1_{KP-2} were determined by SDS-PAGE and the Bradford method, respectively (Laemmli 1970; Bradford 1976).

Gel permeation chromatography (GPC) analysis of products of hydrolysis of tri(Asp)s and di(Asp)s by PahZ1_{KP-2}

The hydrolysis of synthetic tri(Asp)s by PahZ1_{KP-2} was investigated for one α -tri(Asp) and eight β -tri(Asp)s as follows. The tri(Asp) substrate (1 mM) was incubated with 1 μ M or 200 nM PahZ1_{KP-2} at 37°C in 10 mM phosphate buffer (pH 7.0). For di(Asp)s [(β -L-Asp)-(L-Asp) and (β -L-Asp)-(D-Asp)], the dimers (1 mM) were hydrolyzed at 10 μ M PahZ1_{KP-2}. The mixture after the enzymatic reaction was heated at 100°C for 10 min. After centrifugation of the mixture at 2,200 \times g and 4°C for 10 min, the resultant supernatant was subjected to GPC using Superdex peptide PE7.5/300 (GE Healthcare). Phosphate-buffered saline (PBS) was used as the eluent at a rate of 0.25 mL/min. The hydrolyzed products were detected at 214 nm using a UV spectrophotometer.

Detection of L-Asp generated during β -tri(Asp) hydrolysis by PahZ1_{KP-2}

L-Asp generated during β -tri(Asp) hydrolysis by PahZ1_{KP-2} was determined as follows. The hydrolysis was

conducted under the above-mentioned conditions except the enzyme concentration (10 μ M) and reaction temperature (30°C). After the reaction, the amount of L-Asp generated during the hydrolysis was determined under the following conditions. The reaction mixture (50 μ L) was added to a solution containing 7.5 μ g/mL glutamic oxaloacetic transaminase (GOT), 6.6 μ g/mL malate dehydrogenase (MDH), 4 mM α -ketoglutarate, and 0.4 mM NADH in 50 μ L of 10 mM phosphate buffer (pH 7.0), and absorbance was measured at 340 nm. L-Asp generated during the hydrolysis was calculated from the disappearance rate of the absorbance at 340 nm derived from the decrease in the concentration of NADH, and sodium L-Asp was used as standard.

Results

Enzymatic hydrolysis of (α -L-Asp)-(α -L-Asp)-(L-Asp) and (β -L-Asp)-(β -L-Asp)-(L-Asp) by PahZ1_{KP-2}

To examine the effects of α - and β -amide linkages on the hydrolysis by PahZ1_{KP-2}, the products of the enzymatic hydrolysis of (α -L-Asp)-(α -L-Asp)-(L-Asp) and (β -L-Asp)-(β -L-Asp)-(L-Asp) (LLL) were analyzed by GPC. Figure 1 shows the elution profiles of (α -L-Asp)-(α -L-Asp)-(L-Asp) and LLL treated with or without PahZ1_{KP-2} for 24 h. In the figure, the Asp monomer was hardly detected because of its low absorbance. The elution profile of (α -L-Asp)-(α -L-Asp)-(L-Asp) treated with PahZ1_{KP-2} was identical to that treated without PahZ1_{KP-2} (Figure 1a). In contrast, when LLL was used as a substrate, its peak area decreased and a new peak of (β -L-Asp)-(L-Asp) appeared (Figure 1b).

GPC analysis of products on hydrolysis of β -tri(Asp)s by PahZ1_{KP-2}

To elucidate the importance of the sequences of L- and D-Asp units in β -tri(Asp)s in enzymatic cleavage, eight β -tri(Asp)s with all possible combinations of L- and D-Asp units were designed and enzymatically hydrolyzed by 1 μ M PahZ1_{KP-2}. The GPC profiles of the hydrolytic products of β -tri(Asp)s after 24 h are shown in Figure 2. After incubation for 24 h, the degree of hydrolysis of β -tri(Asp)s was in the order of LLD = DLD \gg DLL > LDD > LLL = LDL \gg DDL = DDD. When DDL and DDD were used as substrates, only the peaks of the trimers were observed. In contrast, when LLD and DLD were treated with PahZ1_{KP-2} for 24 h, their peaks completely disappeared and new peaks of Asp dimers were concomitantly generated. Moreover, when the products of LLD and DLD after hydrolysis for 1 and 3 h were analyzed, the peaks of the trimers completely disappeared and those of the dimers appeared (data not shown). Even when the reaction was carried out at a low concentration of PahZ1_{KP-2} (200 nM), the peaks of the trimers completely disappeared and those of the dimers appeared after





Figure 1 GPC curves of products during the enzymatic hydrolysis of (α -L-Asp)-(α -L-Asp)-(L-Asp) (**a**) and LLL (**b**) with or without PahZ1_{KP-2}. Each substrate (1 mM) was incubated with or without the enzyme (1 μ M) in 10 mM phosphate buffer (pH 7.0) at 37°C for 24 h.

incubation for only 1 h (data not shown). In addition, the peak areas of the dimers after treatment with 200 nM PahZ1_{KP-2} for 1 h were identical to those after treatment with 1 μ M enzyme for 24 h.

Enzymatic hydrolysis of (β -L-Asp)-(L-Asp) and (β -L-Asp)-(D-Asp) by PahZ1_{KP-2}

To investigate the minimum units for cleavage to occur, the hydrolysis of (β -L-Asp)-(L-Asp) and (β -L-Asp)-(D-Asp) dimers by PahZ1_{KP-2} was conducted as described in “Materials and methods” section. Figure 3 shows the GPC profiles of the reaction mixture treated with or without PahZ1_{KP-2} for 24 h. For both dimers, the peak areas of the dimers treated with the enzyme were identical to those treated without the enzyme.




L-Asp generation during enzymatic hydrolysis of β -tri(Asp)s

To identify the part in β -tri(Asp)s hydrolyzed by PahZ1_{KP-2}, L-Asp generated during the enzymatic hydrolysis was measured. The results are shown in Figure 4. When LLD, DLD, DDL, and DDD were used, very little L-Asp was detected. However, this is most likely due to the auto-oxidation of NADH to NAD during the L-Asp quantification assay. When DDL and DDD were treated with PahZ1_{KP-2}, no L-Asp was generated on hydrolysis. In the case of LLL, LDL, LDD, and DLL, L-Asp was generated. In contrast, when LLD and DLD were used as substrates, no L-Asp was detected despite their complete hydrolysis by PahZ1_{KP-2}, as shown in Figure 2.


Discussion

In this study, the substrate stereoselectivity of PahZ1_{KP-2} was investigated to reveal the substrate recognition mechanism of PahZ1_{KP-2} in tPAA hydrolysis. First, the enzymatic hydrolysis of α -tri(L-Asp) and β -tri(L-Asp) by PahZ1_{KP-2} was carried out to examine the effects of α - and β -amide linkages on the hydrolysis. The results indicate that PahZ1_{KP-2} can hydrolyze the β -amide bond, but not the α -amide bond, which are consistent with the results of our previous NMR study of the products of tPAA hydrolysis by PahZ1_{KP-2} (Hiraishi et al. 2009).

To determine the effects of the sequences of L- and D-Asp units on the β -tri(Asp) hydrolysis by PahZ1_{KP-2}, we conducted GPC analysis of the enzymatic hydrolysis of eight β -tri(Asp)s with all possible combinations of L- and D-Asp units by PahZ1_{KP-2}. When DDL and DDD were used as substrates, no enzymatic hydrolysis of the



trimers was observed, indicating that PahZ1_{KP-2} cannot recognize (D-Asp)-(L-Asp) and (D-Asp)-(D-Asp) sequences in the substrates. Although LLL was hydrolyzed by PahZ1_{KP-2}, its hydrolysis rate was not very high, demonstrating that the (L-Asp)-(L-Asp) sequence can be recognized by PahZ1_{KP-2}. In the case of LLD and DLD, these trimers were quickly and completely hydrolyzed to generate the dimers. As the (L-Asp)-(L-Asp) sequence was cleaved with low efficiency and the (D-Asp)-(L-Asp) sequence was not hydrolyzable by PahZ1_{KP-2}, the (L-Asp)-(D-Asp) sequence may be the most acceptable sequence for PahZ1_{KP-2}. The present findings are consistent with those of our previous study (Hiraishi et al. 2009), and the substrate stereoselectivity of PahZ1_{KP-2} is probably responsible for its specific but incomplete



cleavage of the amide bonds between β -Asp units in tPAA.


In addition, the GPC elution profiles of LLD and DLD treated with 200 nM PahZ1_{KP-2} for 1 h were identical to those treated with 1 μ M enzyme for 24 h, respectively. The results illustrate that the possible Asp dimers [(β -L-Asp)-(L-Asp), (β -L-Asp)-(D-Asp), and (β -D-Asp)-(L-Asp)] generated upon the hydrolysis of LLD and DLD were not acceptable as substrates for PahZ1_{KP-2}. To determine the minimum units for cleavage to occur, the hydrolysis of (β -L-Asp)-(L-Asp) and (β -L-Asp)-(D-Asp) dimers was carried out at 10 μ M PahZ1_{KP-2}. GPC analysis showed that the peak areas of (β -L-Asp)-(L-Asp) and (β -L-Asp)-(D-Asp) treated with the enzyme were identical to those treated without the enzyme, respectively. This means that no enzymatic hydrolysis of both dimers proceeds and the Asp trimers are the minimum units for the hydrolysis by PahZ1_{KP-2}.

When DDL was treated with PahZ1_{KP-2}, no L-Asp was generated on hydrolysis, suggesting that the (D-Asp)-(L-Asp) sequence was not digested by PahZ1_{KP-2}, consistent with the results shown in Figure 2. In contrast, L-Asp generation was observed during the hydrolysis of LLL, LDD, and DLL. This indicated that the amide bonds of the (L-Asp)-(L-Asp) and (L-Asp)-(D-Asp) sequences in β -tri(Asp)s were truncated by the enzyme. During the hydrolysis of LDL, as the (D-Asp)-(L-Asp) sequence was not an acceptable substrate for PahZ1_{KP-2} as stated above, L-Asp was generated by cleaving the amide bond between (L-Asp)-(D-Asp) in LDL. In the case of LLD and DLD hydrolysis, no L-Asp was detected despite their complete hydrolysis by PahZ1_{KP-2}, as shown in Figure 2, indicating that only the amide bond between (β -L-Asp)-(D-Asp) was cleaved by PahZ1_{KP-2} to generate D-Asp. Taken together,

the results attest that PahZ1_{KP-2} cleaves the amide bond at the carboxyl part of the β -L-Asp unit in stereoisomeric β -tri(Asp)s to generate (L-Asp)-(L-Asp), (D-Asp)-(L-Asp), and (D-Asp)-(D-Asp) dimers.

On the basis of the present findings, we propose the following model of substrate binding of PahZ1_{KP-2} (Figure 5). PahZ1_{KP-2} cleaves the β -amide bond between the (L-Asp)-(L-Asp) sequence as well as that between the (L-Asp)-(D-Asp) sequence when the Asp unit attaches to the N-terminus or the C-terminus of those sequences to form Asp trimers. In addition, the optical isomerism of the attached Asp unit affects the hydrolysis rate of the trimers (Figure 2). These indicate that the substrate-binding site of PahZ1_{KP-2} is composed of at least four subsites (subsites 2, 1, -1, and -2). When three of the four subsites are occupied by Asp units, amide bond cleavage occurs between subsites 1 and -1. Subsite 1 can recognize only the L-Asp unit, whereas the other subsites can accept both the L- and D-Asp units. Among the dimer sequences, the (L-Asp)-(D-Asp) sequence is the most acceptable as the two central subsites.

Except for the tPAA-hydrolyzing enzymes, five β -peptidyl aminopeptidases (three BapA enzymes, one BapF enzyme, and one DmpA enzyme) are known as the enzymes hydrolyzing short β -peptides and β -amino-acid-containing peptides (Geueke and Kohler 2007; Heck et al. 2009; Fuchs et al. 2011). Their general reaction involves the N-terminal cleavage of β -amino acid units from oligopeptides, amides, and esters via an exo-type process. Geueke et al. (2006) demonstrated that BapA enzymes from 3-2W4 and Y2 strains can accept β -dipeptides as substrates as well as β -tripeptides. They also investigated



the hydrolysis of mixed β/α -tripeptides and suggested that a peptide required a β -amino acid unit at its N-terminus in order to be a substrate of BapA. The effects of the optical isomerism of the N-terminal unit in β -tripeptides on the hydrolysis by BapA enzymes indicated that the enzymes preferred the peptide with the L-configuration of the N-terminal unit as a substrate. Heck et al. (2006) examined the substrate specificity of DmpA and demonstrated that DmpA can cleave α -peptides in addition to β -peptides, but the hydrolysis rate of α -peptides was lower than that of β -peptides. According to the MEROPS database (Rawlings et al. 2010), these enzymes are classified into the peptidase family P1 containing aminopeptidases and self-processing proteins. From structural features of DmpA and BapA, they belong to the N-terminal nucleophile (Ntn) hydrolases that self-activate to produce two subunits (α and β -subunits) for forming the active enzymes (Merz et al. 2012).

In contrast to these β -peptidyl aminopeptidases, PahZ1_{KP-2} degrades the β -amide bonds in tPAA polymer via an endo-type process (Hiraishi et al. 2009) and cleaved both the N- and C-terminal Asp units of β -tri(Asp)s depending on the position of the β -L-Asp unit in the molecule, as stated above. In addition, PahZ1_{KP-2} accepts β -tri(Asp)s as substrates, but not β -di(Asp)s. From the MEROPS database, PahZ1_{KP-2} is classified into the peptidase family S9, which contains various sets of Ser-dependent peptidases and generally has an α/β -hydrolase fold in their structure. From the viewpoint of structural features, PahZ1_{KP-2} exists in a monomer form to exert its hydrolysis activity (Hiraishi et al. 2009).

Previous sequence analyses demonstrated that the amino acid sequence of PahZ1_{KP-2} has a high similarity to that of PAA hydrolase-1 from *Sphingomonas* sp. KT-1 (PahZ1_{KT-1}) showing similarity to poly(*R*-3-hydroxybutyrate) (PHB) depolymerases (Hiraishi et al. 2003a, 2009). PHB depolymerases are monomer enzymes having the α/β -hydrolase fold and cleave the β -ester bonds in PHB via an endo-type process (Jendrossek and Handrick 2002; Hisano et al. 2006; Wakadkar et al. 2010). Earlier studies using oligo(3-hydroxybutyrate)s having well-defined sequences provided general information about the substrate-recognition site of PHB depolymerases as follows: (1) the active site contains four subsites (2, 1, -1, and -2), three of which are occupied by monomer units for cleavage to occur; (2) for the hydrolysis to proceed, subsite 1 and -1 should be occupied by the *R*-3-hydroxybutyrate unit, whereas the other two subsites may accept both *R*- and *S*-3-hydroxybutyrate units (Bachmann and Seebach 1999; Hiraishi et al. 2000; Scherer et al. 2000). Thus, the substrate recognition mechanism of PHB depolymerases seems to be similar to that of PahZ1_{KP-2},

although the mechanism of recognition of optical isomers at subsite 1 differs from each other. On the basis of these functional and structural findings, it is assumed that PahZ1_{KP-2} shares a common ancestor with PHB depolymerases rather than β -peptidyl aminopeptidases.

Abbreviations

LLL: (β -L-Asp)-(β -L-Asp)-(β -L-Asp); LLD: (β -L-Asp)-(β -L-Asp)-(β -D-Asp); LDL: (β -L-Asp)-(β -D-Asp)-(β -L-Asp); LDD: (β -L-Asp)-(β -D-Asp)-(β -D-Asp); DLL: (β -D-Asp)-(β -L-Asp)-(β -L-Asp); DLD: (β -D-Asp)-(β -L-Asp)-(β -D-Asp); DDL: (β -D-Asp)-(β -D-Asp)-(β -L-Asp); DDD: (β -D-Asp)-(β -D-Asp)-(β -D-Asp).

Authors' contributions

TH conceived and designed this study, performed the experiment, and drafted the manuscript. HA and MM revised the manuscript for important intellectual content. All authors read and approved the final manuscript.

Author details

¹ Bioengineering Laboratory, RIKEN, 2-1 Hirosawa, Wako, Saitama 351-0198, Japan. ² Bioplastic Research Team, Biomass Engineering Program Cooperation Division, RIKEN Center for Sustainable Resource Science (CSRS), 2-1 Hirosawa, Wako, Saitama 351-0198, Japan.

Acknowledgements

This work was supported by a Grant-in-Aid for Scientific Research (C) from the Ministry of Education, Culture, Sports, Science and Technology of Japan (No. 24550180 to T.H.) and in part by a grant for Biomass Engineering Program Cooperation Division of RIKEN Center for Sustainable Resource Science (CSRS). We thank the Support Unit for Bio-material Analysis, RIKEN BSI Research Resources Center, for help in DNA sequence analysis. We also thank Ms. Naoko Nakata for her technical support.

Compliance with ethical guidelines

Competing interests

The authors declare that they have no competing interests.

Received: 5 April 2015 Accepted: 18 May 2015

Published online: 04 June 2015

References

- Bachmann BM, Seebach D (1999) Investigation of the enzymatic cleavage of diastereomeric oligo(3-hydroxybutanoates) containing two to eight HB units. A model for the stereoselectivity of PHB depolymerase from *Alcaligenes faecalis* T1. *Macromolecules* 32:1777–1784
- Bradford MM (1976) A rapid and sensitive method for the quantitation of microgram quantities of protein utilizing the principle of protein-dye binding. *Anal Biochem* 72:248–254
- Freeman MB, Paik YH, Swift G, Wilczynski R, Wolk SK, Yocum KM (1996) Biodegradability of polycarboxylates: structure-activity studies. In: Ottenbrite RM, Huang SJ, Park K (eds) *Hydrogels and biodegradable polymers for bioapplications*, ACS Symposium Series. American Chemical Society, Washington, DC, pp 118–136
- Fuchs V, Jaeger KE, Wilhelm S, Rosenau F (2011) The BapF protein from *Pseudomonas aeruginosa* is a β -peptidyl aminopeptidase. *World J Microbiol Biotechnol* 27:713–718
- Geueke B, Kohler HPE (2007) Bacterial β -peptidyl aminopeptidases: on the hydrolytic degradation of β -peptides. *Appl Microbiol Biotechnol* 74:1197–1204
- Geueke B, Heck T, Limbach M, Seebach D, Kohler HPE (2006) Bacterial β -peptidyl aminopeptidases with unique substrate specificities for β - and mixed β/α -oligopeptides. *FEBS J* 273:5261–5272
- Heck T, Limbach M, Geueke B, Zacharias M, Gardiner J, Kohler HPE et al (2006) Enzymatic degradation of β - and mixed α, β -oligopeptides. *Chem Biodivers* 3:1325–1348

- Heck T, Seebach D, Osswald S, ter Wiel MKJ, Kohler HPE, Geueke B (2009) Kinetic resolution of aliphatic β -amino acid amides by β -aminopeptidases. *Chembiochem* 10:1558–1561
- Hiraishi T, Maeda M (2011) Poly(aspartate) hydrolases: biochemical properties and applications. *Appl Microbiol Biotechnol* 91:895–903
- Hiraishi T, Ohura T, Ito S, Kasuya K, Doi Y (2000) Function of the catalytic domain of poly(3-hydroxybutyrate) depolymerase from *Pseudomonas stutzeri*. *Biomacromolecules* 1:320–324
- Hiraishi T, Kajiyama M, Tabata K, Yamato I, Doi Y (2003a) Genetic analysis and characterization of poly(aspartic acid) hydrolase-1 from *Sphingomonas* sp. KT-1. *Biomacromolecules* 4:80–86
- Hiraishi T, Kajiyama M, Tabata K, Abe H, Yamato I, Doi Y (2003b) Biochemical and molecular characterization of poly(aspartic acid) hydrolase-2 from *Sphingomonas* sp. KT-1. *Biomacromolecules* 4:1285–1292
- Hiraishi T, Kajiyama M, Yamato I, Doi Y (2004) Enzymatic hydrolysis of α - and β -oligo(L-aspartic acid)s by poly(aspartic acid) hydrolases-1 and 2 from *Sphingomonas* sp. KT-1. *Macromol Biosci* 4:330–339
- Hiraishi T, Masuda E, Kanayama N, Nagata M, Doi Y, Abe H et al (2009) Cloning of poly(aspartic acid) (PAA) hydrolase-1 gene from *Pedobacter* sp. KP-2 and hydrolysis of thermally synthesized PAA by its gene product. *Macromol Biosci* 9:10–19
- Hiraishi T, Masuda E, Miyamoto D, Kanayama N, Abe H, Maeda M (2011) Enzymatic synthesis of poly(α -ethyl β -aspartate) by poly(ethylene glycol) modified poly(aspartate) hydrolase-1. *Macromol Biosci* 11:187–191
- Hisano T, Kasuya K, Tezuka Y, Ishii N, Kobayashi T, Shiraki M et al (2006) The crystal structure of polyhydroxybutyrate depolymerase from *Penicillium funiculosum* provides insights into the recognition and degradation of biopolyesters. *J Mol Biol* 356:993–1004
- Jendrossek D, Handrick R (2002) Microbial degradation of polyhydroxyalkanoates. *Annu Rev Microbiol* 56:403–432
- Joentgen W, Müller N, Mitschker A, Schmidt H (2003) Polyaspartic acids: polyamides and complex proteinaceous materials I. In: Fahnstock SR, Steinbüchel A (eds) *Biopolymers*, 7th edn. WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim, pp 175–199
- Kim CL, Wheeler AP, Koskan LP (1996) Commercial poly(aspartic acid) and its uses: hydrophilic polymers. In: Glass JD (ed) *Advances in chemistry*, 248th edn. American Chemical Society, Washington, DC, pp 99–111
- Laemmli UK (1970) Cleavage of structural proteins during the assembly of the head of bacteriophage T4. *Nature* 227:680–685
- Matsubara K, Nakato T, Tomida M (1998) End group and irregular structure analysis in thermally prepared sodium polyaspartate by ^1H and ^{13}C NMR spectroscopy. *Macromolecules* 31:1466–1472
- Merz T, Heck T, Geueke B, Mittl PRE, Briand C, Seebach D et al (2012) Autoproteolytic and catalytic mechanisms for the β -aminopeptidase BapA—a member of the Ntn hydrolase family. *Structure* 20:1850–1860
- Nakato T, Yoshitake M, Matsubara K, Tomida M, Kakuchi T (1998) Relationships between structure and properties of poly(aspartic acid)s. *Macromolecules* 31:2107–2113
- Osada K, Christie RJ, Kataoka K (2009) Polymeric micelles from poly(ethylene glycol)-poly(amino acid) block copolymer for drug and gene delivery. *J R Soc Interface* 6:S325–S339
- Pivcova H, Saudek V, Drobnik J, Vlasak J (1981) NMR study of poly(aspartic acid). I. α - and β -Peptide bonds in poly(aspartic acid) prepared by thermal polycondensation. *Biopolymers* 20:1605–1614
- Pivcova H, Saudek V, Drobnik J (1982) ^{13}C n.m.r. study of the structure of poly(aspartic acid). *Polymer* 23:1237–1241
- Rawlings ND, Barrett AJ, Bateman A (2010) MEROPS: the peptidase database. *Nucleic Acids Res* 38:D227–D233
- Ross RJ, Mazo GY, Mazo J (2001) New methods in the synthesis of thermal poly(aspartates). In: Gross R, Scholz C (eds) *Biopolymers from polysaccharides and agroproteins*, ACS Symposium Series. American Chemical Society, Washington, DC, pp 172–181
- Sambrook J, Russell DW (2001) *Molecular cloning: a laboratory manual*, 3rd edn. Cold Spring Harbor Laboratory Press, Cold Spring Harbor
- Scherer TM, Fuller RC, Goodwin S, Lenz RW (2000) Enzymatic hydrolysis of oligomeric models of poly-3-hydroxybutyrate. *Biomacromolecules* 1:577–583
- Seebach D, Gardiner J (2008) β -Peptidic peptidomimetics. *Acc Chem Res* 41:1366–1375
- Seebach D, Beck AK, Bierbaum DJ (2004) The world of β - and γ -peptides comprised of homologated proteinogenic amino acids and other components. *Chem Biodivers* 1:1111–1239
- Tabata K, Kasuya K, Abe H, Masuda K, Doi Y (1999) Poly(aspartic acid) degradation by a *Sphingomonas* sp. isolated from freshwater. *App Environ Microbiol* 65:4268–4270
- Tabata K, Abe H, Doi Y (2000) Microbial degradation of poly(aspartic acid) by two isolated strains of *Pedobacter* sp. and *Sphingomonas* sp. *Biomacromolecules* 1:157–161
- Tabata K, Kajiyama M, Hiraishi T, Abe H, Yamato I, Doi Y (2001) Purification and characterization of poly(aspartic acid) hydrolase from *Sphingomonas* sp. KT-1. *Biomacromolecules* 2:1155–1160
- Tang Y, Wheeler AP (2001) Environmental factors that influence biodegradation of thermal poly(aspartate). In: Gross R, Scholz C (eds) *Biopolymers from polysaccharides and agroproteins*, ACS Symposium Series. American Chemical Society, Washington, DC, pp 157–171
- Thombre SM, Sarwade BD (2005) Synthesis and biodegradability of polyaspartic acid: a critical review. *J Macromol Sci Part A Pure Appl Chem* 42:1299–1315
- Wakadkar S, Hermawan S, Jendrossek D, Papageorgiou AC (2010) The structure of PhaZ7 at atomic (1.2 Å) resolution reveals details of the active site and suggests a substrate-binding mode. *Acta Cryst F* 66:648–654
- Wolk SK, Swift G, Paik YH, Yocom KM, Smith RL, Simon ES (1994) One- and two-dimensional nuclear magnetic resonance characterization of poly(aspartic acid) prepared by thermal polymerization of L-aspartic acid. *Macromolecules* 27:7613–7620

Submit your manuscript to a SpringerOpen[®] journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at ► springeropen.com