

# Photocatalytic Hydrogen Production using Polymeric Carbon Nitride with a Hydrogenase and a Bioinspired Synthetic Ni Catalyst\*\*

Christine A. Caputo, Manuela A. Gross, Vincent W. Lau, Christine Cavazza, Bettina V. Lotsch, and Erwin Reisner\*

**Abstract:** Solar-light-driven  $H_2$  production in water with a [NiFeSe]-hydrogenase ( $H_2ase$ ) and a bioinspired synthetic nickel catalyst (NiP) in combination with a heptazine carbon nitride polymer, melon ( $CN_x$ ), is reported. The semibiological and purely synthetic systems show catalytic activity during solar light irradiation with turnover numbers (TONs) of more than  $50\,000\ mol\ H_2\ (mol\ H_2ase)^{-1}$  and approximately  $155\ mol\ H_2\ (mol\ NiP)^{-1}$  in redox-mediator-free aqueous solution at pH 6 and 4.5, respectively. Both systems maintained a reduced photoactivity under UV-free solar light irradiation ( $\lambda > 420\ nm$ ).

Efficient and noble metal-free water photolysis using sunlight is a primary focus of research to advance sustainable solar energy generation.<sup>[1]</sup> Photocatalytic  $H_2$  production can be achieved by employing hybrid systems with a solid-state light absorber such as an inorganic semiconductor assisted by a metallic, synthetic, or enzymatic electrocatalyst.<sup>[2]</sup> These systems typically contain expensive, inefficient, and/or unstable components, but high performance solar fuel devices need to be constructed from parts without these limitations.

Hydrogenases ( $H_2ases$ ) are  $H_2$ -cycling enzymes and are by far the most efficient noble-metal-free electrocatalysts for  $H_2$  generation with an unrivalled turnover frequency (TOF) benchmark of more than  $10^3\ s^{-1}$  even at a modest overpotential.<sup>[3]</sup> This excellent electrocatalytic activity of  $H_2ases$  was exploited in photocatalytic schemes with a light absorber in the absence of a soluble redox mediator: a homogeneous photocatalytic system with a molecular organic dye,<sup>[4]</sup> and semiheterogeneous systems, in which the  $H_2ase$  is immobi-

lized on Ru dye-sensitized  $TiO_2$  nanoparticles,<sup>[5]</sup> and on Cd-containing quantum dots,<sup>[6]</sup> displaying excellent photocatalytic activity in sacrificial schemes.

An efficient class of  $H_2ase$ -inspired synthetic catalysts containing non-noble metal centers have been developed by DuBois and co-workers.<sup>[7]</sup> They possess a Ni bis(diphosphine) ligand core bearing pendant amino groups, which, much like those found in the active site of [FeFe]- $H_2ases$ ,<sup>[8]</sup> can act as catalytically active proton relays in the second coordination sphere of the 3d metal center. Photocatalytic  $H_2$  generation with such Ni bis(diphosphine) catalysts has only been achieved in combination with a costly Ru dye in purely aqueous solution.<sup>[9]</sup>

Amorphous polymeric carbon nitride ( $CN_x$ ) with a poly-(tri-*s*-triazine) (polyheptazine) building block (often referred to as melon or g- $C_3N_4$ ) has recently emerged as an attractive visible-light absorber and can generate  $H_2$  photocatalytically.<sup>[10]</sup> It can be easily synthesized by condensation of cyanamide, dicyandiamide, or melamine at elevated temperatures and displays high activities and photostability of more than 72 h.<sup>[10b]</sup> The material has well-suited band positions for water splitting and a band gap of approximately 2.7 eV with a conduction band potential at  $-0.8\ V$  vs. RHE.<sup>[10a,b]</sup> Cocatalyst integration of non-noble metals,<sup>[11]</sup> Pt,<sup>[10b,12]</sup> Ni-(TEOA)<sub>3</sub><sup>2+</sup> (TEOA = triethanolamine),<sup>[13]</sup> and cobaloximes<sup>[14]</sup> with  $CN_x$  has previously been used as a strategy to enhance  $H_2$  evolution rates.

In this study, we report a photocatalytic  $CN_x$ -enzyme hybrid system for visible-light-driven  $H_2$  generation (Figure 1). This  $CN_x$ - $H_2ase$  hybrid assembly operates in an

[\*] Dr. C. A. Caputo, M. A. Gross, Dr. E. Reisner  
Christian Doppler Laboratory for Sustainable SynGas Chemistry  
Department of Chemistry, University of Cambridge  
Lensfield Road, Cambridge CB2 1EW (UK)  
E-mail: reisner@ch.cam.ac.uk  
Homepage: <http://www-reisner.ch.cam.ac.uk/>  
Dr. V. W. Lau, Prof. B. V. Lotsch  
Max Planck Institute for Solid State Research  
Heisenbergstrasse 1, 70569 Stuttgart (Germany)  
and  
Department of Chemistry  
Ludwig-Maximilians-Universität München  
Butenandtstrasse 5–13 (Haus D), 81377 München (Germany)  
Dr. C. Cavazza  
CEA, CNRS, Université Grenoble Alpes, IBS  
71 Avenue des Martyrs, 38044 Grenoble (France)

[\*\*] We acknowledge support by the Christian Doppler Research Association (Austrian Federal Ministry of Science, Research, and Economy and the National Foundation for Research, Technology,


and Development), the OMV Group, the EPSRC (EP/H00338X/2 to E.R.), and a Marie Curie fellowship (GAN 624997 to C.C.). Financial support by the Max Planck Society, the Deutsche Forschungsgemeinschaft (LO 1801/1-1), Nanosystems Initiative Munich (NIM), and the Fonds der Chemischen Industrie (FCI) is also gratefully acknowledged. We thank Dr. J. C. Fontecilla-Camps for providing us with *Dmb* [NiFeSe] hydrogenase, Marielle Bauzan for growing the bacteria (Biomass and Biohydrogen Platform, IMM, CNRS, Marseilles, France), Dirk Mersch for preliminary experiments with  $C_3N_4$ - $H_2ase$  and Dr. Jenny Zhang for help with the photoluminescence measurements.



Supporting information for this article is available on the WWW under <http://dx.doi.org/10.1002/anie.201406811>.



© 2014 The Authors. Published by Wiley-VCH Verlag GmbH & Co. KGaA. This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.



**Figure 1.** Representation of the photo- $\text{H}_2$  production with  $\text{CN}_x$  and *Dmb* [NiFeSe]- $\text{H}_2$ ase (PDB ID: 1CC1)<sup>[15a]</sup> or  $\text{CN}_x$  and NiP (counterions omitted) in aqueous EDTA solution. Irradiation of  $\text{CN}_x$  results in the photoinduced direct electron transfer to the catalysts with  $\text{H}_2$  formation and hole quenching in  $\text{CN}_x$  by EDTA.

aqueous sacrificial electron donor solution and does not require an expensive or fragile light absorber for visible light promoted photocatalysis as reported for the previous  $\text{H}_2$ ase-based systems. We selected *Desulfomicrobium baculatum* (*Dmb*) [NiFeSe]- $\text{H}_2$ ase because of its well-known<sup>[15]</sup> and excellent  $\text{H}_2$  evolution rate as well as tolerance toward  $\text{H}_2$  and  $\text{O}_2$ , allowing for the accumulation of  $\text{H}_2$  during irradiation and the handling of the enzyme in the absence of strictly anaerobic conditions.<sup>[4,5,15b]</sup>

The photocatalytic  $\text{H}_2$  generation systems were assembled in a photoreactor (total volume 7.74 mL) by dispersing  $\text{CN}_x$  (5 mg, approx.  $1 \mu\text{m}$ -sized particles with a Brunauer–Emmett–Teller surface area of  $9 \text{ m}^2 \text{ g}^{-1}$ ; see Figures S1–S4 for FTIR, XRD, SEM, and zeta-potential measurements) in an aqueous solution of the electron donor (0.1 M, 3 mL). The catalyst ( $\text{H}_2$ ase or NiP, see below) was added to the suspension and the light-protected reactor was sealed and purged with 2%  $\text{CH}_4$  (as an internal gas chromatography standard) in  $\text{N}_2$  before irradiating the stirred mixture at  $25^\circ\text{C}$ . Irradiation was provided by a solar light simulator (air mass 1.5 G,  $100 \text{ mW cm}^{-2}$ ) and headspace  $\text{H}_2$  was quantified at regular time intervals by gas chromatography. The reaction conditions were optimized for a high rate of  $\text{H}_2$  production per catalyst (as expressed by the TOF) by varying the pH of the solution, the amount of catalyst and by screening different electron donors (Table S1; Figures S5 and S6).


The optimized standard system for  $\text{CN}_x$ - $\text{H}_2$ ase comprises 50 pmol  $\text{H}_2$ ase with 5 mg melon in 3 mL ethylenediamine tetraacetic acid (EDTA, 0.1 M) at pH 6 under simulated solar irradiation at  $\lambda > 300 \text{ nm}$  (Figure 2). Under these conditions, a  $\text{TOF}_{\text{H}_2\text{ase}}$  of  $(5532 \pm 553) \text{ mol H}_2 (\text{mol H}_2\text{ase})^{-1} \text{ h}^{-1}$  and  $(55.3 \pm 5.5) \mu\text{mol H}_2 (\text{g CN}_x)^{-1} \text{ h}^{-1}$  are photogenerated with almost linear  $\text{H}_2$  evolution, producing  $(0.82 \pm 0.08) \mu\text{mol H}_2$  during the first four hours. Photoinduced direct electron transfer from  $\text{CN}_x$  to the  $\text{H}_2$ ase was therefore observed, making a soluble redox mediator unnecessary. The  $\text{CN}_x$ - $\text{H}_2$ ase suspension was photoactive for 48 h, whereupon  $(2.5 \pm 0.2) \mu\text{mol}$  of  $\text{H}_2$  was produced with a  $\text{TON}_{\text{H}_2\text{ase}}$  of  $> 50000$ . Control experiments in the dark and in the absence of  $\text{CN}_x$  or  $\text{H}_2$ ase showed no  $\text{H}_2$  formation. Only minimal

amounts of  $\text{H}_2$  were produced when the electron donor buffer EDTA was replaced by potassium phosphate buffer ( $\text{KP}_i$ ; 41 mM, pH 7, Table S1).

The amount of  $\text{H}_2$ ase per mg of  $\text{CN}_x$  and the light intensity were varied to gain insight into the performance-limiting factors of the  $\text{CN}_x$ - $\text{H}_2$ ase hybrid. Increasing the  $\text{H}_2$ ase loading from 50 to 200 pmol per 5 mg  $\text{CN}_x$  resulted in a linear increase in overall  $\text{H}_2$  generation with an unchanged  $\text{TOF}_{\text{H}_2\text{ase}}$  (Table S1, Figure S6). Decreasing the solar light intensity with neutral density filters from 100 to  $50 \text{ mW cm}^{-2}$  did not result in a significant reduction of the

photoactivity, although a further reduction to  $20 \text{ mW cm}^{-2}$  resulted in approximately 40% decreased activity (Table S2; Figure S7). These experiments suggest that the optimized  $\text{CN}_x$ - $\text{H}_2$ ase system is not limited by light absorption at  $\text{CN}_x$ , and support that enzyme adsorption and interaction with the  $\text{CN}_x$  is performance limiting (see below).

The  $\text{CN}_x$ - $\text{H}_2$ ase system was also studied under visible light irradiation ( $\lambda > 420 \text{ nm}$ ). A decrease in photoactivity was observed giving rise to a  $\text{TOF}_{\text{H}_2\text{ase}}$  of  $(768 \pm 77) \text{ h}^{-1}$ , which corresponds to 14% of the activity under UV/Vis irradiation (Figure 2). This can be attributed to the significantly reduced light absorption of  $\text{CN}_x$  above 420 nm (Figure S8). The external quantum efficiency (EQE) of the system was determined by irradiation of samples under standard conditions using a monochromatic LED light source at two wavelengths ( $\lambda = 365 \text{ nm}$ ,  $I = 3.5 \text{ mW cm}^{-2}$  and  $\lambda = 460 \text{ nm}$ ,  $I = 47 \text{ mW cm}^{-2}$ ). UV-irradiation gave an unoptimized EQE of approximately  $7 \times 10^{-2}\%$ , whereas an EQE of  $5 \times 10^{-3}\%$  was obtained at  $\lambda = 465 \text{ nm}$  (Figure S8).



**Figure 2.**  $\text{H}_2$  production under optimized conditions using *Dmb* [NiFeSe]- $\text{H}_2$ ase (50 pmol) in EDTA (pH 6, 0.1 M, 3 mL) and  $\text{CN}_x$  (5 mg) under 1 sun irradiation in the absence ( $\lambda > 300 \text{ nm}$ ) and presence of a 420 nm UV filter. Control experiments without EDTA,  $\text{CN}_x$ , or  $\text{H}_2$ ase are also shown.

A centrifugation test was performed to gain insight into the strength of interaction between the enzyme and  $\text{CN}_x$  particles. First,  $\text{H}_2$  production was monitored for 2 h with  $\text{CN}_x$ - $\text{H}_2$ ase under standard conditions. The suspension was then centrifuged (5000 rpm, 5 min) followed by washing the pellet with water and redispersion of the particles in aqueous EDTA (0.1M, pH 6). This suspension was then irradiated again after purging the headspace with 2%  $\text{CH}_4$  in  $\text{N}_2$ . The remaining activity of this mixture was 12% relative to the activity prior to centrifugation, indicating that a relatively weak interaction suffices for electron transfer to occur from  $\text{CN}_x$  to the  $\text{H}_2$ ase. Physical adsorption of the  $\text{H}_2$ ase on the  $\text{CN}_x$  surface can be expected and we speculate that the  $\text{H}_2$ ase<sup>[16]</sup> may form hydrogen bonds with the  $-\text{NH}-$ , terminal  $-\text{NH}_2$  or Lewis basic heptazine edge nitrogens in  $\text{CN}_x$ .<sup>[10a,17]</sup> The isoelectric point of  $\text{CN}_x$  was determined by zeta potential measurements as 3.3<sup>[18]</sup> and, at pH 6, the surface of  $\text{CN}_x$  is therefore negatively charged ( $\approx -15$  mV) (Figure S4).


Although the direct electron transfer was observed from the photoexcited  $\text{CN}_x$  to the  $\text{H}_2$ ase, the  $\text{CN}_x$ - $\text{H}_2$ ase system displayed a significantly increased photoactivity under standard conditions upon addition of an excess of the redox mediator, methyl viologen (MV),<sup>[19]</sup> producing up to 18.7  $\mu\text{mol H}_2$  after 4 h (Figure S9). A long-term experiment with  $\text{H}_2$ ase (50 pmol),  $\text{CN}_x$  (5 mg), and added MV (5  $\mu\text{mol}$ ) in aqueous EDTA (0.1M) at pH 6 was also performed. The photoreactor was purged with 2%  $\text{CH}_4/\text{N}_2$  after 24 and 48 h and additional MV (5  $\mu\text{mol}$ ) was added at the same time intervals. After 69 h, the  $\text{CN}_x$ -MV- $\text{H}_2$ ase system produced 77  $\mu\text{mol H}_2$  with a TON of  $1.5 \times 10^6$  and an initial TOF of 12.3  $\text{s}^{-1}$  (Figure S10). Replenishment of MV was required due to decomposition of the organic mediator during irradiation. The substantially increased  $\text{H}_2$  production activity in the presence of MV suggests that the electron transfer from  $\text{CN}_x$  to  $\text{H}_2$ ase is not yet fully optimized, presumably due to weak and nonspecific interactions at the  $\text{CN}_x$ - $\text{H}_2$ ase interface.

Steady-state photoluminescence (PL) measurements were also performed with the  $\text{CN}_x$  in suspension upon photoexcitation at  $\lambda = 365$  nm and following the PL emission at 450 nm (Figure S11). The PL emission of sonicated  $\text{CN}_x$  (0.22  $\text{g mL}^{-1}$  in 0.1M EDTA pH 6) is more strongly quenched upon addition of 50 pmol MV compared to 50 pmol  $\text{H}_2$ ase. These results further support that the photoinduced electron transfer from  $\text{CN}_x$  to MV is more efficient than that to the  $\text{H}_2$ ase.

The reported semibiological hybrid system provides a novel “per active site” activity benchmark for a cocatalyst on a  $\text{CN}_x$  material.<sup>[7g,11a,b,20]</sup> Photocatalytic  $\text{H}_2$  generation schemes previously reported with  $\text{H}_2$ ases and other light absorbers show a high TOF <sub>$\text{H}_2$ ase</sub> (approximately  $10^6$   $\text{h}^{-1}$ ), but these systems rely on an expensive (Ru dye), toxic (Cd-based quantum dot), and/or fragile (organic dye) visible light absorber.<sup>[4,5b,6c]</sup> This study demonstrates that the biocompatibility of  $\text{CN}_x$  can be exploited to overcome these limitations and that by improving the coupling of  $\text{CN}_x$  to the  $\text{H}_2$ ase, the photoactivity will be further enhanced.

Successful  $\text{H}_2$  production with  $\text{CN}_x$ - $\text{H}_2$ ase prompted us to investigate a water-soluble and functional synthetic  $\text{H}_2$ ase-mimic,  $[\text{Ni}^{\text{II}}(\text{P}^{\text{Ph}}_2[\text{NPhCH}_2\text{P}(\text{O})(\text{OH})_2]_2)]\text{Br}_2$  (NiP;

Figure 1),<sup>[9]</sup> for comparison. Ni bis(diphosphine)<sup>[7a-c]</sup> complexes are among the most active  $\text{H}_2$  generation electrocatalysts and, importantly, NiP has recently been shown to act as an excellent electrocatalyst in aqueous solution.<sup>[9]</sup> The purely synthetic  $\text{CN}_x$ -NiP assembly is photoactive and conditions were optimized for the highest TOF<sub>NiP</sub>. Aqueous EDTA solutions (0.1M) at pH 4.5 containing NiP (20 nmol) and suspended  $\text{CN}_x$  (5 mg) were studied under simulated solar irradiation at  $\lambda > 300$  nm (Table S3, Figures S12–S14). Under these conditions, solar  $\text{H}_2$  generation by  $\text{CN}_x$ -NiP gave an initial activity of  $(437.1 \pm 43.7) \mu\text{mol H}_2 (\text{g CN}_x)^{-1} \text{h}^{-1}$  producing  $(2.2 \pm 0.2) \mu\text{mol H}_2$  in the first hour and giving a TOF<sub>NiP</sub> of  $(109.3 \pm 10.9) \text{mol H}_2 (\text{mol NiP})^{-1} \text{h}^{-1}$ .  $\text{CN}_x$ -NiP was photoactive for three hours, whereupon  $(3.3 \pm 0.4) \mu\text{mol}$  of  $\text{H}_2$  with a TON of  $(166.1 \pm 20.6) \text{mol H}_2 (\text{mol NiP})^{-1}$  was produced (Figure 3). A 64% decrease in photocatalytic  $\text{H}_2$



**Figure 3.**  $\text{H}_2$  production under optimized conditions using NiP (20 nmol) in aqueous EDTA (0.1 M, pH 4.5, 3 mL) and  $\text{CN}_x$  (5 mg) under 1 sun irradiation. Data collected under standard conditions ( $\lambda > 300$  nm), with UV-light-filtered irradiation ( $\lambda > 420$  nm) and control experiments without NiP catalyst or  $\text{CN}_x$  are also shown.

generation yield was observed for  $\text{CN}_x$ -NiP when irradiating with  $\lambda > 420$  nm instead of  $> 300$  nm solar light. Decomposition of NiP is the likely reason for the ceased activity after three hours, because the photoactivity is fully regenerated if additional NiP is added (Figure S15).

Photo- $\text{H}_2$  generation with  $\text{CN}_x$ -NiP is thus significantly higher than for previously reported  $\text{CN}_x$  systems with immobilized noble-metal-free cocatalysts in aqueous solution. A TOF of  $< 0.5 \text{ h}^{-1}$  and a TON of 4 was reported for a cobaloxime,  $[\text{CoCl}(\text{dimethylglyoximate})_2(\text{pyridine})]$ , after 8 h irradiation with  $\text{CN}_x$  in aqueous TEOA at pH 10.4.<sup>[14a]</sup> Other systems comprising a cobaloxime with a pyrene-functionalized pyridine<sup>[14c]</sup> and  $\text{NiCl}_2$  with TEOA and  $\text{CN}_x$ <sup>[13]</sup> showed TONs of 160 and 281 and TOFs of approximately 40 and 6.7  $\text{h}^{-1}$ , respectively, but required excess organic solvent. Previously, photo- $\text{H}_2$  generation with NiP was only reported with a molecular Ru dye, in which a TOF<sub>NiP</sub> of up to 460  $\text{h}^{-1}$  and a TON<sub>NiP</sub> of up to 723 in pH 4.5 ascorbic acid solution were reported.<sup>[9]</sup>

The photo- $\text{H}_2$  generation activity of  $\text{CN}_x$ -NiP is dependent on the NiP concentration (Figures S13 and S14) and

reduction of the light intensity ( $I$ ) with neutral density filters has a substantial impact on the photoactivity. The NiP-based TOF decreases from  $(71.1 \pm 7.1) \text{ h}^{-1}$  ( $I=100\%$ ) to  $(32.4 \pm 3.2)$  ( $I=50\%$ ) and  $(13.1 \pm 1.4) \text{ h}^{-1}$  ( $I=20\%$ ; Table S4; Figure S16). The purely synthetic system is therefore limited both by catalyst concentration and light absorption. The unoptimized EQE for the  $\text{CN}_x$ -NiP system was determined to be  $(0.37 \pm 0.02)\%$  under UV light ( $\lambda = 365 \text{ nm}$ ) and  $(0.04 \pm 0.01)\%$  under blue light irradiation ( $\lambda = 460 \text{ nm}$ ) after 2 h. The wavelength-dependent EQE is consistent with the decrease in light absorption by  $\text{CN}_x$  at higher wavelengths (Figure S17).

Centrifugation experiments in analogy to the enzyme system were performed to examine the strength of the interaction between  $\text{CN}_x$  and NiP. After centrifugation, washing, and redispersion in fresh EDTA solution, 8% of the photoactivity remained for the synthetic system implying a weak interaction between the  $\text{CN}_x$  and NiP (Figure S18). Electronic absorption spectrophotometry was used to quantify the amount of NiP adsorbed to  $\text{CN}_x$ . By comparing UV-visible spectra of NiP ( $6.7 \mu\text{M}$ ;  $\lambda_{\text{max}} = 320$  and  $450 \text{ nm}$ ) in aqueous EDTA solution ( $3 \text{ mL}$ ;  $0.1 \text{ M}$ ,  $\text{pH } 4.5$ ) before and after the addition of  $\text{CN}_x$  and centrifugation, an estimate of approximately 20% NiP was adsorbed on  $\text{CN}_x$  (Figure S19). The physical adsorption and H-bonding between the phosphonic acid groups in NiP and the terminal  $-\text{NH}_2$  and  $-\text{NH}-$  groups in  $\text{CN}_x$  are possible modes of interaction.<sup>[10a,17]</sup>

The addition of MV ( $20 \mu\text{mol}$ ) to a standard photocatalytic experiment showed an approximately 20% decreased  $\text{H}_2$  production activity. The reaction mixture turned dark blue upon irradiation, indicative of the presence of reduced MV, and implies that MV successfully scavenged electrons from the photoexcited  $\text{CN}_x$ , but was unable to transfer them to NiP (Figure S20).

The comparison of the  $\text{CN}_x$ - $\text{H}_2$ ase with the  $\text{CN}_x$ -NiP hybrid system shows the expected higher “per active site” activity of the enzymatic system, whereas the purely synthetic system shows an overall higher  $\text{H}_2$  production rate due to the larger amount of NiP ( $20 \text{ nmol}$ ) used compared to  $\text{H}_2$ ase ( $50 \text{ pmol}$ ). Thus, we also studied the  $\text{CN}_x$  catalyst systems with the same amount of NiP and  $\text{H}_2$ ase ( $200 \text{ pmol}$ ) on  $\text{CN}_x$  ( $5 \text{ mg}$ ) in aqueous EDTA solution ( $\text{pH } 4.5$  and  $\text{pH } 7.0$ , respectively). At the same concentration, the enzyme ( $\text{TOF} = 2528 \text{ h}^{-1}$ ) greatly outperforms the NiP cocatalyst ( $\text{TOF} = 64 \text{ h}^{-1}$ ), demonstrating that substantial improvements are still required to develop synthetic catalysts with activities comparable to enzymes (Figure S21, Tables S1 and S3).

Finally, we photodeposited 1 wt% Pt onto  $\text{CN}_x$  ( $5 \text{ mg}$ ) for a direct comparison of this benchmark system with  $\text{CN}_x$ - $\text{H}_2$ ase and  $\text{CN}_x$ -NiP. Following a standard procedure,<sup>[12]</sup> the platinumized  $\text{CN}_x$  system was irradiated with visible light ( $\lambda > 420 \text{ nm}$ ) in an aqueous 10 vol% TEOA solution, generating  $94 \mu\text{mol H}_2(\text{g CN}_x)^{-1} \text{ h}^{-1}$ , which corresponds to a  $\text{TOF}_{\text{Pt}}$  of  $4.3 \text{ mol H}_2(\text{mol Pt})^{-1} \text{ h}^{-1}$ . Thus, the  $\text{CN}_x$ - $\text{H}_2$ ase and  $\text{CN}_x$ -NiP systems compare favorably when using TOF as the metrics of system performance.

In summary, solar-light-driven  $\text{H}_2$  production with hybrid systems consisting of polymeric  $\text{CN}_x$  with  $\text{H}_2$ ase and the bioinspired synthetic catalyst, NiP, has been demonstrated.

The systems operate without a soluble redox mediator and are not limited by a photo-unstable or expensive dye. The semibiological  $\text{CN}_x$ - $\text{H}_2$ ase assembly achieved a record TOF of  $5532 \text{ h}^{-1}$  and TON of  $> 50000$  after two days as a cocatalyst with  $\text{CN}_x$ . The additional use of the redox mediator MV allowed for the photogeneration of  $\text{H}_2$  with a TOF of  $12.3 \text{ s}^{-1}$  and a TON of  $> 1 \times 10^6$ , which displays the further potential of the hybrid assembly after optimization of the biomaterial interface.  $\text{CN}_x$ - $\text{H}_2$ ase also maintains respectable activity under visible light irradiation for more than 48 h. Recent investigations into improving the absorption profile of  $\text{CN}_x$  in the visible range demonstrate the potential of this material and illustrate that its use as a light-harvesting material will continue to develop, as its absorption profile is further improved.<sup>[21]</sup> The entirely synthetic  $\text{CN}_x$ -NiP system displays an unprecedentedly high TOF ( $109 \text{ h}^{-1}$ ) and TON (166) for a hybrid system made of a molecular cocatalyst with  $\text{CN}_x$  in purely aqueous solution. This work advances the use of hybrid photocatalytic schemes by integrating highly active electrocatalysts with the photostable and inexpensive  $\text{CN}_x$ , which is shown to be compatible with biological and bioinspired electrocatalysts, namely hydrogenases and their mimics in aqueous solution.

Received: July 2, 2014

Revised: August 7, 2014

Published online: September 9, 2014

**Keywords:** carbon nitride · enzyme catalysis · hydrogen production · hydrogenases · photocatalysis

- [1] a) S. Ott, M. Kritikos, B. Åkermark, L. Sun, *Angew. Chem. Int. Ed.* **2003**, *42*, 3285–3288; *Angew. Chem.* **2003**, *115*, 3407–3410; b) S. Y. Reece, J. A. Hamel, K. Sung, T. D. Jarvi, A. J. Esswein, J. J. H. Pijpers, D. G. Nocera, *Science* **2011**, *334*, 645–648; c) J. R. McKone, N. S. Lewis, H. B. Gray, *Chem. Mater.* **2014**, *26*, 407–414; d) C.-Y. Lin, Y.-H. Lai, D. Mersch, E. Reisner, *Chem. Sci.* **2012**, *3*, 3482–3487; e) S. Hu, M. R. Shaner, J. A. Beardslee, M. Lichterman, B. S. Brunshwig, N. S. Lewis, *Science* **2014**, *344*, 1005–1009.
- [2] a) A. Kudo, Y. Miseki, *Chem. Soc. Rev.* **2009**, *38*, 253–278; b) X. Chen, S. Shen, L. Guo, S. S. Mao, *Chem. Rev.* **2010**, *110*, 6503–6570; c) F. Lakadamyali, E. Reisner, *Chem. Commun.* **2011**, *47*, 1695–1697; d) H. Tong, S. Ouyang, Y. Bi, N. Umezawa, M. Oshikiri, J. Ye, *Adv. Mater.* **2012**, *24*, 229–251; e) Y. Tachibana, L. Vayssieres, J. R. Durrant, *Nat. Photonics* **2012**, *6*, 511–518; f) Z. Han, F. Qiu, R. Eisenberg, P. L. Holland, T. D. Krauss, *Science* **2012**, *338*, 1321–1324; g) Y. Qu, X. Duan, *Chem. Soc. Rev.* **2013**, *42*, 2568–2580; h) F. Wen, C. Li, *Acc. Chem. Res.* **2013**, *46*, 2355–2364; i) J. Ran, J. Zhang, J. Yu, M. Jaroniec, S. Z. Qiao, *Chem. Soc. Rev.* **2014**, DOI: 10.1039/C3CS60425J.
- [3] a) A. K. Jones, E. Sillery, S. P. J. Albracht, F. A. Armstrong, *Chem. Commun.* **2002**, 866–867; b) K. A. Vincent, A. Parkin, F. A. Armstrong, *Chem. Rev.* **2007**, *107*, 4366–4413; c) F. A. Armstrong, N. A. Belsey, J. A. Cracknell, G. Goldet, A. Parkin, E. Reisner, K. A. Vincent, A. F. Wait, *Chem. Soc. Rev.* **2009**, *38*, 36–51.
- [4] T. Sakai, D. Mersch, E. Reisner, *Angew. Chem. Int. Ed.* **2013**, *52*, 12313–12316; *Angew. Chem.* **2013**, *125*, 12539–12542.
- [5] a) E. Reisner, J. C. Fontecilla-Camps, F. A. Armstrong, *Chem. Commun.* **2009**, 550–552; b) E. Reisner, D. J. Powell, C.

- Cavazza, J. C. Fontecilla-Camps, F. A. Armstrong, *J. Am. Chem. Soc.* **2009**, *131*, 18457–18466.
- [6] a) B. L. Greene, C. A. Joseph, M. J. Maroney, R. B. Dyer, *J. Am. Chem. Soc.* **2012**, *134*, 11108–11111; b) A. Bachmeier, V. C. C. Wang, T. W. Woolerton, S. Bell, J. C. Fontecilla-Camps, M. Can, S. W. Ragsdale, Y. S. Chaudhary, F. A. Armstrong, *J. Am. Chem. Soc.* **2013**, *135*, 15026–15032; c) M. B. Wilker, K. E. Shinopoulos, K. A. Brown, D. W. Mulder, P. W. King, G. Dukovic, *J. Am. Chem. Soc.* **2014**, *136*, 4316–4324.
- [7] a) A. D. Wilson, R. H. Newell, M. J. McNevin, J. T. Muckerman, M. Rakowski DuBois, D. L. DuBois, *J. Am. Chem. Soc.* **2006**, *128*, 358–366; b) M. L. Helm, M. P. Stewart, R. M. Bullock, M. Rakowski DuBois, D. L. DuBois, *Science* **2011**, *333*, 863–866; c) U. J. Kilgore, J. A. S. Roberts, D. H. Pool, A. M. Appel, M. P. Stewart, M. Rakowski DuBois, W. G. Dougherty, W. S. Kassel, R. M. Bullock, D. L. DuBois, *J. Am. Chem. Soc.* **2011**, *133*, 5861–5872; d) U. J. Kilgore, M. P. Stewart, M. L. Helm, W. G. Dougherty, W. S. Kassel, M. Rakowski DuBois, D. L. DuBois, R. M. Bullock, *Inorg. Chem.* **2011**, *50*, 10908–10918; e) A. Jain, S. Lense, J. C. Linehan, S. Rauei, H. Cho, D. L. DuBois, W. J. Shaw, *Inorg. Chem.* **2011**, *50*, 4073–4085; f) S. Wiese, U. J. Kilgore, D. L. DuBois, R. M. Bullock, *ACS Catal.* **2012**, *2*, 720–727; g) S. Wiese, U. J. Kilgore, M.-H. Ho, S. Rauei, D. L. DuBois, R. M. Bullock, M. L. Helm, *ACS Catal.* **2013**, *3*, 2527–2535.
- [8] G. Berggren, A. Adamska, C. Lambert, T. R. Simmons, J. Esselborn, M. Atta, S. Gambarelli, J.-M. Mouesca, E. Reijerse, W. Lubitz, T. Happe, V. Artero, M. Fontecave, *Nature* **2013**, *499*, 66–69.
- [9] M. A. Gross, A. Reynal, J. R. Durrant, E. Reisner, *J. Am. Chem. Soc.* **2014**, *136*, 356–366.
- [10] a) B. V. Lotsch, M. Döblinger, J. Sehnert, L. Seyfarth, J. Senker, O. Oeckler, W. Schnick, *Chem. Eur. J.* **2007**, *13*, 4969–4980; b) X. Wang, K. Maeda, A. Thomas, K. Takanabe, G. Xin, J. M. Carlsson, K. Domen, M. Antonietti, *Nat. Mater.* **2009**, *8*, 76–80; c) J. Zhang, X. Chen, K. Takanabe, K. Maeda, K. Domen, J. D. Epping, X. Fu, M. Antonietti, X. Wang, *Angew. Chem. Int. Ed.* **2010**, *49*, 441–444; *Angew. Chem.* **2010**, *122*, 451–454; d) Y. Zheng, J. Liu, J. Liang, M. Jaroniec, S. Z. Qiao, *Energy Environ. Sci.* **2012**, *5*, 6717–6731; e) Y. Wang, X. Wang, M. Antonietti, *Angew. Chem. Int. Ed.* **2012**, *51*, 68–89; *Angew. Chem.* **2012**, *124*, 70–92; f) Y.-S. Jun, J. Park, S. U. Lee, A. Thomas, W. H. Hong, G. D. Stucky, *Angew. Chem. Int. Ed.* **2013**, *52*, 11083–11087; *Angew. Chem.* **2013**, *125*, 11289–11293; g) G. Zhang, M. Zhang, X. Ye, X. Qiu, S. Lin, X. Wang, *Adv. Mater.* **2014**, *26*, 805–809; h) S. Cao, J. Yu, *J. Phys. Chem. Lett.* **2014**, *5*, 2101–2107.
- [11] a) J. Hong, Y. Wang, Y. Wang, W. Zhang, R. Xu, *ChemSusChem* **2013**, *6*, 2263–2268; b) Y. Hou, A. B. Laursen, J. Zhang, G. Zhang, Y. Zhu, X. Wang, S. Dahl, I. Chorkendorff, *Angew. Chem. Int. Ed.* **2013**, *52*, 3621–3625; *Angew. Chem.* **2013**, *125*, 3709–3713; c) Y. Hou, Y. Zhu, Y. Xu, X. Wang, *Appl. Catal. B* **2014**, *156–157*, 122–127.
- [12] K. Maeda, X. Wang, Y. Nishihara, D. Lu, M. Antonietti, K. Domen, *J. Phys. Chem. C* **2009**, *113*, 4940–4947.
- [13] J. Dong, M. Wang, X. Li, L. Chen, Y. He, L. Sun, *ChemSusChem* **2012**, *5*, 2133–2138.
- [14] a) S.-W. Cao, X.-F. Liu, Y.-P. Yuan, Z.-Y. Zhang, J. Fang, S. C. J. Loo, J. Barber, T. C. Sum, C. Xue, *Phys. Chem. Chem. Phys.* **2013**, *15*, 18363–18366; b) X. Li, A. J. Ward, A. F. Masters, T. Maschmeyer, *Chem. Eur. J.* **2014**, *20*, 7345–7350; c) X.-W. Song, H.-M. Wen, C.-B. Ma, H.-H. Cui, H. Chen, C.-N. Chen, *RSC Adv.* **2014**, *4*, 18853–18861.
- [15] a) E. Garcin, X. Vernede, E. C. Hatchikian, A. Volbeda, M. Frey, J. C. Fontecilla-Camps, *Structure* **1999**, *7*, 557–566; b) A. Parkin, G. Goldet, C. Cavazza, J. C. Fontecilla-Camps, F. A. Armstrong, *J. Am. Chem. Soc.* **2008**, *130*, 13410–13416; c) C. S. A. Baltazar, M. C. Marques, C. M. Soares, A. M. DeLacey, I. A. C. Pereira, P. M. Matias, *Eur. J. Inorg. Chem.* **2011**, 948–962; d) C. Wombwell, E. Reisner, *Dalton Trans.* **2014**, *43*, 4483–4493.
- [16] E. Reisner, *Eur. J. Inorg. Chem.* **2011**, 1005–1016.
- [17] Y. Ishida, L. Chabanne, M. Antonietti, M. Shalom, *Langmuir* **2014**, *30*, 447–451.
- [18] Y. Di, X. Wang, A. Thomas, M. Antonietti, *ChemCatChem* **2010**, *2*, 834–838.
- [19] J. C. Hoogvliet, L. C. Lievense, C. van Dijk, C. Veeger, *Eur. J. Biochem.* **1988**, *174*, 273–280.
- [20] a) D. Wang, Y. Zhang, W. Chen, *Chem. Commun.* **2014**, *50*, 1754–1756; b) C. Gimbert-Suriñach, J. Albero, T. Stoll, J. Fortage, M.-N. Collomb, A. Deronzier, E. Palomares, A. Llobet, *J. Am. Chem. Soc.* **2014**, *136*, 7655–7661.
- [21] a) K. Schwinghammer, B. Tuffy, M. B. Mesch, E. Wirnhier, C. Martineau, F. Taulelle, W. Schnick, J. Senker, B. V. Lotsch, *Angew. Chem. Int. Ed.* **2013**, *52*, 2435–2439; *Angew. Chem.* **2013**, *125*, 2495–2499; b) K. Schwinghammer, M. B. Mesch, V. Duppel, C. Ziegler, J. Senker, B. V. Lotsch, *J. Am. Chem. Soc.* **2014**, *136*, 1730–1733; c) D. J. Martin, K. Qiu, S. A. Shevlin, A. D. Handoko, X. Chen, Z. Guo, J. Tang, *Angew. Chem. Int. Ed.* **2014**, *53*, 9240–9245; *Angew. Chem.* **2014**, *126*, 9394–9399; d) G. Algara-Siller, N. Severin, S. Y. Chong, T. Björkman, R. G. Palgrave, A. Laybourn, M. Antonietti, Y. Z. Khimyak, A. V. Krashennnikov, J. P. Rabe, U. Kaiser, A. I. Cooper, A. Thomas, M. J. Bojdys, *Angew. Chem. Int. Ed.* **2014**, *53*, 7450–7455; *Angew. Chem.* **2014**, *126*, 7580–7585.