

**LETTER TO THE EDITOR**

**Open Access**

# Reply to comment on Fischella et al. (2012), “Intestinal toxicity evaluation of TiO<sub>2</sub> degraded surface-treated nanoparticles: a combined physico-chemical and toxicogenomics approach in Caco-2 cells” by Faust et al.

Matthieu Fischella<sup>1</sup>, Frédéric Bérenguer<sup>1</sup>, Gérard Steinmetz<sup>1</sup>, Mélanie Auffan<sup>2,3</sup>, Jérôme Rose<sup>2,3</sup> and Odette Prat<sup>1,3\*</sup>

## Abstract

In this response, we discuss the major differences that clearly distinguish our results from those mentioned by Faust et al. In particular, the experiments have been conducted on nanoparticles of different nature, what mainly explains the observed discrepancies. This is a reply to <http://www.particleandfibretoxicology.com/content/pdf/1743-8977-9-39.pdf>.

## Background

We thank our colleagues, Faust et al. for reading our manuscript that was published in *Particle and Fibre Toxicology* recently [1] and pointing out differences relative to their own publication [2]. In their letter, Faust et al. indicated that: “The Fischella et al. study employed surface-treated TiO<sub>2</sub> nanoparticles (NPs) ... Although these conflicting data may be a result of the nanomaterials employed. . .”

We claim that this is not just a slight discrepancy, but the key difference between these two studies; indeed we do not use the same nanoparticles. The various physico-chemical features of nanoparticles are now well known to lead to different interactions with biological systems and induce various toxicities [3]. We used surface-treated TiO<sub>2</sub> nanoparticles, whereas Koeneman et al. used unmodified TiO<sub>2</sub> nanoparticles.

- In their study, Koeneman et al. observed adsorption of unmodified TiO<sub>2</sub> NPs on Caco-2 cells and they conclude as follows:” Results of this investigation support our hypothesis that TiO<sub>2</sub>, although not

toxic, has previously undescribed non-lethal effects on microvilli and intracellular-free calcium”.

- Fischella et al. do not observe any internalization, nor any cytotoxicity nor genomics effects in Caco-2 cells after exposure to surface-treated TiO<sub>2</sub> NPs.

In their study, after 24h exposure to 100 µg/ mL of unmodified TiO<sub>2</sub> NPs, Koeneman et al. observed that 29.6% of TiO<sub>2</sub> NPs were absorbed on the cell surface, with 0.4% of the cells occupied by NPs (Figure four). Their SEM image (Figure seven) indicated that microvilli are damaged in the presence of 1000 µg/mL of unmodified TiO<sub>2</sub> NPs, and “no longer stood erect” at 10 µg/mL due to NPs absorption onto cell surface. We considered that our results were consistent with those of Koeneman, regarding the lack of toxicity observed in their study for similar doses (10 µg/mL) of TiO<sub>2</sub> NPs in identical cells.

In our work, after the ‘environmental’ or ‘acidic’ alteration of the T-liteSF (composed of a nanoTiO<sub>2</sub> core coated with aluminum hydroxide and PDMS layers), 90% of the organic layer is desorbed while the aluminum hydroxide layer persists at the surface of the nano-TiO<sub>2</sub> core. Faust et al. invoke a possible degradation of the aluminum layer, seen by others [4] in chlorine for 7 days, but this is not the process we used (3h under acidic conditions to mimic gastric degradation) and the protective

\* Correspondence: [odette.prat@cea.fr](mailto:odette.prat@cea.fr)

<sup>1</sup>CEA, IBEB, SBTN, LEPC, Bagnols-sur-Cèze F-30207, France

<sup>3</sup>International Consortium for the Environmental Implications of Nanotechnology (iCEINT), Aix-en-Provence, France

Full list of author information is available at the end of the article

aluminum layer remains at the NPs surface in our experimental conditions. This is confirmed by the similar  $^{27}\text{Al}$  NMR spectra of the T-LiteSF before and after alteration [5] showing that the aluminum hydroxide layer at the surface of the nanoTiO<sub>2</sub> is intact after alteration. The persistence of this aluminum hydroxide layer is also confirmed by chemical analysis (ICP-AES measurements). We demonstrated [1] the lack of generation of superoxide by the surface-treated TiO<sub>2</sub> NPs, degraded or not, while unmodified TiO<sub>2</sub> NPs have photocatalytic activity. The ability of unmodified TiO<sub>2</sub> NPs to generate superoxides likely explains the adverse effects (very relative, given the high tested concentrations) observed by our colleagues. On the contrary, the protective effect of the remaining aluminum hydroxide layer explains the absence of toxicity described in Fisichella et al.

Faust et al. do not have the same interpretation of our SEM pictures of Caco-2 cells (Figure 5B, Lanes 2 and 3); they observed possible distorted microvilli as a proof of harmful effects of our surface-treated TiO<sub>2</sub> NPs. However it is important to note that the same figure shows untreated cells (Figure 5B, lane 1) displaying the same features of microvilli. Faust et al. claim that our TEM images: "do not resemble Caco-2 images and show a significant effect of their NP treatment" because "normal Caco-2 epithelium exhibit cells with polarized cytoplasm containing many electron-dense organelles and cytoplasmic granules with a well-ordered array of microvilli at the cellular apex".

The absence of well-ordered microvilli is simply due to the cutting method, which involved a parallel cut to the bottom of the Petri dish in order to collect larger fragments, and not transversally as was done by Koeneman et al. [2]. This is a key point in our method that explains the apparent disorder of the MV in Figure 6. A propos the invisible organelles, the lack of contrast of the TEM image on the right in Figure 6 is due to the strong density of NPs on the cell surface, occulting intracellular details.

To conclude, these two studies do not lead to conflicting data, but are complementary studies, based on different nanoparticles, showing the importance of taking into account the surface properties of the NPs in toxicological studies.

Our colleagues will certainly agree with us that these data underscore the need to further examine the toxicological effects, not only of unmodified nanoparticles (i.e. at the beginning of the nanomaterials lifecycle), but of surface-treated nanoparticles used in engineered nanomaterials. At each stage of the lifecycle, from production to the end of life, the surface properties of the nanoparticles will be different leading to different toxicological effects.

We would like to emphasize the importance of evaluating the toxicity of engineered nanomaterials throughout

their life cycle in order to design them more safely in the future.

#### Competing interests

The authors declare that they have no competing interests.

#### Authors' contributions

All authors read and approved the final manuscript.

#### Author details

<sup>1</sup>CEA, IBEB, SBTN, LEPC, Bagnols-sur-Cèze F-30207, France. <sup>2</sup>CEREGE, UMR 7330 CNRS/ Aix-Marseille Université, ECCOREV, Europôle de l'Arbois, Aix-en-Provence F-13545, France. <sup>3</sup>International Consortium for the Environmental Implications of Nanotechnology (ICEINT), Aix-en-Provence, France.

Received: 17 October 2012 Accepted: 17 October 2012

Published: 1 November 2012

#### References

1. Fisichella M, Berenguer F, Steinmetz G, Auffan M, Rose J, Prat O: **Intestinal toxicity evaluation of TiO<sub>2</sub> degraded surface-treated nanoparticles: a combined physico-chemical and toxicogenomics approach in caco-2 cells.** *Part Fibre Toxicol* 2012, **9**:18.
2. Koeneman BA, Zhang Y, Westerhoff P, Chen Y, Crittenden JC, Capco DG: **Toxicity and cellular responses of intestinal cells exposed to titanium dioxide.** *Cell Biol Toxicol* 2009, **26**:225–238.
3. Rivera Gil P, Oberdorster G, Elder A, Puentes V, Parak WJ: **Correlating physico-chemical with toxicological properties of nanoparticles: the present and the future.** *ACS Nano* 2010, **4**:5527–5531.
4. Virkutyte JA-ASR, Dionysiou DD: **Depletion of the protective aluminum hydroxide coating in TiO<sub>2</sub>-based sunscreens by swimming pool water ingredients.** *Chem Eng J* 2012, **191**:95–103.
5. Auffan M, Pedetour M, Rose J, Masion A, Ziarelli F, Borschneck D, Chaneac C, Botta C, Chaurand P, Labille J, Bottero JY: **Structural degradation at the surface of a TiO(2)-based nanomaterial used in cosmetics.** *Environ Sci Technol* 2010, **44**:2689–2694.

doi:10.1186/1743-8977-9-39

**Cite this article as:** Fisichella et al.: Reply to comment on Fisichella et al. (2012), "Intestinal toxicity evaluation of TiO<sub>2</sub> degraded surface-treated nanoparticles: a combined physico-chemical and toxicogenomics approach in Caco-2 cells" by Faust et al.. *Particle and Fibre Toxicology* 2012 9:39.

**Submit your next manuscript to BioMed Central and take full advantage of:**

- Convenient online submission
- Thorough peer review
- No space constraints or color figure charges
- Immediate publication on acceptance
- Inclusion in PubMed, CAS, Scopus and Google Scholar
- Research which is freely available for redistribution

Submit your manuscript at  
www.biomedcentral.com/submit

