



OPEN

## Effect of TiO<sub>2</sub> nanoparticles on the tribological properties of lubricating oil: an experimental investigation

Corina Birleanu<sup>1</sup>, Marius Pustan<sup>1✉</sup>, Mircea Cioaza<sup>1</sup>, Andreia Molea<sup>2</sup>, Florin Popa<sup>3</sup> & Glad Contiu<sup>4</sup>

Nano-lubricants offer improved tribological properties in many applications, such as machines and engines. The presence of nanoparticles in the lubricating oil affects its wear, friction, thermal, chemical and physical properties in many ways. Titanium dioxide (TiO<sub>2</sub>) is a promising lubricant additive for enhanced engine efficiency. This article reports the effect of 10 W-30 pure base engine oil suspended TiO<sub>2</sub> nanoparticles. Four different volume concentrations (0.01%, 0.025%, 0.050% and 0.075%) of TiO<sub>2</sub> nanoparticles in the base lubricating oil are used for the analysis. The tribological tests were performed at ambient temperature as well as at 75 °C using a four ball tribometer. Scanning electron microscope (SEM) and Alicona Inginite Focus G5 microscope were used to analyze the worn surface. The results show that the surface-modified TiO<sub>2</sub> nanoparticles can remarkably improve the load-carrying capacity, the friction reducing, and anti-wear abilities of the additive oil. The diameter of the wear trace and the coefficient of friction are the tribological properties analyzed for the nano-lubricant prepared at different volume concentration (VC). It was found that the diameter of the wear scar and the coefficient of friction increase with increasing VC of TiO<sub>2</sub> nanoparticles in the lubricating oil. The main objective of the paper is to present the recent progress and, consequently, to develop a comprehensive understanding of the tribological behavior of engine oil mixed with TiO<sub>2</sub> nanoparticles.

### Abbreviations

ASTM	American Society for Testing and Materials
AW	Antiwear
COF	Coefficient of friction
μ	Coefficient of friction
Eps	Extreme pressure properties
FTP	Flash temperature parameter
NPs	Nanoparticles
RT	Room temperature
SEM	Scanning electron microscopy
TBN	Total basicity number
WPs	Wear preventive properties
wt.%	Weight percent
E	Elastic modulus
HRC	Rockwell hardness
EDS	Energy dispersive X-ray spectroscopy
VC	Volume concentration

<sup>1</sup>MicroNano Systems Laboratory, Technical University from Cluj-Napoca, Blv. Muncii nr. 103-105, 400641 Cluj-Napoca, Romania. <sup>2</sup>Department of Automotive Engineering and Transports, Technical University from Cluj-Napoca, Cluj-Napoca, Romania. <sup>3</sup>Department of Materials Science and Engineering, Technical University from Cluj-Napoca, Cluj-Napoca, Romania. <sup>4</sup>Department of Manufacturing Engineering, Technical University from Cluj-Napoca, Cluj-Napoca, Romania. ✉email: Marius.Pustan@omt.utcluj.ro

Research conducted in recent years on the addition of nanoparticles (NPs) to oils used in industry by increasing the load-bearing capacity of friction parts in mechanical systems highlighted the friction modifiers and improved the properties of anti-wear. Moreover, increasing the severity of loading and speed conditions in machines is a constant challenge for tribologists to develop improved solutions to increase the performance properties of used oil. Nanoparticles, due to their small size, can access areas with extremely small surface roughness and therefore have great potential in improving the tribological properties of lubricants and contact surfaces. Numerous studies have been conducted in the last two decades regarding the use of nanoparticles as lubricating additives<sup>1–3</sup>. The addition of nanoparticles to the base oil can reduce friction and wear, and it can be said that the nanoparticles could be beneficial lubricating additives, although some may be hard and abrasive<sup>4–7</sup>. In recent years, various nanoparticles have been investigated<sup>4,6–8</sup>. The nanoparticles used are generally metals such as Cu, Ni, Mo, Ag, and Pd; metal oxides including TiO<sub>2</sub>, SiO<sub>2</sub>, ZnO, ZrO<sub>2</sub>, and CuO; and sulfides WS<sub>2</sub>, MoS<sub>2</sub>, and PbS<sup>2</sup>.

Several hypotheses emerge from the open literature about how nanoparticles contribute to the reduction of friction and wear under different laboratory testing conditions. However, useful information can be detached if prototypical materials are used together with a balance between the applied mechanical parameters (loads, speeds, temperatures, contact pressures) and surface conditions.

The transfer and adhesion of the nanoparticles leads to the change of the surface condition, the self-reduction, and the formation of a thin TiO<sub>2</sub> tribo-film which conduct to the decrease of the coefficient of friction, of the pressure and the temperature in the contact area, therefore of the wear phenomenon.

The addition of TiO<sub>2</sub> nanoparticles to the lubricating oil showed stable friction due to the formation of protective films on the worn surfaces<sup>9</sup>. Shenoy et al.<sup>10</sup> analyzed the influence of TiO<sub>2</sub> nanoparticles in lubricating oil. The results obtained showed a higher bearing capacity by approximately 35% compared to the use of lubricating oil without the addition of nanoparticles. The experiments performed by Kao and Lin<sup>11</sup> using an alternative sliding tester to analyses friction and wear in the presence of additive rapeseed oil showed that there was an 80.84% reduction in mean surface roughness. The average diameter of TiO<sub>2</sub> was 50 nm, and the particle concentration was 5 weight percent (wt.%). Using a low concentration of TiO<sub>2</sub> nanoparticles is enough to improve the tribological characteristics. The coefficient of friction and the wear scars decreased by approximately 15.2% and 11%, respectively<sup>12</sup>.

Several studies have been conducted on nanoparticles as oil additives<sup>10–17</sup>. The particle size of TiO<sub>2</sub> affected the wear behavior of the composite material<sup>18</sup>. It was found that the microscale particles of TiO<sub>2</sub> damaged the surface due to severe adhesion and abrasion. The surface damage due to nanoscale TiO<sub>2</sub> particles was due to slight abrasion. More investigations have been carried out on TiO<sub>2</sub> as a coating material<sup>12,13,18–21</sup> or reinforcement in composites<sup>10</sup> for better tribological performance<sup>13</sup>. Gupta et al.<sup>14</sup> presents for some commercial lubricants the friction coefficient (COF) values in different experimental conditions for instance: for SAE20W40 the  $\mu = 0.102$  under testing parameters: 200 rpm, 392 N, 75 °C, 3600 s, for mineral oil  $\mu = 0.104$  under testing parameters 20 Hz, 10 N, 3600 s. Anand et al.<sup>20</sup> studies the effects of varying concentrations by weight (0.5 and 1 wt.%) of rice bran oil/TiO<sub>2</sub> nanofluid an revealed an improvement in the viscosity with an increase in nanoparticle concentration. Furthermore, an improvement in viscosity in hybrid fluids at higher temperatures was observed.

The lubrication mechanism in the presence of nanoparticles produces (Fig. 1): (a) the surface properties will be modified and two friction surfaces will be separated with tribo-film formation, thus offering promising tribological performance; (b) the nanoparticles roll between the friction surfaces, reducing friction and wear; and (c) the heat and pressure generated during operation lead to the compaction of the nanoparticles following wear, which is considered a mending effect of the surface and a polishing effect<sup>7</sup>.

In this paper, the antifriction and antiwear behaviors of TiO<sub>2</sub> nanoparticle suspensions in 10 W-30 oil with different percentages (0.010, 0.025, 0.050 and 0.075 wt.%/v) were evaluated using a tribometer with four balls. The results present the influence of the nanoparticle percentage on the tribological behavior of the mixed oil, the evaluation of worm surface structure through the various operating conditions tested by scanning electron microscopy (SEM), and the depth of wear marks on the spheres measured using the Alicona Inginité Focus G5 Microscope.


A 4-ball tribometer was used in this study, for which the friction force (the coefficient of friction) between the samples was continuously recorded according to the normal load and the elapsed time. Four nano-oil samples were prepared and tested repeatedly with various specimens from the 4-ball tribometer to evaluate the direct effect and the surface-enhancing effect of nanoparticles in the lubricating oil.

Therefore, the purpose of this paper is dedicated to finding the possibility of tribological performance improvement of conventional engine oil using TiO<sub>2</sub> nanoparticle additives. This promising technology has a large impact on fuel consumption and engine durability for a greener future.

## Samples description

Experimental studies involve the formulation of stable TiO<sub>2</sub>-based nano lubricant samples at different concentrations. The physicochemical properties, such as density, viscosity, and viscosity index, were measured using an automated SVM 3000 Anton-Paar rotational Stabinger viscometer. Density was measured using a vibrating U-tube densimeter, and for the determination of viscosity, a Peltier element was used to thermoregulate the samples.

**Materials.** Against the background that TiO<sub>2</sub> is best suited for many tribological applications (including solid lubricants) due to its excellent tribological behavior, these nanoparticles were chosen for the current investigation. Commercial TiO<sub>2</sub> Degussa P25 nanoparticles supplied from Sigma–Aldrich and Motul 5100 4T 10 W-30 engine oil were used in the formulation of nano lubricant samples. The average sizes of the TiO<sub>2</sub> nanoparticles were 18–21 nm.



**Figure 1.** Lubricating mechanisms by NPs based lubricant<sup>5,15</sup>.

Raw materials	Properties	Value
TiO <sub>2</sub> Degussa P25	Crystalline phases	75% anatase, 25% rutile
	Average particle size	21 nm
	Surface area	> 30 m <sup>2</sup> /g
	Density	3900 kg/m <sup>3</sup>
Motul 5100 4T	SAE Viscosity grade	10 W-30
	Density at 20 °C	871 kg/m <sup>3</sup>
	Viscosity at 40 °C	74.6 mm <sup>2</sup> /s
	Viscosity at 100 °C	11.5 mm <sup>2</sup> /s
	Pour point	−36 °C
	Flash point	226 °C
	Total basicity number (TBN)	7.5 mg KOH/g

**Table 1.** Properties of commercial TiO<sub>2</sub> Degussa P25 and Motul 5100 4T 10 W-30 engine oil.


Lubricant sample	LS	L0	L1	L2	L3
TiO <sub>2</sub> (wt.%)	0	0.010	0.025	0.050	0.075
Pure base oil (%)	100	99.99	99.75	99.50	99.25

**Table 2.** Concentrations of the prepared nano lubricants.

The properties of the raw materials are presented in Table 1. The varying concentrations of TiO<sub>2</sub> for the engine oil used in the experiments were 0.010, 0.025, 0.050 and 0.075 wt.%, as shown in Table 2. To demonstrate the effect of nanoparticles on the engine oil additives, tribological tests were conducted using commercial lubricant engine oil—Motul 5100 4T10 W-30.

**Nano lubricants preparation.** The mixing of nanoparticles with engine oil is an important step towards the improvement of engine oil quality. Different amounts of TiO<sub>2</sub> nanoparticles (Table 2) were dispersed into engine oil, and 0.2 mM Triton X surfactant was added to increase the stability of the nano lubricants. The 0.2 mM Triton X surfactant plays an important role in blending the nanoparticles in a manner that makes them soluble in the engine oil, also providing stability for the nanoparticles, preventing the agglomeration of the nanoparticles within engine oils. The uniform dispersion of TiO<sub>2</sub> nanoparticles in base oil is a challenge because of the high surface energy of the nanoparticles, they tend to agglomerate and settle down<sup>13</sup>. Hence, before friction tests, to increase the stability over time, the prepared suspensions were subjected to magnetic stirring, followed by ultrasound treatment for 30 min. For preparation of the nano lubricants was used both mechanical and chemical methods to increase the stability. Thus, in the first stage, 0.2 mM Triton X surfactant was added in the suspensions and in the second stage, the magnetically stirring, followed by an ultrasound treatment were used. These methods were used to decrease the agglomeration effect which acquired when the Brownian motion and Van der Waals intermolecular attractive forces from the suspensions were greater than the repulsive forces<sup>16,22</sup>.

The stability studies were performed using UV–Vis JASCO V-550 spectrometer, with scanning range between 200–900 nm and the baseline was made with oil lubricant and surfactant mixture due to emphasizing the



**Figure 2.** UV-Vis absorption spectra of the TiO<sub>2</sub> nano lubricants in time.

Sample	Density at 15 °C (kg/m <sup>3</sup> )	Kinematic viscosity at 40 °C (mm <sup>2</sup> /s)	Kinematic viscosity at 100 °C (mm <sup>2</sup> /s)	Viscosity index
LS (pure base oil)	862	89.7	13.6	154
L0	863	91.6	14.1	158
L1	863	92.1	14.1	158
L2	863	92.0	14.1	158
L3	864	92.3	14.2	158


**Table 3.** The physicochemical properties of engine oil and TiO<sub>2</sub> nanolubricants.

absorption band of TiO<sub>2</sub> (monitoring of TiO<sub>2</sub> concentration from the suspensions). Thus, in Fig. 2 are presented the UV-Vis spectra of the TiO<sub>2</sub> nano lubricants. A decrease of the UV-Vis absorbance was observed after 2 h for the nano lubricants, while at 168 h it was observed that the absorbance tends to maintain at the same value. This is attributed to the coating of the nanoparticles with the surfactant molecules, which due to the large molecular chain; separate the nanoparticles from each other, reducing the agglomeration effect, a phenomenon called electrostatic stabilization<sup>23</sup>.

The physicochemical properties of engine oil and TiO<sub>2</sub> nano lubricants are presented in Table 3. An extended discussion regarding the physicochemical properties of TiO<sub>2</sub> nano lubricants were presented in previous work<sup>24</sup>. It can be observed that with an increase in the TiO<sub>2</sub> amount in the engine oil, the density tends to increase by 0.2% (from 862 kg/m<sup>3</sup> for the base oil up to 864 kg/m<sup>3</sup> for the nano lubricant, which contains 0.075 wt.%/v) due to the high density of the nanoparticles (3900 kg/m<sup>3</sup>), even if the concentration of TiO<sub>2</sub> is very small. Additionally, kinematic viscosity at both 40 °C and 100 °C tends to increase with TiO<sub>2</sub> concentration in nano lubricants to 3% and 4%, respectively (from 89.7 to 92.3 mm<sup>2</sup>/s and from 13.6 to 14.2 mm<sup>2</sup>/s, respectively). According to Ali et al.<sup>16</sup>, this behavior is related to the fact that the nanoparticles act as catalysts in a cracking reaction and have quite good heat transfer properties. The high viscosity of the nano lubricant oils improves the lubricating property because it reduces friction and prevents rapid wear. The viscosity index increases up to 158 when TiO<sub>2</sub>

Chemical properties						
%Fe	%C	%Si	%Cr	%P	%S	%Mn
96.5–97.3	0.93–1.1	0.15–0.35	0.14–0.16	0–0.025	0–0.015	0.25–0.45
Mechanical properties						
Hardness (HRC)	Tensile strength (MPa)	Yield strength (MPa)	Young's modulus (GPa)	Poisson's ratio (-)	Roughness $R_a$ ( $\mu\text{m}$ )	
54–58	2100–2200	2000	200	0.3	0.1	

**Table 4.** Chemical and mechanical properties of ball material.



**Figure 3.** Schematic representation of four-ball tribometer.

nanoparticles are added into the oil, which means that the variation of viscosity with temperature is lower for nano lubricant oils than base oil.

**Ball materials.** The standard ball test material was 52100 grade 25 chrome alloy steel, 12.7 mm in diameter with a surface roughness ( $R_a$ ) of 0.1  $\mu\text{m}$ , extra polish (EP) grade of 25 and hardness of 54–58 HRC. Four new balls were used for each test. Before starting a new test each time, the balls were cleaned with a technical cleaner (isoparaffinic-based solvent cleaner) and wiped dry using tissues. 52100 steel is commonly used as ball and roller bearings in industry and for a variety of automotive applications. It is known for its excellent surface quality, superior wear resistance, hardness, and high load capacity. Some of the chemical composition and mechanical properties of 52100 steel used in this investigation are listed in Table 4.

### Experimental method and device

The American Society of Lubrication Engineers has published a catalog of friction and wears testing devices that describes in detail over 230 different tribometers<sup>7</sup>. Each device has its strengths and weaknesses. For this work, we used the four-ball wear test geometry, which has been selected to provide the following test conditions: high contact pressures that ensure operation in boundary lubrication mode; good control of the operating parameters of load, temperature, speed, operating time, atmosphere; high sensitivity of wear and friction measurements; simple samples for testing, small dimensions, and easy manufacture.


The four-ball tester is an excellent tool for checking and determining the quality of lubricants and additives. This tribometer can be used to determine the wear preventive properties (WPs), extreme pressure properties (EPs) and friction behavior of lubricants. The widespread acceptance of Four Ball Tester test results makes it an excellent tribological device.

This tribometer consists of a device where an upper ball can be rotated and is in contact with three fixed balls that are immersed in the oil sample. Different loads are applied to the ball by weights applied to a system with the load lever. The upper rotary ball is held in a special chuck located at the lower end of the vertical axis of an electric motor and rotates at a constant speed. The lower fixed balls are held in contact with each other in a steel pot by a clamping ring and a locking nut. The arrangement is illustrated in Fig. 3. The basic sample configuration (Fig. 4) consists of a tetrahedral arrangement of four balls.


These tests were carried out under the American Society for Testing and Materials (ASTM) condition and ASTM D 4172 method test B. The tests were conducted under dry conditions at a room temperature RT ( $23 \pm 2$ )°C and then at ( $75 \pm 2$ )°C and relative humidity RH ( $35 \pm 2$ )%, the speed ( $1200 \pm 60$ ) rpm, the time test ( $30 \pm 1$ ) minutes and the load: ( $396 \pm 4$ ) N. The tests were repeated at least three times for every measurement. All presented results in this work are the arithmetic mean value of the measured values, unless otherwise stated. The corresponding standard deviation is indicated by the error bars, describing the scatter of the results.

The experimental procedure can be followed in the flow chart shown in the Fig. 5.

The viscosity is a very important parameter for a lubricant, as it affects the film thickness and the wear rate of the sliding surface. It is used for the identification of individual grades of oil and for monitoring the changes occurring in the oil while in service. Increasing the viscosity normally shows that the used oil has been



**Figure 4.** Four ball of tribological system.



**Figure 5.** Four-ball tribometer—flow chart experimental procedure.

deteriorated by contamination or oxidation. Additionally, decreased viscosity usually indicates dilution of the oil. The oil viscosity was measured with a viscosity meter at experimental temperatures of 23 °C and 75 °C. In test B method ASTM D 4172, the load was 396 N, and in the four-ball test machine, the load cell was mounted 80 mm from the center of the shaft. In addition, the wear was measured with the average of horizontal and



vertical scars with SEM, and the depth of wear marks on the spheres was measured using an Alicona Inginité Focus G5 microscope. The duration of the test was selected to ensure that the running-in period was less than 30% of the total duration of the test.

The RDS (Energy-dispersive X-ray spectroscopy) analysis of the samples before and after tribological tests was measured using Oxford EDS—Ultim<sup>™</sup> Max EDS with AZtecLive software. AZtecLive enables the quick and comprehensive investigation of a sample with real-time chemical feedback via the AZtecLive interface.

## Results and discussion

**Wear scar images of balls.** Micrographs of the wear scar formed on the balls for each of the formulations are shown in Figs. 6 and 7. The addition of TiO<sub>2</sub> led to reduction in the diameter of the wear scar.

Figures 6 and 7 reveal the wear scar maps of the tested ball sliding against the bearing steel balls. This shows that the wear degree of the samples containing TiO<sub>2</sub> was obviously improved compared to that of the base oil. When the base oil was a lubricant, the worn surface of the ball presented black sediment, which confirmed that the main component was Fe resulting from ball-on-ball milling. Moreover, the 0.01 wt.% and 0.025 wt.% samples also presented black sediment, but the wear radii were visibly reduced. In particular, the radius of the 0.075 wt.% oil sample in the stabilized state after rubbing was smaller than that of the other samples, showing the superior anti-wear performance of this sample.

To further investigate the wear mechanism, SEM images of worn surfaces of the lower balls lubricated by the base engine oil and the engine oil samples containing 0.01, 0.025, 0.050 and 0.075 wt.% TiO<sub>2</sub> nanoparticles were investigated. The tests were performed at two different working temperatures, 23 °C (RT) and with oil heated to 75 °C.

Following the evaluation of the wear traces with SEM, radius differences of the circular wear trace are observed, and the radius difference is approximately 5–10%. This should not greatly influence the mechanism of wear (generation of wear residues, increase of the tribo-layer, etc.).

Figure 6 shows that for samples LS and L0, there were obvious plowing and some pits on the worn track, which were due to the second local rupture of debris during the sliding process; moreover, the friction of debris at the sliding interface clearly furrows on the worn surface.

Figure 6 (L2 and L3) shows that the worn surface presented finer mesh-like grooves, in agreement with the COF result in Fig. 14. For the 0.05 wt.% sample, the worn surface was covered by fine grooves and detachments after the rolling test, as shown in Fig. 4 (L1), and the mechanism of wear was dominated by microplowing. Furthermore, Fig. 6 (L2 and L3) shows that the wear scratch was almost invisible; through a local zoom of the images in Fig. 6, slight furrows of wear could be observed. This is mostly attributed to the increase in TiO<sub>2</sub>, which could reduce the wear of frictional interfaces. This indicates that TiO<sub>2</sub> played a lubricating role and prevented wear in the rolling process. The above results agree with the tribological results showing the decrease in the friction coefficient in Fig. 14.

The wear scar diameter of each of the three bottom test balls was measured to determine the lubricity performance of the test lubricant. In general, the larger the wear scar diameter is, the more severe the wear, but we also consider the depth of the wear trace. The wear scar diameter was determined for each of the three fixed balls.

The temperature of the test lubricants was measured by a thermocouple attached to the four-ball tester to record the temperature changes throughout the duration of the experiment.


The base oil and nano-oils were tested at temperatures of 23 °C and 75 °C (close to the temperature service for engine oil). Increasing the temperature results in nanoparticle movement, which is associated with reducing the fluid resistance over the flow; therefore, the viscosity is reduced. With respect to viscosity, either of the base oils or nano-oils are non-Newtonian fluids. However, the temperature of the contact point for the balls is also influenced by the sliding speed. A sliding speed of 0.80 ms<sup>-1</sup> (calculated based on input parameters) was selected to provide the minimum and extreme heating due to sliding.

Figure 6 provides SEM images of the rubbed surface lubricated with pure oil and TiO<sub>2</sub> nanoparticles added with 0.01 wt.%, 0.025 wt.%, 0.050 wt.% and 0.075 wt.%, respectively at RT (room temperature). The worn surface lubricated with pure oil shown in Fig. 4—LS is rough with many thick and deep furrows due to the strong adhesion and ploughing between contacted asperities on the rubbed surface of the tribological pair. The worn surface of the ball when the base oil was used as a lubricant showed a combination of abrasive wear and adhesive. The surface damage was highlighted in these tests, which can be seen in Fig. 4—LS. The presence of oil at the interface reduced COF, but it fluctuated during the test. The hard debris generated during slipping in the oil could have further damaged the surface. The contamination with these particles (the third body) could have caused the COF fluctuation. However, there was no evidence of free debris on worn surfaces after these tests. The debris was not welded or formed a transfer film on the sliding surfaces.

The worn surface is lubricated with TiO<sub>2</sub> nanoparticles added with oil is smoother than that lubricated with pure oil. And with the increase of the addition of the concentration of TiO<sub>2</sub> nanoparticles in pure, thick oil and the deep furrows on the surfaces of the wear scars become smaller and shallower. There was no indication that the nanoparticles had settled on the sliding surface. The deterioration of the surface was due to the combination of abrasive wear and adhesive.

TiO<sub>2</sub> nanoparticles were deposited on the surface, acted as third body particles which further decreased the shear stress. These deposited nanoparticles were more stable than the debris of the sliding materials. It appears that the surface of the wear path has been smoothed. But there were some places where serious damage occurred. It is evident that the higher wt.% TiO<sub>2</sub> content has higher polishing effect.


With the increase of the temperature (Fig. 7) it is seen that the surface of the wear track showed signs of wear that indicate wear of the adhesive with very slight abrasion marks. There was no indication of debris left on the surface. As the temperature rises, the addition of TiO<sub>2</sub> nanoparticles to the base oil has less effect on wear.



**Figure 6.** SEM images of worn-out samples corresponding to pure base oil and additive 0.01, 0.25, 0.050 and 0.075 wt.% TiO<sub>2</sub> at RT, 396 N load at 1200 rpm after a 30-min period of testing.

Usually, the surfaces have been worn due to the adhesive wear. However, the severity was different. It can be seen from Fig. 7 that the signs of worn surface area observed decreased with the increase in TiO<sub>2</sub> wt.%. When the TiO<sub>2</sub> nanoparticles were added to the base oil, the wear of the surface was due to micro abrasion and minimally due to the adhesive wear. The surface damaged by nanoscale TiO<sub>2</sub> particles was caused by slight abrasion<sup>13</sup>. This observation is consistent with the current investigation. In addition, the presence of lubricant at the sliding interface could reduce the severity of abrasion due to nanoparticles.






**Figure 7.** SEM images of worn-out samples corresponding to pure base oil and additive 0.01, 0.025, 0.050 and 0.075 wt.%  $\text{TiO}_2$  at 75 °C, 396 N load at 1200 rpm after a 30-min period of testing.

**RDS analyses of the balls.** The chemical characterization/elemental analysis of materials of the samples used in this investigation was done based on the EDS analysis using Oxford EDS—Ultim<sup>®</sup> Max EDS with AZtecLive software. From the multiple set of test samples, several representatives were chosen for which this analysis was done.

Figures 8 and 9 show the EDS images obtained for a 75 °C test with pure base oil and 75 °C test with the oil-added 0.075 wt.%  $\text{TiO}_2$  nanoparticles, respectively.




**Figure 8.** SEM and EDS analysis of worn surface of steel ball after four-ball test lubricated by the pure based oil at 75 °C.

Using the EDS elemental quantification of elements, allow us to deliver a qualitative analysis of the worn and unworn surface of the balls after tribological tests. In the worn area are found elements not detected on the unworn surface. The new elements are S (up to 1 wt.%), P (0.5 wt.%), O (up to 3 wt.%), Zn (up to 3 wt.%), and Ca (up to 1 wt.%). These new elements occurring suggest the formation of a stable tribofilm at wear track. The above observation is sustained by the friction coefficient modification for the 0.075 wt.% TiO<sub>2</sub> addition to oil compared with the pure oil. The friction coefficient decreases from 1.20 (pure oil) to 0.05 (oil with 0.075 wt.% TiO<sub>2</sub>) at 75 °C and from 1.8 (pure oil) to 0.4 (oil with 0.075 wt.% TiO<sub>2</sub>) at room temperature.

**Wear depth scar on the balls.** The depth of the wear scar on the spheres was measured using an Alicona Inginitive Focus G5 microscope. The surfaces were scanned with a microscope using 50× magnification, and the light source was coaxial with the eyepiece (lenses) and supplemented with a light ring. Scanning was performed using Image Field mode with a vertical resolution between 0.003 and 0.032 µm and a horizontal resolution of 2.13 µm. The duration of a scan was between 1.5 and 3 min. The average scan height was 0.150 mm. This gives a Vertical Dynamic of 150/0.032 = 4687.5.

The evaluation of the wear depth was performed by measuring the distance from the ideal circle, constructed using a fixed 6.35 mm beam with the Measure Circle function. The traces of the intersection between the scanned surface and the plane in which the depth measurement was performed were used to orient and position the ideal circle. The depth of wear (difference between the ideal circle and the trace on the sphere) was measured using the measure height step function or maximum distance. The 2D profiles of the worn surfaces for different lubricant oils after the wear test are shown in Figs. 10 and 11.




**Figure 9.** SEM and EDS analysis of worn surface of steel ball after four-ball test lubricated by the oil-added 0.075 wt.% TiO<sub>2</sub> nanoparticles at 75 °C.

Compared with pure oil, TiO<sub>2</sub> nanoparticles added in the base oil had a significant improvement in the wear surface. After the wear test at RT, only small grooves could be observed, and the wear mechanism was mainly formed by microplowing. Although the wear depth of the 0.01 wt.% sample was much smoother than that of the base oil, microplowing still existed, with a corresponding wear depth of 1.2 µm at RT and 0.41 µm at 75 °C. Moreover, the anti-wear property is improved with the amount of TiO<sub>2</sub> nanoparticles added in the base oil. This indicates that TiO<sub>2</sub> nanoparticles added in engine oil prevents the plowing wear that existed in the control sample.


The results of the wear traces analyzed in Figs. 10 and 11 were concatenated in Fig. 12. Figure 12 shows a chart of the amount of ball wear, as measured using the Alicona Inginité Focus G5 microscope. Very little wear protection was provided by the base oil, but the addition of nanoparticles to the base oil significantly reduced wear. In addition to the fact that it indicates the amount of wear obtained for the 4 types of tests, Fig. 12 also indicates the mode of wear behavior depending on the 2 temperature conditions for which the tests were performed (RT and 75 °C).

The wear rate of the lower balls at RT was somewhere  $70 \times 10^3 \mu\text{m}^3$  for the base oil, gradually reaching up to  $10 \times 10^3 \mu\text{m}^3$  for the concentration of 0.075 wt.% TiO<sub>2</sub>. At a temperature of 75 °C, the wear decreased to  $33 \times 10^3 \mu\text{m}^3$  for the base oil, and then with the addition of wt.% TiO<sub>2</sub> nanoparticles, it decreased to  $5 \times 10^3 \mu\text{m}^3$ . The measurements of the wear depths produced on the balls were accurate and repeatable with the help of the Alicona Inginité Focus G5 microscope.

In the current study, the authors tried to avoid overloading the tribocouple due to a high risk of layer deformation and change in the wear mechanism. Considering the wear rates of the balls studied by the authors ( $33\text{--}70 \times 10^3 \mu\text{m}^3$ ) at RT, it can be concluded that the wear of the balls is a few orders of magnitude larger for




**Figure 10.** Wear depth scar ( $\mu\text{m}$ ) of lower balls at room temperature (RT).



**Figure 11.** Wear depth scar (μm) of lower balls at 75 °C.





**Figure 12.** Ball wear volume for oils used in this work at different temperature.

balls lubricated at 75 °C. This can be explained by the fact that the connecting rods are always in contact, and therefore, the phenomenon of continuous overheating occurs.

No transfer film was observed on the balls at a slip velocity of 0.80 ms<sup>-1</sup>. However, the tests were accompanied by vibrations and unwanted noise.

**Friction property of lubricating oils with TiO<sub>2</sub> additives.** The tribological performance of engine oil (Motul 5100 4T10 W-30) with TiO<sub>2</sub> additive loading as a lubricant additive is shown in Fig. 14. The coefficient of friction (COF) of engine oil with different additive TiO<sub>2</sub> amounts was measured at an applied load of 10 N at the arm of the tribometer, 396 ± 4 N normal load applied on balls and rotation 1200 rpm, as presented in Fig. 13. Relative fluctuations in the friction response of base engine oil were observed in comparison to the additive response, and the COF was found to increase with time in the initial stage during the running period.

The coefficients of friction were remarkably reduced by the addition of TiO<sub>2</sub> nanoparticles to the base lubricant. At a normal applied force of 396 N, the coefficient of friction of the nano lubricant was reduced by approximately 60% of the COF value for the base lubricant at RT and by approximately 80% at a temperature of 75 °C.

Clearly, the nano lubricant with more TiO<sub>2</sub> nanoparticles had the best coefficient of friction (Fig. 13). These results indicate that the TiO<sub>2</sub> nanoparticles decrease the ball-to-ball friction contact compared to the base lubricant.

The medium lowest COF of 0.01 was obtained by the oil sample with 0.075 wt.% TiO<sub>2</sub> under a 75 °C lubricant temperature. Moreover, Fig. 13 shows the influence of particle concentration on the COF of oil suspensions, indicating that the average COF was influenced by the TiO<sub>2</sub> concentration. The average COF obviously fell from 0.112 to 0.05 in the range of 0.01 wt.% to 0.075 wt.% TiO<sub>2</sub>, reflecting that the addition of nanoparticle lubricants straightened the sliding response when stabilizing additive amounts below 0.025 wt.% TiO<sub>2</sub>. However, the average COF showed a slightly decreasing trend from 0.010–0.088 in the range of 0.010 wt.% to 0.025 wt.% at RT. On the other hand, at 75 °C, the average COF obviously fell from 0.095 to 0.015 in the range of 0.01 wt.% to 0.075 wt.% TiO<sub>2</sub>. Furthermore, the COF tended to be stable after rubbing, and the corresponding average COF in the stable period for higher concentrations of TiO<sub>2</sub> presented a lower antifriction property, as shown in Figs. 13 and 14. The relevant tribological mechanism at RT is due to TiO<sub>2</sub> particles at higher concentrations accumulating in the inlet of the ball-on-ball contact area, which causes an insufficient supply of lubricant and starvation in the contact area.


The running-in period is of great significance to the regulation of tribological performance to a certain extent. Reducing the running-in period is beneficial to improving the antifriction property. The formation of a boundary lubrication film is the main reason for the stability of the friction coefficient. The coefficients of friction stabilized in the second part of the test time. The rubbing period of nano-oil with a 0.1 wt.% concentration lasted longer than that of the others with a time of 780 s. In addition, it is noteworthy that the rubbing time obviously decreased with increasing concentration. The 0.05 and 0.075 wt.% samples had the shortest rubbing time in terms of friction properties.

The friction coefficient was calculated according to IP-239 (EP and AW tests for lubricants) and is expressed as follows:


$$\mu = 0.22248 \cdot \frac{1000 \cdot T}{F} \quad (1)$$

where T is the frictional torque in kg·mm and F is the applied load in kg<sup>12</sup>. The frictional torque data were recorded by software, and the friction coefficient was calculated.

The frictional curve (Fig. 13) showed a slight increase in the value of COF at the start. However, after 25–30 min, the steady-state condition was attained, and curve remained approximately stable thereafter. No abrupt behavior or sharp peak was observed in the steady-state region. The improved performance is attributed to the film formation capability of TiO<sub>2</sub> nanoparticles.




**Figure 13.** Coefficient of friction (COF) for different additive amounts of TiO<sub>2</sub> at RT (23 °C) and 75 °C.



**Figure 14.** Average coefficient of friction (COF) for different additive amount of TiO<sub>2</sub> at RT (23 °C) and 75 °C and COF in steady state after rubbing effect.

**Flash temperature parameter.** The flash temperature parameter is a unique number that gives us indications of the critical flash temperature above which the lubricant used will be out of use<sup>16</sup>. The flash temperature parameter for operating conditions in the four-ball tribometer:



**Figure 15.** Plot of TiO<sub>2</sub> as a lubricant additive vs. flash temperature parameter FTP for different temperature.

$$FTP = \frac{F}{d^{1.4}} \quad (2)$$

A flash temperature parameter (FTP) was calculated for all the experimental conditions according to Eq. (2). In this equation, F is the normal load in kilograms and d is the mean wear scar diameter in millimeters at the load. A detailed explanation of the parameter is given by Lane<sup>16,17</sup>.

High values for the flash temperature parameter indicate that the lubricant shows good performance with a reduced possibility of lubricant breakdown<sup>15</sup>.

Figure 15 shows the plot of TiO<sub>2</sub> percentage vs. flash temperature parameter (FTP) for different testing temperatures, more exactly room temperature RT and 75 °C. From the figure, the maximum and minimum FTPs were obtained from 0.075 wt.% contaminated lubricant and pure lubricant, respectively. The maximum FTP value means that good lubricating performance occurred, indicating a lower possibility of lubricant film breakdown. This phenomenon has also been observed by other researchers<sup>11</sup>. This seems to indicate that TiO<sub>2</sub> nano additives are a potential anti-wear additive for lubricating oil. The 0.075 wt.% TiO<sub>2</sub> in this investigation improved the lubricant performance based on the higher value of FTP observed compared with pure lubricant. The graphs also show the effect of temperature on the FTP of lubricants.

## Conclusions

For the tests performed on a four-ball wear machine with different percentages of TiO<sub>2</sub>-contaminated lubricant, the conclusions drawn are as follows.

The wear of the ball specimens decreases with the increase in wt.% TiO<sub>2</sub> addition. Compared with pure lubricant, 0.075% TiO<sub>2</sub> improves the lubricant performance based on the higher value of the flash temperature parameter (FTP).

The medium lowest COF of 0.01 was obtained by the oil sample with 0.075 wt.% TiO<sub>2</sub> under a 75 °C lubricant temperature. The average COF obviously fell from 0.112 to 0.05 in the range of 0.01 wt.% to 0.075 wt.% TiO<sub>2</sub>, reflecting that the addition of nanoparticle lubricants straightened the sliding response when stabilizing additive amounts below 0.025 wt.% TiO<sub>2</sub>. On the other hand, at 75 °C, the average COF obviously fell from 0.095 to 0.015 in the range of 0.01 wt.% to 0.075 wt.% TiO<sub>2</sub>. The lowest COF was obtained for the 0.075 wt.% TiO<sub>2</sub> oil sample, which dropped by approximately 60% compared to the pure base oil at RT and by approximately 80% at a temperature of 75 °C. Furthermore, the rubbing time obviously decreased with the increase in TiO<sub>2</sub>.

The main wear type of the worn surfaces lubricated by the engine base oil with TiO<sub>2</sub> could be attributed to slight ploughing wear. Pure oil presented an obvious furrow and indentation, with a corresponding maximum depth of 1.2 μm. From physical observations on worn surfaces of specimens, it can be suggested that nano-oil with TiO<sub>2</sub> (0.075 wt.%) acts as an anti-wear lubricant additive. Micrographs showed that wear scar surfaces in the 0.075% TiO<sub>2</sub>-contaminated lubricant tests appear to be much smoother, thus having less material transfer.

TiO<sub>2</sub> plays a decisive role in the improvement of the tribological performance. Additionally, spherical TiO<sub>2</sub> has a probable ball-bearing lubrication effect during the friction process. The optimum concentration of TiO<sub>2</sub> nanoparticles further helps to form the film for a long time, due to its inherent characteristics. Thus, the experiment showed that the developed nano-fluids could serve potential engineering applications and help achieve the goals of sustainable development.

Received: 29 November 2021; Accepted: 18 March 2022

Published online: 25 March 2022

## References

- Dai, W., Kheireddin, B., Gao, H. & Liang, H. Roles of nanoparticles in oil lubrication. *Tribol. Int.* **102**, 88–98. <https://doi.org/10.1016/j.triboint.2016.05.020> (2016).
- Binu, K. G., Shenoy, B. S., Rao, D. S. & Pai, R. Static characteristics of a fluid film bearing with TiO<sub>2</sub> based nanolubricant using the modified Krieger–Dougherty viscosity model and couple stress model. *Tribol. Int.* **75**, 69–79. <https://doi.org/10.1016/j.triboint.2014.03.013> (2014).

3. Ingole, S. *et al.* Tribological behavior of nano TiO<sub>2</sub> as an additive in base oil. *Wear* **301**, 776–785. <https://doi.org/10.1016/j.wear.2013.01.037> (2013).
4. Demas, N. G., Erck, R. A., Lorenzo-Martin, C., Ajayi, O. O. & Fenske, G. R. Experimental evaluation of oxide nanoparticles as friction and wear improvement additives in motor oil. *J. Nanomater.* <https://doi.org/10.1155/2017/8425782> (2017).
5. Wu, Y. Y., Tsui, W. C. & Liu, T. C. Experimental analysis of tribological properties of lubricating oils with nanoparticle additives. *Wear* **262**, 819–825. <https://doi.org/10.1016/j.wear.2006.08.021> (2007).
6. Lee, K. *et al.* Understanding the role of nanoparticles in nano-oil lubrication. *Tribol. Lett.* **35**, 127–131. <https://doi.org/10.1007/s11249-009-9441-7> (2009).
7. Jason, Y. J. J., How, H. G., Teoh, Y. H. & Chuah, H. G. A study on the tribological performance of nanolubricants. *Processes* **8**, 1372. <https://doi.org/10.3390/pr8111372> (2020).
8. Ilie, F. & Covaliu, C. Tribological properties of the lubricant containing titanium dioxide nanoparticles as an additive. *Lubricants* **4**, 12. <https://doi.org/10.3390/lubricants4020012> (2016).
9. Shenoy, B., Binu, K., Pai, R., Rao, D. & Pai, R. S. Effect of nanoparticles additives on the performance of an externally adjustable fluid film bearing. *Tribol. Int.* **45**, 38–42. <https://doi.org/10.1016/j.triboint.2011.10.004> (2012).
10. Kao, M. J. & Lin, C. R. Evaluating the role of spherical titanium oxide nanoparticles in reducing friction between two pieces of cast iron. *J. Alloys Compd.* **483**, 456–459. <https://doi.org/10.1016/j.jallcom.2008.07.223> (2009).
11. Arumugam, S. & Sriram, G. Preliminary study of nano and micro scale TiO<sub>2</sub> additives on tribological behavior of chemically modified rapeseed oil. *Tribol. Trans.* **56**, 797–805. <https://doi.org/10.1080/10402004.2013.792977> (2013).
12. Wang, Y., Lei, T., Guo, L. & Jiang, B. Fretting wear behaviour of microarcoxidation coatings formed on titanium alloy against steel in unlubrication and oil lubrication. *Appl. Surf. Sci.* **252**(23), 8113–8120. <https://doi.org/10.1016/j.apsusc.2005.10.032> (2006).
13. Ingolea, S. *et al.* Tribological behavior of nano TiO<sub>2</sub> as an additive in base oil. *Wear* **301**, 776–785. <https://doi.org/10.1016/j.wear.2013.01.037> (2013).
14. Gupta, G. *et al.* Rheological and tribological behavior of sunflower oil: Effect of chemical modification and tungsten disulfide nanoparticles. *J. Bio Tribo Corros.* **7**, 157. <https://doi.org/10.1007/s40735-021-00593-6> (2021).
15. Raina, A. *et al.* Nanodiamond particles as secondary additive for polyalphaolefin oil lubrication of steel-aluminium contact. *Nanomaterials* **11**, 1438. <https://doi.org/10.3390/nano11061438> (2021).
16. Anand, R. *et al.* Synergism of TiO<sub>2</sub> and graphene as nano-additives in bio-based cutting fluid—An experimental investigation. *Tribol. Trans.* **64**(2), 350–366. <https://doi.org/10.1080/10402004.2020.1842953> (2021).
17. Kerni, L., Raina, A. & Ul Haq, M. I. Friction and wear performance of olive oil containing nanoparticles in boundary and mixed lubrication regimes. *Wear* <https://doi.org/10.1016/j.wear.2019.01.022> (2019).
18. Abdullah, M. I. H. C., Abdollah, M. F. B., Amiruddin, H., Tamalidin, N. & Nuri, N. R. M. The potential of hBN nanoparticles as friction modifier and antiwear additive in engine oil. *Mech. Ind.* **17**(1), 104. <https://doi.org/10.1051/meca/2015037> (2016).
19. Habibullah, M. *et al.* Effect of biolubricant on tribological characteristics of steel. *Procedia Eng.* **90**, 740–745. <https://doi.org/10.1016/j.proeng.2014.11.807> (2014).
20. Ali, M. K. A., Xianjun, H., Turkson, R. F., Peng, Z. & Chen, X. Enhancing the thermophysical properties and tribological behaviour of engine oils using nanolubricant additives. *R. Soc. Chem. Adv.* **6**, 77913–77924. <https://doi.org/10.1039/C6RA10543B> (2016).
21. Masjuki, H. H., Saifullah, M. G., Husnawan, M., Faizul, M. S. & Shaaban, M. G. Flash temperature parameter number prediction model by design of tribological experiments for basestock mineral oil containing palm olein and aminophosphate additives. Proceedings of the World Tribology Congress III, 451–452. <https://doi.org/10.1115/WTC2005-63193> (2005).
22. Ali, M. K. A. *et al.* Improving the tribological characteristics of piston ring assembly in automotive engines using Al<sub>2</sub>O<sub>3</sub> and TiO<sub>2</sub> nanomaterials as nano-lubricant additives. *Tribol. Int.* **103**, 540–554. <https://doi.org/10.1016/j.triboint.2016.08.011> (2016).
23. Yang, L., Du, K., Zhang, X. S. & Cheng, B. Preparation and stability of Al<sub>2</sub>O<sub>3</sub> nano-particle suspension of ammonia-water solution. *Appl. Therm. Eng.* **31**, 3643–3647. <https://doi.org/10.1016/j.applthermaleng.2010.11.031> (2011).
24. Molea, A., Barabas, I. & Suci, R. Influence of TiO<sub>2</sub> nano-particles content on physicochemical and tribological properties of lubricant oil. Proceeding of the 4th International Congress of Automotive and Transport Engineering (AMMA 2018), Book Series: Proceedings in Automotive Engineering, 190–196. [https://doi.org/10.1007/978-3-319-94409-8\\_23](https://doi.org/10.1007/978-3-319-94409-8_23) (2019).

## Author contributions

C.B. and M.P. conceived the experiments, M.C., A.M., F.P. and G.C. conducted the experiments, C.B., M.C. and G.C. analyzed the results, C.B. and M.P. supervised the work. All authors reviewed the manuscript.

## Competing interests

The authors declare no competing interests.

## Additional information

**Correspondence** and requests for materials should be addressed to M.P.

**Reprints and permissions information** is available at [www.nature.com/reprints](http://www.nature.com/reprints).

**Publisher's note** Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.



**Open Access** This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2022