



# Applications of Green Synthesized Metal Nanoparticles — a Review

Seerengaraj Vijayaram<sup>1</sup> · Hary Razafindralambo<sup>2,3</sup> · Yun-Zhang Sun<sup>1</sup> · Seerangaraj Vasantharaj<sup>4</sup> · Hamed Ghafarifarsani<sup>5</sup> · Seyyed Hossein Hoseinifar<sup>6</sup> · Mahdiah Raeeszadeh<sup>7</sup>

Received: 10 December 2022 / Accepted: 20 March 2023

© The Author(s), under exclusive licence to Springer Science+Business Media, LLC, part of Springer Nature 2023

## Abstract

Green nanotechnology is an emerging field of science that focuses on the production of nanoparticles by living cells through biological pathways. This topic plays an extremely imperative responsibility in various fields, including pharmaceuticals, nuclear energy, fuel and energy, electronics, and bioengineering. Biological processes by green synthesis tools are more suitable to develop nanoparticles ranging from 1 to 100 nm compared to other related methods, owing to their safety, eco-friendliness, non-toxicity, and cost-effectiveness. In particular, the metal nanoparticles are synthesized by top-down and bottom-up approaches through various techniques like physical, chemical, and biological methods. Their characterization is very vital and the confirmation of nanoparticle traits is done by various instrumentation analyses such as UV–Vis spectrophotometry (UV–Vis), Fourier transform infrared spectroscopy (FT-IR), scanning electron microscope (SEM), transmission electron microscopy (TEM), X-ray diffraction (XRD), atomic force microscopy (AFM), annular dark-field imaging (HAADF), and intracranial pressure (ICP). In this review, we provide especially information on green synthesized metal nanoparticles, which are helpful to improve biomedical and environmental applications. In particular, the methods and conditions of plant-based synthesis, characterization techniques, and applications of green silver, gold, iron, selenium, and copper nanoparticles are overviewed.

**Keywords** Plants · Metal/metal oxide nanoparticles · Antimicrobial · Anticancer · Dye degradation · Wastewater treatment

## Introduction

Green synthesis of nanoparticles using living cells through biological pathways is more efficient techniques and yields a higher mass when compared to other related methods. Plants are the sources of several components and biochemicals that can role as stabilizing and reducing agents to synthesize green nanoparticles. The green synthesized methods are eco-friendly, non-toxic, cost-effective, and also more stable when compared to other biological, physical, and chemical methods [1]. Green synthesis of nanoparticles is categorized into three groups, viz. extracellular, intracellular, and phytochemicals. The nanoparticle synthesis from plant extract is an inexpensive process and it results in higher yield due to the huge quantity of phytochemical components in the plant extract that can also act as reducing and stabilizing agents converting metal ions into metal nanoparticles [2]. Green synthesized metal and metal oxide nanoparticles have emerging applications in the biomedical sector like diagnostics, wound healing, tissue treatment, immunotherapy, regenerative medicine, dentistry, and biosensing

✉ Yun-Zhang Sun  
jmusunyunzhang@163.com

✉ Hamed Ghafarifarsani  
hamed\_ghafari@alumni.ut.ac.ir

<sup>1</sup> Fisheries College, Jimei University, Xiamen 361021, China

<sup>2</sup> ProBioLab, Teaching and Research Centre, Gembloux Agro-Bio Tech, University of Liege, Liège, Belgium

<sup>3</sup> BioEcoAgro Joint Research Unit, TERRA Teaching and Research Centre, Microbial Processes and Interactions, Gembloux AgroBio Tech/Université de Liège, Gembloux, Belgium, University of Liege, Liège, Belgium

<sup>4</sup> Department of Biotechnology, Hindusthan College of Arts and Science, Coimbatore 641028, Tamil Nadu, India

<sup>5</sup> Department of Fisheries, Faculty of Natural Resources, Urmia University, Urmia, Iran

<sup>6</sup> Department of Fisheries, Faculty of Fisheries and Environmental Sciences, Gorgan University of Agricultural Sciences and Natural Resources, Gorgan, Iran

<sup>7</sup> Department of Basic Sciences, Sanandaj Branch, Islamic Azad University, Sanandaj, Iran

platforms. Biototoxicology and its antimicrobial, antifungal, and antiviral characteristics were passionately contested [3]. Plant-mediated copper oxide nanoparticles synthesized from various plant extracts play a various role like diverse biological activities, environmental remediation, photocatalysis, catalytic reduction, sensing, energy storage, and several organic transformations such as coupling, reduction, and multicomponent reactions [4]. Green synthesized selenium nanoparticles are helpful to improve the activity in antioxidant, catalysis, anticancer, photocopyers, xerography, rectifiers, and solar cells [5]. Green synthesized cerium oxide nanoparticles have potential photocatalytic dye degradation, antioxidant activity, antidiabetic, anticancer antibacterial, and antifungal activity properties [6]. Green synthesized stannic oxide nanoparticles have potential photocatalytic, antioxidant, and antibacterial activity, and these nanoparticles are helpful to enhance the environment and human health applications [7]. Green synthesized silver chloride nanoparticles are used to develop environmental and biomedical applications [8]. Green synthesized metal nanoparticles are produced from different parts of the plants and also these methods are eco-friendly, non-toxic, and cost-effective method. Green synthesized nanoparticles have more active performance to remove dyes, antibiotics, and metal ions compared to other physical and chemical methods [9]. Green synthesis method is the best method for the preparation of nanoparticles, and these methods are helpful to reduce the toxicity, increase the stability, eco-friendly, and cost-effective methods. Green synthesis methods have more beneficial response in environmental and biomedical applications [10]. Plants contain many types of phytochemical compounds like phenolics, terpenoids, polysaccharides, and flavonoids that possess oxidation–reduction capabilities. Thus, they are preferably utilized for the green synthesis of nanoparticles [11]. Phytochemical compound synthesis of nanoparticles is not a general procedure as essential knowledge of the exact phytochemical components is needed for the synthesis of stabilized nanoparticles [12]. It is a general point of view that plants' secondary metabolites (polyphenols) are the mainly significant elements playing a very important function in the progression of the green synthesis of nanoparticles. The green synthesis practice is more advanced, safe and cost-effective, easily reproduce, and stable [13]. There are some positive impacts on the plant-based green synthesis of nanoparticles when compared to the other related biological methods using bacteria, fungi, actinomycetes, and algae [14]. Diverse plant parts (roots, stem, leaf, seed, and fruit) are concerned with such synthesized green nanoparticles because of the presence of notable phytochemicals [15]. Plant-synthesized nanoparticles in dissimilar parts of plants involve washing the particular part with tap or distilled water followed by squeezing, filtering, and adding particular salt solutions. Then, metallic salt was added and nanoparticles

are extracted. A variety of metallic nanoparticles are synthesized by this method. The green nanoparticles are used in personal care, medicine, nano-enabled devices, food, aquaculture sciences, and agricultural products. Green synthesis of nanoparticles is eco-friendly; this method is generally used for the industrial production of metal nanoparticles. Green synthesized metal nanoparticles are produced from physicochemical methods [16]. A biosynthesis approach is a vital mechanism to avoid harmful by-products via eco-friendly and sustainable development. The biosynthesis process is involved in several biological structures, namely plant extracts, bacteria, yeast, seaweeds, and algae to produce metal and metal oxide nanoparticles [17]. Sharma et al. (2015) reported the green synthesis, characterization, and application of a variety of metal nanoparticles, which can eliminate pollutant dyes from water such as azo dyes, acid dyes, and cationic dyes. The metallic nanoparticles are used to remove water pollutants from water bodies such as rivers, lakes, and other water streams, thereby enhancing aquatic life. Green synthesized nanoparticles can be applied to treat environmental pollutants. Earlier studies report that the catalytic characteristics of some nanoparticles can reduce the toxicity of environmental pollutants [18, 19]. Green synthesis processes to metal nanoparticles are eco-friendly, non-toxic, and cost-effective. Also, these methods are playing a very significant role in the pharmaceutical industry [20]. The broad application of metallic nanoparticles utilized in various fields like biology, medicine, pharma, and other fields has led to high demand for these nanoparticles and thereby resulting in a significant need for better production of such nanoparticles. The efficiency of metallic nanoparticles used against human pathogenic microbes has made nanoparticles attractive in biomedical fields [21]. Particularly, metal nanoparticles have elevated outside the region and more attractive sites to support quicker response which enhances production yields. These metallic nanoparticles are generally divided into two groups, namely noble and non-noble metallic groups based on nanoparticle types. The metallic nanoparticles are inexpensive, eco-friendly, non-toxic, and reduce the accumulation of hazardous wastes. Green syntheses of metallic nanoparticles are safer for biomedical and environmental applications [22, 23]. A notable perspective of different metal nanoparticles is to be used as antimicrobial medicine (antiviral, antibacterial, fungicidal, antiparasitic, and pesticide agents, etc.) alongside some plant diseases [24]. A cancer nanobullet is significant in treating cancer because it is very effective and safe. The use of cancer nanodrugs considerably increased drug delivery to the target when compared to the conventional drug administration system. It notably improves the safety and competence of the regularly utilized anticancer drugs. Effective targeting, delayed release, long-lasting half-life, and reduced toxicity are the major positive effects of nanomedicine delivery

systems [25]. This review paper overviews the only green synthesis and characterization of metal nanoparticles, namely silver, gold, iron, selenium, and copper, and the applications of such nanoparticles are used to treat antimicrobial, anticancer, reduce metal toxicity, dye degradation, and wastewater treatment and not for other biological, chemical, and physical methods. The green synthesized different metal nanoparticles are eco-friendly, non-toxic, cost-effective, and also more stable when compared to other ones as well as these nanoparticles have more active performance compared to other methods.

## Nanoparticle Synthesis Methods


### Top-down and Bottom-up Approaches

The nanoparticles synthesized through a biological system have numerous advantages like non-toxicity, high yield production, easy scaling up, and well-defined morphology. Hence, it has to turn into an innovative way of nanoparticle production. The green synthesis technique has been established to synthesize extremely effective nanoparticles. The green synthesized nanoparticles are safe, eco-friendly, and easy to handle [26–28]. Different practices of green

synthesis of nanoparticles have been reviewed by Saratale et al. [29] and their biomedical and agricultural applications have been summarized (Saratale et al. 2018a). The synthesis of green nanoparticles is categorized into two classes, namely “top-down” and “bottom-up” based on the way of nanoparticle formation (Fig. 1). In the “top-down” approach, the dimension of nanoparticles was larger and hence a mechanical method or the additions of acids are necessary to decrease the particle size of the nanoparticles. Generally, the top-down approach requires the use of complex analysis (thermal decomposition method, mechanical method/ball-milling method, lithographic methods, laser ablation, sputtering). The “bottom-up” approach was quite different from the top-down process and was commenced at the atomic level via forming molecules. The bottom-up methods are carried out using different manners (chemical vapor deposition (CVD) method, sol–gel method, spinning, pyrolysis) [30].

### Factors Influencing the Green Synthesis of Various Nanoparticles

The green synthesis of nanoparticle morphology characterization can be adapted by different specifications such as pH, temperature, reaction time, and reactant concentration.



**Fig. 1** Summary of the top-down and bottom-up approaches to green synthesizing nanoparticles

These parameters have majorly recognized the impact of environmental factors on the synthesis of nanoparticles as well as these elements may play an imperative function during the optimization of metallic nanoparticle synthesis [31].

### Temperature

Different levels of study reports are being undertaken worldwide to learn the control of temperature over nanoparticles. Temperature is the most important factor in disturbing the dimension and form of the nanoparticles and their level of synthesis. Dissimilar types of shapes (triangle, octahedral platelets, spherical, and rod) and the dimension of the synthesis of nanoparticles can be tailored as a function of temperature. As the temperature level increases, the reaction response rate is also strengthening the formation of nucleation centers [32]. During the green synthesis of nanoparticles, the reaction time is a major factor that plays the most important function in influencing the shape, size, and yield of synthesized nanoparticles [33, 34].

### pH


The pH of response plays a significant function in the structure of nanoparticles. Namely, pH and temperature also control the formation of nucleation centers. The pH level increases mean automatically enlarged the number of nucleation centers, which is most important to boost the formation of metal nanoparticles. It has been recognized that pH takes a significant function in formulating the structural morphology and size of the nanoparticles [35]. The medium pH reaction is a major function in the formation of nanoparticles [36].

### Reaction Time

The reaction time is the most important aspect that controls the structural morphology of nanoparticles along with temperature and pH. Karade et al. [37] mentioned that reaction time plays a crucial role in the synthesis of magnetic nanoparticles [38].

## Characterization of Nanomaterials

The nanoparticle characterization can be classified according to the physical and chemical instrumentation analysis used (Fig. 2), including UV–Vis spectroscopy, Fourier transforms infrared spectroscopy (FT-IR), scanning electron microscope (SEM), X-ray diffraction (XRD), atomic force microscopy (AFM), dynamic light scattering (DLS), surface-enhanced Raman spectroscopy (SERS), atomic absorption spectroscopy (AAS), energy dispersive spectroscopy (EDS), ray photoelectron spectroscopy (XPS), and high angle annular dark-field (HAADF) [39, 40].



**Fig. 2** Summary of the various techniques characterizing metal and metal oxide nanoparticles

### FTIR

In FTIR analysis, infrared red rays are passed through the sample, some IR rays are engrossed by the sample, and the remaining rays pass through it. The spectrum provides absorption or transmission as a function of wavelength, which characterizes the sample substances [41]. FTIR analysis is a suitable, cost-effective, simple, and non-invasive practice to recognize the function of biomolecules in the decrease of nanoparticles (silver nitrate to silver) [42].

### UV–Vis Spectrophotometry

In the characterization of nanoparticles by using UV–Vis absorption spectroscopy, the nanoparticle size level is varying from several metals while the size range is 2–100 nm. Generally, the nanoparticles confirmed by UV–Vis absorption spectroscopy are analyzed with wavelengths ranging from 300 to 800 nm. The metallic nanoparticles synthesized under particular salt conditions have strong absorption to give a point spectrum in the noticeable area [43]. Previous study reports exposed that absorption of wavelength 200–800 was appropriate for the categorization of nanoparticle size range 2–100 nm [44].

### Scanning Electron Microscope (SEM)

Nanoparticles can be characterized by SEM. This instrumentation investigation is used to identify the shape, size, morphology, and distribution of synthesized nanoparticles [39, 40]. The SEM analysis assessed the alteration of a morphological structure before and after treatment. Previous studies reported that noticeable modifications in cell shape and perforations of nanoparticles in the cell wall have been used as indicators of the antimicrobial action of nanoparticles [45, 46].

## X-ray Diffraction (XRD)

Material atomic structures can be analyzed XRD. This system is helpful to identify the qualitative and quantitative levels of materials. XRD investigation was used to recognize and confirm crystalline nanoparticle size and structure [39, 40]. To analyze the particle dimension of nanomaterials from XRD data, the Debye–Scherrer formula was applied by ruling the width of the Bragg reflection law according to the equation:  $d = K\lambda/\beta \cos \theta$ , where  $d$  is the particle size (nm),  $K$  is the Scherrer constant,  $\lambda$  is the wavelength of X-ray,  $\beta$  is the full width half maximum, and  $\theta$  is the diffraction angle (half of Bragg angle) that corresponds to the lattice plane [47].

## Atomic Force Microscopy (AFM)

Atomic force microscopy (AFM) classified and confirmed the size, shape, and outside the region of synthesized nanoparticles [39, 40].

## Transmission Electron Microscopy (TEM)

Transmission electron microscopy (TEM) categorized and confirmed the crystal structure and particle size of material at the nanoscale level [39, 40].

## Annular Dark-Field Imaging (HAADF)

Annular dark-field imaging (HAADF) recognized the interaction of nanoparticles with bacteria while providing information on the size distribution of nanoparticles interacting with each type of bacteria [39, 40].

## Intracranial Pressure (ICP)

Intracranial pressure (ICP) spectrometry was confirmed by the metal concentration in deionized and original nanoparticle solutions. Experimentally, coupled plasma mass spectrometry (ICP-MS) and coupled emission spectroscopy (ICP-ES) are used to calculate the concentration of metal nanoparticles [39, 40].

## Green Synthesis of Metal Nanoparticles and Their Applications

Researchers affirmed that biologically synthesized nanoparticles are more pharmacological active compared to other physicochemical methods. Plant extract synthesized metallic nanoparticles are stable and monodispersed easily by controlling different influencing factors such as pH,


temperature, retention time, and mixing ratio. Green metal nanoparticles synthesized by different plants such as neem leaves (*Azadirachta indica*), tulsi leaves (*Ocimum tenuiflorum*), curry leaves (*Murraya koenigii*), guava leaves (*Psidium guajava*), and mango leaves (*Mangifera indica*) [48]. The metallic nanoparticles green synthesized using diverse medicinal plants have shown the most important therapeutic properties, namely antimicrobial activity, insecticidal activity, antioxidant activity, wound healing properties, antidiabetic activity, immunomodulatory activity, hepatoprotective activity, and anticancer activity (Fig. 3). The medicinal plant-based synthesized metallic nanoparticles have a huge beneficiary effect in the sector of biomedicine [49]. The major significant concept of using green nanotechnology in agriculture reduced harmful environmental effects and the high expenditure of fertilizers, while green nanoparticles (GNPs) synthesized from dissimilar plants reduced the harmful emission of carbon dioxide, nitrous oxide, and methane. Also, green nanoparticles are used to increase productivity in agriculture and lower health risks concerned agricultural farmers [50]. Naturally, plants contain numerous phytochemical components (Table 1). These factors are eco-friendly and inexpensive. Green synthesized nanoparticles are exposed to the significant importance of heavy metal detoxification from the environment. In view of the number of heavy metals polluting soil and water, green nanoparticles are helpful to reduce metal toxicity in the environment [51]. As the different parts of plants roots, stem, leaf, seed, and fruit contain many phytochemical substances, the green synthesis metallic nanoparticles approach is cost-effective, non-toxic, and eco-friendly and is more efficient compared to other biological methods [14]. For the synthesis of green nanoparticles, it is important for selected plant parts to be washed with tap or distilled water, after squeezing, filtering, and adding particular salt solutions. The color modification of the solution confirms the synthesized nanoparticles. Phytochemical components (phenolic acids: ellagic acid, caffeic acid, protocatechuic acid, and gallic acid) play an important role in the synthesis of metal nanoparticles. The phytochemical factors are reducing and stabilizing agents of synthesized metal nanoparticles [52].

## Green Synthesis of Silver (Ag) Nanoparticle and Its Applications

Different kinds of plant parts like root, stem, latex, leaf, and seed are utilized for the synthesis of metal nanoparticles. Earlier studies have reported that silver nanoparticles are synthesized by plant extract [23, 54, 168, 169]. López-Miranda et al. [170] pointed out that plant synthesized silver nanoparticle by plant extract French tamarisk (*Tamarix gallica*). Chinnappan et al. [171] described that



**Fig. 3** Green synthesis of metal and metal oxide nanoparticles and their applications



butterfly tree (*Bauhinia purpurea*) flower extract synthesized silver nanoparticles as a simple and cost-effective method. Lakshmanan et al. [172] pointed out that plant extract of Asian spider flower (*Cleome viscosa*) synthesized silver nanoparticles. This has an enhanced ability to reduce silver nitrate into metallic silver. Similarly, plant oregano (*Origanum vulgare* L.) synthesized silver nanoparticles in an aqueous solution. The synthesis of the nanoparticle is based on the reduction of  $\text{Ag}^+$  ions and also color changes (light brown to dark brown) of the nanoparticle solution [173]. The methanolic leaf extract of a five-leaved chaste tree (*Vitex negundo*) is synthesized by spherical shape silver nanoparticles; this nanoparticle has a broad-spectrum antibacterial response [174]. Rodriguez-Luis et al. [175] pointed out that licorice (*Glycyrrhiza glabra*) root extract and cuachalalate (*Amphipterygium adstringens*) bark extract synthesized by the spherical shape of silver nanoparticles in the size range 3–9 nm (TEM). Ibrahim [176] mentioned that banana (*Musa paradisiaca* Linn.) peel extract synthesized by spherical and crystalline silver nanoparticles in the size range of 23.7 nm, and showed that the same material was a better capping and reducing agent by characterizing nanoparticles with various instrumentation techniques such as TEM, SEM, FE-SEM, DLS, and SAED.

Silver nanoparticles are broadly explored in the structure range 1–100 nm. Primarily, the silver nanoparticle is the alternative way to improve biomedical applications such as drug delivery, wound healing action, tissue scaffolding, and protective coating applications. In addition, nanosilver has a notable accessible surface area that allows the binding of any ligands. Silver nitrate is commonly used in the form of antimicrobial activity. A silver nanoparticle is a unique and emerging field against harmful microbes [177]. A such nanoparticle is of significant importance in its physical,

chemical, and biological properties. Silver nanoparticles are considerably more positive effects such as broad-spectrum antimicrobial response, non-toxic, anticancer properties, and other therapeutic purposes, and also capable to form unique, diverse nanostructures and low-cost production [178–180]. Several researchers reported that silver nanoparticles are strong antibacterial effects against *E. coli*, *S. aureus*, *S. typhus*, *P. aeruginosa*, *V. cholera*, and *B. subtilis* [40, 181, 182]. A silver nanoparticle is used to break down the cell wall of organisms and interrupt the whole synthesis process [183, 184]. Martinez et al. (2018) examined that silver nanoparticles are good bactericidal properties depending on the size and shape of the nanoparticle, the size range of the nanoparticle decreasing and increasing the antibacterial response. The silver nanoparticle has different shapes like spherical, rod-shaped, and truncated triangular. The truncated triangular shape of the silver nanoparticle has strong antibacterial effects against *E. coli*. Truncated triangular silver nanoplates have a high contact area and surface reaction [185, 186]. Green synthesis of silver nanoparticle structure and dimension also plays a most important role in catalyzing various types of dyes and photocatalytic degradation [134] and in the wastewater treatment process [187]. Green synthesized and characterization of silver nanoparticles used to treat antibacterial, antifungal, antimycobacterial, and antimalarial activity against *Pseudomonas aeruginosa* MTCC-1688, *Streptococcus pyogenes* MTCC-442, *Staphylococcus aureus* MTCC-96, *Escherichia coli* MTCC-44, *Candida albicans* MTCC 227, *Aspergillus niger* MTCC 282, *Aspergillus clavatus* MTCC 1323, *Mycobacterium tuberculosis* H 37 RV, and *Plasmodium falciparum* [188]. Green synthesized (*Leucaena leucocephala*) silver nanoparticles have potential antibacterial, antimycobacterial, and antimalarial activity against *Streptococcus pyogenes*,

**Table 1** List of green synthesized metal nanoparticles and their response

Plants (scientific name)	Plants (common name)	Source of the plant (leaf, stem, root, flower, fruit)	Metal salts or powder	Phytochemical components	Applications	References
<i>Vitex negundo</i>	Five-leaved chaste tree	Leaf extract	Silver	Alkaloids, glycosides, flavonoids, phenolic compounds, reducing sugars, resin, tannins	Broad spectrum antibacterial response	[53]
<i>Musa paradisiaca</i> Linn	Banana	Peel extract	Silver	Alkaloids, glycosides, steroids, saponins, tannins, flavanoids, and terpenoids	Antibacterial response	[54]
<i>Carica papaya</i>	Pawpaw	Leaf extract	Silver	Alkaloids, saponin, tannin, flavonoids, anthraquinone (free and bound), phlobatannin, cardiac glycosides, terpenoids, and proanthocyanidin	Antiviral activity	[55, 56]
<i>Andrographis paniculata</i>	Bitter weed	Leaf extract	Silver	Diterpenoids, flavonoids, and polyphenols	Antiviral activity	[57, 58]
<i>Piper nigrum</i>	Black pepper	Leaf extract	Silver	Palmitic, hexadecenoic, stearic, linoleic, oleic, higher saturated acids, arachidic, and behenic acids	Anticancer activity	[59, 60]
<i>Viburnum opulus</i>	European cranberry	Fruit extract	Silver	Polyphenol anthocyanins	Antiinflammatory activity	[61]
<i>Moringa oleifera</i>	Drumstick tree	Leaf extract	Silver	Phenols, B-sitosterol, caffeoylquinic acid, quercet in, kaempferol	Antibacterial response	[62, 63]
<i>Ficus benghalensis</i>	Banyan	Leaf extract	Silver	Flavonoids, phenols, terpenoids, and terpenes	Antimicrobial response	[64, 65]
<i>Syzygium cumini</i>	Java plum	Seed extract	Silver	Gallic acid, P-coumaric acid, quercet in, 3,4-dihydroxybenzoic acid	Antifungal activity	[66, 67]
<i>Panax ginseng</i>	Korean ginseng	Leaf extract	Silver	Ginsenosides, polysaccharides, alkaloids, glucosides, and phenolic acids	Anticancer activity	[68, 69]
<i>Artemisia vulgaris</i>	Mugwort	Leaf extract	Silver	Sabinene, B-thujone, chrysanthemone, camphor, borneol, and germacrene D	Antibacterial, antifertility, antimalarial, antitumor	[70, 71]
<i>Andrographis echinoides</i>	False waterwillow	Leaf extract	Silver	Two new 2'-oxygenated flavonoids and two new phenyl glycosides	Antibacterial activity	[72, 73]
<i>Coffea arabica</i>	Arabian coffee	Seed extract	Silver	Caffeic, P-coumaric, vanillic, ferulic, and protocatechuic acids	Antibacterial activity	[74, 75]
<i>Alcea rosea</i>	Hollyhock	Flower extract	Silver	Ferulic acid, caffeic acid, triclin, luteolin-3',4'-dimethyl ether	Antibacterial activity	[76, 77]
<i>Centella asiatica</i>	Gotu kola	Leaf extract	Silver	Isoprenoids and phenylpropanoid derivatives	Antimicrobial activity	[78, 79]
<i>Achillea biebersteinii</i>	Yellow milfoil	Flower extract	Silver	Flavonoids, phenolic acids, coumarins, terpenoids, and sterols	Anticancer activity	[80, 81]

Table 1 (continued)

Plants (scientific name)	Plants (common name)	Source of the plant (leaf, stem, root, flower, fruit)	Metal salts or powder	Phytochemical components	Applications	References
<i>Ocimum sanctum</i> and <i>Azadirachta indica</i>	Tulasi and Indian lilac	Leaf extract	Silver	Oleanolic acid, rosmarinic acid, ursolic acid eugenol, linalool, carvacrol, $\beta$ elemene, $\beta$ caryophyllene, germacrene and nimbolid, azarirachtin, and gedunin	Antiplasmodium activity	[82]
<i>Anethum graveolens</i>	Dill	Leaf extract	Silver	Anethine, phellandrene, and d-limonene, and its leaves are rich in tannins, steroids, terpenoids, and flavonoids	Antiparasitic activity	[83]
<i>Nigella arvensis</i>	Wild fennel flower	Leaf extract	Gold	Arachidonic, eicosadienoic, linoleic, and linolenic), campestrol, stigmasterol, B-sitosterol, A-spinasterol, (+)-limonene, and (+)-citronellol	Antioxidant, antibacterial, anticancer activity	[84, 85]
<i>Punica granatum</i>	Pomegranate	Fruit extract	Gold	Phenolic acids, hydrolysable tannins, and flavonoids	Antibacterial activity	[86, 87]
<i>Mentha piperita</i>	Peppermint	Leaf extract	Gold	Diterpenes, steroids, tannin, flavonoids, cardial glycosides, alkaloids, phenols, coumarin, and saponin	Antibacterial activity	[88, 89]
<i>Anacardium occidentale</i>	Cashew nut	Leaf extract	Gold	Phenols, alkaloids, anthraquinones, flavonoids, glycosides, tannins, glycoside, terpenoids, and tannins	Antibacterial activity	[90, 91]
<i>Phyllanthus amarus</i>	Gale of the wind	Leaf extract	Gold	Flavonoids, alkaloids, terpenoids, lignans, polyphenols, tannins, coumarins, and saponins	Anticancer activity	[92, 93]
<i>Mimusops elengi</i>	Tanjong tree	Leaf extract	Gold	Tannin, some caoutchouc, wax, coloring matter, starch, and ash-forming inorganic salts	Anticancer activity	[94, 95]
<i>Allium cepa</i>	Onion	Extract	Gold	Flavonoids, carbohydrates, glycosides, proteins, alkaloids, saponins, acid compounds, reducing sugars, and oils	Anticancer activity	[96, 97]
<i>Syzygium aromaticum</i>	Clove buds	Bud extract	Gold	Sesquiterpenes, monoterpenes, hydrocarbon, and phenolic compounds	Anticancer activity	[98, 99]
<i>Linnophila rugosa</i>	Wrinkled marsh weed	Leaf extract	Gold	Phenolics, flavonoids, terpenoids, and amino acids	Catalytic activity in the reduction of different nitrophenols	[100, 101]



**Table 1** (continued)

Plants (scientific name)	Plants (common name)	Source of the plant (leaf, stem, root, flower, fruit)	Metal salts or powder	Phytochemical components	Applications	References
<i>Lantana camara</i>	Lantana	Leaf extract	Gold	Flavonoids, carbohydrates, proteins, alkaloids, glycosides, saponins, steroids, triterpenes, and tannin	Antibacterial activity and dye degradation	[102, 103]
<i>Phragmites australis</i>	Common reed	Leaf extract	Gold	Tannin, terpenoids, glycosides, and flavonoids	Anticancer activity	[104, 105]
<i>Sageretia theezans</i>	Mock buckthorn	Leaf extract	Gold	Friedelene syringic acid, bet a-sitosterol, daucosterol, gluco-syringic acid, and taraxerol	Antibacterial activity and antioxidant activity	[106, 107]
<i>Syzygium jambos</i> (L.) Alston	Rose apple	Leaf extract	Iron	Flavonoids, ellagitannins, phloroglucinols, and phenolic acids	Removal of chromium metal from environment	[108, 109]
<i>Cupressus sempervirens</i>	Mediterranean cypress	Leaf extract	Iron	Cosmosiin, caffeic acid, and P-coumaric acid cupressuflavone, amentoflavone, rutin, quercitrin, quercet in, myricitrin	Wastewater treatment	[110, 111]
<i>Camellia sinensis</i>	Tea plant	Leaf extract	Iron	Epigallocatechingallate (EGCG) ranged from 117 to 442 mg/L, epicatechin 3-gallate (EGC) from 203 to 471 mg/L, epigallocatechin (ECG) from 16.9 to 150 mg/L, epicatechin (EC) from 25 to 81 mg/L and catechin (C) from 9.03 to 115 mg/L	Reduction of bromophenol blue indicator	[112, 113]
<i>Eucalyptus globules</i>	Gum trees	Leaf extract	Iron	Saponins, tannins, phenols, and glycosides	Wastewater treatment	[114, 115]
<i>Albizia adianthifolia</i>	Flat-crown	Leaf extract	Iron	Apocarotenoids, chalcone, dipeptide, elliptosides, essential oils, fatty acids, flavonoids, histamine, imidazolyl carboxylic acid, prosapogenins, steroids, triterpene saponins, and triterpenoids	Anticancer activity	[116, 117]
<i>Psoralea corylifolia</i>	Babchi	Leaf extract	Iron	Coumarins, flavonoids, and meroterpenes	Antitumor activity	[118, 119]
<i>Camellia sinensis</i>	Green tea	Leaf extract	Iron	Alkaloids, flavonoids, steroids, terpenoids, carotenoids, benzoic acid, ascorbic acid, tocopherols, folic acid, and tannins consisting of catechin (flavonol), and gallic acids	Dye degradation	[120, 121]
<i>Sageretia thea</i>	Mock buckthorn	Leaf extract	Iron	Alkaloids, flavonoids, steroids, terpenoids	Antibacterial activity	[122]

Table 1 (continued)

Plants (scientific name)	Plants (common name)	Source of the plant (leaf, stem, root, flower, fruit)	Metal salts or powder	Phytochemical components	Applications	References
<i>Albizia adianthifolia</i>	Flat-crown	Leaf extract	Iron	Apocarotenoids, chalcone, dipeptide, ellipstosides, essential oils, fatty acids, flavonoids, histamine, imidazolyl carboxylic acid, prosapogenins, steroids, triterpene saponins, and triterpenoids	Anticancer activity	[123, 124]
<i>Dodonaea viscosa</i>	Hop bush	Leaf extract	Iron	Flavonoids such as tannins, santonin, pendlet on, saponins, and pinocembrin	Antibacterial activity	[125, 126]
<i>Eucalyptus</i>	Gum trees	Leaf extract	Iron	Quinones, saponins, carbohydrates, tannins, phenols, flavonoids	Wastewater treatment	[127, 128]
<i>Allium sativum</i>	Garlic	Bud extract	Selenium	Alkaloid, saponins, flavonoids, glycoside, anthraquinones, tannin, and terpenoids	Antioxidant activity	[129, 130]
<i>Pelargonium zonale</i>	Horseshoe geranium	Leaf extract	Selenium	Linalool, citronellol and geraniol, and their esters, menthone, nerol, isomenthone, rose oxides, terpinol, pinene, and myrcene	Antibacterial and antifungal activity	[32, 131]
<i>Diospyros montana</i>	Bombay ebony	Leaf extract	Selenium	Alkaloids, flavonoids, tannin, terpenoids, and essential oils	Antibacterial, antioxidant and anticancer activity	[132, 133]
<i>Allium sativum</i>	Garlic	Bud extract	Selenium	Alkaloid, saponins, flavonoids, glycoside, anthraquinones, tannin, and terpenoids	Anticancer activity	[134, 135]
<i>Aloe vera</i>	True Aloe	Leaf extract	Selenium	Flavonoids, steroids, terpenoids, proteins, phenols, carbohydrates, reducing sugar, starch, tannins, glycosides	Antimicrobial activity	[136, 137]
<i>Asteriscus graveolens</i>	Graveolens	Leaf extract	Selenium	Phenolic compounds and flavonoids	Anticancer activity	[138, 139]
<i>Clausena dentate</i>	Dentate clausena	Leaf extract	Selenium	Coumarins, carbazole alkaloid, and sesquiterpenes	Larvicidal activity	[140, 141]
<i>Psidium guajava</i>	Common guava	Leaf extract	Selenium	Quercet in, avicularin, apigenin, guaijaverin, kaempferol, hyperin, myricet in, gallic acid, catechin, epicatechin, chlorogenic acid, epigallocatechin gallate, and caffeic acid	Antibacterial and anticancer activity	[142, 143]
<i>Spermacoce hispada</i>	Shaggy button weed	Leaf extract	Selenium	B-sitosterol, ursolic acid, quercet in, dalspinin, rutin, kaempferol, tannic acid, and epigallocatechin	Antibacterial, antioxidant, anti-inflammatory, and anticancer activity	[58, 144]
<i>Theobroma cacao</i>	Cocoa	Seed extract	Selenium	Procyanidins, theobromine, (-)-epicatechin, catechins, and caffeine	Antibacterial activity	[145, 146]

**Table 1** (continued)

Plants (scientific name)	Plants (common name)	Source of the plant (leaf, stem, root, flower, fruit)	Metal salts or powder	Phytochemical components	Applications	References
<i>Syzygium aromaticum</i>	Clove	Bud extract	Copper	Sesquiterpenes, monoterpenes, hydrocarbon, and phenolic compounds	Antimicrobial and antioxidant	[147, 148]
<i>Magnolia kobus</i>	Kobus magnolia	Leaf extract	Copper	Flavonoids, phenols, citric acid, ascorbic acid, polyphenolic, terpenes, alkaloids, and reductase	Antibacterial activity	[149]
<i>Hibiscus rosa-sinensis</i>	China-rose	Leaf extract	Copper	Proteins, vitamin C, organic acids (essentially malic acid), flavonoids, anthocyanins	Antibacterial activity	[150, 151]
<i>Duranta erecta</i>	Golden dewdrop	Fruit extract	Copper	Flavonoids, phenols, saponins, sterols, tannins, alkaloids	Water treatment process	[152, 153]
<i>Gnidia glauca</i>	Fish poison bush	Leaf extract	Copper	Alkaloids, saponin, steroids, tannin, coumarin, flavonoids, diterpenes, cardial glycosides, phenols, and phytosterol	Antidiabetic	[154, 155]
<i>Citrus medica</i> Linn	Citron	Fruit extract	Copper	Iso-limonene, citral, limonene, phenolics, flavonones, vitamin C, pectin, linalool, decanal, and nonanal	Antibacterial activity	[156, 157]
<i>Euphorbia nivulia</i>	Dog's tongue	Leaf extract	Copper	Glycosides, alkaloids, saponins, flavonoids, phenols, tannins, carbohydrates	Antibacterial activity and antioxidant	[158, 159]
<i>Capparis zeylanica</i>	Ceylon caper	Leaf extract	Copper	Fatty acids, flavonoids, tannins, alkaloids, E-octadec-7-en-5-ynoic acid, saponins glycosides, terpenoids, saponin, P-hydroxybenzoic, syringic, vanillic, ferulic, and P-coumaric acid	Antibacterial activity and antioxidant	[160, 161]
<i>Arevalanata leaves</i>	Mountain knot grass	Leaf extract	Copper	Phenol and alkaloids	Antimicrobial and catalytic properties	[162, 163]
<i>Tinosporia cardifolia</i>	Guduchi	Leaf extract	Copper	Tinosponone, tinosporin, berberine, palmitine, choline, tembet arine, isocolumbin and tetrahydro-palmatine and other alkaloids, steroids, lactones, glycosides, and sesquiterpenoids	Antimicrobial activity	[164, 165]
<i>Calotropis procera</i>	Calotrope	Leaf extract	Copper	Cardenolides, flavonoids, and saponins	Antitumor activity	[166, 167]

*Pseudomonas aeruginosa*, *Bacillus subtilis*, *Staphylococcus aureus*, *Escherichia coli*, *Salmonella typhi*, *Mycobacterium tuberculosis*, and *Plasmodium falciparum* [189].

The silver nanoparticle is considered to be a successful and novel pharmacological agent that regulates efficient antiviral activity against *Influenza virus*, *Human parainfluenza virus type 3*, *Chikungunya virus*, *Herpes simplex virus*, *Norovirus*, *bovine Herpes virus*, *Dengue virus*, *Adenovirus*, *feline coronavirus* (FCoV), and HIV [55, 190–199]. The silver nanoparticle was used to suppress antiviral effects in a dose-dependent manner by in vitro methods. It also showed that at 9.3 g/mL (EC50 concentration) for 2-h incubation time, the silver nanoparticle can only affect virally infected cells, and not toxic to uninfected cells [197]. Likewise, silver nanoparticles have decreased the transmission of viruses in personal protection instruments. Graphene-silver nanocomposite was inhibited against feline coronavirus infection  $4.7 \times 10^4$  TCID50 (tissue culture infective dose required to kill 50% of the infected host) at a lower concentration (0.1 mg/mL) of nanoparticle [198]. The red flush flower (*Lampranthus coccineus*) extract synthesis of silver nanoparticles has significant antiviral activity against *Coxsackievirus* infection at a lower concentration (12.74 µg/mL). In addition, a molecular docking report pointed out that green synthesized silver nanoparticle was an active binding *Coxsackievirus 3c* protease against antiviral infection [200]. Kaushik et al. [201] showed that a plant pawpaw (*Carica papaya*) leaf extract synthesized silver nanoparticles (125 µg/mL and 62.5 µg/mL) performed as the antiviral factor against *chikungunya* infection using Vero cells. A lower-level concentration of silver nanoparticles (62.5 µg/mL) was inhibited by 52% against the *chikungunya virus*. Sharma et al. [202] reported that bitterweed (*Andrographis paniculata*) leaf extract synthesized silver nanoparticle has significant antiviral activity against *chikungunya* viral infection. Maximum non-toxic dose concentration 31.25 µg/mL (MNTD) and 15.63 µg/mL (½MNTD) showed that level of inhibition (75–100% and 25–49%) was a cytopathogenic response, respectively.

Cancer is one of the mainly dangerous diseases in the world. The several side effects performed in classical cancer therapy and their poor tolerance performance became the purpose for an enormous level of search for novel drugs of natural origin that are capable to regulate the disease's progress and heal it. The silver nanoparticle is a wide noteworthy factor for cancer analysis. The silver nanoparticles were stimulated to activate the p53 tumor suppressor. In addition, silver nanoparticles are performed to treat higher toxic response against cancer cells compared to non-cancer fibroblasts [203]. The plant catmint (*Nepeta deflersiana*) synthesized silver nanoparticle provoked apoptosis and cell death through cell necrosis HeLa stops the sub G1 cell cycle [61]. Jacob et al. [204] examined that pepper black pepper

(*P. nigrum*) leaf extract synthesized silver nanoparticle has induced cytotoxic activity against cancer cells. The Indian gooseberry (*Phyllanthus emblica*) leaf extract synthesized silver nanoparticle has significant anticancer properties against *Hepatocellular carcinoma* (HCC) [205]. The two different size variations of silver nanoparticles demonstrated anticancer activity against MCF-7 and T-47D cells. The silver nanoparticle induced endoplasmic reticulum stress (EPR) through unfolded protein, and also increased the activation of caspase 9 and caspase 7, causing cell death [206]. The silver nanoparticles are recognized with an antiinflammatory reaction via playing a role in the wound healing progression, due to interleukin 1 and TNF-α interferons and also suppression of COX-2 and MMP-3 expressions. The silver nanoparticle has significantly reduced the function of TNF-α during the inflammatory process [207–210]. The black pepper (*Piper nigrum*) leaf extract synthesized silver nanoparticle has a selected cytokine inhibitory factor for IL-1 and IL-6 [211]. European cranberry (*Viburnum opulus*) bush fruit extracts synthesizing Ag nanoparticle was noted to show an antiinflammatory response by in vitro and in vivo methods, the Ag nanoparticles being used to enhance the potential therapeutic analysis for the treatment of inflammation [182]. Ag nanoparticle is an efficient tool for numerous biomedical applications such as antimicrobial, antifungal, antiviral, catalysis, wound healing and dressing, implanted materials, tissue engineering, anticancer therapy, and medical devices (catheters, prostheses, vascular grafts). In addition, an Ag nanoparticle is used in some diagnostic processes like anti-permeability factors, bio-sensing, and dental preparations [212].

### Green Synthesis of Gold (Au) Nanoparticle and Its Applications

Green synthesized Au nanoparticles are in natural form. They also have chemical and thermal functionality. Gold-based nanoparticles can join photosensitizers for photodynamic antimicrobial chemotherapy [118, 213]. Green synthesized gold nanoparticle was a good catalytic reaction without a capping agent and non-toxic carrier, the gold nanoparticle was used to improve the drug and gene delivery applications [214]. With these systems, the gold core provides stability to the congregation through the single layer recognition to change the surface properties like charge and hydrophobicity. In addition, a characteristic feature of gold nanoparticles was connected to thiols, as long as the efficiency of controlled intracellular release [215]. The gold nanoparticles contain different kinds of characteristics; the distinguishing features can be changed in size, shape, and aspect ratio of nanoparticles. The gold nanoparticle is non-toxic and biocompatible for drug delivery and gene therapeutic applications. The gold nanoparticle has various

aspects of the biomedical progression such as easily detecting and diagnosis heart disease, cancer, and infectious factor [216, 217].

The pummelo (*Citrus maxima*) aqueous extract solution synthesized gold nanoparticles [218]. The Indian long pepper (*Piper longum*) extract synthesized gold nanoparticle size range of 56 nm was confirmed by the DLS particle size analyzer [219]. The onion (*Allium cepa*) extract synthesized gold nanoparticles in the size range of 100 nm [220]. The wild spinach (*Chenopodium album*) leaf extract synthesized gold nanoparticle sizes ranging from 10 to 30 nm and its shape is quasi-spherical [221]. The Japanese Honeysuckle (*Lonicera Japonica*) flower extract synthesized gold nanoparticle size ranging from 8.02 nm (average diameter) [222]. The gold nanoparticle detected, diagnose, and healing of many diseases. Au nanoparticle is a very important tool for biomedical applications [223, 224]. The green synthesized gold nanoparticles are considered through various instrumentation techniques such as UV–Vis, Fourier transforms infrared (FTIR), SEM, and high-resolution transmission electron microscopy (HRTEM), and also the gold nanoparticle is mainly concerned to enhance various biomedical applications such as antibacterial, drugs delivering factor for therapeutic cancer level from chemical hazardous to biomolecules, catalysis, photonics, electronics, and sensing [84, 225–228]. The view-rakot (*Nepenthes khasiana*) leaf extract synthesized gold nanoparticles categorized by different instrumental analyses like XRD, SEM, and TEM after analysis to confirm the size range of 50–80 nm of nanoparticle [229]. The influencing factor is significantly important in the synthesis of nanoparticles; the gold nanoparticle factors range as follows: pH (6–9), temperature (20 to 80 °C), the concentration of mixture (5 to 10 mL), UV–Vis spectrum wavelength of 550 nm. These ranges are helpful to verify and synthesis gold nanoparticles [230–232].

Lysenko et al. [233] examined the synthesis of two gold nanoparticles coated with silicon dioxide shells and gold–silicon dioxide carrier nanoparticles; these gold nanoparticles reduced the toxicity of gold ions, and also both gold nanoparticles are strong antiviral effects against adenovirus. The synthesized gold nanoparticles were treated to antiviral activity against the dengue virus and were associated with the suppress action of RNA against the dengue virus. The gold nanoparticles performed to go into the infected Vero cells and reduced the response of dengue virus serotype 2 (DENV-2) replication and infectious virion release; these treatments were carried out during post- and pre-infection conditions [234]. The novel vaccine with hybrid coated gold nanoparticles and domain III of the viral envelope protein (EDIII) response antiviral activity against the dengue virus. The complex coated hybrid gold nanoparticle response differs, depending on the size and concentration [235]. The ethanolic and hydroalcoholic extract of gold nanoparticles

showed antitubercular activity, and two different types of concentrations are identified as the response such as MIC (2.5 µg/mL and 20 µg/mL) and the highest concentration level (50 µg/mL and 75 µg/mL), respectively [236]. The wild fennel flower (*Nigella arvensis*) (NA- gold nanoparticles) leaf extract synthesized gold nanoparticles looked into that different applications such as antioxidant, catalytic activities antibacterial, and cytotoxicity. The plant-mediated synthesis of gold nanoparticles improved cytotoxic activity against cancer cell lines (H1299 and MCF-7) with an IC<sub>50</sub> value of (10 and 25 µg/mL) and a catalytic reaction against methylene blue was 44%, respectively [237]. Au nanoparticles with size and shape range have some excellent characteristic features of biomedical applications such as antimicrobial and antibacterial activities, antiviral treatments, anticancer therapy, targeted drug delivery, medical imaging, molecular imaging in living cells, photothermal therapy, hyperthermic property to treat tumors, biocatalysis and biomarkers, biosensors, and intracellular analysis [238].

## Green Synthesis of Iron (Fe) Nanoparticles and Their Applications

The green synthesized zero-valent iron nanoparticles are produced from different plants such as *thyme* (*Thymus vulgaris* (TV)), Damask rose (*Rosa damascene* (RD)), and stinging nettle (*Urtica dioica* (UD)) [239]. Green synthesized iron nanoparticles from various plants such as common water-hyacinth (*Eichhornia crassipes*), lantana (*Lantana Camara*), and sensitive plants (*Mimosa pudica*). This plant synthesized iron nanoparticle standard size ranges 20–60 nm and morphological structure is irregular and aggregated quasi-spherical shape respectively [240]. However, the green synthesis of iron nanoparticles was a major process in enhancing the physical, chemical, and biological properties of nanoparticles [241, 242]. Plant extract synthesized iron nanoparticle has antioxidant capability following some procedures like 2, 2-diphenyl- 1-picryl-hydroxyl (DPPH) radical scavenging assay, Folin-Ciocalteu method, and ferric reducing antioxidant power (FRAP) [243–245]. Different phytochemical components (polyphenols, flavonoids, and amino acids) played an imperative role in the synthesis of iron nanoparticles. These phytochemical synthesized nanoparticles are efficient antioxidant activity [108, 246, 247].

The green synthesis approach in developing zero-valent iron nanoparticles was an important process for the treatment of brominated organic compounds, pesticides, azo dyes, alkaline-earth metals, malachite green, nitrate, monochlorobenzene, antibiotics, and conversion of some metals like chromium, cobalt, and copper [112, 247–255]. The aqueous solution of rose apple (*Syzygium jambos* (L.) Alston) leaf extract synthesized zerovalent iron nanoparticles eliminated to hexavalent chromium metal. Complete removal of chromium



was based upon nanoparticles dosage, temperature, and pH. The appropriate pH and concentration of nanomaterials are considerable factors in the removal of chromium metal [256]. However, the coconut husk extract synthesized magnetite iron nanoparticles absorbed a low level of calcium and cadmium [257]. The aqueous solution leaf extract at various ratios and temperatures synthesized zero-valent iron nanoparticles. The process confirmed by color changes of the nanosolution as well as phyto components was the significant agent for reducing and stabilizing factors in the synthesis of zero-valent iron nanoparticles [250, 258, 259]. Similarly, zero-valent iron nanoparticles are characterized by the following methods such as SEM, TEM, and zeta potential. The classification analysis was confirmed by the shape, size, and stability of nanoparticles. The zero-valent iron nanoparticle was helpful in the removal of lead based on time duration and concentration (low quantity of lead removal takes lesser time and low concentration higher quantity removal of lead takes high concentration and more time) [260, 261]. Nanotechnology and iron nanomaterials have different kinds of applications such as drug delivery [262, 263], electronics, biotechnology, catalysis [110, 264, 265], environmental remediation [114, 266], cosmetics, space industry, anticancer and drug delivery [116, 267, 268], and materials science. Wei et al. [220] pointed out that those citrus maxima peel extract synthesized iron nanoparticles played a major role in waste minimization and well-organized resource utilization. The most comprehensive study reports pointed out that the synthesis of iron nanoparticles was utilized for remediation of water and soil, and the zero-valent iron nanoparticles are efficient catalytic properties [269].

The Mediterranean cypress (*Cupressus sempervirens*) aqueous leaf extract synthesized iron nanoparticle was important effects to removing dye from wastewater depending on time and concentration manner. The synthesized iron nanoparticle was used to remove methyl orange (95% at 6 h) [270]. In addition, tea plant (*Camellia sinensis*) leaf extracts synthesized iron nanoparticle was utilized for the reduction of bromophenol blue pH indicator [250]. The green leaf extract synthesized iron nanoparticle was used to treat malachite green dye degradation [271]. The gum trees (*Eucalyptus globules*) leaf extract synthesized iron nanoparticles demonstrated that the marvelous reduction possible against eutrophic wastewater [272]. The tangerine (*Citrus reticulata*) peel extract synthesized iron nanoparticles utilized to remove the cadmium in the water system [273]. The green synthesis approach to developing iron nanoparticles has reduced the level of chromium depending on the concentration manner (1 mg of iron nanoparticle reduces 500 mg of chromium) [274].

Iron nanoparticles are more significant in the biomedical field. The flat-crown (*Albizia adianthifolia*) leaf extract synthesized iron nanoparticles utilized to treat MCF-7 and AMJ-13 cancer cell lines and cause apoptosis [275]. In

addition, sugar apple (*Annona squamosa*) leaf extract synthesized iron nanoparticles showed an efficient cytotoxic reaction against cancer cell line (HepG2) [274]. Similarly, Babchi (*Psoralea corylifolia*) leaf extract synthesized iron nanoparticle exhibited antitumor activity against renal carcinoma cell line (Caki-2 cells) [276]. The green synthesis approach to developing nanoparticles was of significant importance to treat human pathogens [277].

## Green Synthesis of Selenium (Se) Nanoparticle and Its Applications

Green synthesis of selenium nanoparticles is environmentally safe, cost-effective, non-toxic, and easily produced in large quantities [278, 279]. The plant-mediated synthesis of selenium nanoparticles is non-toxic and cost-effective method as well as the plant phytochemical components (polyphenols, flavones, carboxylic acids aldehydes, amides, and ketones) were a significant role in the reduction of metal ions during the synthesis of selenium nanoparticle [132, 280–286]. Different types of plant parts such as leaf extracts, fruit, seed, fruit peels, and root synthesized selenium nanoparticle in different shapes and sizes [129, 132, 287–291].

The plant-mediated synthesis of selenium nanoparticles performs to remove the heavy metal from the contaminated solution depending on the size and shape of the nanoparticles. In addition, green synthesized selenium nanoparticles carry out to remove heavy metals (zinc, copper, and nickel) from the soil, and also another study reported that selenium nanoparticles performed to remove elemental mercury from soil and air [281, 292, 293].

The selenium nanoparticle applications in different ways include as follows: (1) increasing shelf life of food; (2) antioxidant and antimicrobial response in preserved food; (3) maintenance of health and growth [283, 294–296]. The selenium nanoparticle is the most imperative food supplement as well as increased the bioavailability, controlled release of selenium in organisms. Selenium nanoparticle medicine is a major biotherapeutic agent without any side effects [297]. The selenium nanoparticle has various kinds of physiological responses in humans like antioxidant action, preventing tumor formation, and regulating the immune system [298, 299]. Vyas and Rana [300] pointed out that cultivated garlic (*Allium sativum*) bud extract synthesized selenium nanoparticles demonstrated an antioxidant response following assays FRAPS, ABTS, and DPPH. The tea extract synthesized selenium nanoparticle was established for its antioxidant activity by using different methods such as ABTS and DPPH assays [301].

The cultivated garlic (*Allium sativum*) buds extract synthesized selenium nanoparticles investigated for its antibacterial response against *Bacillus subtilis* and *Staphylococcus aureus* by using the disc diffusion method [302]. The horseshoe geranium (*Pelargonium zonale*) leaf extract synthesized selenium

nanoparticle was revealed antibacterial and antifungal activity against pathogenic bacteria, namely *Escherichia coli*, *Staphylococcus aureus*, and fungi, namely black dot of potato (*Colletotrichum coccodes*) and green mold (*Penicillium digitatum*) [136]. The bombay ebony (*Diospyros montana*) leaf extract synthesized selenium nanoparticles expressed by antibacterial activity against *Escherichia coli*, *Aspergillus niger*, and *Staphylococcus aureus*, anticancer activity in (MCF-7) concentration manner, and antioxidant activity (DPPH), respectively [291]. Selenium nanoparticle was significantly active against enterovirus. Combined with oseltamivir, the combined drugs strongly inhibited enterovirus and also reduced ROS production in astrocytoma cells [303]. The selenium nanoparticle was indicated to suppress p38 kinase, ROS production, and Jun amino-terminal kinase (JNK) signaling pathway. The selenium nanoparticles reduced the viral protein and viral yield, and control the ROS production [304, 305]. *Ulva fasciata* (UF extract) synthesized selenium nanoparticles have strong antibacterial activity against *S. aureus* and *P. aeruginosa* and also potential anticancer agents [306]. Green synthesized (*Solanum nigrum*) selenium nanoparticles have strong inhibitory action against gram-positive and gram-negative bacteria as well as antioxidant and anticancer (inhibition of breast cancer cells) efficacy posed by selenium nanoparticles [307].

Cancer nanobiotechnology is a new way to detect, diagnose, and treatment of cancer. Green synthesized selenium nanoparticle is a rapid technique in different cancer cells, namely human colon adenocarcinoma, liver cancer cells, human breast cancer cells, and Ehrlich ascites carcinoma [291]. The cultivated garlic (*Allium sativum*) bud extract synthesized selenium nanoparticles demonstrated a positive cytotoxic response against the Vero cell line [308]. The smaller size of selenium nanoparticles connected with cancer cells through the action of DNA breakage ultimately leads to cause cell death and also performs cytotoxic activity against cancer cells [309]. The green synthesized selenium nanoparticle exhibited anticancer properties in some cancer cells (human cervical carcinoma cells, liver cancer, and lung cancers) whereas a few cancer cells (ovarian cancer, leukemia cancer, colon cancer, skin cancer, prostate cancer) are still needed to be investigated [310]. The green synthesized selenium nanoparticle still needs to be investigated in the therapeutic approaches in glioma, and also the size and spherical shape of the selenium nanoparticle were a significant response to anticancer activity [311].

## Green Synthesis of Copper (Cu) Nanoparticle and Its Applications

The green synthesis technique is a significantly imperative approach for the production of nanoparticles. The process is an effective and efficient tool compared to other methods,

while being non-toxic, eco-friendly, and cost-effective. The copper nanoparticles are utilized to enhance biomedical applications such as antibacterial, antifungal, and antiviral activity [312]. Plant-mediated synthesized copper nanoparticles from various types of plants such as fire lily (*Gloriosa superba* L.), common grape (*Vitis vinifera*, *Nerium*), *Nerium* (*Nerium oleander*), Ceylon caper (*Capparis zeylanica*), and jackfruit-Champa (*Artabotrys odoratissimus*) [147, 152, 154, 313, 314]. The fire lily (*Gloriosa Superba* L) leaf extract and bark extract of pomegranate (*Punica granatum*) synthesized copper nanoparticle enhanced reducing and capping agents size range of nanoparticle 23 nm [315–317]. Different kinds of plant extract, namely Magnolia (*Nag Champa*) (*Artabotrys Odoratissimus*) and angel's trumpet (*Datura innoxia*) synthesized by copper nanoparticles in 8–10 min and size range of 4–100 nm [152]. Saranyaadevi et al. [154] showed the classification confirmation of green synthesized copper nanoparticles through the UV–Vis absorption peak 531 nm, XRD — particle size 5 nm, and TEM — size (50–100 nm).

Copper is an essential micronutrient for plants, and also 70% of total copper presence in chloroplasts as well as copper plays a significant role in the synthesis of plant pigments, chlorophyll, carbohydrate metabolism, and amino acids [150]. Copper is an important mineral for humans with dissimilar kinds of functions: strength of the skin, blood vessels, the connective tissue of the body, production of hemoglobin, myelin, and melanin, and regulation of the thyroid functions [318]. The copper nanoparticles role in many fields such as agricultural, industrial engineering, and technological fields. The green synthesis of the copper nanoparticle is a cost-effective, cheap, non-toxic, and eco-friendly method. The copper nanoparticles were confirmed to provide an efficient antibacterial response in agricultural research fields [319]. Copper nanoparticles have numerous types of properties such as mechanical, thermal, magnetic, and electrical and are also used for antimicrobial coatings for surgical tools, water treatment, and heat transfer processes [320].


Golden dewdrop (*Duranta erecta*) fruit extract synthesized copper nanoparticle reduced toxic dye (methyl orange, azo dyes, Congo red) degradation from water [321]. The fish poison bush (*Gnidia glauca*) leaf extract and Ceylon leadwort (*Plumbago zeylanica*) leaf extract synthesized copper nanoparticle's response as an antidiabetic factor [322].

The clove (*Syzygium aromaticum*) bud extract synthesized copper nanoparticles are a more effective response in antimicrobial and antioxidant function [323]. The copper nanoparticles act as a fungicide agent against different plant pathogens, namely black rot (*Alternaria alternata*), basal rot (*Fusarium oxysporum*), crown and root rot (*Rhizoctonia solani*), blue mold (*Penicillium italicum*), fruit and stem rot (*Phoma destructive*), basal rot (*Fusarium* sp.) green mold (*Penicillium digitatum*), and

black kernel (*Curvularia lunata*) [324]. Similarly, Kobus magnolia (*Magnolia kobus*) leaf extract synthesized copper nanoparticle was a significant antibacterial response against *E. coli* [325]. Green synthesized copper oxide nanoparticles have strong antibacterial and antifungal effects against *Staphylococcus aureus* (*S. aureus*), *Streptococcus pyogenes* (*S. pyogenes*), *Pseudomonas aeruginosa* (*P. aeruginosa*), and *Escherichia coli* (*E. coli*), and good antifungal performance against *Aspergillus niger* (*A. niger*), *Candida albicans* (*C. albicans*), *Aspergillus clavatus* (*A. clavatus*), and *Epidermophyton floccosum* (*E. floccosum*) [326]. Green synthesized copper nanoparticles have potential antibiofilm, antibacterial, and antioxidant activity, and these nanoparticles used as an alternative therapy for microorganisms that have been improved antibiotic resistance [327]. Green synthesized (*Sesbania aculeata* leaf extract) copper nanoparticles are helpful to increase plant growth of *Brassica nigra* at lower dose (25 and 30 mg/100 mL) and also play a good antimicrobial

agent, and these nanoparticles are helpful to enhance protection and production of plants [328].

Several studies report strongly that copper nanoparticle was a good antiviral agent [329]. The green synthesis of copper nanoparticle size about 160 nm demonstrated the antiviral activities against influenza virus of swine-origin by plate titration assay. The copper nanoparticle reduced the viral protein so these nanoparticles are utilized to produce face masks and kitchen cloths. The copper nanoparticle (40–120 µg/mL) size (39.3 nm) and spherical shape were significant cytotoxic effects against human cancer cell lines such as human skin carcinoma cells (B16F10) and normal mouse embryonic fibroblasts (NiH3T3) within 24 h [330]. The China-rose (*Hibiscus rosa-Sinensis*) leaf extract synthesized copper nanoparticles are confirmed that an effective antimicrobial response against clinical pathogens like *E. coli* and *Bacillus subtilis*, and also this element reaction is an achievement against lung cancer [53].



**Fig. 4** Mechanism of metal nanoparticles in biomedical and environmental applications

## Toxicity of Metal Nanoparticle Aspects

The toxicity of metal nanoparticles is associated with oxidative stress reactions and intracellular reactive oxygen species (ROS) production, as well as the activation of pro-inflammatory mediators. As a result of this, DNA and protein damage, lysosomal hydrolases, mitochondrial dysfunction, apoptosis, cell membrane damage, cytoplasm disorder, changes in ATP, and cell membrane permeability can be considered, which finally includes cell dysfunction. However, depending on the size, type of particles, individual particles, and mixtures, it can change the toxic effects (Fig. 4) [56].

## Conclusion

Nanoparticles are an effective tool in different fields such as food, agriculture, medicine, micro-wiring, electronics, and energy harvesting. The synthesis of nanoparticles uses physical, chemical, and biological methods. Green synthesis ways appear more effective and efficient compared to other related methods. The green synthesis method is an eco-friendly, non-toxic, and cost-effective method. In this review, we summarize especially information about various syntheses, characterization, and applications of plant-based synthesized metal and metal oxide nanoparticles are utilized to analyze antibacterial, antifungal, anti-malarial antioxidant, anticancer, photocatalytic, and metal-toxicity properties. These studies strongly recommended green synthesis approach to develop metal and metal oxide nanoparticles more beneficial response in environmental and biomedical applications. In the future, our research group focuses to synthesis different types of green nanoparticles utilize to develop the application different sectors like pharmaceutical, medical, environment, aquaculture, and agriculture. This study result enlightens the direction of future research in the green nanoparticle development in environmental and biomedical sectors.

**Author Contribution** SV did the supervision, resources, writing — original draft of the paper. HR, YZS, HG, SHH, and MR performed writing — review and editing the paper. SV did the process of investigation and conceptualization. SV wrote and prepared the original draft. SV had close supervision on the process of preparing paper, too. HR, YZS, and SHH did the project administration. All authors have read and agreed to the published version of the manuscript.

**Funding** We wish to acknowledge the National Natural Science Foundation of China (Grant No. 32072990), Xiamen Marine and Fisheries Development Fund (Grant No. 19CZP018HJ04), and Industry-University Cooperation Project of Fujian Province (Grant No. 2018N5011) for supporting this research work.

**Data Availability** The datasets generated during and/or analyzed during the current study are available from the corresponding author on reasonable request.

All applicable international, national, and/or institutional guidelines for the care and use of animals were followed.

## Declarations

**Conflict of Interest** The authors declare no competing interests.

## References

1. Mustapha T, Misni N, Ithnin NR, Daskum AM, Unyah NZ (2022) A review on plants and microorganisms mediated synthesis of silver nanoparticles, role of plants metabolites and applications. *Int J Environ Res Public Health* 19(2):674
2. Venkataraman S (2022) Plant molecular pharming and plant-derived compounds towards generation of vaccines and therapeutics against coronaviruses. *Vaccines* 10(11):1805
3. Pandit C, Roy A, Ghotekar S, Khushro A, Islam MN, Emran TB, Bradley DA (2022) Biological agents for synthesis of nanoparticles and their applications. *J King Saud Univ-Sci* 34(3):101869
4. Cuong HN, Pansambal S, Ghotekar S, Oza R, Hai NTT, Viet NM, Nguyen VH (2022) New frontiers in the plant extract mediated biosynthesis of copper oxide (CuO) nanoparticles and their potential applications: a review. *Environ Res* 203:111858
5. Korde P, Ghotekar S, Pagar T, Pansambal S, Oza R, Mane D (2020) Plant extract assisted eco-benevolent synthesis of selenium nanoparticles—a review on plant parts involved, characterization and their recent applications. *J Chem Rev* 2(3):157–168
6. Pansambal S, Oza R, Borgave S, Chauhan A, Bardapurkar P, Vyas S, Ghotekar S (2022) Bioengineered cerium oxide (CeO<sub>2</sub>) nanoparticles and their diverse applications: a review. *Appl Nanosci* 1–26
7. Matussin S, Harunsani MH, Tan AL, Khan MM (2020) Plant-extract-mediated SnO<sub>2</sub> nanoparticles: synthesis and applications. *ACS Sustain Chem Eng* 8(8):3040–3054
8. Kashid Y, Ghotekar S, Bilal M, Pansambal S, Oza R, Varma RS, Mane D (2022) Bio-inspired sustainable synthesis of silver chloride nanoparticles and their prominent applications. *J Indian Chem Soc* 100335
9. Kaur M, Gautam A, Guleria P, Singh K, Kumar V (2022) Green synthesis of metal nanoparticles and their environmental applications. *Curr Opin Environ Sci Health* 100390
10. Jeevanandam J, Kiew SF, Boakye-Ansah S, Lau SY, Barhoum A, Danquah MK, Rodrigues J (2022) Green approaches for the synthesis of metal and metal oxide nanoparticles using microbial and plant extracts. *Nanoscale* 14(7):2534–2571
11. Widatalla HA, Yassin LF, Alrasheid AA, Ahmed SAR, Widatallah MO, Eltilib SH, Mohamed AA (2022) Green synthesis of silver nanoparticles using green tea leaf extract, characterization and evaluation of antimicrobial activity. *Nanoscale Adv* 4(3):911–915
12. Ye L, Cao Z, Liu X, Cui Z, Li Z, Liang Y, Wu S (2022) Noble metal-based nanomaterials as antibacterial agents. *J Alloys Compd* 904:164091
13. Vankudoth S, Dharavath S, Veera S, Maduru N, Chada R, Chirumamilla P, ... and Taduri S (2022) Green synthesis, characterization, photoluminescence and biological studies of silver nanoparticles from the leaf extract of *Muntingia calabura*. *Biochem Biophys Res Commun* 630:143–150
14. Brar KK, Magdoui S, Othmani A, Ghaneji J, Narisetty V, Sindhu R, Pandey A (2022) Green route for recycling of low-cost waste



- resources for the biosynthesis of nanoparticles (NPs) and nanomaterials (NMs)—a review. *Environ Res* 207:112202
15. Parmar M, Sanyal M (2022) Extensive study on plant mediated green synthesis of metal nanoparticles and their application for degradation of cationic and anionic dyes. *Environ Nanotechnol, Monit Manag* 17:100624
  16. Sikiru S, Ayodele OA, Sanusi YK, Adebukola SY, Soleimani H, Yekeen N, Haslija AA (2022) A comprehensive review on nanotechnology application in wastewater treatment a case study of metal-based using green synthesis. *J Environ Chem Eng* 10:108065
  17. Liu S, Guo Y, Yi S, Yan S, Ouyang C, Deng F, ... and Li Q (2023) Facile synthesis of pure silicon zeolite-confined silver nanoparticles and their catalytic activity for the reduction of 4-nitrophenol and methylene blue. *Sep Purif Technol* 307:122727
  18. Haghighi P, Alijani S, Bazyari A, Thompson LT (2022) Visible light dye degradation over fluorinated mesoporous TiO<sub>2</sub>–WO<sub>3</sub>–Bi<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> nanocomposite photocatalyst-adsorbent using immersion well reactor. *J Photochem Photobiol, A* 426:113790
  19. Madani M, Hosny S, Alshangiti DM, Nady N, Alkhursani SA, Alkhaldi H, ... and Gaber GA (2022) Green synthesis of nanoparticles for varied applications: green renewable resources and energy-efficient synthetic routes. *Nanotechnol Rev* 11(1):731–759
  20. El Shafey AM (2020) Green synthesis of metal and metal oxide nanoparticles from plant leaf extracts and their applications: a review. *Green Process Synth* 9(1):304–339
  21. Akintelu SA, Folorunso AS, Ademosun OT (2009) Instrumental characterization and antibacterial investigation of silver nanoparticles synthesized from *Garcinia kola* leaf. *J. Drug Deliv Ther* 9(6-s):58–64
  22. Olga M, Jana M, Anna M, Irena K, Jan M, and Alena Č (2022) Antimicrobial properties and applications of metal nanoparticles biosynthesized by green methods. *Biotechnol Adv* 107905
  23. Alshameri AW, Owais M (2022) Antibacterial and cytotoxic potency of the plant-mediated synthesis of metallic nanoparticles Ag NPs and ZnO NPs: a review. *OpenNano* 8:100077
  24. Kumar P, Malik S, Dubey KK (2023) A review on the use of nanomaterials in agriculture: benefits and associated health risks. *Curr Nanomater* 8(1):44–57
  25. Andleeb A, Andleeb A, Asghar S, Zaman G, Tariq M, Mehmood A, Abbasi BH (2021) A systematic review of biosynthesized metallic nanoparticles as a promising anti-cancer-strategy. *Cancers* 13(11):2818
  26. Fardood ST, Ramazani A, Moradi S (2017) A novel green synthesis of nickel oxide nanoparticles using Arabic gum. *Chem J Mol* 12(1):115–118
  27. Ramazani A, Taghavi Fardood S, Hosseinzadeh Z, Sadri F, Joo SW (2017) Green synthesis of magnetic copper ferrite nanoparticles using tragacanth gum as a biotemplate and their catalytic activity for the oxidation of alcohols, Iranian. *J Catal* 7(3):181–185
  28. Chatterjee R, Sarkar S, Dutta AK, Akinay Y, Dasgupta S, Mukhopadhyay M (2003) Scope and challenges for green synthesis of functional nanoparticles. In novel applications of carbon based nano-materials 274–318. CRC Press
  29. Saratale RG, Karuppusamy I, Saratale GD, Pugazhendhi A, Kumar G, Park Y, Shin HS (2018) A comprehensive review on green nanomaterials using biological systems: recent perception and their future applications. *Colloids Surf, B* 170:20–35
  30. Ijaz I, Gilani E, Nazir A, Bukhari A (2020) Detail review on chemical, physical and green synthesis, classification, characterizations and applications of nanoparticles. *Green Chemi Lett Rev* 13(3):223–245
  31. Zhang D, Ma XL, Gu Y, Huang H, Zhang GW (2020) Green synthesis of metallic nanoparticles and their potential applications to treat cancer. *Front Chem* 799
  32. Rana A, Yadav K, Jagadevan S (2020) A comprehensive review on green synthesis of nature-inspired metal nanoparticles: mechanism, application and toxicity. *J Clean Prod* 272:122880
  33. Roy A, Pandit C, Gacem A, Alqahtani MS, Bilal M, Islam S, Jameel M (2022) Biologically derived gold nanoparticles and their applications. *Bioinorganic Chem Appl* 2022:1
  34. Mughal SS, Hassan SM (2022) Comparative study of AgO nanoparticles synthesize via biological, chemical and physical methods: a review. *American J Mat Synth Proc* 7(2):15–28
  35. Singh A, Gautam PK, Verma A, Singh V, Shivapriya PM, Shivalkar S, Samanta SK (2020) Green synthesis of metallic nanoparticles as effective alternatives to treat antibiotics resistant bacterial infections: a review. *Biotechnol Rep* 25:e00427
  36. Mosquera-Romero S, Anaya-Garzon J, Garcia-Timmermans C, Van Dorpe J, Hoorens A, Commenges-Bernole N, Varia J (2022) Combined gold recovery and nanoparticle synthesis in microbial systems using fractional factorial design. *Nanomater* 13(1):83
  37. Karade VC, Dongale TD, Sahoo SC, Kollu P, Chougale AD, Patil PS, Patil PB (2018) Effect of reaction time on structural and magnetic properties of green-synthesized magnetic nanoparticles. *J Phy Chem Sol* 120:161–166
  38. Razali Z, Norrizah JS, Abdullah S (2022) Impact of temperature and pH on antioxidant activity of green silver nanoparticles fabricated from Ananas comosus peel extracts. *IOP Conf Ser: Earth Environ Sci* 1019(1):012006 (**IOP Publishing**)
  39. Habeeb Rahuman HB, Dhandapani R, Narayanan S, Palanivel V, Paramasivam R, Subbarayalu R, Muthupandian S (2022) Medicinal plants mediated the green synthesis of silver nanoparticles and their biomedical applications. *IET Nanobiotechnol* 16(4):115–144
  40. Habeeb Rahuman HB, Dhandapani R, Narayanan S, Palanivel V, Paramasivam R, Subbarayalu R, ... and Muthupandian S (2022) Medicinal plants mediated the green synthesis of silver nanoparticles and their biomedical applications. *IET Nanobiotechnol* 16(4):115–144
  41. Rozali NL, Azizan KA, Singh R, Jaafar SNS, Othman A, Weckwerth W, Ramli US (2023) Fourier transform infrared (FTIR) spectroscopy approach combined with discriminant analysis and prediction model for crude palm oil authentication of different geographical and temporal origins. *Food Control* 146:109509
  42. Naganthran A, Verasoundarapandian G, Khalid FE, Masarudin M J, Zulkharnain A, Nawawi NM, ... and Ahmad SA (2022) Synthesis, characterization and biomedical application of silver nanoparticles. *Materials* 15(2):427
  43. Khan MQ, Kumar P, Khan RA, Ahmad K, Kim H (2022) Fabrication of sulfur-doped reduced graphene oxide modified glassy carbon electrode (S@ rGO/GCE) based acetaminophen sensor. *Inorganics* 10(12):218
  44. Begum SJ, Pratibha S, Rawat JM, Venugopal D, Sahu P, Gowda A, Jaremko M (2022) Recent advances in green synthesis, characterization, and applications of bioactive metallic nanoparticles. *Pharmaceuticals* 15(4):455
  45. Nahari MH, Ali Al A, Asiri A, Mahnashi MH, Shaikh IA, Shettar AK, J. (2022) Hoskeri, Green synthesis and characterization of iron nanoparticles synthesized from aqueous leaf extract of Vitex leucoxylon and its biomedical applications. *Nanomaterials* 12(14):2404
  46. Wu X, Fang F, Zhang B, Wu JJ, Zhang K (2022) Biogenic silver nanoparticles-modified forward osmosis membranes with mitigated internal concentration polarization and enhanced antibacterial properties. *npj Clean Water* 5(1):41
  47. Alaallah NJ, Abd Alkareem E, Ghaidan A, Imran NA (2023) Eco-friendly approach for silver nanoparticles synthesis from lemon extract and their anti-oxidant, anti-bacterial, and anti-cancer activities. *J Turkish Chem Soc Sect A: Chem* 10(1):205–216



48. Devatha CP, Thalla AK (2018) Green synthesis of nanomaterials. In *Synthesis of inorganic nanomaterials* (pp. 169–184) Woodhead Publishing
49. Muhammad Mailafiya M, Abubakar K, Danmaigoro A, Musa Chiroma S, Bin Abdul Rahim E, Aris Mohd Moklas M, Abu Bakar Zakaria Z (2019) Cockle shell-derived calcium carbonate (aragonite) nanoparticles: a dynamite to nanomedicine. *Appl Sci* 9(14):2897
50. Raja RK, Hazir S, Balasubramani G, Sivaprakash G, Obeth ESJ, Boobalan T, ... and Arun A (2022) Green nanotechnology for the environment. In *Handbook of microbial nanotechnology* (pp. 461–478). Academic Press
51. Jadoun S, Chauhan NPS, Zarrintaj P, Barani M, Varma RS, Chinnam S, Rahdar A (2022) Synthesis of nanoparticles using microorganisms and their applications: a review. *Environ Chem Lett* 20(5):3153–3197
52. Ali M, Khan T, Fatima K, Ali QUA, Ovais M, Khalil AT, Idrees M (2018) Selected hepatoprotective herbal medicines: evidence from ethnomedicinal applications, animal models, and possible mechanism of actions. *Phytother Res* 32(2):199–215
53. Mukhopadhyay R, Kazi J, Debnath MC (2018) Synthesis and characterization of copper nanoparticles stabilized with *Quisqualis indica* extract: evaluation of its cytotoxicity and apoptosis in B16F10 melanoma cells. *Biomed Pharmacol* 97:1373–1385
54. Goel M, Sharma A, Sharma B (2023) Recent advances in biogenic silver nanoparticles for their biomedical applications. *Sustain Chem* 4(1):61–94
55. Sharma P, Pant S, Dave V, Tak K, Sadhu V, Reddy KR (2019) Green synthesis and characterization of copper nanoparticles by *Tinospira cardifolia* to produce nature-friendly copper nano-coated fabric and their antimicrobial evaluation. *J Microbial Meth* 160:107–116
56. Kausar, S. (2022). Application of copper-based nanomaterials against parasitic nematodes. In *Copper nanostructures: next-generation of agrochemicals for sustainable agroecosystems* (pp. 263–290). Elsevier.
57. Hashemi SF, Tasharofi N, Saber MM (2020) Green synthesis of silver nanoparticles using *Teucrium polium* leaf extract and assessment of their antitumor effects against MNK45 human gastric cancer cell line. *J Mol Struct* 1208:127889
58. Vennila K, Chitra L, Balagurunathan R, Palvannan T (2018) Comparison of biological activities of selenium and silver nanoparticles attached with bioactive phytoconstituents: green synthesized using *Spermocoe hispida* extract. *Adv Nat Sci: Nanosci Nanotechnol* 9(1):015005
59. Singh PG, Madhu SB, Shailasreeseekhar GTS, Basalingappa KM, Sushma BV (2020) In vitro antioxidant, anti-inflammatory and anti-microbial activity of *Carica papaya* seeds. *Global Journal of Medical Research* 20:19–38
60. Chao WW, Kuo YH, and Lin BF (2021) Isolation and identification of *Andrographis paniculata* (Chuanxinlian) and its biologically active constituents inhibited enterovirus 71-induced cell apoptosis. *Front Pharmacol* 3229
61. Al-Sheddi ES, Farshori NN, Al-Oqail MM, Al-Massarani SM, Saquib Q, Wahab R, Siddiqui MA (2018) Anticancer potential of green synthesized silver nanoparticles using extract of *Nepeta deflersiana* against human cervical cancer cells (HeLa). *Bioinorg Chem Appl*
62. İlhan S, Pulat ÇÇ (2021) Biogenic silver nanoparticles synthesized from *Piper longum* fruit extract inhibit HIF-1 $\alpha$ /VEGF mediated angiogenesis in prostate cancer cells. *Cumhuriyet Science Journal* 42(2):236–244
63. Soltani L, and Darbemamieh M (2021) Biosynthesis of silver nanoparticles using hydroethanolic extract of *Cucurbita pepo* L. fruit and their anti-proliferative and apoptotic activity against breast cancer cell line (MCF-7). *Multidiscip Cancer Invest* 5(3):1–10
64. Unni C (2021) *Biofabrication of silver nanoparticles from Withania somnifera root extract and its investigation of anti-inflammatory and anti-bacterial activity* (Doctoral dissertation, Nandha College of Pharmacy, Erode)
65. Khor KZ, Joseph J, Shamsuddin F, Lim V, Moses EJ, Samad NA (2020) The cytotoxic effects of *Moringa oleifera* leaf extract and silver nanoparticles on human Kasumi-I cells. *Int J Nanomed* 15:5661–5671
66. Kar S (2022) Green synthesis of gold nanoparticles for bio-applications. *Journal of Sustainable Science and Transformative Research-Reviews & Letters* 1(2):59–62
67. Murugesu S, Selamat J, Perumal V (2021) Phytochemistry, pharmacological properties, and recent applications of *Ficus benghalensis* and *Ficus religiosa*. *Plants* 10(12):2749
68. Jalal M, Ansari MA, Alzohairy MA, Ali SG, Khan HM, Almatroudi A, Siddiqui MI (2019) Anti candidal activity of biosynthesized silver nanoparticles: effect on growth, cell morphology, and key virulence attributes of *Candida* species. *Int J Nanomed* 14:4667
69. Atale N, Mishra CB, Kohli S, Mongre RK, Prakash A, Kumari S, ... and Rani V (2021) Anti-inflammatory effects of *S. cumini* seed extract on gelatinase-B (MMP-9) regulation against hyperglycemic cardiomyocyte stress. *Oxidative Med Cell Long* 2021
70. Yugay Y, Rusapetova T, Mashtalyar D, Grigorchuk V, Vasyutkina E, Kudanova O, ... and Shkryl Y (2021) Biomimetic synthesis of functional silver nanoparticles using hairy roots of *Panax ginseng* for wheat pathogenic fungi treatment. *Colloids Surf B: Biointerfaces* 207:112031
71. Yang Y, Ju Z, Yang Y, Zhang Y, Yang L, Wang Z (2021) Phytochemical analysis of *Panax* species: a review. *J Ginseng Res* 45(1):1–21
72. Radulović M, Rajčević N, Gavrilović M, Novaković J, Stešević D, Marin PD, Janačković P (2021) Five wild-growing *Artemisia* (Asteraceae) species from Serbia and Montenegro: essential oil composition and its chemophenetic significance. *J Serb Chem Soc* 86(12):1281–1290
73. Singh NB, Devi ML, Biona T, Sharma N, Das S, Chakravorty J, ... and Rajashekar Y (2023) Phytochemical composition and antimicrobial activity of essential oil from the leaves of *Artemisia vulgaris* L. *Molecules* 28(5):2279
74. Uddin AR, Siddique MAB, Rahman F, Ullah AA, Khan R (2020) *Cocos nucifera* leaf extract mediated green synthesis of silver nanoparticles for enhanced antibacterial activity. *J Inorg Organomet Polym Mater* 30:3305–3316
75. Villedieu-Percheron E, Ferreira V, Campos JF, Destandau E, Pichon C, Berteina-Raboin S (2019) Quantitative determination of Andrographolide and related compounds in *Andrographis paniculata* extracts and biological evaluation of their anti-inflammatory activity. *Foods* 8(12):683
76. Galdames A, Ruiz-Rubio L, Orueta M, Sánchez-Arzálluz M, Vilas-Vilela JL (2020) Zero-valent iron nanoparticles for soil and groundwater remediation. *Int J Environ Res Public Health* 17(16):5817
77. Bencsik T, Papp N (2019) Phytochemical overview and medicinal importance of Coffea species from the past until now. *Asian Pac J Trop Med* 9(12):1101–1110
78. Hashemi Z, Shirzadi-Ahoozad M, Ebrahimzadeh MA (2021) Antileishmanial and antibacterial activities of biologically synthesized silver nanoparticles using *Alcea rosea* extract (AR-AgNPs). *Journal of Water and Environmental Nanotechnology* 6(3):265–276
79. Nawaz H, Akram H, Ishaq QHM, Khalid A, Zainab B, Mazhar A (2022) Polarity-dependent response of phytochemical extraction

- and antioxidant potential of different parts of *Alcea rosea*. *Free Radicals and Antioxidants* 12(2):49–54
80. Pirtarighat S, Ghannadnia M, Baghshahi S (2019) Green synthesis of silver nanoparticles using the plant extract of *Salvia spinosa* grown in vitro and their antibacterial activity assessment. *Journal of Nanostructure in Chemistry* 9:1–9
  81. Gray NE, Alcazar Magana A, Lak P, Wright KM, Quinn J, Stevens JF, Soumyanath A (2018) *Centella asiatica*: phytochemistry and mechanisms of neuroprotection and cognitive enhancement. *Phytochemistry Rev* 17(1):161–194
  82. Darvish S, Saeed Kahrizi M, Özbolat G, Khaleghi F, Morteza-nia Z, Sakhaei D (2022) Silver nanoparticles: biosynthesis and cytotoxic performance against breast cancer MCF-7 and MDA-MB-231 cell lines. *Nanomedicine Research Journal* 7(1):83–92
  83. Barda C, Grafakou ME, Tomou EM, and Skaltsa H (2021) Phytochemistry and evidence-based traditional uses of the genus *Achillea* L.: an update (2011–2021). *Sci Pharm* 89(4):50
  84. Deepa K, Sridhar A, and Panda T (2022) Biogenic gold nanoparticles: current applications and future prospects. *J Cluster Sci* 1–21
  85. Guilger-Casagrande M, Lima RD (2019) Synthesis of silver nanoparticles mediated by fungi: a review. *Frontiers in bioengineering and biotechnology* 7:287
  86. Ahmad SA, Das SS, Khatoun A, Ansari MT, Afzal M, Hasnain MS, Nayak AK (2020) Bactericidal activity of silver nanoparticles: a mechanistic review. *Materials Science for Energy Technologies* 3:756–769
  87. Alshweh HA, Aldosary SK, Ilowefah MA, Shahzad R, Shehzad A, Bilal S, Mediani A (2022) Biological potentials and phytochemical constituents of raw and roasted *Nigella arvensis* and *Nigella sativa*. *Molecules* 27(2):550
  88. Shreyash N, Bajpai S, Khan MA, Vijay Y, Tiwary SK, Sonker M (2021) Green synthesis of nanoparticles and their biomedical applications: a review. *ACS Applied Nano Materials* 4(11):11428–11457
  89. Magangana TP, Makunga NP, Fawole OA, Opara UL (2020) Processing factors affecting the phytochemical and nutritional properties of pomegranate (*Punica granatum* L) peel waste: a review. *Molecules* 25(20):4690
  90. Vijayan R, Joseph S, Mathew B (2019) *Costus speciosus* rhizome extract mediated synthesis of silver and gold nanoparticles and their biological and catalytic properties. *Inorganic and Nano-Metal Chemistry* 49(8):249–259
  91. Gardia D, Mishra AK, Tanty R, Parua B, Khamari A (2023) Phytochemical analysis of *Mentha piperita* (Peppermint). *American Journal of Life Science Researches* 11(1):54–58
  92. Sunderam V, Thiagarajan D, Lawrence AV, Mohammed SSS, Selvaraj A (2019) In-vitro antimicrobial and anticancer properties of green synthesized gold nanoparticles using *Anacardium occidentale* leaves extract. *Saudi J Biol Sci* 26(3):455–459
  93. Ngozika ONF, Nnachetam UV, Ndi ONC, Chike AB (2020) Phytochemical and antibacterial activities of *Anacardium occidentale* fruits extracts (cashew) on two drug resistant bacteria. *Int J Sci Healthcare Res* 5(2):81–87
  94. Uzma M, Sunayana N, Raghavendra VB, Madhu CS, Shanmuganathan R, Brindhadevi K (2020) Biogenic synthesis of gold nanoparticles using *Commiphora wightii* and their cytotoxic effects on breast cancer cell line (MCF-7). *Process Biochem* 92:269–276
  95. Bishoyi SK, and Tripathy UP (2022) Phytochemical, pharmacological potential and ethnomedicinal uses on *Phyllanthus amarus*: a review
  96. Bhavikatti SK, Karobari MI, Zainuddin SLA, Marya A, Nadaf SJ, Sawant VJ, ... and Scardina GA (2021) Investigating the antioxidant and cytocompatibility of *Mimusops elengi* Linn extract over human gingival fibroblast cells. *Int J Environ Res Public Health* 18(13):7162
  97. Acharya P, Jayaprakasha GK, Crosby KM, Jifon JL, Patil BS (2019) Green-synthesized nanoparticles enhanced seedling growth, yield, and quality of onion (*Allium cepa* L.). *ACS Sustain Chem Eng* 7(17):14580–14590
  98. Masood S, Rehman AU, Bashir S, Imran M, Khalil P, Khursheed T, ... and Javaid N (2020) Proximate and sensory analysis of wheat bread supplemented with onion powder and onion peel extract. *Biosci Res*
  99. Nadaf SJ, Jadhav NR, Naikwadi HS, Savekar PL, Sapkal ID, Kambli MM, and Desai IA (2022) Green synthesis of gold and silver nanoparticles: updates on research, patents, and future prospects. *OpenNano* 100076
  100. Batiha GES, Alkazmi LM, Wasef LG, Beshbishy AM, Nadwa EH, Rashwan EK (2020) *Syzygium aromaticum* L.(Myrtaceae): traditional uses, bioactive chemical constituents, pharmacological and toxicological activities, *Biomole* 10(2)
  101. Le VT, Ngu NNQ, Chau TP, Nguyen TD, Nguyen VT, Nguyen TLH, Cao XT, Doan VD (2021) Silver and gold nanoparticles from *Limnophila rugosa* leaves: biosynthesis, characterization, and catalytic activity in reduction of nitrophenols. *J Nanomater* 2021:5571663
  102. Hota R, Kumar Nanda B, Behera B, Kumar Dalai M (2023) Ethno-botanical and phytopharmacological study of *Limnophila rugosa* Roth. Merr.(Scrophulariaceae): mini review. *Curr Tradit Med* 9(5):137–149
  103. Guliani A, Kumari A, Acharya A (2021) Green synthesis of gold nanoparticles using aqueous leaf extract of *Populus alba*: characterization, antibacterial and dye degradation activity. *Int J Environ Sci Technol* 6:1–12
  104. Bashir S, Jabeen K, Iqbal S, Javed S, Naeem A (2019) *Lantana camara*: phytochemical analysis and antifungal prospective. *Planta Daninha* 37
  105. El-Borady OM, Fawzy M, Hosny M (2021) Antioxidant, anticancer and enhanced photocatalytic potentials of gold nanoparticles biosynthesized by common reed leaf extract. *Appl Nanosci* 3:1–12
  106. Samir D, Manel A, Abir H (2019) Phytochemical analysis and antioxidant property of rhizome extracts aqueous of *Phragmites australis* in alloxan diabetic rats. *Asian J Pharm Technol* 9(4):249–252
  107. Li S, Al-Misned FA, El-Serehy HA, Yang L (2020) Green synthesis of gold nanoparticles using aqueous extract of *Mentha Longifolia* leaf and investigation of its anti-human breast carcinoma properties in the in vitro condition. *Arab J Chem* 14:102931
  108. Kamsonlian S, and Agarwal V (2022) Review on synthesis of plant-mediated green iron nanoparticles and their application for decolorization of dyes. *Mater Today: Proc*
  109. Khalil AT, Ovais M, Ullah I, Ali M, Shinwari ZK, Maaza M (2020) Physical properties, biological applications and biocompatibility studies on biosynthesized single phase cobalt oxide (Co3O4) nanoparticles via *Sageretia thea* (Osbeck). *Arab J Chem* 13(1):606–619
  110. Arumugam V, Sriram P, Yen TJ, Redhi GG, Gengan RM (2018) Nano-material as an excellent catalyst for reducing a series of nitroanilines and dyes: triphosphonated ionic liquid-CuFe2O4-modified boron nitride. *Appl Catal B: Env* 222:99–114
  111. Rocchetti G, Lucini L, Ahmed SR, Saber FR (2019) *In vitro* cytotoxic activity of six *Syzygium* leaf extracts as related to their phenolic profiles: an untargeted UHPLC-QTOF-MS approach. *Food Res Int* 126:108715
  112. Modwi A, Idriss H, Khezami L, Albadri A, Ismail M, Assadi AA, Nguyen-Tri P (2023) Ba2+ removal from aquatic medium

- via TiY2O5@ g-C3N4 nanocomposites. *Diamond Relat Mater* 135:109830
113. Anka L, Rammal H, Kobeissi A, Saab HB (2020) Chemical composition and biological potentials of Lebanese *Cupressus sempervirens* L. leaves extracts. *J Med Plants Res* 14(6):292–299
  114. Fang L, Xu C, Zhang W, Huang L (2018) The important role of polyvinylpyrrolidone and Cu on enhancing dechlorination of 2,4-dichlorophenol by Cu/Fe nanoparticles : performance and mechanism study. *Appl Surface Sci* 435:55–64
  115. Zhu C, Zhang S, Fu H, Zhou C, Chen L, Li X, ... and Guo Y (2019) Transcriptome and phytochemical analyses provide new insights into long non-coding RNAs modulating characteristic secondary metabolites of oolong tea (*Camellia sinensis*) in solar-withering. *Front Plant Sci* 10:1638
  116. Singh A, Bajpai J, Bajpai AK, Mongre RK, Lee MS (2020) Encapsulation of cytarabine into casein coated iron oxide nanoparticles (CCIONPs) and study of in vitro drug release and anti-cancer activities. *J Drug Deliv Sci Technol* 55:101396
  117. Mengiste B, Zenebe T, Dires K, Lulekal E, Mekonnen A, Zegeye N, Shiferaw Y (2020) Safety evaluation of *Eucalyptus globulus* essential oils through acute and sub-acute toxicity and skin irritation in mice and rats. *Curr Chem Biol* 14(3):187–195
  118. Hossain MM, Polash SA, Saha T, Sarker SR (2022) Gold nanoparticles: a lethal nanoweapon against multidrug-resistant bacteria. Nano-strategies for addressing antimicrobial resistance: nano-diagnostics, nano-carriers, and nano-antimicrobials. Springer International Publishing, Cham, pp 311–351
  119. Maroyi (2018) *Albizia adianthifolia*: botany, medicinal uses, phytochemistry, and pharmacological properties. *Sci World J*
  120. Ariantari NP, Ratnasantasyacitta ES (2022) Pharmacologically active secondary metabolites from *Psoralea corylifolia*. *J Trop Pharm Chem* 6(2):177–189
  121. Hassan AK, Al-Kindi GY, Ghanim D (2020) Green synthesis of bentonite-supported iron nanoparticles as a heterogeneous Fenton-like catalyst: kinetics of decolorization of reactive blue 238 dye. *Water Sci Eng* 13(4):286–298
  122. Zhu C, Zhang S, Fu H, Zhou C, Chen L, Li X, ... and Guo Y (2019) Transcriptome and phytochemical analyses provide new insights into long non-coding RNAs modulating characteristic secondary metabolites of oolong tea (*Camellia sinensis*) in solar-withering. *Front Plant Sci* 10:1638
  123. Khalil AT, Ovais M, Ullah I, Ali M, Shinwari ZK, Maaza M (2017) Biosynthesis of iron oxide (Fe2O3) nanoparticles via aqueous extracts of *Sageretia thea* (Osbeck) and their pharmacognostic properties. *Green Chem Lett Rev* 10(4):186–201
  124. Sulaiman GM, Tawfeeq AT, Naji AS (2018) Biosynthesis, characterization of magnetic iron oxide nanoparticles and evaluations of the cytotoxicity and DNA damage of human breast carcinoma cell lines. *Art Cells Nanomed Biotechnol* 46(6):1215–1229
  125. Maroyi A (2018) *Albizia adianthifolia*: botany, medicinal uses, phytochemistry, and pharmacological properties. *Sci World J*
  126. Göl F, Aygün A, Seyrankaya A, Gür T, Yenikaya C, Şen F (2020) Green synthesis and characterization of *Camellia sinensis* mediated silver nanoparticles for antibacterial ceramic applications. *Mater Chem Phys* 250:123037
  127. Sangode CM, Mahant SA, Tidke PC, Umekar MJ, Lohiya RT (2021) Green synthesized of novel iron nanoparticles as promising antimicrobial agent: a review. *GSC Biol Pharm Sci* 15(2):117–127
  128. Yang F, Cen R, Feng W, Liu J, Qu Z, Miao Q (2020) Effects of super-absorbent polymer on soil remediation and crop growth in arid and semi-arid areas. *Sustainability* 12(18):7825
  129. Alvi GB, Iqbal MS, Ghaith MMS, Haseeb A, Ahmed B, Qadir MI (2021) Biogenic selenium nanoparticles (SeNPs) from citrus fruit have anti-bacterial activities. *Sci Rep* 11(1):4811
  130. Kaur S, Gupta S, Gautam PB (2019) Phytochemical analysis of eucalyptus leaves extract. *J Pharmaco Phytochem* 8(1):2442–2446
  131. Ali M, Ibrahim IS (2019) Phytochemical screening and proximate analysis of garlic (*Allium sativum*). *Arc Org Inorg Chem Sci* 4(1):478–482
  132. Puri A, Patil S (2022) Biogenic synthesis of selenium nanoparticles using *Diospyros montana* bark extract: characterization, antioxidant, antibacterial, and antiproliferative activity. *Biosci, Biotechnol Res Asia* 19(2):423–441
  133. Narnoliya LK, Jadaun JS, Singh SP (2019) The phytochemical composition, biological effects and biotechnological approaches to the production of high-value essential oil from geranium. In *Essential oil research* (pp. 327–352) Springer, Cham
  134. Gokul Eswaran S, Shahid Afridi P, and Vasimalai N (2022) Effective multi toxic dyes degradation using bio-fabricated silver nanoparticles as a green catalyst. *Appl Biochem Biotechnol* 1–16
  135. Shwe HH, Win KK, Moe TT, Myint AA, Win T (2019) Isolation and structural characterization of lupeol from the stem bark of *Diospyros ehretioides* Wall. *IEEE-SEM* 7(8):140–144
  136. Fardsadegh B, Jafarizadeh-Malmiri H (2019) Aloe vera leaf extract mediated green synthesis of selenium nanoparticles and assessment of their in vitro antimicrobial activity against spoilage fungi and pathogenic bacteria strains. *Green Process Synth* 8(1):399–407
  137. Bista R, Ghimire A, Subedi S (2020) Phytochemicals and antioxidant activities of Aloe vera (*Aloe barbadensis*). *J Nutri Sci Healthy Diet* 1(1):25–36
  138. Zeebaree SYS, Zeebaree AYS, Zebari OIH (2020) Diagnosis of the multiple effect of selenium nanoparticles decorated by *Asteriscus graveolens* components in inhibiting HepG2 cell proliferation. *Sus Chem Pharm* 15:100210
  139. Belhadi F, Ouafi S, Bouguedoura N (2020) Phytochemical composition and pharmacological assessment of callus and parent plant of *Asteriscus graveolens* (Forssk) Less from Algerian Sahara. *Trop J Pharm Res* 19(9):1895–1901
  140. Sowndarya P, Ramkumar G, Shivakumar MS (2017) Green synthesis of selenium nanoparticles conjugated *Clausena dentata* plant leaf extract and their insecticidal potential against mosquito vectors. *Art Cells Nanomed Biotechnol* 45(8):1490–1495
  141. Anh H, Xuan TD, Thuy D, Thi N, Quan NV, Trang LT (2020) Antioxidant and  $\alpha$ -amylase inhibitory activities and phytochemicals of *Clausena indica* fruits. *Medicines* 7(3):10
  142. Alam H, Khatoon N, Raza M, Ghosh PC, Sardar M (2019) Synthesis and characterization of nano selenium using plant biomolecules and their potential applications. *BioNanoScience* 9(1):96–104
  143. Kumar M, Tomar M, Amarowicz R, Saurabh V, Nair MS, Maheshwari C, Satankar V (2021) Guava (*Psidium guajava* L.) leaves: nutritional composition, phytochemical profile, and health-promoting bioactivities. *Foods* 10(4):752
  144. Sundaram RL, Vasanthi HR (2022) *Spermacoce hispida* Linn: a critical review on pharmacognosy, phytochemistry, and pharmacology based on traditional claims. *Phytomed Plus* 2(1):100143
  145. Mellinas C, Jiménez A, Garrigós MDC (2019) Microwave-assisted green synthesis and antioxidant activity of selenium nanoparticles using *Theobroma cacao* L. Bean Shell Extract. *Molecules* 24(22):4048
  146. Rebollo-Hernanz M, Cañas S, Braojos C, Cano-Muñoz P, and Martín-Cabrejas MA (2022) Cocoa shell: source of novel bioactive ingredients for the prevention of cardiometabolic diseases. *Mol Mech Funct Food* 485–519
  147. Wu S, Rajeshkumar S, Madasamy M, Mahendran V (2020) Green synthesis of copper nanoparticles using *Cissus vitiginea* and its antioxidant and antibacterial activity against urinary

- tract infection pathogens. *Artificial Cells, Nanomed Biotechnol* 48(1):1153–1158
148. Batiha GES, Alkazmi LM, Wasef LG, Beshbishy AM, Nadwa EH, Rashwan EK (2020) *Syzygium aromaticum* L. (Myrtaceae): traditional uses, bioactive chemical constituents, pharmacological and toxicological activities. *Biomolecules* 10(2)
  149. Benassai E, Del Bubba M, Ancillotti C, Colzi I, Gonnelli C, Calisi N, ... and Ristori S (2021) Green and cost-effective synthesis of copper nanoparticles using extracts of non-edible and waste plant materials from *Vaccinium* species: characterization and antimicrobial activity. *Mater Sci Eng: C* 119:111453
  150. Ricci M, Tilbury L, Daridon B, Sukalac K (2019) General principles to justify plant biostimulant claims. *Front Plant Sci* 10:494
  151. Ng HC, Khe CS, Yau XH, Liu WW, Aziz A (2019) Green synthesis of silver nanoparticles using hibiscus *rosa-sinensis* leaf extract. *Nanosci Nanotechnology-Asia* 9(4):472–478
  152. Sebeia N, Jabli M, Ghith A (2019) Biological synthesis of copper nanoparticles, using *Nerium oleander* leaves extract: characterization and study of their interaction with organic dyes. *Inorg Chem Commun* 105:36–46
  153. Donkor S, Larbie C, Komlaga G, Emikpe BO (2019) Phytochemical, antimicrobial, and antioxidant profiles of *Duranta erecta* L. parts. *Biochem Res Int*
  154. Khatami M, Ebrahimi K, Galehdar N, Moradi MN, Moayyedkazemi A (2020) Green synthesis and characterization of copper nanoparticles and their effects on liver function and hematological parameters in mice. *Turk J Pharm Sci* 17(4):412
  155. Chiocchio I, Mandrone M, Tacchini M, Guerrini A, Poli F (2023) Phytochemical profile and in vitro bioactivities of plant-based by-products in view of a potential reuse and valorization. *Plants* 12(4):795
  156. Akintelu SA, Oyebamiji AK, Olugbeko SC, Latona DF (2021) Green chemistry approach towards the synthesis of copper nanoparticles and its potential applications as therapeutic agents and environmental control. *Curr Res Green Sustain Chem* 4:100176
  157. Chhikara N, Kour R, Jaglan S, Gupta P, Gat Y, Panghal A (2018) *Citrus medica*: nutritional, phytochemical composition and health benefits—a review. *Food Funct* 9(4):1978–1992
  158. Alahdal FA, Qashqoosh MT, Manea YK, Mohammed RK, Naqvi S (2023) Green synthesis and characterization of copper nanoparticles using *Phragmanthera austroarabica* extract and their biological/environmental applications. *Sustain Mater Technol* 35:e00540
  159. Younus M, Hasan MM, Ali S, Saddq B, Sarwar G, Ullah MI, Darwish H (2021) Extracts of *Euphorbia nivulia* Buch.-Ham. showed both phytotoxic and insecticidal capacities against *Lemna minor* L. and *Oxycarenus hyalinipennis* Costa. *Plos One* 16(4):e0250118
  160. Nilavukkarasi M, Vijayakumar S, Kumar SP (2020) Biological synthesis and characterization of silver nanoparticles with *Caparis zeylanica* L. leaf extract for potent antimicrobial and anti proliferation efficiency. *Mater Sci Energy Technol* 3:371–376
  161. Amit L, Kumar CA, Vikas G, Parveen B, Renu B (2021) www.ijrap. Net. *Int J Res Ayu. Pharm* 1(2) 384–389
  162. Amin F, Khattak B, Alotaibi A, Qasim M, Ahmad I, Ullah R, ... and Ahmad R (2021) Green synthesis of copper oxide nanoparticles using *Aerva javanica* leaf extract and their characterization and investigation of in vitro antimicrobial potential and cytotoxic activities. *Evid-Based Complement Altern Med* 2021
  163. Devi B, Jeet K, and Nigam V (n.d.) A review study over: pharmacognostic study, phytochemical and pharmacological studies over whole plant of *Aerva lanata* (L.)
  164. Sharma P, Pant S, Dave V, Tak K, Sadhu V, Reddy KR (2019) Green synthesis and characterization of copper nanoparticles by *Tinospora cordifolia* to produce nature-friendly copper nano-coated fabric and their antimicrobial evaluation. *J Microbiol Methods* 160:107–116
  165. Krupanidhi S, Abraham Peele K, Venkateswarulu TC, Ayyagari VS, Nazneen Bobby M, John Babu D, Aishwarya G (2021) Screening of phytochemical compounds of *Tinospora cordifolia* for their inhibitory activity on SARS-CoV-2: an in silico study. *J Biomol Struct Dyn* 39(15):5799–5803
  166. Dashtizadeh Z, Kashi FJ, Ashrafi M (2021) Phytosynthesis of copper nanoparticles using *Prunus mahaleb* L. and its biological activity. *Mater Today Commun* 27:102456
  167. Abdellattif MH, Alrefae SH, Dagdag O, Verma C, Quraishi MA (2021) *Calotropis procera* extract as an environmental friendly corrosion inhibitor: computational demonstrations. *J Mol Liq* 337:116954
  168. Oves M, Rauf MA, Aslam M, Qari HA, Sonbol H, Ahmad I, ... and Saeed M (2022) Green synthesis of silver nanoparticles by *Conocarpus lancifolius* plant extract and their antimicrobial and anticancer activities. *Saudi J Biol Sci* 29(1):460–471
  169. El-Waseif AA, El-Ghani GSA, Maaty SA, Hassan MG (2022) Cytotoxicity and promising anti-biofilm of *Curcuma* silver nanoparticles against *Candida albicans*. *Res J Pharm Technol* 15(8):3355–3359
  170. Sánchez-Hernández E, González-García V, Correa-Guimarães A, Casanova-Gascón J, Martín-Gil J, Martín-Ramos P (2023) Phytochemical profile and activity against *Fusarium* species of *Tamarix gallica* bark aqueous ammonia extract. *Agronomy* 13(2):496
  171. Chinnappan S, Kandasamy S, Arumugam S, Seralathan KK, Thangaswamy S, Muthusamy G (2018) Biomimetic synthesis of silver nanoparticles using flower extract of *Bauhinia purpurea* and its antibacterial activity against clinical pathogens. *Env Sci Poll Res* 25(1):963–969
  172. Lakshmanan G, Sathiyaseelan A, Kalaichelvan PT, Murugesan K (2018) Plant-mediated synthesis of silver nanoparticles using fruit extract of *Cleome viscosa* L.: assessment of their antibacterial and anticancer activity. *Karbala Int J Mod Sci* 4(1):61–68
  173. Shaik MR, Khan M, Kuniyil M, Al-Warthan A, Alkhathlan HZ, Siddiqui MRH, Adil SF (2018) Plant-extract-assisted green synthesis of silver nanoparticles using *Origanum vulgare* L. extract and their microbicidal activities. *Sustainability* 10(4):913
  174. Shanwaz MM, Shyam P (2022) Synthesis of silver nanoparticles from *Vitex negundo* plant by green method and their bactericidal effects. *Lett Appl NanoBiosci* 12(2):59–62
  175. Khane Y, Benouis K, Albukhaty S, Sulaiman GM, Abomughaid MM, Al Ali A, ... and Dizge N (2022) Green synthesis of silver nanoparticles using aqueous *Citrus limon* zest extract: characterization and evaluation of their antioxidant and antimicrobial properties. *Nanomaterials* 12(12):2013
  176. Wulandari IO, Pebriatin BE, Valiana V, Hadisaputra S, Ananto AD, Sabarudin A (2022) Green synthesis of silver nanoparticles coated by water soluble chitosan and its potency as non-alcoholic hand sanitizer formulation. *Materials* 15(13):4641
  177. Wankar S, Walake S, Gumathannavar R, Sapre N, Kulkarni A (2022) The era of green nanomaterials for sensing. In *Innovations in green nanoscience and nanotechnology* (pp. 209–225). CRC Press
  178. Cadinoiu AN, Rata DM, Daraba OM, Ichim DL, Popescu I, Solcan C, Solcan G (2022) Silver nanoparticles biocomposite films with antimicrobial activity: In vitro and in vivo tests. *Int J Mol Sci* 23(18):10671
  179. Yang Y, Duan S, Xiao W, Zhao H (2022) Silver nanowire-based stretchable strain sensors with hierarchical wrinkled structures. *Sens Actuators, A* 343:113653
  180. Safaya M, Rotliwala Y (2022) Neem oil based nano-emulsion formulation by low energy phase inversion composition method:

- characterization and antimicrobial activity. *Mat Today: Proceedings* 57:1793–1797
181. Kanniah P, Chelliah P, Thangapandi JR, Thangapandi EJJB, Kasi M, and Sivasubramaniam S (2022) Benign fabrication of metallic/metal oxide nanoparticles from algae. In *Agri-waste and microbes for production of sustainable nanomaterials* (pp. 465–493). Elsevier
  182. Azeem MNA, Ahmed OM, Shaban M, Elsayed KN (2022) In vitro antioxidant, anticancer, anti-inflammatory, anti-diabetic and anti-Alzheimer potentials of innovative macroalgae bio-capped silver nanoparticles. *Environ Sci Pollut Res* 29(39):59930–59947
  183. Buyukunal SK, Muratoglu K, Koluman A (2022) The in vitro effect of heat, lactic acid-silver nanoparticle combination on shiga toxigenic *Escherichia coli*. *Emirates J Food Agric*
  184. Dat NM, Thinh DB, Huong LM, Tinh NT, Linh NTT, Hai ND, Hieu NH (2022) Facile synthesis and antibacterial activity of silver nanoparticles-modified graphene oxide hybrid material: the assessment, utilization, and anti-virus potentiality. *Mat Today Chem* 23:100738
  185. Miranda A, Akpobolokemi T, Chung E, Ren G, Raimi-Abraham BT (2022) pH alteration in plant-mediated green synthesis and its resultant impact on antimicrobial properties of silver nanoparticles (AgNPs). *Antibiotics* 11(11):1592
  186. Tang S, Zheng J (2018) Antibacterial activity of silver nanoparticles: structural effects. *Adv healthcare mat* 7(13):1701503
  187. Ghotekar S, Pansambal S, Pawar SP, Pagat T, Oza R, Bangale S (2019) Biological activities of biogenically synthesized fluorescent silver nanoparticles using *Acanthospermum hispidum* leaves extract. *SN Appl Sci* 1:1–12
  188. Ghotekar S, Savale A, Pansambal S (2018) Phytofabrication of fluorescent silver nanoparticles from *Leucaena leucocephala* L. leaves and their biological activities. *J Water Environ Nanotechnol* 3(2):95–105
  189. Sharma K, Pandit S, Thapa BS, Pant M (2022) Biodegradation of Congo red using co-culture anode inoculum in a microbial fuel cell. *Catalysts* 12(10):1219
  190. Kim M, Nguyen DV, Heo Y, Park KH, Paik HD, Kim YB (2020) Antiviral activity of *fritillaria thunbergii* extract against human influenza virus H1N1 (PR8) in vitro, in ovo and in vivo
  191. Srisimal D, Krishnan S, Thirunavukkarasu A (2022) In vitro virucidal activity of silver nanoparticles against H1N1 influenza A virus and herpes simplex virus-1
  192. Pan X, Zhang Y, Zhao Y, Yao S, Guan C, Wang L, Chen L (2022) Inhibitory activity and mechanism of silver nanoparticles against herpes simplex virus type 1. *Adv Virol* 167(8):1619–1636
  193. Luceri A, Francese R, Lembo D, Ferraris M, Balagna C (2023) Silver nanoparticles: review of antiviral properties, mechanism of action and applications. *Microorganisms* 11(3):629
  194. El-Mohamady RS, Ghattas TA, Zawrah MF, Abd El-Hafeiz YGM (2018) Inhibitory effect of silver nanoparticles on bovine herpesvirus-1. *Int J Vet Sci Med* 6(2):296–300
  195. Zohra T, Khalil AT, Saeed F, Latif B, Salman M, Ikram A, ... and Murthy HC (2022) Green nano-biotechnology: a new sustainable paradigm to control dengue infection. *Bioinorg Chem Appl* 2022
  196. Ga'al H, Fouad H, Mao G, Tian J, Jianchu M (2018) Larvicidal and pupicidal evaluation of silver nanoparticles synthesized using *Aquilaria sinensis* and *Pogostemon cablin* essential oils against dengue and Zika viruses vector *Aedes albopictus* mosquito and its histopathological analysis. *Art Cells, Nanomed, Biotechnol* 46(6):1171–1179
  197. Ganguly B, Verma AK, Singh B, Das AK, Rastogi SK, Seidavi A, Giannenas I (2023) Green synthesis of silver nanoparticles with extract of Indian ginseng and in vitro inhibitory activity against infectious bursal disease virus thereof. *Poultry* 2(1):12–22
  198. Er SG, Edirisinghe M, and Tabish TA (2022) Graphene-based nanocomposites as antibacterial, antiviral, and antifungal agents. *Adv Healthcare Mater* 2201523
  199. Mukherjee S, Bytesnikova Z, Martin S, Svec P, Ridoskova A, Pekarkova J, Adam V (2022) Silver nanoparticles synthesized using a new phase of HIV-1 infection. *Adv Materials Int* 10:2201996
  200. Haggag EG, Elshamy AM, Rabeh MA, Gabr NM, Salem M, Youssif KA, Abdelmohsen UR (2019) Antiviral potential of green synthesized silver nanoparticles of *Lampranthus coccineus* and *Malephora lutea*. *Int J Nanomed* 14:6217
  201. Kaushik S, Sharma V, Chhikara S, Yadav JP, Kaushik S (2019) Anti-chikungunya activity of green synthesized silver nanoparticles using *Carica papaya* leaves in animal cell culture model. *Asian J Pharm Clin Res* 12(6):170–174
  202. Sharma V, Kaushik S, Pandit P, Dhull D, Yadav JP, Kaushik S (2019) Green synthesis of silver nanoparticles from medicinal plants and evaluation of their antiviral potential against *chikungunya virus*. *Appl Microbiol Biotechnol* 103(2):881–891
  203. Abdel-Fattah WI, Ali GW (2018) On the anti-cancer activities of silver nanoparticles. *J Appl Biotechnol Bioeng* 5(1):43–46
  204. Banerjee S, Islam S, Chattopadhyay A, Sen A, Kar P (2022) Synthesis of silver nanoparticles using underutilized fruit *Baccaurea ramiflora* (Latka) juice and its biological and cytotoxic efficacy against MCF-7 and MDA-MB 231 cancer cell lines. *South African J Botany* 145:228–235
  205. Singh D, Yadav E, Falls N, Kumar V, Singh M, Verma A (2019) Phytofabricated silver nanoparticles of *Phyllanthus emblica* attenuated diethyl nitrosamine-induced hepatic cancer via knock-down oxidative stress and inflammation. *Inflammo Pharmacol* 27(5):1037–1054
  206. Dey S, Fageria L, Sharma A, Mukherjee S, Pande S, Chowdhury R, Chowdhury S (2022) Silver nanoparticle-induced alteration of mitochondrial and ER homeostasis affects human breast cancer cell fate. *Toxicol Rep* 9:1977–1984
  207. Singh P, Ahn S, Kang JP, Veronika S, Huo Y, Singh H, Yang DC (2018) In vitro anti-inflammatory activity of spherical silver nanoparticles and monodisperse hexagonal gold nanoparticles by fruit extract of *Prunus serrulata*: a green synthetic approach *Art cells*. *Nanomed Biotechnol* 46(8):2022–2032
  208. Younis NS, Mohamed ME, El Semary NA (2022) Green synthesis of silver nanoparticles by the *Cyanobacteria* *synechocystis* sp.: characterization, antimicrobial and diabetic wound-healing actions. *Marine Drugs* 20(1):56
  209. Alkhalaf MI, Hussein RH, Hamza A (2020) Green synthesis of silver nanoparticles by *Nigella sativa* extract alleviates diabetic neuropathy through anti-inflammatory and antioxidant effects. *Saudi J Biol Sci* 27(9):2410–2419
  210. Govindappa M, Hemashekhar B, Arthikala MK, Rai VR, Ramachandra YL (2018) Characterization, antibacterial, antioxidant, antidiabetic, anti-inflammatory and antityrosinase activity of green synthesized silver nanoparticles using *Calophyllum tomentosum* leaves extract. *Resul Phy* 9:400–408
  211. Mudigonda S, Dahms HU, Hwang JS, Li WP (2022) Combined effects of copper oxide and nickel oxide coated chitosan nanoparticles adsorbed to styrofoam resin beads on hydrothermal vent bacteria. *Chemosphere* 308:136338
  212. Moldovan B, David L, Vulcu A, Olenic L, Perde-Schrepler M, Fischer-Fodor E, Filip GA (2017) In vitro and in vivo anti-inflammatory properties of green synthesized silver nanoparticles using *Viburnum opulus* L. fruits extract. *Mat Sci Eng: C* 79:720–727
  213. Shivaramkrishnan B, Gurumurthy B, Balasubramanian A (2017) Potential biomedical applications of metallic nanobio-materials: a review. *Int J Pharma Sci Res* 8(3):985



214. Liu Y, Wang X, Shi X, Sun M, Wang L, Hu Z, Zhao C (2022) A colorimetric sensor for *Staphylococcus aureus* detection based on controlled click chemical-induced aggregation of gold nanoparticles and immunomagnetic separation. *Microchim Acta* 189(3):104
215. Karuvantevida N, Razia M, Bhuvaneshwar R, Sathishkumar G, Prabukumar S, Sivaramakrishnan S (2022) Bioactive flavonoid used as a stabilizing agent of mono and bimetallic nanomaterials for multifunctional activities. *J Pure Appl Microbiol* 16:1652
216. Kumar M, Kumar U, Singh AK (2022) Therapeutic nanoparticles: recent developments and their targeted delivery applications. *Nano Biomed Eng* 14(1)
217. Aminabad NS, Farshbaf M, Akbarzadeh A (2019) Recent advances of gold nanoparticles in biomedical applications: state of the art. *Cell Biochem Biophys* 77(2):123–137
218. Hu X, Zhang Y, Ding T, Liu J, Zhao H (2020) Multifunctional gold nanoparticles: a novel nanomaterial for various medical applications and biological activities. *Front Bioeng Biotechnol* 8:990
219. Bawazeer S, Khan I, Rauf A, Aljohani AS, Alhumaydhi FA, Khalil AA, ... and Khan SA (2022) Black pepper (*Piper nigrum*) fruit-based gold nanoparticles (BP-AuNPs): synthesis, characterization, biological activities, and catalytic applications—a green approach. *Green Process Synthesis* 11(1):11–28
220. Tran NDN, Bui TH, Nguyen AP, Nguyen TT, Nguyen VM, Duong NL, Nguyen T (2022) The ability of silver-biochar green-synthesized from *Citrus maxima* peel to adsorb pollutant organic compounds and antibacterial activity. *Green Chem Lett Rev* 15(1):18–27
221. Nadaf SJ, Jadhav NR, Naikwadi HS, Savekar PL, Sapkal ID, Kambli MM, Desai IA (2022) Green synthesis of gold and silver nanoparticles: updates on research, patents, and future prospects. *OpenNano* 100076
222. Dalal R, Singh S, Sangwan S, Moond M, Beniwal R (2022) Biochemical and molecular mechanism of plant-mediated synthesis of silver nanoparticles—a review. *Mini-Rev Organic Chem* 19(8):939–954
223. Alzahrani S, Ali HM, Althubaiti EH, Ahmed MM (2022) Green synthesis of gold nanoparticles, silver nanoparticles and gold-silver alloy nanoparticles using *Ziziphus spina-christi* leaf extracts and antibacterial activity against multidrug-resistant bacteria. *Indian J Pharma Sci* 42–53
224. Patil T, Gambhir R, Vibhute A, and Tiwari AP (2022) Gold nanoparticles: synthesis methods, functionalization and biological applications. *J Cluster Sci* 1–21.
225. Rocha-Rocha O, Cortez-Valadez M, Calderón-Ayala G, Martínez-Núñez CE, Pedroza-Montero M, Flores-Acosta M (2019) Confined clustering of AuCu nanoparticles under ambient conditions. *Phy Lett A* 383(34):125985
226. Alshameri AW, Owais M (2022) Antibacterial and cytotoxic potency of the plant-mediated synthesis of metallic nanoparticles Ag NPs and ZnO NPs: A Review. *Open Nano* 8:100077
227. Taha RH (2022) Green synthesis of silver and gold nanoparticles and their potential applications as therapeutics in cancer therapy; a review. *Inorg Chem Commun* 143:109610
228. Naseer F, Ahmed M, Majid A, Kamal W, and Phull AR (2022) Green nanoparticles as multifunctional nanomedicines: insights into anti-inflammatory effects, growth signaling and apoptosis mechanism in cancer. In *Seminars in Cancer Biology*. Academic Press
229. Zhang Y, Chen Q, Guo A, Wang X, Wang Y, Long Y, Fan G (2022) Carbon-nanosheet-driven spontaneous deposition of Au nanoparticles for efficient electrochemical utilizations toward H<sub>2</sub>O<sub>2</sub> generation and detection. *Chem Eng J* 445:136586
230. Muddapur UM, Alshehri S, Ghoneim MM, Mahnashi MH, Alshahrani MA, Khan AA, ... and Ahmad MZ (2022) Plant-based synthesis of gold nanoparticles and theranostic applications: a review. *Molecules* 27(4):1391
231. Chugh R, and Kaur G (2022) A mini review on green synthesis of nanoparticles by utilization of *Musa-balbisiana* waste peel extract. *Mater Today: Proc*
232. Halder A, Biswas R, Kushwaha PP, Halder KK, Ahmed I, Singh H, ... and Haldar KK (2022) Green synthesis of bimetallic Au/Ag nanostructures using aqueous extract of *Eichhornia crassipes* for antibacterial activity. *Bionanoscience* 12(2):322–331
233. Shirzadi-Ahodshtii M, Mizwari ZM, Jafarkhani B, Abbastabar M, Motafeghi F, Lalerdi FS, ... and Mortazavi-Derazkola S (2022) Biogenic synthesis of spherical-shaped noble metal nanoparticles using *Vicia faba* extract (X@ VF, X= Au, Ag) for photocatalytic degradation of organic hazardous dye and their in vitro antifungal, antibacterial and anticancer activities. *Inorg Chem Commun* 146:110042
234. Lysenko V, Lozovski V, Lokshyn M, Gomeniuk YV, Dorovskikh A, Rusinchuk N, Bolbukh Y (2018) Nanoparticles as antiviral agents against adenoviruses. *Adv Nat Sci: Nanosci Nanotechnol* 9(2):025021
235. Rodriguez-Salazar CA, Recalde-Reyes DP, Bedoya JP, Padilla-Sanabria L, Castaño-Osorio JC, Giraldo MI (2022) In vitro inhibition of replication of dengue virus serotypes 1–4 by siRNAs bound to non-toxic liposomes. *Viruses* 14(2):339
236. Quach QH, Ang SK, Chu JHJ, Kah JCY (2018) Size-dependent neutralizing activity of gold nanoparticle-based subunit vaccine against *dengue virus*. *Acta Biomater* 78:224–235
237. Gupta A, Pandey S, Variya B, Shah S, Yadav JS (2019) Green synthesis of gold nanoparticles using different leaf extracts of *Ocimum gratissimum* Linn for anti-tubercular activity. *Curr Nanomed* 9(2):146–157 (**Formerly: Recent Patents on Nanomedicine**)
238. Chahardoli A, Karimi N, Sadeghi F, Fattahi A (2018) Green approach for synthesis of gold nanoparticles from *Nigella arvensis* leaf extract and evaluation of their antibacterial, antioxidant, cytotoxicity and catalytic activities Art cells. *Nanomed Biotechnol* 46(3):579–588
239. Dykman LA, Khlebtsov NG (2019) Gold nanoparticles in chemo-, immuno-, and combined therapy: review. *Biomed Optics Exp* 10(7):3152–3182
240. Wen J, Fu W, Ding S, Zhang Y, Wang W (2022) Pyrogallol acid modified nanoscale zero-valent iron efficiently removed Cr (VI) by improving adsorption and electron selectivity. *Chem Eng J* 443:136510
241. Garvasi J, Prasad AR, Shamsheera KO, Roy TN, Joseph A (2023) A facile one-pot synthesis of phyto-conjugate superparamagnetic magnetite nanoparticles for the rapid removal of hexavalent chromium from water bodies. *Mater Res Bull* 160:112130
242. Birusanti AB, Espenti CS, and Mala S (2022). Plant-extract-assisted eco-friendly synthesis of iron oxide nanoparticles using cape gooseberry extract and their antibacterial study
243. Yazdani M, Rostamzadeh P, Rahbar M, Alam M, Abbasi K, Tahmasebi E, ... and Yazdani A (2022) The potential application of green-synthesized metal nanoparticles in dentistry: a comprehensive review. *Bioinorg Chem Appl* 2022
244. Wan F, Feng C, Luo K, Cui W, Xia Z, Cheng A (2022) Effect of steam explosion on phenolics and antioxidant activity in plants: a review. *Trends Food Sci Technol* 124:13
245. Cong-Hau N, Anh-Dao LT, Minh-Phuc D, Minh-Huy D, Thanh-Nho N, and Nhu-Trang TT (2022) Assessment of total flavonoid contents and ferric reducing antioxidant power of several Green and oolong tea products in Vietnam. In *AIP Conference Proceedings* 2610(1):060014. AIP Publishing LLC

246. Popoola OO (2022) Phenolic compounds composition and in vitro antioxidant activity of Nigerian *Amaranthus viridis* seed as affected by autoclaving and germination. *Measurement Food* 6:100028
247. Ningthoujam R, Sahoo B, Ghosh P, Shivani A, Ganguli P, and Chaudhuri S (2023) Green production of zero-valent iron nanoparticles using pomegranate peel extracts and its use in lindane degradation. *Nanotechnol Environ Eng* 1–9
248. Lei M, Tang Y, Zhu L, and Tang H (2022) Chemical reductive technologies for the debromination of polybrominated diphenyl ethers: a review. *J Environ Sci*
249. Gibert O, Sánchez D, Cortina JL (2022) Removal of nitrate and pesticides from groundwater by nano zero-valent iron injection pulses under biostimulation and bioaugmentation scenarios in continuous-flow packed soil columns. *J Environ Manage* 321:115965
250. Panić S, Petronijević M, Vukmirović J, Grba N, and Savić S (2023) Green synthesis of nanoscale zero-valent iron aggregates for catalytic degradation of textile dyes. *Catal Lett* 1–15
251. Zhang J, Niu Y, Zhou Y, Ju S, Gu Y (2022) Green preparation of nano-zero-valent iron-copper bimetal for nitrate removal: characterization, reduction reaction pathway, and mechanisms. *Adv Powder Technol* 33(11):103807
252. Jain R, Mendiratta S, Kumar L, Srivastava A (2021) Green synthesis of iron nanoparticles using *Artocarpus heterophyllus* peel extract and their application as a heterogeneous Fenton-like catalyst for the degradation of Fuchsin Basic dye. *Curr Res Green Sustain Chem* 4:100086
253. Lin CC, Cheng YJ (2021) Effectiveness of using nanoscale zero-valent iron and hydrogen peroxide in degrading sulfamethazine in water. *J Taiwan Inst Chem Eng* 118:179–186
254. Torasso N, Vergara-Rubio A, Rivas-Rojas P, Huck-Iriart C, Larrañaga A, Fernández-Cirelli A, ... and Goyanes S (2021) Enhancing arsenic adsorption via excellent dispersion of iron oxide nanoparticles inside poly (vinyl alcohol) nanofibers. *J Environ Chem Eng* 9(1):104664
255. Du C, Xu N, Yao Z, Bai X, Gao Y, Peng L, ... and Zhao J (2022) Mechanistic insights into sulfate and phosphate-mediated hexavalent chromium removal by tea polyphenols wrapped nano-zero-valent iron. *Sci The Total Environ* 850:157996
256. Constantinou D, Samanides CG, Koutsokeras L, Constantiniades G, Vyrides I (2023) Hydrogen generation by soluble CO<sub>2</sub> reaction with zero-valent iron or scrap iron and the role of weak acids for controlling FeCO<sub>3</sub> formation. *Sustain Energy Technol Assess* 56:103061
257. Pan Z, Lin Y, Sarkar B, Owens G, Chen Z (2020) Green synthesis of iron nanoparticles using red peanut skin extract: synthesis mechanism, characterization and effect of conditions on chromium removal. *J Colloid Interface Sci* 558:106–114
258. Wang H, Wang Z, Yue R, Gao F, Ren R, Wei J, ... and Kong Z (2020) Functional group-rich hyperbranched magnetic material for simultaneous efficient removal of heavy metal ions from aqueous solution. *J Hazard Mater* 384:121288
259. Lakkaboyana SK, Khantong S, Asmel NK, Obaidullah S, Kumar V, Kannan K, ... and Yaacob WZW (2021) Indonesian Kaolin supported nZVI (IK-nZVI) used for the efficient removal of Pb (II) from aqueous solutions: kinetics, thermodynamics and mechanism. *J Environ Chem Eng* 9(6):106483
260. Fan C, Chen N, Qin J, Yang Y, Feng C, Li M, Gao Y (2020) Biochar stabilized nano zero-valent iron and its removal performance and mechanism of pentavalent vanadium (V (V)). *Colloids Surf, A* 599:124882
261. Eljamal O, Thompson IP, Maamoun I, Shubair T, Eljamal K, Lueangwattanapong K, Sugihara Y (2020) Investigating the design parameters for a permeable reactive barrier consisting of nanoscale zero-valent iron and bimetallic iron/copper for phosphate removal. *J Mol Liq* 299:112144
262. Das S, and Patra CR (2021) Green synthesis of iron oxide nanoparticles using plant extracts and its biological application. In *Handbook of greener synthesis of nanomaterials and compounds* (pp. 139–170). Elsevier
263. Nobahari M, Shahanipour K, Fatahian S, and Monajemi R (2022) Curcumin-loaded iron oxide nanoparticles coated with sodium alginate and hydroxyapatite and their cytotoxic effects against the HT-29 and MCF-7 cancer cell lines. *Jundishapur J Nat Pharm Prod* 17(1)
264. Isaad J, El Achari A (2018) Synthesis and spectroscopic characterization of azoic dyes based on pyrazolone derivatives catalyzed by an acidic ionic liquid supported on silica-coated magnetite nanoparticle. *J Mol Stru* 1154:557–564
265. Rethinasabapathy M, Kang SM, Haldorai Y, Jonna N, Jankiraman M, Lee GW, ... and Huh YS (2019) Quaternary PtRuFeCo nanoparticles supported N-doped graphene as an efficient bifunctional electrocatalyst for low-temperature fuel cells. *J Ind Eng Chem* 69:285–294
266. Huang X, Xu C, Ma J, Chen F (2018) Ionothermal synthesis of Cu-doped Fe<sub>3</sub>O<sub>4</sub> magnetic nanoparticles with enhanced peroxidase-like activity for organic wastewater treatment. *Adv Powder Technol* 29:796
267. Hoffmann M, Gerlach S, Hoffmann C, Richter N, Hersch N, Csizsár A, ... and Hoffmann B (2022) PEGylation and folic-acid functionalization of cationic lipoplexes—improved nucleic acid transfer into cancer cells. *Front Bioeng Biotechnol* 10
268. Nosrati H, Sefidi N, Sharafi A, Danafar H, Manjili HK (2018) Bovine serum albumin (BSA) coated iron oxide magnetic nanoparticles as biocompatible carriers for curcumin-anticancer drug. *Bioorganic Chem* 76:501–509
269. Harshiny M, AiswaryaDevi S, Matheswaran M (2019) Spiny amaranth leaf extract mediated iron oxide nanoparticles: biocidal photocatalytic propensity, stability, dissolubility and reusability. *Biocatal Agric Biotechnol* 21:101296
270. Ebrahiminezhad A, Taghizadeh S, Ghasemi Y, Berenjian A (2018) Green synthesized nanoclusters of ultra-small zero valent iron nanoparticles as a novel dye removing material. *Sci Total Environ* 621:1527–1532
271. Shahrashoub M, Bakhtiari S, Afroosheh F, Googheri MS (2021) Recovery of iron from direct reduction iron sludge and biosynthesis of magnetite nanoparticles using green tea extract. *Colloids Surf, A* 622:126675
272. Xu Q, Li W, Ma L, Cao D, Owens G, Chen Z (2020) Simultaneous removal of ammonia and phosphate using green synthesized iron oxide nanoparticles dispersed onto zeolite. *Sci Total Environ* 703:135002
273. Selvaraj R, Pai S, Vinayagam R, Varadavenkatesan T, Kumar PS, Duc PA, Rangasamy G (2022) A recent update on green synthesized iron and iron oxide nanoparticles for environmental applications. *Chemosphere* 308:136331
274. Banerjee S, Banerjee I, Dutta M, Pal R (2021) Fabrication of iron nanoparticles using *Leptolyngbya valderiana* and investigation of its Cr (VI) removal potential in the free and biomass associated forms. *Algal Res* 58:102373
275. Sulaiman GM, Tawfeeq AT, Naji AS (2018) Biosynthesis, characterization of magnetic iron oxide nanoparticles and evaluations of the cytotoxicity and DNA damage of human breast carcinoma cell lines, Art cells. *Nanomed Biotechnol* 46(6):1215–1229
276. Rajendran A, Alsawalha M, Alomayri T (2021) Biogenic synthesis of husked rice-shaped iron oxide nanoparticles using coconut pulp (*Cocos nucifera* L.) extract for photocatalytic degradation of Rhodamine B dye and their in vitro antibacterial and anticancer activity. *J Saudi Chem Soc* 25(9):101307

277. Gul AR, Shaheen F, Rafique R, Bal J, Waseem S, Park TJ (2021) Grass-mediated biogenic synthesis of silver nanoparticles and their drug delivery evaluation: a biocompatible anti-cancer therapy. *Chem Eng J* 407:127202
278. Ghotekar S (2019) A review on plant extract mediated biogenic synthesis of CdO nanoparticles and their recent applications. *Asian J Green Chem* 3(2):187–200
279. Pagar T, Ghotekar S, Pagar K, Pansambal S, Oza R (2019) A review on bio-synthesized Co<sub>3</sub>O<sub>4</sub> nanoparticles using plant extracts and their diverse applications. *J Chem Rev* 1(4):260–270
280. Poinern GEJ, and Fawcett D (2019) Sustainable utilization of renewable plant-based food wastes for the green synthesis of metal nanoparticles. In *Harnessing nanoscale surface interactions* (pp. 1–39). Elsevier
281. Zohra E, Ikram M, Omar AA, Hussain M, Satti SH, Raja NI, Ehsan M (2021) Potential applications of biogenic selenium nanoparticles in alleviating biotic and abiotic stresses in plants: a comprehensive insight on the mechanistic approach and future perspectives. *Green Process Synthesis* 10(1):456–475
282. Kowsalya E, MosaChristas K, Balashanmugam P, Tamil SA, Jaquiline CRI (2019) Biocompatible silver nanoparticles/poly (vinyl alcohol) electrospun nanofibers for potential antimicrobial food packaging applications. *Food Packa Shelf Life* 21:100379
283. Menon S, Shrudhi DKS, Agarwal H, Shanmugam VK (2019) Efficacy of biogenic selenium nanoparticles from an extract of ginger towards evaluation on anti-microbial and anti-oxidant activities. *Coll Inter Sci Communi* 29:1–8
284. Shahabadi N, Zendehecheshm S, Khademi F (2021) Selenium nanoparticles: synthesis, in-vitro cytotoxicity, antioxidant activity and interaction studies with ct-DNA and HSA, HHb and Cyt c serum proteins. *Biotechnol Rep* 30:e00615
285. Anukiruthika T, Priyanka S, Moses JA, and Anandharam-akrishnan C (2020) Characterisation of green nanomaterials. *Green Nanomater: Process, Properties, Appl* 43–79
286. Rajeshkumar S, Veena P, Santhiyaa RV (2018) Synthesis and characterization of selenium nanoparticles using natural resources and its applications. In: *Exploring the realms of nature for nanosynth.* (edited by R. Prasad et al.) 63–79
287. Habibi G, Aleyasin Y (2020) Green synthesis of Se nanoparticles and its effect on salt tolerance of barley plants. *Int J Nano Dimens* 11(2):145–157
288. Pyrzyńska K, and Sentkowska A (2021) Biosynthesis of selenium nanoparticles using plant extracts. *J Nanostructure Chem* 1–14
289. Rajagopal G, Nivetha A, Ilango S, Muthudevi GP, Prabha I, Arthimanjur R (2021) Phytosynthesis of selenium nanoparticles using *Azolla pinnata*: evaluation of catalytic properties in oxidation, antioxidant and antimicrobial activities. *J Environ Chem Eng* 9(4):105483
290. Li H, Liu D, Li S, Xue C (2019) Synthesis and cytotoxicity of selenium nanoparticles stabilized by  $\alpha$ -Dglucan from *Castanea mollissima* Blume. *Int J Biol Macromol* 129:818–826
291. Shahbaz M, Akram A, Raja NI, Mukhtar T, Mashwani ZU, Mehak A, ... and Yousaf T (2022) Green synthesis and characterization of selenium nanoparticles and its application in plant disease management: a review. *Pak J Phytopathol* 34(1):189–102
292. Ramezani M, Rad FA, Ghahari S, Ghahari S, Ramezani M (2021) Nano-bioremediation application for environment contamination by microorganism. *Microb Rejuvenation Polluted Environ* 2:349–378
293. Wang X, Zhang D, Qian H, Liang Y, Pan X, Gadd GM (2018) Interactions between biogenic selenium nanoparticles and goethite colloids and consequence for remediation of elemental mercury contaminated groundwater. *Sci Total Env* 613:672–678
294. Laslo V, Pinzaru SC, Zagula G, Kluz M, Vicas SI, Cavalu S (2022) Synergic effect of selenium nanoparticles and lactic acid bacteria in reduction cadmium toxicity. *J Mol Struct* 1247:131325
295. Qiu WY, Wang YY, Wang M, Yan JK (2018) Construction, stability, and enhanced antioxidant activity of pectin-decorated selenium nanoparticles. *Colloids Surf, B* 170:692–700
296. Nastulyavichus A, Kudryashov S, Smirnov N, Saraeva I, Rudenko A, Tolordava E, Ionin A, Romanova Y, Zayarny D (2019) Antibacterial coatings of Se and Si nanoparticles. *Appl Surface Sci* 469:220–225
297. Hosnedlova B, Kepinska M, Skalickova S, Fernandez C, Ruttkay-Nedecky B, Peng Q, Kizek R (2018) Nano-selenium and its nanomedicine applications: a critical review. *Int J Nanomed* 13:2107
298. Yan JK, Qiu W, Wang Y, Wang W, Yang Y (2018) Fabrication and stabilization of biocompatible selenium nanoparticles by carboxylic curdlans with various molecular properties. *Carbohydrate Poly* 179:19–27
299. Tang S, Wang T, Jiang M, Huang C, Lai C, Fan Y, Yong Q (2019) Construction of arabinogalactans/selenium nanoparticles composites for enhancement of the antitumor activity. *Int J Biol Macromol* 128:444–451
300. Al-Qaraleh SY, Al-Zereini WA, Oran SA, Al-Sarayreh AZ, Sa'ed M (2022) Evaluation of the antioxidant activities of green synthesized selenium nanoparticles and their conjugated polyethylene glycol (PEG) form in vivo. *OpenNano* 8:100109
301. Zhang W, Zhang J, Ding D, Zhang L, Muehlmann LA, Deng SE, Zhang W (2018) Synthesis and antioxidant properties of *Lycium barbarum* polysaccharides capped selenium nanoparticles using tea extract. *Art Cells Nanomed Biotechnol* 46(7):1463–1470
302. Rana JVS (2018) Synthesis of selenium nanoparticles using *Allium sativum* extract and analysis of their antimicrobial property against gram positive bacteria
303. Zhong J, Xia Y, Hua L, Liu X, Xiao M, Xu T, Cao H (2019) Functionalized selenium nanoparticles enhance the anti-EV71 activity of oseltamivir in human astrocytoma cell model. *Art cells Nanomed Biotechnol* 47(1):3485–3491
304. Dechtawewat T, Roytrakul S, Yingchutrakul Y, Charoenlappanit S, Siridechadilok B, Limjindaporn T, ... and Noisakran S (2021) Potential phosphorylation of viral nonstructural protein 1 in dengue virus infection. *Viruses* 13(7):1393
305. Shahzamani K, Lashgarian HE, Karkhane M, Ghaffarizadeh A, Ghotekar S, Marzban A (2022) Bioactivity assessments of phyco-assisted synthesized selenium nanoparticles by aqueous extract of green seaweed. *Ulva fasciata* Emerg Mater Res 5(6):1689–1698
306. Saranya T, Ramya S, Kavithaa K, Paulpandi M, Cheon YP, Harish Winster S, Narayanasamy A (2022) Green synthesis of selenium nanoparticles using solanum nigrum fruit extract and its anti-cancer efficacy against triple negative breast cancer. *J Clust Sci* 1–11
307. Veskoukis AS (2020) Redox signaling and antioxidant defense in pathogenic microorganisms: a link to disease and putative therapy. In *Pathology* (pp. 87–95). Academic Press
308. Johnson J, Shanmugam R, Lakshmi T (2022) A review on plant-mediated selenium nanoparticles and its applications. *J Popul Ther Clin Pharmacol* 28(2):e29–e40
309. Menon S, Ks SD, Santhiya R, Rajeshkumar S, Kumar V (2018) Selenium nanoparticles: a potent chemotherapeutic agent and an elucidation of its mechanism. *Colloids Surf, B* 170:280–292
310. Morshed RA, Young JS, Hervey-Jumper SL, Berger MS (2019) The management of low-grade gliomas in adults. *J Neurosurg Sci* 63(4):450–457
311. Cui D, Liang T, Sun L, Meng L, Yang C, Wang L, Li Q (2018) Green synthesis of selenium nanoparticles with extract of *hawthorn* fruit induced HepG2 cells apoptosis. *Pharma Biol* 56(1):528–534

312. Ali A, Wu H, Ponnampalam EN, Cottrell JJ, Dunshea FR, Suleria HA (2021) Comprehensive profiling of most widely used spices for their phenolic compounds through LC-ESI-QTOF-MS2 and their antioxidant potential. *Antioxidants* 10(5):721
313. Sathiyavimal S, Vasantharaj S, Veeramani V, Saravanan M, Rajalakshmi G, Kaliannan T, ... and Pugazhendhi A (2021) Green chemistry route of biosynthesized copper oxide nanoparticles using *Psidium guajava* leaf extract and their antibacterial activity and effective removal of industrial dyes. *J Environ Chem Eng* 9(2):105033
314. Li Z, and Sun Z (2022) In vitro anti-human gastric cancer property of silver nanoparticles green-synthesized by *Vitis vinifera* leaf aqueous extract. *Inorg Chem Commun* 109832
315. Shnoudeh AJ, Hamad I, Abdo RW, Qadumii L, Jaber AY, Surchi HS, and Alkelany SZ (2019) Synthesis, characterization, and applications of metal nanoparticles. In *Biomaterials and bionanotechnology* (pp. 527–612). Academic Press
316. Murthy HC, Desalegn T, Kassa M, Abebe B, and Assefa T (2020) Synthesis of green copper nanoparticles using medicinal plant *hagenia abyssinica* (Brace) JF. Gmel. leaf extract: antimicrobial properties. *J Nanomater* 2020
317. Jahan I, and İşildak İ (2020) Microwave irradiation system for a rapid synthesis of non-toxic metallic copper nanoparticles from green tea. *Trakya Univ J Nat Sci*
318. Palecek M (2020) The evolution of ‘culture’: juggling a concept. *Anthropological Theory* 20(1):53–76
319. Maurya KK, Rawat A, Jha G (2020) Smart materials and electro-mechanical impedance technique: a review. *Mater Today: Proc* 33:4993–5000
320. Mohamed EA (2020) Green synthesis of copper copper oxide nanoparticles using the extract of seedless dates. *Heliyon* 6(1):e03123
321. Chandraker SK, Lal M, Ghosh MK, Tiwari V, Ghorai TK, Shukla R (2020) Green synthesis of copper nanoparticles using leaf extract of *Ageratum houstonianum* Mill. and study of their photocatalytic and antibacterial activities. *Nano Exp* 1(1):010033
322. Ismail M, Gul S, Khan MI, Khan MA, Asiri AM, Khan SB (2019) Green synthesis of zerovalent copper nanoparticles for efficient reduction of toxic azo dyes congo red and methyl orange. *Green Process Synth* 8(1):135–143
323. Jamdade DA, Rajpali D, Joshi KA, Kitture R, Kulkarni AS, Shinde VS, Ghosh S (2019) *Gnidia glauca*-and *Plumbago zeylanica*-mediated synthesis of novel copper nanoparticles as promising antidiabetic agents. *Adv Pharmacol Sci*
324. Kaur K, Kaushal S (2019) Phytochemistry and pharmacological aspects of *Syzygium aromaticum*: a review. *J Pharmacogn Phytochem* 8(1):398–406
325. Pariona N, Mtz-Enriquez AI, Sánchez-Rangel D, Carrión G, Paraguay-Delgado F, Rosas-Saito G (2019) Green-synthesized copper nanoparticles as a potential antifungal against plant pathogens. *RSC Adv* 9(33):18835–18843
326. Nagore P, Ghotekar S, Mane K, Ghoti A, Bilal M, Roy A (2021) Structural properties and antimicrobial activities of *Polyalthia longifolia* leaf extract-mediated CuO nanoparticles. *Bio Nano Science* 11:579–589
327. Marzban A, Mirzaei SZ, Karkhane M, Ghotekar SK, Danesh A (2022) Biogenesis of copper nanoparticles assisted with seaweed polysaccharide with antibacterial and antibiofilm properties against methicillin-resistant *Staphylococcus aureus*. *J Drug Deliv Sci Technol* 74:103499
328. Tamil Elakkiya V, Meenakshi RV, Senthil Kumar P, Karthik V, Ravi Shankar K, Sureshkumar P, Hanan A (2022) Green synthesis of copper nanoparticles using *Sesbania aculeata* to enhance the plant growth and antimicrobial activities. *Int J Environ Sci Technol* 19:1–10
329. Jahan I, Erci F, Isildak I (2021) Facile microwave-mediated green synthesis of non-toxic copper nanoparticles using *Citrus sinensis* aqueous fruit extract and their antibacterial potentials. *J Drug Deliv Sci Technol* 61:102172
330. Edis Z, Haj Bloukh S, Ashames A, and Ibrahim M (2019) Copper-based Nanoparticles, their chemistry and Antibacterial properties: a review. *Chem Clean Healthy Planet* 401–428

**Publisher's Note** Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Springer Nature or its licensor (e.g. a society or other partner) holds exclusive rights to this article under a publishing agreement with the author(s) or other rightsholder(s); author self-archiving of the accepted manuscript version of this article is solely governed by the terms of such publishing agreement and applicable law.