


 Cite this: *RSC Adv.*, 2021, 11, 4810

# Synthesis of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures for enhanced photocatalytic reduction of U(vi) in water

 Yuelin Liu,<sup>ab</sup> Shanshan Wu,<sup>c</sup> Jun Liu,<sup>id d</sup> Shuibo Xie<sup>\*ce</sup> and Yingjiu Liu<sup>c</sup>

Photocatalytic technology is a valid solution for the remediation of wastewater containing uranium. In this study, the synthesis of Z-scheme g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> catalysts was made by a thermal synthetic approach for photocatalytic U(vi) reduction. The characterization results revealed the successful synthesis of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures. The g-C<sub>3</sub>N<sub>4</sub> surface was uniformly coated with TiO<sub>2</sub> nanoparticles. The depletion of U(vi) in water evaluated the photocatalytic activity of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> under UV light irradiation. The photocatalytic tests showed that g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> exhibited more effective photocatalytic activity than the raw materials (1.64 and 56.97 times higher than TiO<sub>2</sub>(P25) and g-C<sub>3</sub>N<sub>4</sub>, respectively). Besides, a pseudo-first-order model was followed by the experimental kinetic data for the photocatalytic process. Moreover, g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> still presented high photocatalytic activity after four reacting cycles. Based on these experiment results, the improved photocatalytic activity could be attributed to the Z-scheme mechanism, which decreased the recombination of photo-produced electrons and holes. The synthesis of these g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanomaterials provides a facile and inexpensive method for treating wastewater containing U(vi).

Received 21st December 2020

Accepted 2nd January 2021

DOI: 10.1039/d0ra10694a

[rsc.li/rsc-advances](https://rsc.li/rsc-advances)

## 1. Introduction

As nuclear energy develops, uranium increasingly has entered the water environment, which seriously threatens human health.<sup>1</sup> Therefore, the treatment of wastewater containing uranium has become a research focus. The primary idea to solve this problem is to convert soluble U(vi) into insoluble U(IV) to separate it from the water.<sup>2</sup> Under light illumination, photocatalysts can produce electrons and holes for redox reactions. It has been proven to be an effective approach of treating wastewater containing U(vi). Compared with traditional treatment methods, photocatalysis has the advantages of simple operation, low energy consumption and no secondary pollution.<sup>3</sup>

The photocatalyst is the main point in a photocatalytic reaction process. As the most classic photocatalyst, TiO<sub>2</sub> has attracted the attention of researchers for its high activity and stability.<sup>4</sup> TiO<sub>2</sub> commodity P25 is the only photocatalyst used in commercials currently. However, the poor visible light responsiveness limits its further applications.<sup>5,6</sup> Recently, various new photocatalysts have been developed such as graphitic carbon nitride (g-C<sub>3</sub>N<sub>4</sub>), iron oxide (α-Fe<sub>3</sub>O<sub>4</sub>), ZnO and noble metals.<sup>7–12</sup>

Among them, g-C<sub>3</sub>N<sub>4</sub> has been a new focus issue in the photocatalytic field because of its narrow bandgap, which can increase the range of light absorption. Moreover, researchers have tried to improve the photocatalytic performance by modifying the photocatalysts. At present, there are three main modification methods for catalysts, such as morphology control, element doping and a variety of materials for composites.<sup>13,14</sup> Among these modification methods, composite materials could avoid many disadvantages and limitations of a single semiconductor in a photocatalytic process. In many mechanisms of composite, the Z-scheme photocatalytic mechanism was proposed on a composite, whereby the photo-produced electrons (with less potential energy) of a semiconductor photocatalyst and the holes (with less potential energy) of another semiconductor were recombined through an interface connection, thus leaving the photo-produced electrons with higher potential energy and holes on their respective semiconductors to form active sites.<sup>15,16</sup> It could efficiently separate photo-produced electrons and holes, thereby inhibiting their recombination.<sup>17,18</sup> According to an authoritative report, there are no more than 40 studies about the photocatalytic reduction of U(vi).<sup>19</sup> Among these reports are even fewer reports on the application of Z-scheme photocatalyst to reduce U(vi).<sup>20–23</sup> However, there have been numerous reports about the application of Z-scheme photocatalysts to remove other pollutants in water.<sup>24,25</sup> Therefore, the research on the application of Z-scheme photocatalysts for photocatalytic reduction of U(vi) is innovative. Moreover, the research on the mechanism of U(vi) reduction by the Z-scheme photocatalyst would help increase photocatalytic efficiency.

<sup>a</sup>Key Discipline Laboratory for National Defence for Biotechnology in Uranium Mining and Hydrometallurgy, University of South China, Hengyang 421001, China

<sup>b</sup>School of Civil Engineering, Hunan University of Technology, Zhuzhou 412007, China

<sup>c</sup>Hunan Province Key Laboratory of Pollution Control and Resources Reuse Technology, University of South China, Hengyang 421001, China. E-mail: xiesbmr@263.net

<sup>d</sup>Hunan Key Laboratory of Biomedical Nanomaterials and Devices, School of Life Science and Chemistry, Hunan University of Technology, Zhuzhou 412007, China

<sup>e</sup>School of Civil Engineering, University of South China, Hengyang 421001, China



In this paper,  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  composites were presented for photocatalytic  $\text{U}(\text{vi})$  reduction application.  $\text{TiO}_2$  (P25) nanoparticles were coated on  $g\text{-C}_3\text{N}_4$  to form a Z-scheme photocatalyst by a thermal synthetic method. The morphology and structure characterizations were presented subsequently.  $\text{U}(\text{vi})$  reduction in aqueous was employed for evaluating the photocatalytic activities of this  $g\text{-C}_3\text{N}_4/\text{TiO}_2$ . Moreover, the Z-scheme photocatalytic mechanism of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  was investigated, which could decrease the recombination of photo-produced electrons and holes.

## 2. Experimental

### 2.1 Preparation of material

Chemical reagents applied in this research were all at analytical grade without further purification. All the reagents were domestic. The  $\text{TiO}_2$  particle used in this study was P25, which was purchased from King Chemical. Standard  $\text{U}(\text{vi})$  solution was prepared by dissolving  $\text{U}_3\text{O}_8$  (99%) with  $\text{HCl}$  and  $\text{H}_2\text{O}_2$  under heating conditions. The porcelain crucible containing some urea was placed in a muffle furnace, and the temperature was raised from room temperature to  $600\text{ }^\circ\text{C}$  for 2 h, and then cooled down naturally. The ceramic crucible was removed, and its content was grounded into powder to obtain the yellow  $g\text{-C}_3\text{N}_4$  photocatalyst. A certain amount of  $\text{TiO}_2$  and  $g\text{-C}_3\text{N}_4$  were placed into three beakers. The surface-mass ratio of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  was maintained at 1 : 1, 2 : 1 and 3 : 1, marked as  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$ ,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-2}$  and  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-3}$ , respectively. The raw materials were then added into deionized water, stirred evenly, and ultrasonic mixed for 15 min until the powder had completely dispersed. The suspension was transferred into a ceramic crucible and heated to powder form at  $80\text{ }^\circ\text{C}$  for 5 h. Then, the ceramic crucible was calcined at  $400\text{ }^\circ\text{C}$  for 2 h in a muffle furnace. After being cooled to indoor temperature, the ceramic

crucible was removed and its content grounded into powder to obtain the composite photocatalyst.

### 2.2 Characterization

The characterization was performed on the  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$  sample. X-ray diffraction (XRD) characterized the crystal structure of the photocatalyst by applying a D/MAX-RB diffractometer (Bruker, D8 advance, Germany) and adopting  $\text{Cu K}\alpha$  radiation (ranging from  $5^\circ$  to  $95^\circ$ , Step length:  $0.01^\circ$ , each step 0.1 s). Scan electron microscopy (SEM), which was tested by a SUPRATM55 high-resolution field emission scanning electron microscope (operating voltage of 2 kV, standard aperture diaphragm of  $30\text{ }\mu\text{m}$ , SE2 secondary electron detector imaging) (Zeiss, Germany), analyzed the surface morphology of the photocatalyst. X-ray photoelectron spectroscopy (XPS, Thermo Scientific, Escalab 250Xi, UK) was used to perform the surface elemental analysis of the photocatalyst by applying an ESCALAB II XPS system. UV-vis Diffuse Reflectance Spectra (DRS) was examined to obtain the optical absorption property of the photocatalyst (Shimadzu, UV-3600, Japan, equipped with an integrating sphere). The specific surface area was calculated by the Brunauer–Emmett–Teller (BET) method (Micromeritics ASAP 2460 instrument at 77 K with  $\text{N}_2$  as absorbate). A Xe lamp, as an excitation source, was used to record the PL spectra on a fluorescence spectrophotometer (FS5, Edinburgh Instruments Ltd., UK).

### 2.3 Photocatalytic activities of photocatalysts

The photocatalytic reduction of  $\text{U}(\text{vi})$  solution evaluated the photocatalytic activities of the photocatalysts prepared. In the photocatalytic process, 0.02 g of as-prepared photocatalysts was added into 50 mL of  $\text{U}(\text{vi})$  solution (initial concentration of  $10\text{ mg L}^{-1}$ ). Moreover, 2 mL of methanol was added into the




Fig. 1 (a) XRD patterns of  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$  and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  prepared, the labels of ♥ and ♣ are the corresponding peaks of anatase  $\text{TiO}_2$  and rutile  $\text{TiO}_2$ , respectively; (b) the complete XPS spectra of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$ , main peaks of Ti 2p (c), C 1s (d), N 1s (e) and O 1s (f) for  $g\text{-C}_3\text{N}_4/\text{TiO}_2$ .

suspension, which was used as the hole scavenger in the reaction. The mixture was ultrasonic oscillated for 30 min to disperse the photocatalysts. The pH of the suspension was adjusted to about 5.0 by hydrochloric acid and sodium hydroxide. For the elimination of the dissolved oxygen and realization of the adsorption–desorption equilibrium under anaerobic conditions, the suspension was bubbled with nitrogen (99.99%) for 30 min in the dark. Then, the mixture was illuminated by an ultraviolet light of 500 W. The photocatalytic process was carried out in the photocatalytic apparatus (GG-GHX-V, Shanghai Guigo Industrial Co. Ltd). Arsenazo III Spectrophotometric Method, used after centrifugation at regular intervals, determined the  $U(\text{VI})$  concentration of the mixture. The following expression was used to calculate the removal ratios ( $R_{U(\text{VI})}$ ) of  $U(\text{VI})$ :

$$R_{U(\text{VI})} = 1 - C_t/C_0 = (A_0 - A_t)/A_0 \times 100\%$$

where  $R_{U(\text{VI})}$  is the removal ratios of  $U(\text{VI})$ ;  $C_t$  and  $C_0$  are the concentration of  $U(\text{VI})$  at 0 and  $t$  time; and  $A_0$  and  $A_t$  are the absorbance intensity corresponding to 0 and  $t$  time, respectively. The stability of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  was assessed by reusing the photocatalyst in four repeated tests for the decrease of  $U(\text{VI})$  under the same conditions.

### 3. Results and discussion

#### 3.1 Structural characterization of $g\text{-C}_3\text{N}_4/\text{TiO}_2$ nanostructures

The characterization of the as-obtained  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$  (P25) and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures were made by XRD and XPS techniques. The XRD patterns for these nanostructures are presented in Fig. 1a. In the XRD pattern of pure  $g\text{-C}_3\text{N}_4$  (blue line), the significant diffraction peaks appeared at positions of  $13.1^\circ$  and  $27.3^\circ$ , and are indexed to (100) and (002) planes of  $g\text{-C}_3\text{N}_4$ . These are attributed to the planar, which repeats cell structure and sandwich stack reflection of  $g\text{-C}_3\text{N}_4$ .<sup>26,27</sup> The average interlayer distances were 0.675 nm and 0.326 nm, respectively, calculated by the Scherrer equation. After compositing with  $\text{TiO}_2$  (P25), the significant peaks of  $g\text{-C}_3\text{N}_4$  still had decreased peak intensity. The apparent diffraction peaks of anatase  $\text{TiO}_2$  and rutile  $\text{TiO}_2$  are shown in the  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures (red line), where most of these peaks displayed (101), (004), (200), (105), (211), (204), (116), (220) and (215) planes of anatase  $\text{TiO}_2$ ,<sup>28</sup> while other peaks were attributed to (110), (101), (111) and (220) planes of rutile  $\text{TiO}_2$ . These peaks are according to the XRD results of pure P25 (black line).

Moreover, Fig. 1b–f show the XPS spectra of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures. In Fig. 1b, the full XPS spectrum presented all




Fig. 2 SEM images of pure  $g\text{-C}_3\text{N}_4$  (a and b),  $\text{TiO}_2$  (P25, c and d) and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures (e and f).

the peaks (C 1s, N 1s, Ti 2p, O 1s) of g-C<sub>3</sub>N<sub>4</sub> plus TiO<sub>2</sub> nano-materials. Fig. 1c–f showed high-resolution XPS spectra of Ti 2p, C 1s, N 1s and O 1s. After employing the XPS-peak-differentiation-imitating analysis method, Ti 2p<sub>1/2</sub> and Ti 2p<sub>3/2</sub> peaks appeared in Fig. 1c. C 1s and N 1s further confirmed the successful synthesis of g-C<sub>3</sub>N<sub>4</sub> (Fig. 1d and e). The two C 1s that peaked at 284.8 and 288.0 eV, respectively, were caused by an aromatic carbon atom and C–N–C coordination (Fig. 1d). The O 1s identified that the TiO<sub>2</sub> existed in these nanostructures (Fig. 1f). Thus, the generation of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures can be confirmed by these structural characterizations.

### 3.2 Morphology of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures

The SEM images of as-synthesized pure g-C<sub>3</sub>N<sub>4</sub>, TiO<sub>2</sub> (P25) and g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures are presented in Fig. 2. The g-C<sub>3</sub>N<sub>4</sub> polymer with a blocky structure was gathered by many irregularly shaped wrinkled sheets, as displayed in Fig. 2a. These blocky structures with holes of g-C<sub>3</sub>N<sub>4</sub> polymers could be reported as per the magnified SEM image of g-C<sub>3</sub>N<sub>4</sub> (Fig. 2b). These holes may give the g-C<sub>3</sub>N<sub>4</sub> many active reaction sites for various applications. The SEM images of the pure TiO<sub>2</sub> (P25) are shown in Fig. 2c and d. As shown in these images, the particle size of TiO<sub>2</sub> (P25) was too small (less than 100 nm) compared with g-C<sub>3</sub>N<sub>4</sub>. It was more favorable for TiO<sub>2</sub> to disperse on the

surface of g-C<sub>3</sub>N<sub>4</sub>. After compositing TiO<sub>2</sub> with g-C<sub>3</sub>N<sub>4</sub>, TiO<sub>2</sub> nanoparticles uniformly adhered to g-C<sub>3</sub>N<sub>4</sub> (Fig. 2e and f). This combination could promote the charge transfer between g-C<sub>3</sub>N<sub>4</sub> and TiO<sub>2</sub> by the Z-scheme route. However, as presented in Fig. 2e, there still certain parts of g-C<sub>3</sub>N<sub>4</sub> that were uncovered due to the imprecise control of the hydrothermal method. This result further displays the successful synthesis of the g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures.

### 3.3 Surface area of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures

Adsorption and desorption experiments by N<sub>2</sub> were carried out at 77 K, and N<sub>2</sub> isotherms have been applied to calculate the specific surface area by the multi-point BET method. As shown in Fig. 3a, the shape of the isotherm with two capillary condensation steps is like a type IV isotherm according to the IUPAC classification, indicating the presence of mesopores. The shape of the hysteresis loop was of the type H3, and the hysteresis loop shifts at high relative pressures ( $P/P_0$ ) between 0.8 and 1.0, which suggests a mesoporous structure. Mesoporosity is typical of wrinkled, sheet-like particles, and this result is consistent with SEM images. This mesopore size distribution was confirmed by the pore size distributions shown in the inset in Fig. 3a. The average pore diameter of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures is estimated as 37 Å, which suggests the




Fig. 3 (a) N<sub>2</sub> adsorption–desorption isotherm of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures. Inset: pore size distribution of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures; (b) UV-vis diffuse reflectance spectra of pure g-C<sub>3</sub>N<sub>4</sub>, TiO<sub>2</sub> (P25) and g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures; (c) plots of the  $(Ah\nu)^2$  versus  $(h\nu)$  for pure g-C<sub>3</sub>N<sub>4</sub>, TiO<sub>2</sub> (P25) and g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures, (d) PL spectra of g-C<sub>3</sub>N<sub>4</sub>, TiO<sub>2</sub> (P25) and g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> nanostructures.



existence of mesopores. The BET specific area of the  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures was  $36.2\text{ m}^2\text{ g}^{-1}$ , which is between  $g\text{-C}_3\text{N}_4$  ( $29.4\text{ m}^2\text{ g}^{-1}$ ) and  $\text{TiO}_2$  ( $51.6\text{ m}^2\text{ g}^{-1}$ ).

### 3.4 Optical properties of $g\text{-C}_3\text{N}_4/\text{TiO}_2$ nanostructures

Firstly, UV-vis diffuse reflectance spectroscopy (DRS) was used to investigate the optical properties of pure  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$  (P25) and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures. As shown in Fig. 3b, the significant absorption peak of  $g\text{-C}_3\text{N}_4$  was at  $\sim 398\text{ nm}$ , the absorption end of  $g\text{-C}_3\text{N}_4$  was  $\sim 450\text{ nm}$  (black line). The pure  $\text{TiO}_2$  (P25) showed a high UV-light absorption, and the absorption edge was  $\sim 400\text{ nm}$  (red line). After compositing  $\text{TiO}_2$  with  $g\text{-C}_3\text{N}_4$ , the absorption edge was located on the range between  $400$  and  $450\text{ nm}$ , and the absorption intensity in the UV region was lower than pure  $\text{TiO}_2$  but higher than  $g\text{-C}_3\text{N}_4$  (blue line), which reveals a successful synthesis of the  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures. According to the plot of  $(Ah\nu)^2$  versus  $(h\nu)$ , as shown in Fig. 3c, the bandgap energies ( $E_g$ ) of pure  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$  (P25) and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  have been estimated to be  $2.7\text{ eV}$ ,  $3.2\text{ eV}$  and  $2.75\text{ eV}$ , respectively. The calculation results show that the bandgap width of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures was very close to that of  $g\text{-C}_3\text{N}_4$ , which is narrower than that of  $\text{TiO}_2$  (P25).

PL spectra were the principal approach to test the efficiency of charge separation during the photocatalytic process.<sup>16</sup> The release of energy in the form of PL emission was made while recombining electron-hole pairs. Therefore, greater PL

intensity shows a greater recombination rate of charge carriers. Hence, the PL spectra of pure  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$  (P25) and  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures were performed in Fig. 3d. For pure  $g\text{-C}_3\text{N}_4$  and  $\text{TiO}_2$  (P25), there is a relatively strong emission peak at  $\sim 452\text{ nm}$ , which is displayed in the PL spectra (black line and red line), indicating that there are many photo-produced electrons combined with holes. A large amount of energy is released, which is detected by the PL spectra. For  $g\text{-C}_3\text{N}_4/\text{TiO}_2$ , there is no prominent emission peak in PL spectra (blue line). This phenomenon indicates the decreased recombination efficiency of photo-produced electrons and holes, which enhanced the photocatalytic performance of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  because of its Z-scheme structure.<sup>29</sup>

### 3.5 Photocatalytic reduction of $\text{U}(\text{vi})$

$\text{U}(\text{vi})$  reduction was used to evaluate the photocatalytic activity of the photocatalysts. Fig. 4a and b show the results. Without photocatalysts, there is no obvious change of  $\text{U}(\text{vi})$  concentration, showing  $\text{U}(\text{vi})$  stability under light and negligible self-photocatalysis process. Under the condition of adding photocatalyst, the  $\text{U}(\text{vi})$  concentration reduces slightly after the dark reaction reaches adsorption equilibrium in the first 30 min. It is indicated that photocatalyst has a certain adsorption ability for  $\text{U}(\text{vi})$ . For pure  $g\text{-C}_3\text{N}_4$ ,  $\text{U}(\text{vi})$  concentration does not decline obviously after the light is turned on, which shows that the photocatalytic effect of pure  $g\text{-C}_3\text{N}_4$  for  $\text{U}(\text{vi})$  is greatly restricted.








Fig. 4 (a) The variation of  $\text{U}(\text{vi})$  during the reaction; (b) the rate constant ( $k$ ) of  $\text{U}(\text{vi})$  reduction; (c) cycling runs in the photocatalytic reduction of  $\text{U}(\text{vi})$ ; (d) XPS spectrum of  $\text{U} 4f$  for the  $\text{U}$  element on the surface of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  before (top) and after (bottom) reduction process.

For  $\text{TiO}_2$ ,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$ ,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-2}$  and  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-3}$ , the  $\text{U}(\text{vi})$  concentration drop rapidly in the first 5 min after the light is turned on. The  $\text{U}(\text{vi})$  concentration decreases gradually in the following 20 min. As the most active photocatalyst,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$  removed >99% of  $\text{U}(\text{vi})$  after illumination for 25 min. The reaction kinetics for the removal of  $\text{U}(\text{vi})$  quantitatively was researched by pseudo-first-order kinetics model. As expressed in the formula  $-\ln(C_0/C_t) = kt$ , where  $k$  stands for the apparent reaction rate constant,  $C_0$  and  $C_t$  are the concentrations of aqueous  $\text{U}(\text{vi})$  at reaction time  $t_0$  and  $t$ , respectively. As displayed in Fig. 4b, the apparent rate constants  $k$  for  $g\text{-C}_3\text{N}_4$ ,  $\text{TiO}_2$ ,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$ ,  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-2}$  and  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-3}$  were calculated to be 0.0033, 0.1359, 0.2222, 0.1020 and 0.1073  $\text{min}^{-1}$ , respectively. As the maximum in the series photocatalysts, the  $k$  values of  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$  was 1.64 times of  $\text{TiO}_2$  (the maximum of raw material), indicating that the photocatalytic performance has been significantly improved through the material composite.

The long-time stability of a photocatalyst during the photocatalytic reaction is significant for practical use. Fig. 4c shows the recycling usability of four times for  $g\text{-C}_3\text{N}_4/\text{TiO}_2\text{-1}$  in the photocatalytic process. After each cycle, centrifugation collected and separated the photocatalysts from the suspension aqueous. Photocatalysts were ultrasonic oscillated to peel off surface sediments and then washed by deionized water. Subsequently, the drying of photocatalysts was carried out at 60 °C before the next recycle. As shown in Fig. 4c, the curves for each cycle were very similar. The final removal rate of every cycle was more than 99%, which indicates the stable photocatalytic activity of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  after several recycles.

XPS spectra of U element on  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures were performed for verification of the reduction process. Fig. 4d shows higher resolution XPS spectra of U 4f (after and pre-reduction). After the reduction of  $\text{U}(\text{vi})$  into  $\text{U}(\text{iv})$ , the peak positions of U 4f<sub>5/2</sub> and 4f<sub>7/2</sub> were changed. In the bottom red curve, the peak-differentiating technique was used to obtain four peaks located at 379.6, 381.9, 390.4, and 391.3 eV. The two peaks at 381.9 and 391.3 eV originated from  $\text{U}(\text{vi})$ , these positions were matched well with that of  $\text{U}(\text{vi})$  sample without reduction (up to black line), and peaks at 379.6 and 390.4 eV belong to  $\text{U}(\text{iv})$ . The above results showed that most of the  $\text{U}(\text{vi})$  on the surface of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures were reduced into  $\text{U}(\text{iv})$ .<sup>30</sup>



Scheme 1 Proposed mechanistic steps for  $\text{U}(\text{vi})$  photocatalytic reduction.

### 3.6 Reduction mechanisms of $\text{U}(\text{vi})$

After the above results and discussion, Fig. 5 proposed the possible mechanism of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  photocatalytic reduction of  $\text{U}(\text{vi})$ .  $g\text{-C}_3\text{N}_4$  and  $\text{TiO}_2$  formed their photo-produced electrons and holes, respectively, in their internal parts under light irradiation. According to the relative position of VB and CB in  $g\text{-C}_3\text{N}_4$  and  $\text{TiO}_2$ , the photo-produced electrons produced by  $\text{TiO}_2$  migrate to the interface of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  and integrate holes in the part of  $g\text{-C}_3\text{N}_4$ . The photo-produced electrons produced by  $g\text{-C}_3\text{N}_4$  are used as a reduction site to reduce the  $\text{U}(\text{vi})$  into  $\text{U}(\text{iv})$ . The holes in the VB of  $\text{TiO}_2$  oxidize methanol into  $\text{CO}_2$  and  $\text{H}_2\text{O}$  as oxidation sites. In this way, the photo-produced electrons and holes involved in the redox reaction are reacted on their respective semiconductors. The recombination of photo-produced electrons and holes is effectively avoided, increasing photocatalytic efficiency.<sup>31</sup> At present, there are two mainstream opinions about the reduction process of  $\text{U}(\text{vi})$ .<sup>19</sup> In the first opinion, the reduction process of  $\text{U}(\text{vi})$  consists of two steps,<sup>32</sup> which is shown as eqn (1)–(3) in Scheme 1.  $\text{U}(\text{vi})$  is reduced to  $\text{U}(\text{v})$  by photo-produced electrons in the first step (eqn (1)).  $\text{U}(\text{v})$  can spontaneously react to  $\text{U}(\text{vi})$  and  $\text{U}(\text{iv})$  (eqn (2)), which follows the principle of electronic equilibrium. Moreover,  $\text{U}(\text{v})$  can be further reduced to  $\text{U}(\text{iv})$  by photo-produced electrons (eqn (3)). Another opinion indicated that  $\text{U}(\text{vi})$  could be reduced to  $\text{U}(\text{iv})$  directly just as eqn (4) in Scheme 1.<sup>33</sup> As displayed in Fig. 5, the reduction potential of CB on  $g\text{-C}_3\text{N}_4$  ( $E^0 = -1.3 \text{ eV}$ ) was more passive than the decreased potential for a series of reactions. Theoretically, the reduction reaction can proceed smoothly.

## 4. Conclusions

A thermal synthetic approach was proposed for the synthesis of Z-scheme catalyst  $g\text{-C}_3\text{N}_4/\text{TiO}_2$ . According to the results of characterization, a successful synthesis of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures was revealed. By comparing with raw materials,  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  displayed much greater photocatalytic activities for the reduction of radioactive  $\text{U}(\text{vi})$  under the condition of UV light illumination (1.64 times higher of  $\text{TiO}_2$  and 56.97 times of  $g\text{-C}_3\text{N}_4$ ). More than 99% of  $\text{U}(\text{vi})$  was removed by  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  after illumination for 25 min. XPS analyses showed that most of the  $\text{U}(\text{vi})$  on the surface of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  were reduced into  $\text{U}(\text{iv})$ . After the reaction kinetics analysis, the photocatalytic reaction follows pseudo-first-order kinetics. Moreover, the  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  displayed good stability after four reused tests. Its Z-scheme




Fig. 5 The diagram of the proposed mechanism of  $g\text{-C}_3\text{N}_4/\text{TiO}_2$  nanostructures under simulated sunlight irradiation.

structure, which decreased recombination efficiency of photo-produced electrons and holes, could cause the enhancement of the photocatalytic activities of g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub>. In summary, the g-C<sub>3</sub>N<sub>4</sub>/TiO<sub>2</sub> practically represent a suitable in U(VI) photocatalytic reduction.

## Author contributions

Yuelin Liu contributed to the conception and design of the study. Shanshan Wu contributed to the acquisition of data. Yuelin Liu and Jun Liu contributed to the analysis and interpretation of data. Yuelin Liu contributed to drafting the manuscript. Shuibo Xie and Jun Liu contributed to revising it critically for important intellectual content. Shuibo Xie and Yingjiu Liu contributed to the reagents/materials/analysis tools.

## Conflicts of interest

The authors declare no conflict of interest.

## Acknowledgements

The authors are grateful to the Laboratory of Pollution Control and Resource Technology and the Department of Municipal Engineering at the University of South China for providing the necessary facilities for the research. This research was funded by the National Natural Science Foundation of China (NO. 11475080). Natural Science Foundation of Hunan Province (No. 2019JJ50127).

## References

- 1 M. J. Manos, *et al.*, Layered Metal Sulfides Capture Uranium from Seawater, *J. Am. Chem. Soc.*, 2012, **134**, 16441–16446.
- 2 Y. Liu, *et al.*, Removal of uranium(VI) from aqueous solutions by CMK-3 and its polymer composite, *Appl. Surf. Sci.*, 2013, **285**, 258–266.
- 3 H. Yu, *et al.*, The synergistic effect of graphitic N and pyrrolic N for the enhanced photocatalytic performance of nitrogen-doped graphene/TiO<sub>2</sub> nanocomposites, *Appl. Catal., B*, 2016, 810–817.
- 4 J. Yu, *et al.*, Enhanced Photocatalytic CO<sub>2</sub> Reduction Activity of Anatase TiO<sub>2</sub> by Co exposed {001} and {101} Facets, *J. Am. Chem. Soc.*, 2014, **136**, 8839–8842.
- 5 N. Bao, *et al.*, Self-Templated Synthesis of Nanoporous CdS Nanostructures for Highly Efficient Photocatalytic Hydrogen Production under Visible Light, *Cheminform.*, 2008, **39**, 110–117.
- 6 L. A. Silva, *et al.*, Photocatalytic Hydrogen Production with Visible Light over Pt-Interlinked Hybrid Composites of Cubic-Phase and Hexagonal-Phase CdS, *J. Phys. Chem. C*, 2008, **112**, 12069–12073.
- 7 J. Wen, *et al.*, A review on g-C<sub>3</sub>N<sub>4</sub>-based photocatalysts, *Appl. Surf. Sci.*, 2017, **391**, 72–123.
- 8 Y. Guo, *et al.*, Adsorption and photocatalytic reduction activity of uranium(VI) on zinc oxide/rectorite composite enhanced with methanol as sacrificial organics, *J. Radioanal. Nucl. Chem.*, 2016, 883–890.
- 9 A. Lassoued, *et al.*, Photocatalytic degradation of methylene blue dye by iron oxide (alpha-Fe<sub>2</sub>O<sub>3</sub>) nanoparticles under visible irradiation, *J. Mater. Sci.: Mater. Electron.*, 2018, **29**, 8142–8152.
- 10 Y. Guo, *et al.*, Enhanced photocatalytic reduction activity of Uranium(VI) from aqueous solution using Fe<sub>2</sub>O<sub>3</sub>-Graphene oxide nanocomposite, *Dalton Trans.*, 2017, **46**, 14762–14770.
- 11 J. Liu, *et al.*, Recent progress on photocatalytic heterostructures with full solar spectral responses, *Chem. Eng. J.*, 2020, **393**, 124719.
- 12 J. Liu, *et al.*, Catalytic Application and Mechanism Studies of Argentite Chloride Coupled Ag/Au Hollow Heterostructures: Considering the Interface Between Ag/Au Bimetals, *Nanoscale Res. Lett.*, 2019, **14**, 35.
- 13 X. Wu, *et al.*, Constructing effective photocatalytic purification system with P-introduced g-C<sub>3</sub>N<sub>4</sub> for elimination of UO<sub>2</sub><sup>2+</sup>, *Appl. Surf. Sci.*, 2017, **430**, 371–379.
- 14 W. Zhen, *et al.*, Novel visible-light-driven Z-scheme Bi<sub>12</sub>GeO<sub>20</sub>/g-C<sub>3</sub>N<sub>4</sub> photocatalyst: Oxygen-induced pathway of organic pollutants degradation and proton assisted electron transfer mechanism of Cr(VI) reduction, *Appl. Catal., B*, 2017, **207**, 17–26.
- 15 J. Tian, *et al.*, Novel Z-Scheme g-C<sub>3</sub>N<sub>4</sub>/C@Bi<sub>2</sub>MoO<sub>6</sub> composite with enhanced visible-light photocatalytic activity for beta-naphthol degradation, *Separation and Purification Technology*, 2017, **183**, 54–65.
- 16 J. Liu, *et al.*, Synthesis and photocatalytic application of trinary structural g-C<sub>3</sub>N<sub>4</sub>/Ag/Ag<sub>3</sub>PO<sub>4</sub> composite nanomaterials, *J. Environ. Chem. Eng.*, 2017, **5**, 5777–5785.
- 17 N. Tian, *et al.*, Mediator-free direct Z-scheme photocatalytic system: BiVO<sub>4</sub>/g-C<sub>3</sub>N<sub>4</sub> organic-inorganic hybrid photocatalyst with highly efficient visible-light-induced photocatalytic activity, *Dalton Trans.*, 2015, **44**, 4297–4307.
- 18 M. Mao, *et al.*, Designing all-solid-state Z-Scheme 2D g-C<sub>3</sub>N<sub>4</sub>/Bi<sub>2</sub>WO<sub>6</sub> for improved photocatalysis and photocatalytic mechanism insight, *Green Energy & Environment*, 2018, **3**, 229–238.
- 19 L. Ping, *et al.*, An overview and recent progress in the heterogeneous photocatalytic reduction of U(VI), *J. Photochem. Photobiol., C*, 2019, 100320.
- 20 R. N. Tio, *et al.*, Photocatalytic Reduction of Uranyl Ions over Anatase and Rutile Nanostructured TiO<sub>2</sub>, *Chem. Lett.*, 2013, **42**, 689–690.
- 21 V. N. Salomone, *et al.*, New insights in the heterogeneous photocatalytic removal of U(VI) in aqueous solution in the presence of 2-propanol, *Chem. Eng. J.*, 2015, **261**, 27–35.
- 22 J. Feng, *et al.*, Photocatalytic reduction of Uranium(VI) under visible light with Sn-doped In<sub>2</sub>S<sub>3</sub> microspheres, *Chemosphere*, 2018, **212**, 114–123.
- 23 L. Hu, *et al.*, Integration of adsorption and reduction for uranium uptake based on SrTiO<sub>3</sub>/TiO<sub>2</sub> electrospun nanofibers, *Appl. Surf. Sci.*, 2018, **428**, 819–824.
- 24 C. Chen, *et al.*, Z-scheme structure SnS<sub>2</sub>-Au-CdS with excellent photocatalytic performance for simultaneous removal of Cr(VI) and methyl orange, *Res. Chem. Intermed.*, 2019, **45**, 3513–3524.

- 25 C. Zhu, *et al.*, Fabrication of Z-scheme  $\text{Ag}_3\text{PO}_4/\text{MoS}_2$  composites with enhanced photocatalytic activity and stability for organic pollutant degradation, *Appl. Surf. Sci.*, 2016, **377**, 99–108.
- 26 X. Zhang, *et al.*, Enhanced Photoresponsive Ultrathin Graphitic-Phase  $\text{C}_3\text{N}_4$  Nanosheets for Bioimaging, *J. Am. Chem. Soc.*, 2012, **135**, 18–21.
- 27 S. Yang, *et al.*, Exfoliated Graphitic Carbon Nitride Nanosheets as Efficient Catalysts for Hydrogen Evolution Under Visible Light, *Adv. Mater.*, 2013, **25**, 2452–2456.
- 28 J. Liu, *et al.*, 3D flowerlike  $\alpha\text{-Fe}_2\text{O}_3@ \text{TiO}_2$  core-shell nanostructures: general synthesis and enhanced photocatalytic performance, *ACS Sustainable Chem. Eng.*, 2015, **3**, 2975–2984.
- 29 X. She, *et al.*, High Efficiency Photocatalytic Water Splitting Using 2D  $\alpha\text{-Fe}_2\text{O}_3/\text{g-C}_3\text{N}_4$  Z-Scheme Catalysts, *Adv. Energy Mater.*, 2017, **7**, 1700025.
- 30 C. Lu, *et al.*, Photocatalytic reduction elimination of  $\text{UO}_2^{2+}$  pollutant under visible light with metal-free sulfur doped  $\text{g-C}_3\text{N}_4$  photocatalyst, *Appl. Catal., B*, 2017, **200**, 378–385.
- 31 P. Zhou, *et al.*, All-Solid-State Z-Scheme Photocatalytic Systems, *Advanced Materials*, 2014, **26**, 4920–4935.
- 32 M. I. Litter, Last advances on  $\text{TiO}_2$  photocatalytic removal of chromium, uranium and arsenic, *Current Opinion in Green and Sustainable Chemistry*, 2017, **6**, 150–158.
- 33 C. Lu, *et al.*, Boron doped  $\text{g-C}_3\text{N}_4$  with enhanced photocatalytic  $\text{UO}_2^{2+}$  reduction performance, *Appl. Surf. Sci.*, 2016, **360**, 1016–1022.