

RESEARCH ARTICLE

Biogenic copper nanoparticles from *Avicennia marina* leaves: Impact on seed germination, detoxification enzymes, chlorophyll content and uptake by wheat seedlings

Hanaa L. Essa^{1,2*}, Mohamed S. Abdelfattah³, Alaa S. Marzouk², Zeinab Shedeed⁴, Hania A. Guirguis¹, Mayyada M. H. El-Sayed^{1*}

1 Chemistry Department, American University in Cairo, New Cairo, Egypt, **2** Pesticides Phytotoxicity Department, CAPL, Agriculture Research Centre, Dokki, Giza, Egypt, **3** Natural Products Research Unit (NPRU), Chemistry Department, Faculty of Science, Helwan University, Ain Helwan, Cairo, Egypt, **4** Botany and Microbiology Department, Faculty of Science, Helwan University, Ain Helwan, Cairo, Egypt

* Mayyada@aucegypt.edu (MMHES); Hanaa@aucegypt.edu (HLE)



OPEN ACCESS

Citation: Essa HL, Abdelfattah MS, Marzouk AS, Shedeed Z, Guirguis HA, El-Sayed MMH (2021) Biogenic copper nanoparticles from *Avicennia marina* leaves: Impact on seed germination, detoxification enzymes, chlorophyll content and uptake by wheat seedlings. PLoS ONE 16(4): e0249764. <https://doi.org/10.1371/journal.pone.0249764>

Editor: Amitava Mukherjee, VIT University, INDIA

Received: November 19, 2020

Accepted: March 25, 2021

Published: April 15, 2021

Copyright: © 2021 Essa et al. This is an open access article distributed under the terms of the [Creative Commons Attribution License](https://creativecommons.org/licenses/by/4.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Data Availability Statement: All relevant data are within the manuscript and its [Supporting Information](#) files.

Funding: H.G., UG# 1709695, the American University in Cairo. The funders had no role in study design, data collection and analysis, decision to publish, or preparation of the manuscript.

Competing interests: The authors have declared that no competing interests exist.

Abstract

Biogenic copper nanoparticles (Cu NPs) were synthesized using the aqueous crude extract of mangrove leaves, *Avicennia marina* (CE). GC-MS metabolite profiling of CE showed that their carbohydrates are mainly composed of D-mannose (29.21%), D-fructose, (18.51%), L-sorbose (12.91%), D-galactose (5.47%) and D-Talose (5.21%). Ultra-fine nanoparticles of 11.60 ± 4.65 nm comprising Cu_2O and $\text{Cu}(\text{OH})_2$ species were obtained with a carbohydrate and phenolic content of $35.6 \pm 3.2\%$ and 3.13 ± 0.05 mgGA/g, respectively. The impact of the biogenic Cu NPs on wheat seedling growth was dose-dependent. Upon treatment with 0.06 mg/mL of Cu NPs, the growth was promoted by 172.78 ± 23.11 and $215.94 \pm 37.76\%$ for wheat root and shoot, respectively. However, the lowest relative growth % of 81.94 ± 11.70 and $72.46 \pm 18.78\%$ were recorded for wheat root and shoot, respectively when applying 0.43 mg/mL of Cu NPs. At this concentration, peroxidase activity (POX) of the germinated wheat seeds also decreased, while ascorbic acid oxidase (AAO) and polyphenol oxidase (PPO) activities increased. Higher uptake of copper was observed in the root relative to the shoot implying the accumulation of the nanoparticles in the former. The uptake was also higher than that of the commercial Cu NPs, which showed an insignificant effect on the seedling growth. By treating the wheat leaves in foliar application with 0.06 mg/mL of Cu NPs, their contents of Chlorophyll a, Chlorophyll b, and total chlorophyll were enhanced after 21 days of application. Meanwhile, the high concentration (0.43 mg/mL) of Cu NPs was the most effective in reducing the leaf content of chlorophyll (a, b, and total) after the same time of application. The findings of this study manifest the potential of utilizing controlled doses of the prepared biogenic Cu NPs for inhibition or stimulation of seedling growth.

1. Introduction

Marine plants have been recently the subject of a myriad of studies due to their diverse biological activities. One plant of interest is the mangrove, which grows in small trees along tropical and subtropical coasts. Asia has the largest amount (42%) of the world's mangroves, followed by Africa (21%), Northern, Central America and the Caribbean (15%), Oceania (12%), and South America (11%) [1]. Two of the world's mangrove species exist in Egypt, and are commonly known as gray and red mangroves or scientifically as *Avicennia marina* and *Rhizophora mucronata*, respectively [2].

The former species shortly referred to as *A. marina*, is more abundant in Egypt as it thrives along the Red Sea Coast lining from Ras Mohamed to Mersa-Halaib [3]. Nowadays, several biological activities have been reported for mangroves such as antimicrobial [4], antioxidant [5], antidiabetic [6], antibacterial [7] and anticancer activities [8], and these were owed to its composition, which constitutes phytochemicals as alkaloids, phenolic compounds, steroids, terpenoids, glucosides and flavonoids together with polysaccharides [9–11]. In addition to their bioactivities, the mangrove extracts can be utilized as reducing agents for the synthesis of metal/metal oxide nanoparticles (NPs) that are bioactive, probably due to their unique physicochemical properties that are related to their high surface area, high reactivity, tunable pore size, and particle morphology. Along with their role in bioreduction, the extracts form a stabilizing layer around the NPs, preventing them from agglomeration and contributing to their bioactivity through its active functional groups.

Biosynthesized NPs have been used in agriculture as fertilizers, insecticides, herbicides and fungicides [12–14]. To evaluate the bioactivity of NPs for these applications, a seed germination phytotoxicity test is usually conducted. Germination generally refers to seeds' emergence and seedling growth of seedling shoots and root length [15].

One of the biosynthesized NPs that have not been extensively studied for their impact on seed germination is Cu NPs, which is the focus of our work. In an earlier study, the germination of lettuce (*L. sativa*) seeds in aqueous medium containing Cu NPs showed that CuO NPs were slightly more toxic than their Cu₂O counterparts and this consequently led to reduction of seed germination and root elongation [16]. Another study showed that *Cucumis sativus* Cu NPs accumulated in the roots of the cucumber plant and consequently reduced root length and root biomass [17]. The reported toxicity of Cu NPs could stem from their chemical composition that might lead to release of toxins and/or the stress stimulation they might cause due to their size, shape or surface [12].

This work aims to utilize a new green method for synthesizing biogenic Cu NPs using the crude extract (CE) of *A. marina* as a reducing agent. The proposed synthesis method readily forms NPs that are coated by a capping layer of CE with active functional groups which can potentially affect plant growth. To determine the conditions necessary for the biogenic Cu NPs to function as either growth inhibitors or stimulants, their effect on the germination of wheat seeds, grown in petri dishes, was investigated under different NPs concentrations and was compared with that of commercial Cu NPs as well as that of CE. The germinated wheat seedlings were tested for their copper uptake, while their detoxification enzymes were studied to examine the phytotoxicity effect of the biogenic NPs and the CE on them. In addition to the seed germination studies, pot experiments were conducted where the wheat seeds were planted for 14 days after which a foliar spray of CE or CuNPs (commercial and biogenic) was applied. Fig 1 depicts the outline of this work.

2. Materials and methods

2.1. Chemicals

For chemical analyses, phenol (BDH, England), sulfuric acid of concentration 98% (Penta, Prague, Czech Republic) and Folin & Ciocalteu's phenol reagent (Loba Chemie, Colaba,




Fig 1. Schematic outline of the work conducted in this study. FTIR: Fourier Transform Infrared Spectroscopy, GC-MS: Gas Chromatography-Mass Spectrometry, XRD: X-ray Diffraction, EDX: Energy-dispersive X-ray spectroscopy, TEM: Transmission Electron Microscopy, SEM: Scanning Electron Microscopy, UV-Vis: Ultraviolet-Visible spectrophotometry, Carb: Carbohydrates, TPC: Total Phenolic Content.

<https://doi.org/10.1371/journal.pone.0249764.g001>

Mumbai, India) were used. For nanoparticle synthesis, copper sulfate pentahydrate ($\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$) was purchased from Anachemia Ltd. (Montreal, Canada) and commercial CuO nanoparticles (size $< 50 \pm 7$ nm as detected by TEM) were purchased from NanoTech (Cairo, Egypt). For pot experiment, the fertilizer NPK (20/20/20) was purchased from Misr El-Dawliya for Agricultural & Industrial Development Co. (Kwesna, Egypt) and dimethyl sulfoxide (DMSO) was purchased from Daejung Chemical & Metal Co., Ltd (Korea).

2.2. Sample collection

Fresh mangrove leaves (*Avicennia marina* (Forssk.) Vierh), were collected from Ras Mohamed national park at southern Sinai coast (Gulf of Aqaba) during Winter 2017. Voucher specimens of the plant were identified by Dr. Mohamed Massed Hejazi in the Botany Herbarium lab of Marine Science Department, Suez Canal University, Ismailia, Egypt. Leaves were transferred into moist plastic bags, air-dried and ground in an electric mortar, then powdered samples were stored in the refrigerator at -20°C for future use.

2.3. Aqueous crude extraction

Five grams of ground *A. marina* leaves were suspended in 100 mL of distilled water. The suspension was heated for 20 min at 70°C and subsequently filtered through a cheesecloth. The filtrate was stored in the refrigerator for future use. Extraction was performed in triplicates and the percent yield was $35.2\% \pm 1.5$.

2.4. Gas Chromatography-Mass Spectrometry (GC-MS) analysis of the silylated primary metabolites in the crude extract

Primary metabolites analysis was carried out as follows. Briefly, 20 mg of extract were dissolved with 5 mL of 100% methanol under sonication for 5 min with frequent shaking, followed by

centrifugation at 12,000 x g for 10 min. A volume of 100 μ L of the methanolic extract was aliquoted in screw-cap vials and left to evaporate under a nitrogen gas stream until complete dryness. For derivatization, 150 μ L of N-methyl-N-(trimethylsilyl)-trifluoroacetamide (MSTFA) that was previously diluted to 1/1% with anhydrous pyridine was added to the dried methanol extract and incubated at 60°C for 45 min prior to analysis using GC-MS. Separation of silylated derivatives was accomplished on a low-polarity fused silica column, Rtx-5MS (30 m length, 0.25 mm inner diameter, and 0.25 μ m film) [18]. Identification of silylated components was performed by comparing their retention indices (RI) relative to n-alkanes (C6- C20), and their mass spectral matching to that of the National Institute of Standards and Technology (NIST) in Maryland, USA; as well as by using WILEY library database and standards when available. The separation of the compounds onto the column was based on differences in their volatility and polarity. Peaks were first deconvoluted using AMDIS software (2.70, NIST, Gaithersburg, MD, USA, 2011) prior to mass spectral matching.

2.5. Synthesis of the biogenic copper nanoparticles

In a 250 mL Erlenmeyer flask, 10 mL of *A. marina* leaf extract was added to a 100-mL solution of 4 mM of copper sulfate pentahydrate ($\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$) and the mixture was kept stirring for 3 h at 70°C until its color changed from blue to green [19, 20]. The formation of the biogenic Cu NPs was confirmed and its absorbance was monitored along with that of the commercial CuO nanoparticles using a UV-Vis spectrophotometer (Varian, Cary 500 Scan, Palo Alto, California, USA). To obtain pure nanoparticles; the nano-solution was centrifuged (Heraeus-Christ, GMBH336 Osteode Ma Harz No.39189, Hanau, Germany) for 10 min at -10°C / 5500–6000 rpm. The precipitate was discarded and the supernatant was dialyzed to get rid of the unreacted copper sulfate and obtain the purified nano-suspension.

2.6. Characterization of the biogenic copper nanoparticles

2.6.1. Fourier Transform Infrared (FTIR) spectroscopic analysis. CE and Cu NPs (biogenic and commercial) were mixed with potassium bromide to form 1-mm pellets. Analysis was carried out using a Nicolet 380 Thermogravimetric Analysis/Fourier Transform Infrared (TGA/FTIR) spectrometer range of 500 to 4000 cm^{-1} wavenumbers.

2.6.2. Transmission and Scanning Electron Microscopy with elemental analysis. The size and surface structure of the biogenic nanoparticles were examined using Transmission Electron Microscopy, TEM (Type JEOL-JEM-2100, Software: Gatan Digital Micrograph, Akishima, Tokyo, Japan). Specimens of a few mgs of powdered samples were suspended in distilled water and were well dispersed in an ultrasonic bath for 15 min. Few drops of the suspension were poured onto previously prepared grids covered by a thin film of evaporated carbon, and then the prepared grids were examined under the microscope.

Scanning Electron Microscopy, SEM (ZEISS- LEO SUPRA 55, Jena, Germany) was used to examine the morphology of the biogenic nanoparticles, where a fine gold coat was deposited on the samples under vacuum in a JFC-1100 sputter coater (JEOL) for 3 min at 15 mA. The elemental composition of the biogenic nanoparticles was measured using Energy-dispersive X-ray spectroscopy (EDX) onto a Bench Top SEM + EDX, JEOL, JCM 6000 plus, (Akishima, Tokyo, Japan), under EDX conditions of 15 kV and a working distance of 19 mm.

2.6.3. Zeta potential and X-ray diffraction measurements. The Zeta potential of the biogenic and the commercial copper nanoparticles was determined using Dynamic Light Scattering (DLS) measurements (Malvern Zeta Sizer, Nano ZS, Malvern, UK), with a helium-neon laser operating at 90° scattering angle and 633 nm wavelength at 25°C.

An X-ray diffractometer with Cu K α radiation (Bruker D8 Discover, Karlsruhe, Germany) at a wavelength of 1.54 Å⁰ was used to examine the phase and constitution of the biogenic nanoparticle powders which were precipitated on a silicon holder.

2.7. Chemical analysis of the crude extract and the biogenic Cu NPs

Total carbohydrate contents of CE and the biogenic Cu NPs were determined by the phenol-sulfuric method using glucose as a standard. In addition, the total phenolic content was determined using the Folin-Ciocalteu reagent according to the method described by Singleton & Rossi [21, 22], with minor modifications [23] and using Gallic acid as a standard.

2.8. Testing the biological activities of the crude extract, the biogenic and the commercial Cu NPs

2.8.1. Seed germination assay. This assay was conducted to investigate the effect of CE and Cu NPs (biogenic and commercial) on seed germination and seedling growth. Seeds of monocotyledonous wheat plant (*Triticum aestivum* L.) of the Egyptian Sakha 93 cultivar were collected and classified at the Agricultural Research Centre (ARC) in Egypt to be further examined. The test was carried out according to the ASTM standard germination protocol (ASTM 2003) with slight modifications [24]. The CE, biogenic and commercial Cu NPs were serially diluted with distilled water to the concentrations of 0.00 (control), 0.03, 0.22, and 0.43 mg/mL. Ten seeds of wheat were placed on Whatman filter papers No. 10 in Petri dishes (10-cm diameter), and three mL of each concentration were added per dish. Three replicates were used for each concentration such that the total number of tested samples were 30 samples/treatment. All dishes were covered with a parafilm and were incubated (Thermos Fisher incubator, Marietta, Ohio 45750, United States) at 25±2°C in the dark for 7 days; after which the root and shoot lengths were recorded. The dishes were monitored regularly during the incubation period to ensure they were kept wet. The relative elongation %, relative germination rate and germination index were calculated as follows:

$$\text{Relative germination rate} = \left[\frac{\text{Seeds germinated in tested sample}}{\text{Seeds germinated in control}} \right] * 100 \quad [1]$$

$$\text{Relative shoot/root elongation} = \left[\frac{\text{Mean shoot/root length in tested sample}}{\text{Mean shoot/root length in control}} \right] * 100 \quad [2]$$

$$\text{Germination index} = \left[\frac{\text{Relative germination rate} * \text{relative root elongation}}{100} \right] \quad [3]$$

2.8.2. Antioxidant and oxidase enzymes assay for the crude extract and the biogenic Cu NPs. This assay was used to quantify the enzyme activity in the wheat seeds that were germinated in the petri dishes. The tests were only conducted for the seeds subjected to each of the CE and the biogenic Cu NPs because the commercial Cu NPs did not show a significant effect on the root and shoot growth as will be shown later.

2.8.2.1. Preparation of a crude enzyme extract. A crude enzyme extract was prepared by grinding wheat seedlings (500 mg) that are 3–4 days old in a mortar with 5 mL of cold Na/K phosphate buffer (0.1M) at pH 6.8. The homogenate was centrifuged for 20 min at 6000 rpm and 4°C. Then, the supernatant was used for measuring the activities of the following enzymes spectrophotometrically (Jenway UV-Vis spectrophotometer, model no. 6405, Market Harbourough, LE169AF, United Kingdom). The enzyme activity was expressed as µg /g fresh wt min⁻¹.

2.8.2.1.1. Peroxidase assay (EC.1.11.1.17). Peroxidase activity was measured by Guaiacol method [25] with minor modifications. The 3-mL assayed mixture contained 2.2 mL of 0.1M potassium phosphate buffer (pH 7.0), 0.5 mL of 0.018 mM guaiacol, 0.2 mL of H₂O₂ (30%) and 0.1 mL of the crude enzyme extract. Color intensity was detected at 436 nm by recording the changes in absorbance within 30 s to 3 min.

2.8.2.1.2. Catalase assay (EC.1.11.1.6). Catalase activity was measured using a hydrogen peroxide assay that is based on the formation of its stable complex with ammonium molybdate [26]. In this assay, 0.2 mL of the plant extract was incubated in a 1-mL reaction mixture containing 65 mM of hydrogen peroxide in 60 mM Na/K phosphate buffer, pH 7.4 at 25°C for 4 min. The enzymatic reaction was stopped with 1 mL of 32.4 mM ammonium molybdate, and the concentration of the yellow complex of molybdate and hydrogen peroxide was measured at 405 nm.

2.8.2.1.3. Ascorbic acid oxidase (AAO) assay (EC.1.10.3.3). Ascorbic acid oxidase activity was measured according to a previously reported method [27]. To a quartz cuvette of a UV spectrophotometer, one mL of 0.2 M phosphate buffer (pH 6.2), 0.2 mL of 1 mM ascorbic acid and 0.2 mL of the enzyme extract were added. Distilled water was added to bring the final volume to 3.0 mL. The initial absorbance was recorded, and then the optical densities after 30 s to 3 min were measured in order to monitor the rate of disappearance of ascorbate at 265 nm.

2.8.2.1.4. Polyphenol oxidase (PPO) assay (EC.1.10.3.1). Polyphenol oxidase activity was determined according to a previously reported method [28]. The assayed mixture constituted 3 mL of buffered catechol solution (0.01 M catechol, freshly prepared in 0.1 M phosphate buffer of pH 6.0) along with one mL of the enzyme extract. Changes in absorbance were recorded every 30 s to 5 min using a UV spectrophotometer at 495 nm.

2.8.3. Nanoparticles uptake in shoot and root of wheat seedlings. The copper uptake of the wheat seedlings germinated in the petri dishes and subjected to each of the biogenic and the commercial Cu NPs was determined using a Microwave Plasma Atomic Emission Spectrometer (MPAES, Agilent, Santa Clara, CA 95051, United States). The shoot and root ash were separately placed into digestion vessels containing a mixture of 1: 0.2 of HNO₃-H₂O₂ by volume. These vessels were heated to 85°C for 90 min to ensure digestion of the ash, then filtered through a 0.45-µm nylon sealed filter membrane. The filtered sample was used for (MPAES) analysis in shoots and roots at different concentrations of the biogenic and the commercial Cu NPs.

The translocation factor (TF) was used to evaluate the translocation of copper from wheat root to shoot [29]. This was calculated as the ratio of Cu concentration in wheat shoot to that in plant root:

$$TF = \left[\frac{C_{\text{plant shoot}}}{C_{\text{plant root}}} \right] \quad [4]$$

2.8.4. Pot experiment. In a silt clay soil, Sakha 93 wheat seed (*Triticum aestivum* L.) was planted during the 2018/2019 Winter season. It was thinned to 5 seedlings per pot. After 14 days of planting, a foliar spray of CE or Cu NPs was applied while irrigating the soil to keep it at almost its field capacity for the growing season period. After 15 days from seedling, 2 g of NPK fertilizer were added per pot area, since the rate of application of NPK fertilizer is 1 kg per 1000 m² of the field. NPK constitutes (20/20/20) by weight (on a dry basis) of Nitrogen/ Phosphorus/ Potassium elements. The process was repeated every week throughout the period of the experiment (4 weeks). Foliar treatment was applied using each of CE and Cu NPs, with concentrations of 0.00 (control), 0.06, and 0.43 mg/mL, along with a treatment volume of 15 mL. Fig 2 shows the steps of the pot cultivation process.




Fig 2. Schematic outline of the pot cultivation. Physical and chemical characteristics of the soil used in this study as well as the procedure used for Chlorophyll extraction and estimation of chlorophyll a, b and total chlorophyll contents were previously reported by Essa et al. [20].

<https://doi.org/10.1371/journal.pone.0249764.g002>

2.9. Statistical analysis

The statistical analysis was performed using SPSS program, version 20 for Windows (SPSS Inc, USA). A one-way analysis of variance (ANOVA) was conducted to test the significant differences ($p < 0.05$) between the treatment and control means. Duncan's multiple range test (DMRT) was also performed to determine the significant differences between the tested groups.

3. Results and discussion

3.1. Chemical and phytochemical analyses

Chemical analysis of the CE and the biogenic Cu NPs showed that they have carbohydrate contents of $50.3 \pm 3.1\%$ and $35.6 \pm 3.2\%$, as well as phenolic contents of 27.5 ± 0.1 and 3.13 ± 0.05 mgGA/g, respectively. Obviously, the NPs have lower contents since they are capped by only a layer of the extract. The carbohydrate content of CE was further confirmed by GC-MS analysis as shown in [S1 Fig](#) and [Table 1](#), where CE mainly constitutes the monosaccharaides of D-

Table 1. Identified contents of the crude extract (CE) as measured using metabolite profiling on GC/MS.

Peak no.	rt* (min)	m/z**	Area (%)	Component
M1	4.6648	73	11.410	Propionic acid
M2	5.5986	147	9.118	Oxalic acid
M3	9.5346	205	5.963	Glycerol
M4	23.0428	217	18.510	D-Fructose
M5	23.2624	307	12.914	L- (-)-Sorbitol
M6	23.3852	319	2.196	Ribitol
M7	23.5277	205	29.205	D-Mannose
M8	23.8882	73	5.473	D-Galactose
M9	23.8974	147	5.207	D-(+)-Talose

*retention time

**mass to charge ratio.

<https://doi.org/10.1371/journal.pone.0249764.t001>




Fig 3. UV-Vis spectra of the biogenic and commercial Cu NPs (a), together with the FTIR spectra of the CE, biogenic and commercial Cu NPs (b).

<https://doi.org/10.1371/journal.pone.0249764.g003>

mannose (29.21%), D-fructose, (18.51%), L-sorbose (12.91%), D-galactose (5.47%) and D-Talose (5.21%). To the best of our knowledge, this is the first report on the quantification of sugars of *Avicennia marina* by GC/MS.

3.2. Synthesis and characterization of the biogenic Cu NPs

The formation of the biogenic Cu NPs was confirmed by UV-Vis spectroscopy and FTIR spectroscopy as depicted in (Fig 3A and 3B). Fig 3A shows the UV-visible spectra of the biogenic Cu NPs along with their commercial counterparts. Both spectra exhibit an absorbance peak at the range of 290–320 nm which is in good agreement with the previous literature reported for Cu NPs synthesized through bio-reduction [30, 31]. To determine the functional groups present in the layer capping the biogenic NPs, the FTIR spectrum of the NPs was analyzed then compared to the spectra of CE and the commercial Cu NPs as depicted in Fig 3B. Clearly, CE and both Cu NPs show bands in the range of 3500–3400 cm^{-1} , corresponding to the stretching vibration of the bound hydroxyl (O-H) groups. In addition, CE exhibits a band in the range of 1690–1630 cm^{-1} that could be attributed to the carbonyl stretch of the amide group, as well as two peaks in the ranges of 1385–1380 cm^{-1} and 1200–1000 cm^{-1} that could be ascribed to ester sulfate and acidic polysaccharides, respectively. Furthermore, the appearance of the vibration band of Cu_2O on the spectrum of the biogenic Cu NPs at 670 cm^{-1} confirms the formation of Cu (I) oxide nanoparticles [32]. On the other hand, the vibration band of CuO shown on the spectrum of commercial Cu NPs at 490 cm^{-1} indicates the presence of Cu (II) oxide nanoparticles [32]. Comparing the spectra of CE and the biogenic Cu NPs, it can be deduced that most of the peaks that were clearly exhibited by CE diminished in the Cu NPs implying that most of the functional groups present in CE contributed to form the stabilizing layer onto the biogenic Cu NPs. Previous studies reported that carbonyl groups from amino acid residues and proteins have a strong ability to bind to metals and hence could contribute along with the polysaccharides in capping the nanoparticles [33].

The composition and nano structure of the biogenic Cu NPs were examined by TEM, XRD, SEM, and EDX as depicted in (Fig 4A–4D). The TEM micrograph of the biogenic Cu NPs (Fig 4A) reveals regular homogeneous spherical shaped particles with an average diameter of about 11.60 ± 4.65 nm which is similar to values reported in previous literature [34]. The particles have a sponge like morphology with large surface area as shown in their SEM




Fig 4. TEM image (a), XRD pattern (b), SEM image (c), EDX analysis (d) and of the biogenic Cu NPs.

<https://doi.org/10.1371/journal.pone.0249764.g004>

micrograph (Fig 4C). The EDX elemental composition of the biogenic Cu NPs (Fig 4D) constitutes 47.80% O, 8.86% C, 27.01% S and 16.34% Cu by mass. To determine the Cu phases present in the structure of the NPs, XRD patterns (Fig 4B) of the biogenic and commercial Cu NPs were studied. As clear from the spectrum of the biogenic Cu NPs, peaks are displayed at approximately 11.46°, 18.1°, 22.9°, 32° and 46° and hence could be attributed to a mixture of Cu species [35–37], mainly the orthorhombic phase of $\text{Cu}(\text{OH})_2$ (JCPDS: #80–0656), and the cubic phase of Cu_2O (ICCD-JCPDS: #78–2076) which correspond to the crystallographic planes of reflection of (020), (021), (111) and (200), respectively. Based on the presence of the two major peaks of 18.1° and 22.9°, the constituent ratio of Cu_2O to $\text{Cu}(\text{OH})_2$ was estimated from the relative percentage of each peak to be 2:1. Since the pH of the nano solution was 6–7 and according to Pourbaix diagram, copper oxide would more likely exist in the form of Cu (I) species. Dynamic light scattering (DLS) measurements showed that the biogenic and commercial Cu NPs are nearly neutral with a zeta potential of 1.02 and 0.02 mV, respectively at the working pH range of 6–7.

3.3. Wheat seedlings root and shoot lengths

Fig 5A and 5B show the respective average root and shoot lengths of the germinated wheat seeds (incubated in the petri dishes at $25 \pm 2^\circ\text{C}$ in the dark for 7 days) after their exposure to CE, biogenic and commercial Cu NPs. Relative to the control, both CE and the biogenic Cu NPs significantly enhanced the root and shoot lengths of wheat seedlings when applied at the lower concentrations of 0.03 and 0.06 mg/mL. At these concentrations, the biogenic Cu NPs had a stronger stimulant effect than that of CE on the root length of wheat seedlings, while it showed a comparable effect to that of CE on the shoot length. In this respect, the root length was promoted by 47.77 and 52.22% relative to the control at 0.03 and 0.06 mg/mL of CE, respectively; as opposed to 67.50 and 72.77% at the respective concentrations of the biogenic Cu NPs. However, the effect was not significant on the root and shoot lengths of the seedlings upon their treatment with 0.22 mg/mL. Upon exposure to 0.43 mg/mL of CE, the root length was unaffected while the shoot length decreased by 34.78% relative to the control. A previous




Fig 5. Root (a) and shoot lengths (b) of the germinated wheat seeds after their incubation in CE, biogenic and commercial Cu NPs.

<https://doi.org/10.1371/journal.pone.0249764.g005>

study revealed that root elongation of *Vulgaris phaseolus* was promoted upon exposure to low concentrations of 25-nm copper oxide nanoparticles [38]. The biogenic Cu NPs is the only tested material that significantly inhibited the root and shoot lengths of wheat seedlings when applied at the highest concentration of 0.43 mg/mL. This inhibitory behavior was previously reported for copper nanoparticles (40–50 nm) that were applied on wheat seeds [39].

This dose dependent effect is in agreement with previous studies which recorded a significant increase in root length of wheat seeds upon their exposure to low concentrations of Cu NPs biosynthesized from *Moringa oliefera*, meanwhile an adverse effect was realized at higher concentrations of Cu NPs that exceeded 0.075 mg/mL [40]. In addition, a similar dose dependent effect has been reported in a previous study that examined the effect of copper oxide nanoparticles (< 50 nm) on root and shoot elongation of soybean and chick pea seeds [15], as well as another study that reported the impact of biogenic cuprous oxide nanoparticles (Cu₂O NPs) on *Lycopersicon esculentum* tomato seedling growth [41].

As for the commercial Cu NPs, they did not exhibit any significant effect on the root and shoot lengths of wheat seedlings at all the applied concentrations. This behavior may be owed to the difference in the oxidation states between the cupric oxide commercial Cu NPs (oxidation state: +2) and the primarily cuprous oxide biogenic ones (oxidation state: +1). It is to be noted here that the biogenic nanoparticles constitute mainly Cu (I) oxide as confirmed earlier by XRD. In addition, the commercial Cu NPs do not have a capping layer of active functional groups as in the biogenic Cu NPs. Furthermore, the biogenic Cu NPs have additional Cu(OH)₂ species which might have enhanced the penetrability of the nanoparticles into the root [42].

3.4. % Relative shoot and root lengths and germination index of wheat seedlings

Data pertaining to percent relative growth in shoot and root lengths of the petri dish-germinated wheat seeds relative to the control is shown in (Fig 6A and 6B). Obviously, the CE and




Fig 6. Effect of CE, biogenic and commercial Cu NPs on % relative growth of root (a) and shoot lengths (b) and germination index of wheat seeds (c).

<https://doi.org/10.1371/journal.pone.0249764.g006>

the biogenic Cu NPs had an adverse effect on both shoot and root growth when applied at 0.22 and 0.43 mg/mL. The relative growth % of shoot and root decreased gradually with increasing the concentration of the CE and the biogenic Cu NPs, recording their respective lowest values of 65.22 ± 29.90 and $72.46 \pm 18.78\%$ alongside with 90.83 ± 16.09 and $81.94 \pm 11.70\%$, at the highest employed concentration of 0.43 mg/mL CE or biogenic Cu NPs, respectively. Commercial Cu NPs, on the other hand, showed no significant effect on both shoot and root growth. Fig 6C depicts the germination index (GI) of wheat seedlings, which showed its respective highest values of 117.09 and 123.61 upon exposure to the CE and the biogenic Cu NPs at 0.06 mg/mL. At the highest applied concentration of 0.43 mg/mL for the CE and the biogenic Cu NPs, GI recorded 59.39 and 37.82, respectively. Again, commercial Cu NPs had no significant effect on the germination index of wheat seedlings due to the reasons alluded to earlier.

From the above-mentioned results, it can be deduced that the biogenic Cu NPs could have both positive and negative effects on seed germination and growth depending on the concentration at which they are applied. This behavior was also observed with silver nanoparticles that were applied to 11 species of wetland plant [43], while the reduction in germination index with increasing the concentration of Cu NPs was also reported in previous work on wheat seeds [44]. Similar inhibitory effects were observed on rice (*Oryza sativa*) (monocotyledonous), when treated with copper oxide nanoparticles (< 50 nm) in both stages of seed germination and seedling growth due to the accumulation of Cu in root and leaf tissues. This was indicated by the massive increase of Cu in roots (76-fold) and leaves (5.5-fold) in comparison with the control [45], or the expression of OsCYCD and OsCDC2 genes which inhibited growth [46], or alternatively significant reduction in lengths and weights of shoot and root [47]. In addition, the adverse effect of Cu NPs could have been caused as a result of the oxidative stress induced by the NPs due to their interference with the electron transport system, affecting the biochemical pathways in the seeds through oxidation of proteins, lipids and nucleic acids, or via changing in the phytohormones which alter plant metabolism, and/or through regulation of reactive oxygen species (ROS) by producing antioxidant enzymes for protection of the cellular and sub-cellular system from these cytotoxic effects [45, 46]. Several factors could influence the toxicity of Cu NPs, including their applied concentration, particle size, specific surface area, shape, stability and its physiochemical characteristics. Other

physiological and morphological factors related to the plant species could also be at play such as plant type, age, life cycle, in addition to external growth factors as growth media, and diluting agents [48–51]. All these factors will dictate the extent of accumulation and uptake capacity of the NPs onto the plant. The stimulatory effect of Cu NPs, on the other hand, could be owed to the transfer of some NPs to the meristem where intensive cell division occurs. Thus, cell growth was promoted. This is also supported by a study which showed that Cu NPs induce the modulation of auxin related genes which play a significant role during the growth of apical meristems [46, 52].

3.5. Detoxification enzymes activity in the petri dish-germinated wheat seedlings

To gain more insight into the possible mechanism of inhibition, the effect of each of the CE and the biogenic Cu NPs on the antioxidant and oxidase enzyme activities of peroxidase, catalase, ascorbic acid oxidase, and polyphenol oxidase enzymes in wheat seeds was investigated. (Fig 7A–7D) shows the antioxidant activities after applying the CE and the biogenic Cu NPs on wheat seeds, once in a low concentration of 0.06 mg/L and again at a high concentration of 0.43 mg/mL. These two concentrations were chosen since the former stimulated the plant growth while the latter inhibited it. Commercial Cu NPs, however, were not tested as they did not show any significant effect on the seedlings growth and the germination index of the wheat seeds as discussed earlier.

Peroxidase (POX) and catalase (CAT) are antioxidant enzymes that can detoxify H_2O_2 and scavenge free radicals and oxygen intermediates [53]. As clear from Fig 7A, applying the low concentration (0.06 mg/mL) of the CE or the biogenic Cu NPs to wheat seeds significantly ($P < 0.05$) increased CAT activity relative to the control. In addition, the effect of the biogenic Cu NPs is more pronounced than that of the CE at the low concentration. This behavior is consistent with the promotion in root and shoot growth observed at this concentration. On




Fig 7. Effect of CE and Cu NPs on CAT (a), POX (b), PPO (c) and AAO (d) activities in wheat germinated seeds ($\mu\text{g/g fresh wt min}^{-1}$) at the 4th day of germination.

<https://doi.org/10.1371/journal.pone.0249764.g007>

the other hand, applying the high concentration (0.43 mg/mL) of CE reduced the activity, while employing the same concentration of Cu NPs did not significantly affect the activity relative to the control. This again is in agreement with the inhibition of root and shoot exhibited at this concentration. A similar dose-dependent effect was previously reported for TiO₂ NPs on CAT enzyme during the seed germination of onion [54]. As for POX activity shown in Fig 6B, it decreased significantly relative to the control upon the application of either the low or high concentration of CE, or the high concentration of Cu NPs. A similar inhibitory effect for chitosan NPs in reducing POX activity of broad beans was previously reported [55].

The effect of each of the CE and the biogenic Cu NPs on the activities of PPO and AAO enzymes is shown in (Fig 7C and 7D). The high concentration of Cu NPs (0.43 mg/mL) significantly ($P < 0.05$) enhanced PPO and AAO activities in the wheat germinated seeds as compared to the control (Fig 7C and 7D), while the same concentration for CE did not significantly affect the activities. This finding is in line with the seed germination results which showed inhibition in seedling growth at the higher concentration of 0.43 mg/mL Cu NPs. The phenolics oxidation reaction is enhanced by PPO in plants, and the relation between phenolic content and PPO activity was reported to be inversely proportional in many plants, such as watermelon and tomato plants subjected to heat and cold stresses [56]. Hence, increasing PPO and AAO activities can result in decreasing the antioxidant activity and this might consequently lead to growth inhibition.

3.6. Copper uptake and translocation factor in the petri dish-germinated wheat seedlings

Fig 8A depicts the copper uptake in root tissue at different applied concentrations of the biogenic and the commercial Cu NPs. Relative to the control, the copper uptake increased with increasing the concentration of the biogenic as well as the commercial Cu NPs. It is to be noted that the copper detected in the control is the copper mineral already present in the plant [57]. A respective increase of 1.57 and 1.36-fold in the Cu content was observed in the root treated with 0.43 mg/mL of the biogenic and the commercial Cu NPs as compared to the control. This finding is in agreement with a previous study conducted on copper oxide nanoparticles taken up in *Oryza sativa* leaves [58]. The copper uptake in roots treated with 0.43 mg/mL of the biogenic Cu NPs (467.06 ± 6.89 mg/kg) is greater than that observed in roots treated




Fig 8. Cu uptake in wheat seedlings (a) and Translocation factor of wheat seedlings (b).

<https://doi.org/10.1371/journal.pone.0249764.g008>

with the commercial Cu NPs (403 ± 3.48 mg/kg). This might explain the enhancement in root lengths observed earlier (Fig 6A and 6B) in addition to the stimulation in the activities of the antioxidant enzymes of CAT and POX (Fig 7A and 7B). Previous work reported that copper is a necessary element for plant growth (micronutrient), since it stimulates numerous enzymes and has a role in the synthesis of RNA, therefore it promoted the seedlings growth at a less than 50 μ M concentration [59]. Other studies attributed the stimulation of seed germination by NPs to the increase in the expression levels of a gene encoding catalase, and suggested that CAT is the vital enzyme that controls the recovery of seed vigor in aged seeds [60]. On the other hand, applying the higher concentration of 0.43 mg/mL of the biogenic Cu NPs significantly decreased shoot and root lengths due to the higher accumulation of Cu in the roots as well as the higher PPO and AAO enzyme activities (Fig 6C and 6D) obtained relative to the control.

The translocation of copper from wheat root to shoot is shown in (Fig 8B). Obviously, TF of Cu was less than unity (<1) in all treatments which explains the lower concentrations of Cu observed in shoots than roots as shown in (Fig 8B). The root has the ability to accumulate some metals to protect the aerial parts (edible parts) besides its main functions of fixing the plant in the soil and absorption of water and dissolved minerals [61].

3.7. Chlorophyll contents in the wheat leaves treated with foliar spray

Fig 9 shows the contents of chlorophyll a, b and total chlorophyll in wheat leaves upon their treatment with a foliar application of CE and biogenic Cu NPs. As clear from the figure, chlorophyll a, b and total chlorophyll contents of CE were insignificantly changed as compared to the control at a concentration of 0.06 mg/mL, recording 2.80, 1.94, and 4.74 mg/g fresh weight after 21 days from application. A previous study has reported similar trends where the effect of low concentrations of cyanobacterial extracts on chlorophyll b of lettuce plants was examined during two different seasons [62]. Similarly, the treatment with biogenic Cu NPs followed the same behavior as that of CE at the same concentration resulting in 3.02, 2.15, and 5.17 mg/g fresh weight of chlorophyll a, b, and total chlorophyll contents, respectively after 21 days from application. This behavior resembles that previously reported for the effect of Fe_3O_4 nanoparticles (25 nm) on chlorophyll (a) and total chlorophyll contents of Rocket (*Eruca sativa*) at concentrations of 1 and 2 mg/L after 5 weeks from the application [63].




Fig 9. Chlorophyll a, b and total chlorophyll contents upon exposure to CE and Cu NPs.

<https://doi.org/10.1371/journal.pone.0249764.g009>

On the other hand, the previous growth parameters in wheat leaves decreased insignificantly at the highest concentration of 0.43 mg/mL of CE. Meanwhile, treatment with biogenic Cu NPs showed an inhibitory effect on chlorophyll a, b, and total chlorophyll at the same concentration since it reduced the chlorophyll a, b and total chlorophyll contents relative to the control by 16.85, 26.42, and 20.69%, respectively. The inhibitory effect of Cu NPs was previously examined when studying the impact of 1 mg/L of CuO nanoparticles on total chlorophyll content, as well as chlorophyll (a) and (b) of *Arabidopsis thaliana* seedlings [64].

This current study of biogenic Cu NPs highlights the dose-dependent effect of the nanoparticles in both seed germination and foliar application. Similar findings were reported for the effect of copper oxide nanoparticles on seedlings lengths, germination percentage, and chlorophyll contents of soybean (*Glycine max* (L.)) [65]. Racuciu and Creange [66] found that the content of chlorophyll in maize plants was enhanced at a low concentration of Ag NPs (10–50 $\mu\text{L/L}$), but the chlorophyll content was reduced with a high concentration treatment of NPs. In addition, Gohari et al. [67] found that the high concentration (i.e, 200 mg/L) of titanium dioxide nanoparticles (TiO_2 NPs) decreased the chlorophyll content of *Dracocephalum moldavica* seedlings as opposed to the lower concentration (i.e, 100 mg/L), which enhanced the pigment content.

The nanoparticles were proposed to have the ability to penetrate the coat of the seeds and enhance the uptake and use of water. Consequently, the enzyme systems would be stimulated, and the seed germination and growth would be improved [68]. Additionally, Suriyaprabha et al. [69] explained the role of nano- SiO_2 in enhancing maize germination by providing better growth conditions such as nutrients, pH, and conductivity. In another study, Lu et al. [70] owed the enhancement in soybean seed germination by nano- SiO_2 and nano-titanium dioxide (nano- TiO_2) to the improvement in the nitrate reductase activity. This result was confirmed by Yang et al. [71] and Mishra et al. [72] who found that TiO_2 NPs controlled the activity of the nitrogen metabolism enzymes. Nitrate reductase, glutamate dehydrogenase, glutamine synthase, and glutamic-pyruvic transaminase supported the plants' uptake of nitrate and aided in the conversion of inorganic nitrogen to organic nitrogen which forms protein and chlorophyll, and this probably increased the fresh and dry weights of the plant. In addition, the nanoparticles of metals can stimulate the efficacy of photosynthetic systems and their chemical energy production, since the chlorophyll in the reaction center combines with metal nanoparticles as Ag or Au, forming a unique hybrid system. This new system may produce more excited electrons by plasmon resonance [73].

However, the tendency of the NPs to penetrate walls and interact with cellular structures is owed to their properties as high reactive surfaces and small size. Therefore, they provide cellular capacity and genetic toxicity by oxidative stress introduction [74]. The inhibitory effect exhibited by the high doses of nanoparticles may be related to their phytotoxicity, which is correlated to the dissolution of toxic ions from the NPs [75], production of radicals through NPs reactions with plants, or direct reactions of NPs with plants [76]. Previous work also reported that Cu nanoparticles inhibit the growth of root hairs; these being important for the uptake of immobile nutrients such as phosphorus [74]. To sum up, plant nanotoxicity may depend on the dose, species of plant, and treatment conditions (substrate, temperature, and environment).

4. Conclusion

Biogenic Cu NPs of $\text{Cu}(\text{OH})_2$ and Cu (I) oxide species were successfully synthesized using the crude aqueous extract of *A. marina*. The nanoparticles exhibited a dose-dependent effect on the growth of wheat seedlings. Applying low concentrations of the biogenic Cu NPs onto the

seedlings enhanced their growth, while treating the seedlings with high concentrations of the nanoparticles suppressed the seedling growth relative to the control. At 0.43 mg/mL, the root and shoot growth was inhibited relative to the control by 81.94 ± 11.70 and $72.46 \pm 18.78\%$, respectively. Further in foliar application, the chlorophyll content was either enhanced or inhibited depending on the concentration of Cu NPs which was applied on the wheat leaves (21-days old). Low Cu NPs concentration (0.06 mg/mL) had the tendency to improve the chlorophyll content but the higher one (0.43 mg/mL) suppressed it. These results are consistent with those of seedling growth. Copper uptake by the petri-dish germinated wheat seedlings was also dose dependent; and it reached its maximum value, 467.06 ± 6.89 mg/kg at the highest applied concentration of the biogenic Cu NPs (0.43 mg/mL) with a translocation factor of less than unity indicating the accumulation of Cu in the root. The impact of the biogenic Cu NPs on seedling growth was compared to that of the commercial Cu NPs which showed no significant effect on the growth of shoot or root relative to the control. This was attributed to the difference in the nature of the Cu species present in the biogenic and commercial nanoparticles. The inhibition of wheat seedling growth by the biogenic Cu NPs may be related to the activity of the antioxidant enzymes of catalase, peroxidase, ascorbic acid oxidase and polyphenol oxidase and their role in the antioxidant detoxification. The phytotoxicity of the biogenic Cu NPs on seed germination and plant growth, when applied at a high concentration, suggests their potential to be utilized as natural herbicides whose action can be promoted by inhibition of the peroxidase enzyme activity and enhancement of the ascorbic acid oxidase and polyphenol oxidase activities. However, they can also be used to stimulate seedling growth when applied at low concentrations.

Supporting information

S1 Fig. Representative GC/MS chromatogram for the crude extract.
(DOCX)

S1 Table. Shoot copper content in wheat seedlings.
(DOCX)

Acknowledgments

The authors would like to thank the Chemistry Department at the American University in Cairo for conducting NPs characterization experiments and the Agriculture Research Centre in Cairo for supplying wheat and radish seeds. Gratitude is further extended to Professor Dr. Mohamed Farag and Mr. Erick Dokalahy from the American University in Cairo for helping with the GC-MS analysis. and also, Dr. Zeinab Shedeed from the plant physiology lab in Helwan University for supplying the chemicals of enzymes activity assays.

Author Contributions

Conceptualization: Hanaa L. Essa, Mohamed S. Abdelfattah, Alaa S. Marzouk, Mayyada M. H. El-Sayed.

Data curation: Hania A. Guirguis.

Formal analysis: Mayyada M. H. El-Sayed.

Investigation: Hanaa L. Essa, Hania A. Guirguis.

Methodology: Mohamed S. Abdelfattah, Alaa S. Marzouk, Zeinab Shedeed, Mayyada M. H. El-Sayed.

Supervision: Mohamed S. Abdelfattah, Alaa S. Marzouk, Mayyada M. H. El-Sayed.

Validation: Hanaa L. Essa, Hania A. Guirguis.

Writing – original draft: Hanaa L. Essa, Zeinab Shedeed, Hania A. Guirguis.

Writing – review & editing: Hanaa L. Essa, Mohamed S. Abdelfattah, Alaa S. Marzouk, Mayyada M. H. El-Sayed.

References

1. Shelar P, Reddy S, Shelar G, Reddy V. Medicinal value of mangroves and its antimicrobial properties: a review. *Continental. J. Fish Aqua. Sci.* 2012; 6:26–37.
2. Walker Kira. “Preserving One of Egypt’s Most Efficient Ecosystems: The Mangrove.” *Egypt Independent*, <https://www.egyptindependent.com/preserving-one-egypt-s-most-efficient-ecosystems-mangrove/AI-Masry-Al-Youm>, 12 Feb. 2013.
3. Vijayavel K, Anbuselvam C, Balasubramanian, MP. Free radical scavenging activity of the marine mangrove *Rhizophora apiculata* bark extract with reference to naphthalene induced mitochondrial dysfunction. *Chem. Biol. Interact.* 2006; 163:170–175. <https://doi.org/10.1016/j.cbi.2006.06.003> PMID: 16860784
4. Behbahani BA, Yazdi FT, Shahidi F, Mohebbim M. Antimicrobial activity of *Avicennia marina* extracts ethanol, methanol & glycerin against *Penicillium digitatum* (citrus green mold). *Scientific J. of Microbiol* 2012; 7: 147–151. <https://doi.org/10.1016/j.micpath.2017.12.004> PMID: 29208540
5. Thatoi HN, Patra JK, Das SK. Free Radical Scavenging and Antioxidant Potential of Mangrove Plants: a Review. *Acta Physiol. Plant* 2014; 36: 561–579.
6. Das SK, Samantaray D, Patra JK, Samanta L, Thatoi H. Antidiabetic potential of mangrove plants: a review. *Front. Life Sci.* 2016; 9: 75–88. <https://doi.org/10.1080/21553769.2015.1091386>
7. Ravikumar S, Gnanadesigan M, Suganthi P, Ramalakshmi A. Antibacterial potential of chosen mangrove plants against isolated urinary tract infectious bacterial pathogens. *Int. J. Med. Med. Sci.* 2010; 2: 94–99.
8. Fang Xu-B, Jiang B, Che X-E. Structure Identification of an Acidic Pectin HAM-3-IIb-II from *Avicennia Marina* (Forsk.) Vierh. *Chem. J. of Chinese Universities* 2010; 3:492–496.
9. Zhu F, Chen X, Yuan Y, Huang M, Sun H, Xiang W. The Chemical Investigations of the Mangrove Plant *Avicennia marina* and its Endophytes! *Open Nat. Prod. J.* 2009; 2: 24–32. <https://doi.org/10.2174/1874848100902010024>
10. Sharaf M, El-Ansari MA, Saleh NAM. New flavonoids from *Avicennia marina*. *Fitoterapia* 2000; 71: 274–277. [https://doi.org/10.1016/s0367-326x\(99\)00169-0](https://doi.org/10.1016/s0367-326x(99)00169-0) PMID: 10844167
11. Mouafi FE, Abdel-Aziz SM, Bashir AA, Fyiad AA. Phytochemical analysis and antimicrobial activity of mangrove leaves (*Avicenna marina* and *Rhizophora stylosa*) against some pathogens. *World Appl. Sci. J.* 2014; 29:547–554. <https://doi.org/10.5829/idosi.wasj.2014.29.04.13901>
12. Rastogi A, Zivcak M, Sytar O, Kalaji HM, He X, Mbarki S, et al. Impact of Metal and Metal Oxide Nanoparticles on Plant: A Critical Review. *Front. Chem.* 2017; 5: 1–16. <https://doi.org/10.3389/fchem.2017.00001> PMID: 28154813
13. Ruttikay-Nedecky B, Krystofova O, Nejd L, Adam V. Nanoparticles based on essential metals and their phytotoxicity. *J. Nanobiotechnology* 2017; 15:1–19. <https://doi.org/10.1186/s12951-016-0241-6> PMID: 28049488
14. Behravan M, Hossein Panahi A, Naghizadeh A, Ziaee M, Mahdavi R, Mirzapour A. Facile green synthesis of silver nanoparticles using *Berberis vulgaris* leaf and root aqueous extract and its antibacterial activity. *Int. J. Biol. Macromol.* 2019; 124:148–154. <https://doi.org/10.1016/j.ijbiomac.2018.11.101> PMID: 30447360
15. Adhikari T, Kundu S, Biswas AK, Kundu S, Tarafdar JC, Rao AS. Effect of Copper Oxide Nano Particle on Seed Germination of Selected Crops. *J. Agric. Sci. Technol.* 2012; 2: 815–823.
16. Asmathunisha N, Suji R, Kathiresan K. Antifoliary activity of gold Nanoparticles against *Rhizophora apiculata* saplings. *Int. J. of Advanced Res.* 2016; 4: 522–529.
17. Zhao L, Huang Y, Hu J, Zhou H, Adeleye AS, Keller AA. ¹H NMR and GC-MS Based Metabolomics Reveal Defense and Detoxification Mechanism of Cucumber Plant under Nano-Cu Stress. *Environ. Sci. Technol.* 2016; 50: 2000–2010. <https://doi.org/10.1021/acs.est.5b05011> PMID: 26751164

18. Ali SE, Farag MA, Holvoet P, Hanafi RS, Gad MZ. A Comparative Metabolomics Approach Reveals Early Biomarkers for Metabolic Response to Acute Myocardial Infarction. *Sci. Rep.* 2016; 6: 1–14. <https://doi.org/10.1038/s41598-016-0001-8> PMID: 28442746
19. Saifuddin C, Nian L, Ning K. Chitosan-silver Nanoparticles Composite as Point-of-use Drinking Water Filtration System for Household to Remove Pesticides in Water. *Asian J. Biochem.* 2011; 6: 142–159.
20. Essa HL, Abdelfattah MS, Marzouk AS, Guirguis HA. applied sciences Nano-Formulations of Copper Species Coated with Sulfated Polysaccharide Extracts and Assessment of Their Phytotoxicity on Wheat (*Triticum aestivum* L.) Seedlings in Seed Germination, Foliar and Soil Applications. *Applied sciences* 2020; 10: 6302. <https://doi.org/10.3390/app10186302>.
21. Singleton VL, Vitic AJE. Colorimetry of Total Phenolics with Phosphomolybdic-Phosphotungstic Acid Reagents. *Am. J. Enol. Vitic.* 1965, 16, 144–158.
22. Fleita D, El-Sayed M, Rifaat D. Evaluation of the antioxidant activity of enzymatically-hydrolyzed sulfated polysaccharides extracted from red algae; Pterocladia capillacea. *LWT—Food Sci. Technol.* 2015; 63: 1236–1244. <https://doi.org/10.1016/j.lwt.2015.04.024>
23. Essa H, Fleita D, Rifaat D, Samy S, El-Sayed M. Towards optimizing the conventional and ultrasonic-assisted extraction of sulfated polysaccharides from marine algae. *IOP Conf. Ser. Mater. Sci. Eng.* 464.2018. <https://doi.org/10.1088/1757-899X/464/1/012007>
24. Hillis DG, Fletcher J, Solomon KR, Sibley PK. Effects of ten antibiotics on seed germination and root elongation in three plant species. *Arch. Environ. Contam. Toxicol.* 2011; 60: 220–232. <https://doi.org/10.1007/s00244-010-9624-0> PMID: 21107831
25. Angelini R, Manes F, Federico R. Spatial and functional correlation between diamine-oxidase and peroxidase activities and their dependence upon de-etiolation and wounding in chick-pea stems. *Planta.* 1990; 182: 89–96. <https://doi.org/10.1007/BF00239989> PMID: 24197003
26. Goth L. A simple method for determination of serum catalase and revision of reference range. *Clin. Chim. Acta.* 1991; 196:143–152. [https://doi.org/10.1016/0009-8981\(91\)90067-m](https://doi.org/10.1016/0009-8981(91)90067-m) PMID: 2029780
27. Maxwell DP, Bateman DF. Changes in the activities of some oxidases in extracts of Rhizoctonia infected bean hypocotyles in relation to lesion maturation. *Phytopathol.* 1967; 57:132–135.
28. Mayer AM, Harel E. Polyphenol oxidases in plants. *Phytochemistry.* 1979; 18:193–215.
29. Obinna Elijah Nworio Junhao Qin and Lin Chuxia, Trace Element Uptake by Herbaceous Plants from the Soils at a Multiple Trace Element-Contaminated Site, 2019, 7, 3. <https://doi.org/10.3390/toxics7010003> PMID: 30658443
30. Caroling G, Vinodhini E, Ranjitham AM, Shanthy P. Biosynthesis of Copper Nanoparticles Using Aqueous *Phyllanthus Embilica* (Gooseberry) Extract- Characterisation and Study of Antimicrobial Effects. *Int. J. of Nanomater. and Chem.* 2015; 1(2):253–63. <https://doi.org/10.12785/ijnc/010203>
31. Shaikh RR, Mirza SS, Sawant MR, Dare SB. Biosynthesis of Copper Nanoparticles using *Vitis vinifera* Leaf Extract and Its Antimicrobial Activity. *Der Pharmacia Lettre.* 2016; 8 (4): 265–272.
32. Roy K, Sarkar CK, Ghosh CK. Antibacterial mechanism of biogenic copper nanoparticles synthesized using *Heliconia psittacorum* leaf extract. *Nanotechnol. Rev.* 2016; 5: 529–536. <https://doi.org/10.1515/ntrev-2016-0040>
33. El-Rafie HM, El-Rafie MH, Zahran MK. Green synthesis of silver nanoparticles using polysaccharides extracted from marine macro algae. *Carbohydr. Polym.* 2013; 96: 403–410. <https://doi.org/10.1016/j.carbpol.2013.03.071> PMID: 23768580
34. Ananthi S, Balaji Raghavendran HR, Sunil A, Gayathri V, Ramakrishnan G, Vasanthi HR. In vitro antioxidant and in vivo anti-inflammatory potential of crude polysaccharide from *Turbinaria ornata* (Marine Brown Alga), *Food and Chem Toxicol.* 2010; 48: 187–192. <https://doi.org/10.1016/j.fct.2009.09.036> PMID: 19799956
35. Santos SM, Carbajo JM, Quintana E, Ibarra D, Gomez N, Ladero M, et al. Characterization of purified bacterial cellulose focused on its use on paper restoration. *Carbohydr. Polym.* 2015; 116: 173–181. <https://doi.org/10.1016/j.carbpol.2014.03.064> PMID: 25458287
36. Zhang T, Wang W, Zhang D, Zhang X, Yurong M, Zhou Y, et al. Biotemplated synthesis of cold nanoparticle-bacteria cellulose nanofiber nanocomposites and their application in biosensing. *Adv. Funct. Mater.* 2010; 20: 1152–1160. <https://doi.org/10.1002/adfm.200902104>
37. Hu W, Chen S, Zhou B, Wang H. Facile synthesis of ZnO Nanoparticles based on bacterial cellulose. *Materials Sci. and Eng. B,* 2010; 170: 88–92.
38. Gopalakrishnan K, Ramesh C, Ragunathan V, Thamilselvan M. Antibacterial activity of Cu₂O nanoparticles on *E. coli* synthesized from *Tridax procumbens* leaf extract and surface coating with polyaniline. *Dig. J. Nanomater. Biostructures* 2012; 7: 833–839.
39. Duran NM, Savassa SM, Lima RG De, De Almeida E, Linhares FS, Van Gestel CAM, et al. X-ray Spectroscopy Uncovering the Effects of Cu Based Nanoparticle Concentration and Structure on *Phaseolus*

- vulgaris* Germination and Seedling Development. J. Agric. Food Chem. 2017, 65, 7874–7884. <https://doi.org/10.1021/acs.jafc.7b03014> PMID: 28817280
40. Yasmeen F, Razzaq A, Iqbal MN, Jhanzab HM. Effect of silver, copper and iron nanoparticles on wheat germination. Int. J. Biosci. 2015; 6:112–117. <https://doi.org/10.12692/ijb/6.4.112-117>
 41. Jaleel CA, Riadh K, Gopi R, Manivannan P, Ine's J, Al-Juburi HJ, et al. Antioxidant defense responses: physiological plasticity in higher plants under abiotic constraints. Acta Physiol Plant. 2009; 31: 427–436.
 42. Ananda S., Shobha G., Ks S., & Mahadimane V. Nano-cuprous oxide enhances seed germination and seedling growth in *Lycopersicum esculentum* plants Journal of Drug Delivery and Therapeutics. 2019; 9(2), 296–302.
 43. Spielman-sun E, Lombi E, Donner E, Avellan A, Etschmann B, Howard D L, et al. Temporal evolution of copper distribution and speciation in roots of Triticum aestivum exposed to CuO, Cu (OH)₂, and CuS nanoparticles. Environmental Science & Technology. 2018. <https://doi.org/10.1021/acs.est.8b02111>.
 44. Yin L, Colman BP, McGill BM, Wright JP, Bernhardt ES. Effects of Silver Nanoparticle Exposure on Germination and Early Growth of Eleven Wetland Plants. PLoS One 7.2012. <https://doi.org/10.1371/journal.pone.0047674> PMID: 23091638
 45. Hafeez A, Razzaq A, Mahmood T, Jhanzab H M. Potential of Copper Nanoparticles to Increase Growth and Yield of Wheat, J. of Nanoscience with Advanced Technol. 2015; 1(1): 6–11.
 46. Da Costa MVJ, Sharma PK. Effect of copper oxide nanoparticles on growth, morphology, photosynthesis, and antioxidant response in *Oryza sativa*. Photosynthetica 2016; 54:110–119.
 47. Wang S, Liu H, Zhang Y, Xin H. The effect of CuO NPs on reactive oxygen species and cell cycle gene expression in roots of rice. Environ. Toxicol. Chem. 2015; 34: 554–561. <https://doi.org/10.1002/etc.2826> PMID: 25475023
 48. Shaw A.K.; Hossain Z. Impact of nano-CuO stress on rice (*Oryza sativa* L.) seedlings. Chemosphere 2013; 93: 906–915. <https://doi.org/10.1016/j.chemosphere.2013.05.044> PMID: 23791109
 49. Brunner TJ, Wick P, Manser P, Spohn P, Grass RN, Limbach LK, et al. In vitro cytotoxicity of oxide nanoparticles: comparison to asbestos, silica, and the effect of particle solubility. Environ. Sci. Technol. 2006; 40:4374–4381. <https://doi.org/10.1021/es052069i> PMID: 16903273
 50. Eichert T, Kurtz A, Steiner U, Goldbach HE. Size exclusion limits and lateral heterogeneity of the stomatal foliar uptake pathway for aqueous solutes and water-suspended nanoparticles. Physiol. Plant. 2008; 134: 151–160. <https://doi.org/10.1111/j.1399-3054.2008.01135.x> PMID: 18494856
 51. Lin D, Xing B. Phytotoxicity of nanoparticles: Inhibition of seed germination and root growth. Environ. Pollut. 2007; 150: 243–250. <https://doi.org/10.1016/j.envpol.2007.01.016> PMID: 17374428
 52. Tariq M, Dawar S, Mehdi FS, Zaki MJ. Use of *Avicennia marina* (Forsk.) Vierh in the control of root knot nematode *Meloidogyne javanica* (Treub) Chitwood on okra and mash bean. Turkish J. Biol. 2007; 31: 225–230.
 53. Laware SL, Raskar S. Effect of Titanium Dioxide Nanoparticles on Hydrolytic and Antioxidant Enzymes during Seed Germination in Onion. Int.J.Curr.Microbiol.App.Sci. 2014; 3:749–760.
 54. Abdel-Aziz HMM. Effect of Priming with Chitosan Nanoparticles on Germination, Seedling Growth and Antioxidant Enzymes of Broad Beans, The Egyptian Society for Environmental Sciences. 2019; 18:81–86.
 55. Esmaeili N, Ebrahimzadeh H, Abdi K. Correlation Between Polyphenol Oxidase (PPO) Activity and Total Phenolic Contents in *Crocus sativus* L. Corms During Dormancy and Sprouting Stages. Pharmacogn Mag. 2017; 13: S519–S524. <https://doi.org/10.4103/0973-1296.216333> PMID: 29142408
 56. De Tullio MC, Liso R, Arrigoni O. Ascorbic Acid Oxidase: An Enzyme in Search of a Role. Biologia Plantarum 2013; 48:161–166.
 57. Choudhury FK, Rivero RM, Blumwald E, Mittler R. Reactive oxygen species, abiotic stress and stress combination. The Plant Journal 2017; 90:856–867. <https://doi.org/10.1111/tpj.13299> PMID: 27801967
 58. kocaqaliskan I, demir Y, kabar K. A Study on Polyphenol Oxidase Activity During Seed Germination, Phytol. 1995; 35:37–43.
 59. Verma J P, Singh V, Yadav J. Effect of Copper Sulphate on Seed Germination, Plant Growth and Peroxidase Activity of Mung Bean (*Vigna radiata*), International Journal of Botany 2011; 7(2):200–204.
 60. Bailly C. 2004. Active oxygen species and antioxidants in seed biology.: 93–107.
 61. Radulescu C, Stihl C, Popescu I V, Dulama ID, Chelarescu ED, Chilian A, et al. Heavy Metal Accumulation And Translocation In. 2013; 58:1337–1354.
 62. Salama A.; Salama A. The Effect of Foliar Spray with Cyanobacterial Extracts on Growth, Yield and Quality of Lettuce Plants (*Lactuca sativa* L.), 2016, 90–96.

63. Plaksenkova I.; Jermajonoka M.; Bankovska L.; Gavarāne I.; Gerbreders V.; Sledevskis E.; et al. Effects of Fe₃O₄ Nanoparticle Stress on the Growth and Development of Rocket *Eruca sativa*, Journal of Nanomaterials, 2019, 2019, 1–10. <https://doi.org/10.1155/2019/2678247>
64. Nair PMG, Chung IM. Impact of copper oxide nanoparticles exposure on *Arabidopsis thaliana* growth, root system development, root lignification, and molecular level changes, 2014, 21, 12709–12722. <https://doi.org/10.1007/s11356-014-3210-3> PMID: 24965006
65. Gautam S, Misra P, Shukla PK, and Ramteke PW. Effect of Copper Oxide Nanoparticle on the Germination, Growth and Chlorophyll in Soybean (*Glycine max* L.), VEGETOS, (2016)Vol. 29 (Special): 157–160.
66. Racuciu M, Creanga DE (2007) TMA-OH Coated magnetic nanoparticles internalized in vegetal tissue. Roman J Phys 52:395–402.
67. Gohari G., Mohammadi A., Akbari A., Panahirad S., Dadpour M. R., Fotopoulos V., et al. (2020). Titanium dioxide nanoparticles (TiO₂ NPs) promote growth and ameliorate salinity stress effects on essential oil profile and biochemical attributes of *Dracocephalum moldavica*. *Scientific Reports*. <https://doi.org/10.1038/s41598-020-57794-1> PMID: 31969653
68. Bharali B, Chetia H, Kalita J, Mosahiri P V, Chhillar A K, Bora U, Engineered Nanomaterials and Phytotechnology: Challenges for Plant Sustainability, Volume 87, 1st Edition, Imprint: Elsevier, Published Date: 20th November 2019.
69. Suriyaprabha R, Karunakaran G, Yuvakkumar R, Rajendran V, Kannan N (2012) Silica nanoparticles for increased silica availability in maize (*Zea mays* L) seeds under hydroponic conditions. Curr Nanosci 8:902–908.
70. Lu C, Zhang C, Wen J, Wu G, Tao MX. Research of the effect of nanometer materials on germination and growth enhancement of *Glycine max* and its mechanism. Soybean Sci. 2002; 21:168–171.
71. Yang F, Hong F, You W, Liu C, Gao F, Wu C, et al. (2006) Influence of nano-anatase TiO₂ on the nitrogen metabolism of growing spinach. Biol Trace Elem Res 110(2):179–190. <https://doi.org/10.1385/bter.110.2.179> PMID: 16757845
72. Mishra V, Mishra RK, Dikshit A, Pandey AC (2014) Interactions of nanoparticles with plants: an emerging prospective in the agriculture industry. In: Ahmad P, Rasool S(eds) Emerging technologies and management of crop stress tolerance: biological techniques, vol 1, pp 159–180.
73. Govorov AO, Carmeli I (2007) Hybrid structures composed of photosynthetic system and metal nanoparticles: plasmon enhancement effect. Nano Lett 7(3):620–625 <https://doi.org/10.1021/nl062528t> PMID: 17309315
74. Adhikari T, Kundu S, Biswas AK, Kundu S, Tarafdar JC and Rao AS. (2012). Effect of Copper Oxide Nano Particle on Seed Germination of Selected Crops. Journal of Agricultural Science and Technology A Journal of Agricultural Science and Technology.
75. Navarro E, Piccapietra F, Wagner B, et al. Toxicity of silver nanoparticles to *Chlamydomonas reinhardtii*. Environ Sci Technol. 2008; 42(23):8959–8964. <https://doi.org/10.1021/es801785m> PMID: 19192825
76. Peng C, Duan D, Xu C, et al. Translocation and biotransformation of CuO nanoparticles in rice (*Oryza sativa* L.) <https://doi.org/10.1016/j.envpol.2014.12.008> PMID: 25521412