

Biomaterials for orbital fractures repair

Totir M*, Ciuluvica R**, Dinu I*, Careba I*, Gradinaru S***

*University Emergency Hospital Bucharest, 126 Splaiul Independentei Blvd, Bucharest, Romania

**UMF "Carol Davila" Anatomy Department, 8 Eroilor Sanitari Blvd, Bucharest, Romania

***UMF "Carol Davila" Ophthalmology Department, 8 Eroilor Sanitari Blvd, Bucharest, Romania

Correspondance to: Ciuluvica Radu MD

UMP "Carol Davila" Anatomy Department,

8 Eroilor Sanitari Blvd, Bucharest, Romania,

Tel: 0744.618.555, **Email:** raduciuluvica@yahoo.com

Abstract

The unique and complex anatomy of the orbit requires significant contouring of the implants to restore the proper anatomy. Fractures of the orbital region have an incidence of 10-25% from total facial fractures and the most common age group was the third decade of life.

The majority of cases require reconstruction of the orbital floor to support the globe position and restore the shape of the orbit. The reason for this is that the bony walls are comminuted and/or bone fragments are missing. Therefore, the reconstruction of missing bone is important rather than reducing bone fragments. This can be accomplished using various materials. There is hardly any anatomic region in the human body that is so controversial in terms of appropriate material used for fracture repair: nonresorbable versus resorbable, autogenous/allogenic/xenogenous versus alloplastic material, non-prebent versus preformed (anatomical) plates, standard versus custom-made plates, nonporous versus porous material, non-coated versus coated plates. Thus, the importance of material used for reconstruction becomes more challenging for the ophthalmologist and the oral and maxillofacial surgeon.

Keywords: orbital fracture, titanium mesh, bone graft, reconstruction

Introduction

Fractures of the orbital region has an incidence of 10-25% from total facial fractures [1] and the most common age group was the third decade of life (29%) [2]. The most common etiology seems to be violent assault or nonviolent traumatic injury (49.4%) [2] and the most frequent fracture involved the zygoma (23.6%), followed by the orbital floor (21.4%), maxilla, mandible and nasal bones [3]. For these patients modern imaging analysis offers a unique chance to quantitatively asses the surgical result and stability over the time. This can provide valuable information for future recommendation [4]. Careful assessment of the defect size should be performed preoperatively with the CT scan in the sagittal view which is in the course of the orbital nerve, plus the coronal view [5].

Jaquiéry differentiated between the following classes in orbital trauma [6]:

Class I: Small, isolated defects of the orbital floor or the medial orbital wall of approx. 1 – 2 cm²

Class II: Defects of the orbital floor and/or the medial orbital wall > 2 cm², bony structures of the medial wall of the infraorbital fissure are intact.

Class III: Defects of the orbital floor and/or the medial orbital wall > 2 cm², without bony structures of the infraorbital fissure.

Class IV: Defects of the whole orbital floor and the medial wall to the infraorbital fissure. The timing of surgery has also been debated over the years. Except in the circumstance of a trapdoor fracture with the potential for an ischemic contracture of the entrapped tissue, generally is allowed several days for orbital and eyelid edema to resolve. This delay also allows more accurate assessment of extraocular muscle function [7].

As demonstrated by studies, there is lack of consensus in recognizing one material as the optimal one for orbital reconstruction. Available products are:

1. Titanium meshes presents a series of advantages [8],[9]. In 2009 Scollozzi revealed in his paper a high rate of success with an acceptable rate of major clinical complications (10%) and an anatomic restoration of the bony orbital contour and volume that closely approximates that of the contralateral uninjured orbit.[10]

Advantages:

- Availability
- Stability
- Contouring (eased by the artificial sterile skull)
- Adequate in large three-wall fractures (the pre-bent plate is limited to medial wall and orbital wall fractures only).
- Radio-opacity
- Spaces within the mesh to allow dissipation of fluids
- No donor site needed

- Tissue incorporation may occur

Disadvantages:

- Costs
- Possible sharp edges if not properly trimmed

2. Bone graft: in 2012 a paper by Zunz et al conclude that construction of orbital floor fractures after trauma using autologous bone grafts is safe and associated with a low rate of complications [11].

Advantages:

- Low material costs
- Smooth surface
- Variability in thickness
- Radio-opacity
- Maximal biocompatibility
- Periorbita readily dissects off of the bone in secondary reconstructions

Disadvantages:

- Additional donor site needed (necessitating additional surgery time for harvest, pain, scar and possible surgical complications)
 - Possible contour and dimensional changes due to remodeling
 - Difficult to shape according to patients anatomy
 - Less drainage from the orbit than with titanium mesh
3. Porous polyethylene sheets (PPE) In a study published by Lin was demonstrated that porous polyethylene implants in the repair of orbital wall fractures had good results with few complications [12].

Advantages:

- Availability
- Contouring (eased by the artificial sterile skull)
- Smooth edges
- Allows tissue ingrowth

Disadvantages:

- Not radiopaque (not visible on postoperative images)
- Lack of rigidity when a very thin wafer of PPE is used. When a thicker rigid wafer is used there is a risk of causing a dystopia.
- Less drainage from the orbit than with titanium mesh

4. Composite of porous polyethylene and titanium mesh

By combining titanium mesh with porous polyethylene the material becomes radiopaque and more rigid than porous polyethylene of a similar thickness. Some surgeons also believe that there is less risk of having retained sharp barbs, which can lead to an entrapment of soft tissues during placement [13].

Advantages:

- Availability
- Stability
- Contouring (eased by the artificial sterile skull)
- Adequate in large three-wall fractures (the pre-bent plate is limited to medial wall and orbital wall fractures only).
- Radio-opacity
- No donor site needed
- Tissue incorporation may occur

Disadvantages:

- Less drainage from the orbit than with titanium mesh

5. Resorbable materials :Thermoplastic and non-thermoplastic materials

Thermoplastic blends of cornstarch material with ethylene vinyl alcohol copolymers reinforced with hydroxyapatite were used based on their mechanical properties and their modulus closed to that of human bone [14].

Advantages:

- Availability
- Handling/contourability (only for thermoplastics)
- Smooth surface and smooth edges

Disadvantages:

- No radio-opacity
- Degradation of material with possible contour loss

- Sterile infection / inflammatory response
 - Difficult to shape according to patients anatomy (only for non-thermoplastics)
 - Less drainage from the orbit than with uncovered titanium mesh (in case when non-perforated material is used)
6. Preformed orbital implant: Bittermann shows that using computer-assisted techniques, anatomically preformed orbital implants and intraoperative imaging the surgeon can have precise and predictable results of orbital reconstructions [15].

Advantages:

- Radio-opacity
- Smooth surface
- Minimal or no contouring necessary

Disadvantages:

- Cost

The first step in a choice for an implant is to focus on its most important features in order to reduce complications incidence.

These features should be: light weight, porosity (the implant must allow vascular orbital tissues to invade its structure), biocompatibility (the implant has to be tolerated and accepted by the orbital tissues), low rate complications, easy to insert, economic cost. (**Table 1**) illustrates factors influencing the decision for the implant choice.

Table 1

Factors influencing decision for the choice of the material

Surgeon experience

Severity of fracture

Individual characteristics

Cost

The multitude materials with different results in published studies show that we don't have the answer for the best type of implant for orbital reconstruction. With the increasing need to develop clean, non-toxic and environmentally friendly techniques, hydroxyapatite powders have been extracted using bioproducts from marine sources (e.g. coral, cuttlefish shells), animal teeth and bones (porcine, bovine), natural gypsum or natural calcite [16, 17]. Compared with hydroxyapatite produced by synthetic methods, hydroxyapatite generated partially or entirely from biogenic sources is supposed to be accepted better by the living organisms, because of its physic-chemical similarity to the human bone apatite.

References

1. Erdmann D, Follmar K E, Debruijn M, et al. A retrospective analysis of facial fracture etiologies. Ann Plast Surg. 2008;60:398–403
2. Hwang K, You SH. Analysis of facial bone fractures: An 11-year study of 2,094 patients. Indian J Plast Surg. 2010 Jan;43(1):42-8.
3. Scherer M, Sullivan W G, Smith D J, Jr, Phillips L G, Robson M C. An analysis of 1,423 facial fractures in 788 patients at an urban trauma center. J Trauma. 1989;29:388–390
4. Exadaktylos A K, Sclabas G M, Smolka K, et al. The value of computed tomographic scanning in the diagnosis and management of orbital fractures associated with head trauma: a prospective, consecutive study at a level I trauma center. J Trauma. 2005;58:336–341
5. Dobrovăt B, R. Popescu, A. Nemtoi, O. Ladunca, D. Haba, Orbital trauma: from anatomy to imaging patterns – a pictorial review, Romanian Neurosurgery (2011) XVIII 4: 525 - 532 525
6. Jaquieré C, Aepli C, Cornelius P, Palmowsky A, Kunz C, Hammer B, Reconstruction of orbital wall defects: critical review of 72 patients. Int J Oral Maxillofac Surg. 2007 Mar;36(3):193-9.
7. Hollier L H, Rogers N, Berzin E, Stal S. Resorbable mesh in the treatment of orbital floor fractures. J Craniofac Surg. 2001;12:242–246.
8. Ellis E, III, Tan Y. Assessment of internal orbital reconstructions for pure blowout fractures: cranial bone grafts versus titanium mesh. J Oral Maxillofac Surg. 2003;61:442–453.
9. Gabrielli MF, Silva Monnazzi M, Passeri LA, Carvalho WR, Gabrielli M, Hochuli-Vieira E, Orbital Wall Reconstruction with Titanium Mesh: Retrospective Study of 24 Patients Craniomaxillofac Trauma Reconstr. Sep 2011; 4(3): 151–156.
10. Scolozzi P, Momjian A, Heuberger J, Andersen E, Broome M, Terzic A, Jaques B. Accuracy and predictability in use of AO three-dimensionally preformed titanium mesh plates for posttraumatic orbital reconstruction: a pilot study. J Craniofac Surg. 2009 Jul; 20(4):1108-13.
11. Zunz E, Blanc O, Leibovitch I. Traumatic orbital floor fractures: repair with autogenous bone grafts in a tertiary trauma center. J Oral Maxillofac Surg. 2012 Mar;70(3):584-92
12. Lin IC, Liao SL, Lin LL. Porous polyethylene implants in orbital floor reconstruction. J Formos Med Assoc. 2007 Jan;106(1):51-7.
13. Bratton EM1, Durairaj VD. Orbital implants for fracture repair. Curr Opin Ophthalmol. 2011 Sep;22(5):400-6.
14. Swenson RW, Koopmann CF Jr. Grafts and implants. Otolaryngol Clin North Am. 1984 May;17(2):413-28.
15. Bittermann G, Metzger MC, Schlager S, Lagrèze WA, Gross N, Cornelius CP, Schmelzeisen R. Orbital reconstruction: prefabricated implants, data transfer, and revision surgery. Facial Plast Surg. 2014 Oct;30(5):554-60.
16. Zhou H., Lee J., Nanoscale hydroxyapatite particles for bone tissue engineering, Acta Biomaterialia 7 (2011) 2769–2781
17. Yi-Cheng Huang, Pei-Chi Hsiao, Huey-Jine Chai, Hydroxyapatite extracted from fish scale: Effects on MG63 osteoblast-like cells, Ceramics International, 37, 2011, p. 1825-1831