

# Assessment and comparison of retention of zirconia copings luted with different cements onto zirconia and titanium abutments: An *in vitro* study

Neelima Sreekumar Menon, G. P. Surendra Kumar, K. R. Jnanadev, C. L. Satish Babu, Shilpa Shetty

Department of Prosthodontics, VS Dental College and Hospital, Bengaluru, Karnataka, India

## Abstract

**Aim:** The purpose of this *in vitro* study was to assess and compare the retention of zirconia copings luted with different luting agents onto zirconia and titanium abutments.

**Materials and Methods:** Titanium and zirconia abutments were torqued at 35 N/cm onto implant analogs. The samples were divided into two groups: Group A consisted of four titanium abutments and 32 zirconia copings and Group B consisted of four zirconia abutments and 32 zirconia copings and four luting agents were used. The cemented copings were subjected to tensile dislodgement forces and subjected to ANOVA test.

**Results:** Zirconia abutments recorded a higher mean force compared to titanium. Among the luting agents, resin cement recorded the highest mean force followed by zinc phosphate, glass ionomer, and noneugenol zinc oxide cement, respectively.

**Conclusion:** Highest mean retention was recorded for zirconia implant abutments compared to titanium abutments when luted with zirconia copings.

**Key Words:** Titanium abutment, zirconia abutment, zirconia copings

## Address for correspondence:

Dr. Neelima Sreekumar Menon, Department of Prosthodontics, VS Dental College and Hospital, K R Road, VV Puram, Bengaluru, Karnataka, India.

E-mail: neelimenon@gmail.com

Received: 4<sup>th</sup> February, 2015, Accepted: 19<sup>th</sup> November, 2015

## INTRODUCTION

Main goals of restorations in modern dentistry are optimal function and esthetics.<sup>[1]</sup> The options for restoring edentulous areas have changed dramatically with the introduction of endosseous dental implants. Clinical decisions are not only limited to the selection of the type of implant but also the type of abutment and cement used.<sup>[2]</sup> Initially, implant-supported prostheses were exclusively retained by screws, but with the development of new implant systems

and rehabilitation techniques cement retained prostheses have become popular treatment option. Cement-retained superstructures over the implant abutments assure passive fit because of the cement layer between the framework and abutment. Other advantages of cement-retained implant restorations include improved direction of load, enhanced esthetics, easy access, reduced fabrication cost and time, simplified restorative procedures, and optimum occlusion excluding the interference of screw access openings.

This is an open access article distributed under the terms of the Creative Commons Attribution-NonCommercial-ShareAlike 3.0 License, which allows others to remix, tweak, and build upon the work non-commercially, as long as the author is credited and the new creations are licensed under the identical terms.

For reprints contact: reprints@medknow.com

Access this article online	
Quick Response Code:	Website: www.j-ips.org
	DOI: 10.4103/0972-4052.176540

**How to cite this article:** Menon NS, Surendra Kumar GP, Jnanadev KR, Satish Babu CL, Shetty S. Assessment and comparison of retention of zirconia copings luted with different cements onto zirconia and titanium abutments: An *in vitro* study. J Indian Prosthodont Soc 2016;16:136-41.

Limitations associated with the cement-retained implant restorations include low profile retention, when there is limited interarch space, retrievability, and presence of cement in the sulcus.<sup>[3]</sup> Commercially, pure titanium has been widely used as an abutment material in implant therapy because of its well-documented biocompatibility and mechanical properties. Recently, zirconia implant abutment materials have gained popularity because of their better fracture resistance and superior optical properties over titanium.<sup>[2]</sup> Selection of luting agent is very important for cement-retained implant prostheses and it is largely dependent on operator preference, convenience, and manufacturer recommendations. Ideal luting agent should be strong enough to retain the restorations yet weak enough so that restorations can be removed easily if required.<sup>[4]</sup> The aim of this study was to assess and compare the retentive strengths of different classes of luting agents used to cement zirconia copings to titanium and zirconia implant abutments.

## MATERIALS AND METHODS

### Materials

Materials used in the present study included eight implant analogs (Collagen Meniscus Implant [CMI]), four titanium [Figure 1] abutments (CMI, hexed abutment), four zirconia abutments [Figure 2], and 64 zirconia copings (Lava, Zirconia 3M ESPE) [Figures 3 and 4]. The luting agents used were resin cement (Calibra-Densply), glass ionomer (GC gold label luting and lining cement), zinc phosphate (Harvard Cement), and zinc oxide noneugenol (Rely X™ Temp NE) cements.


### Methodology

#### *Fabrication of resin blocks and embedding specimen*

Eight implant analogs (CMI) were embedded in acrylic resin blocks, titanium and zirconia abutments were torqued into implant analogs. Acrylic resin blocks were fabricated to facilitate mounting the specimen on tensile strength testing machine. Implant analogs were embedded into acrylic block. Abutments were torqued onto implant analogs. An 8 mm diameter hole was drilled at the end of acrylic block to facilitate mounting the specimen on tensile testing machine. A single operator prepared all eight resin blocks and implant analogs were embedded, and abutments were torqued at 35 N/cm. Both zirconia and titanium abutments used in the study were of 7.4 mm in height with 8° convergence angle and 5.8 mm in diameter.<sup>[5]</sup>

#### *Fabrication of zirconia copings*


Samples were divided into two groups. Group A consisted of four titanium abutments and 32 zirconia copings. Group B consisted of four zirconia abutments and 32 copings. Resin pattern were made for zirconia copings; an extension was made on the occlusal surface of each coping parallel to long axis of



**Figure 1:** Titanium abutment mounted on acrylic resin blocks



**Figure 2:** Zirconia abutment mounted on acrylic resin blocks



**Figure 3:** Group A consisting of four titanium abutments and 32 zirconia copings


the tooth to serve as a connector to the tensile strength testing machine. zirconia copings thus designed were milled with computer aided designing – computer aided manufacturing unit.

### Cementation of copings

Both Groups A and B were randomly divided into four groups each comprising specimens Groups I-4. Zirconia copings in Groups AI and BI were cemented with glass ionomer (GC gold label luting and lining cement) cement, Groups A2 and B2 were cemented with resin cement (Calibra-Densply), Groups A3 and B3 were cemented with zinc oxide noneugenol cement (Rely X™ Temp NE), and Groups A4 and B4 were cemented with zinc phosphate cement (Harvard Cement). Each coping of all groups was sandblasted with 50 µm aluminum oxide before cementation. Cements were mixed according to the manufacturer's instructions and were applied in a thin layer to the inner axial walls of the crown. Each coping was seated on its perspective abutment with firm finger pressure and then placed under a 10 kg weight for 5 min and cementation was carried out [Figure 5]. Excess cement was removed with an explorer.

### Thermocycling and tensile testing

Specimens were stored at room temperature for 24 h and immersed in artificial saliva for 7 days, after which specimens were thermo cycled 100 times between 5°C and 55°C with



**Figure 4:** Group B consisting of four zirconia abutments and 32 zirconia copings



**Figure 6:** Tensometer

a dwell time of 10 s, dried and subjected to retention test.<sup>[6]</sup> The cemented copings were subjected to tensile dislodgement forces using crosshead speed of 0.5 mm/min until cement failure occurred<sup>[4]</sup> [Figures 6-8]. The same abutment was used with each of the coping and four cements were evaluated. Abutments were cleaned with a plastic explorer. Abutments were immersed in an ultrasonic cleaner for 15 min and re-used.

### RESULTS


Results obtained from the retention test were statistically analyzed using factorial ANOVA test.

Among the cements, the highest mean force was recorded in resin cement followed by zinc phosphate, glass ionomer, and noneugenol zinc oxide, respectively. The difference in mean force recorded between them was found to be statistically significant ( $P < 0.001$ ) [Table 1].

Between the two abutments, the higher mean force was recorded in zirconia and the difference in mean force between zirconia and titanium was found to be statistically significant ( $P < 0.001$ ) [Table 2].



**Figure 5:** Device used to apply load on coping during cementation



**Figure 7:** Specimens mounted on tensometer

**Table 1: Depicts the mean tensile force recorded for all the four cements**

Cement	Mean	SD	SE of mean	Median	Minimum	Maximum
Glass ionomer	99.38	27.46	6.86	102.0	49	139
Noneugenol zinc oxide	16.31	5.79	1.45	16.0	6	29
Resin cement	552.63	118.39	29.60	575.5	370	720
Zinc phosphate	251.44	49.36	12.34	258.5	176	327

SD: Standard deviation, SE: Standard error

**Table 2: Depicts the mean tensile force recorded for the two abutments**

Abutment	Mean	SD	SE of mean	Median	Minimum	Maximum
Zirconia	271.50	246.26	43.53	200.0	13	720
Titanium	188.38	174.55	30.86	139.0	6	556

SD: Standard deviation, SE: Standard error


The interaction (joint effect) of cement and abutment on force was also found to be statistically significant ( $P < 0.001$ ) [Table 3 and Graph 1].

Noneugenol zinc oxide cement always had a lower mean force when used with titanium or zirconia abutments. Resin cement always has a higher mean force compared to other cements when used either with titanium or zirconia abutment. All the cements yield a higher mean force when used with zirconia abutment compared to titanium abutment.


After resin cement, the higher mean force was recorded in zinc phosphate and glass ionomer, respectively [Table 4 and Graph 2].

**DISCUSSION**


Prosthetic rehabilitation of edentulous areas using implants has become a popular treatment modality. All ceramic crowns are used in implants more often than metal ceramic crowns to enhance esthetics. The most commonly used material in all ceramic being zirconia due to its high flexibility, fracture toughness, biocompatibility, and excellent esthetics. Zirconia abutments in comparison with titanium abutments enhance the esthetic effect especially in case of maxillary anterior implants, since they do not allow display of metal, unlike titanium abutments.<sup>[7]</sup> Mansour *et al.* found that the rank order of cement retentiveness differed when tested on implants rather than on natural teeth.<sup>[8]</sup> Among the four types of cements used to lute Zirconia copings, resin cement showed the highest mean force when used with zirconia as well as titanium abutments. The higher mean retention of resin cement, when used along with Zirconia abutments, is due to the presence of adhesive phosphate monomer in the resin cement that enhances the bonding between them. Sandblasting of zirconia copings also enhances the retention by increasing the microroughness of the surface.<sup>[9,10]</sup> Studies conducted by Barbosa *et al.* have proved that resin cements bond with the titanium alloy by reacting with metal oxides. The phosphate ester group of acidic monomer



**Figure 8:** Samples subjected to dislodging forces



**Graph 1:** Main effects plot depicting the mean tensile force recorded with four cements and zirconia and titanium abutments



**Graph 2:** Interaction plot depicting the mean tensile force recorded with four cements and zirconia and titanium abutments

**Table 3: Depicts the mean tensile force recorded for both cement and abutment**

Cement	Abutment	Mean	SD	SE of mean	Median	Minimum	Maximum
Glass ionomer	Zirconia	120.13	12.29	4.34	120.0	102	139
	Titanium	78.63	21.92	7.75	84.0	49	102
Noneugenol zinc oxide	Zirconia	20.00	4.99	1.76	19.0	13	29
	Titanium	12.63	4.00	1.41	13.5	6	18
Resin cement	Zirconia	654.25	39.31	13.90	649.5	595	720
	Titanium	451.00	69.87	24.70	439.5	370	556
Zinc phosphate	Zirconia	291.63	21.76	7.69	290.5	261	327
	Titanium	211.25	32.50	11.49	208.0	176	256

SD: Standard deviation, SE: Standard error

**Table 4: Depicts the statistical significance**

Source	df	SS	Mean SS	F	P
Cement	3	2,676,346.875	892,115.625	827.080	<0.001*
Abutment	1	110,556.250	110,556.250	102.500	<0.001*
Cement × abutment	3	87,633.125	29,211.042	27.080	<0.001*
Error	56	60,403.500	1078.634	-	-
Total	63	2,934,939.750	-	-	-

SS: Sum of square, The difference in mean force recorded between the cements, between the abutments and interaction between cement and abutment on force were found to be statistically significant. ( $P < 0.001$ )

results in chemical bonding with metal oxides. Studies have also proved that sandblasting the titanium abutment surface with alumina also enhances the bonding between resin cement and titanium abutment.<sup>[11]</sup> D'Amario *et al.*<sup>[3]</sup> noted that bond strength of resin cement decreased when subjected to thermocycling, which resulted in weakening the bond between zirconia and resin cement leading to bond failure.

Following resin cement second highest mean retention was recorded for zinc phosphate cement. Zinc phosphate cement provides retention by micromechanical bonding. The surface irregularities on the abutment/coping improve the retention. In this study, machined abutment (zirconia and titanium) surface was not modified with any preparation or surface treatments and therefore relatively smooth.<sup>[12]</sup> This could have decreased the cement abutment micromechanical interlocking leading to debonding of zirconia copings from the respective abutments. Bond failure may also be affected by thermocycling process since zinc phosphate cement exhibit solubility in water. Following zinc phosphate cement, the next highest mean retentive force recorded was for glass ionomer cement. Adhesion in glass ionomer is as a result of molecular interactions of an ionic/polar nature. It does not adhere to the inert surfaces of metal and metal oxides, unlike resin cements where phosphate ester groups directly bonds with the metal oxides. Studies have revealed that the solubility of glass ionomer cement is more than that of zinc phosphate and is very susceptible to early water contact and desiccation which can dramatically reduce the mechanical properties of cement.<sup>[13]</sup> The least retentive force was recorded with noneugenol zinc oxide cement. It may be due to its poor marginal seal and high solubility in water. Temp-Bond has higher solubility in direct contact with water

and also requires sufficient time for complete setting reaction in order to maximize retention.<sup>[12]</sup>

## CONCLUSION

Within the limitations of this study, following conclusions were drawn:

Highest mean retention was recorded for zirconia copings cemented on to zirconia abutments when compared to titanium abutments. Zirconia copings when luted onto zirconia abutments, highest mean retention were recorded with resin cement followed by zinc phosphate cement and glass ionomer cement. Least mean retention was recorded with noneugenol zinc oxide cement. Zirconia copings when luted onto titanium abutments highest mean retention was recorded with resin cement followed by zinc phosphate cement and glass ionomer cement. Least mean retention was recorded with noneugenol zinc oxide cement. The above study provides a superficial idea about the retention of zirconia copings with four different types of luting on to zirconia as well as titanium abutments, which will help the clinician in deciding during prosthetic rehabilitation with implant-supported restorations. The study also highlights the chemical and mechanical factors that influence retention of cements onto the abutments. Scanning electron microscopic analysis must be required to provide a more accurate analysis on the bonding mechanisms, which is a limitation of the present study.

## Financial support and sponsorship

Nil.

## Conflicts of interest

There are no conflicts of interest.

## REFERENCES

- Ebert A, Hedderich J, Kern M. Retention of zirconia ceramic copings bonded to titanium abutments. *Int J Oral Maxillofac Implants* 2007;22:921-7.
- Abbo B, Razzoog ME, Vivas J, Sierraalta M. Resistance to dislodgement of zirconia copings cemented onto titanium abutments of different heights. *J Prosthet Dent* 2008;99:25-9.
- D'Amario, Campidoglio M, Morresi AL, Luciani L, Marchetti E, Baldi M.

- Effect of thermo cycling on the bond strength between dual cured resin cements and zirconium oxide ceramics. *J Oral Sci* 2010;52:425-30.
4. Goknil EK, Ceylan G, Nergiz Y, Bahar EK. Luting agent effectiveness on implant crown retention. *Int J Oral Implantol Clin Res* 2011;2:7-11.
  5. Kokubo Y, Kano T, Tsumita M, Sakurai S, Itayama A, Fukushima S. Retention of zirconia copings on zirconia implant abutments cemented with provisional luting agents. *J Oral Rehabil* 2010;37:48-53.
  6. Pan YH, Lin CK. The effect of luting agents on the retention of dental implant-supported crowns. *Chang Gung Med J* 2005;28:403-10.
  7. Kim SM, Yoon JY, Lee MH, Oh NS. The effect of resin cements and primer on retentive force of zirconia copings bonded to zirconia abutments with insufficient retention. *J Adv Prosthodont* 2013;5:198-203.
  8. Mansour A, Ercoli C, Graser G, Tallents R, Moss M. Comparative evaluation of casting retention using the ITI solid abutment with six cements. *Clin Oral Implants Res* 2002;13:343-8.
  9. Blatz MB, Dent M, Sadan A, Kern M. Resin-ceramic bonding: A review of the literature. *J Prosthet Dent* 2003;89:268-74.
  10. Usume A, Hamdemirci N, Koroglu BY, Simsek I, Parlar O, Sari T. Bond strength of resin cement to zirconia ceramic with different surface treatments. *Lasers Med Sci* 2013;28:259-66.
  11. Barbosa SH, Pelógia F, Daniel O, Antonio M. Durability of bond strength between titanium alloy and resin cement. *Cienc Odontol Bras* 2008;11:13-8.
  12. Squier RS, Agar JR, Duncan JP, Taylor TD. Retentiveness of dental cements used with metallic implant components. *Int J Oral Maxillofac Implants* 2001;16:793-8.
  13. Yu H, Zheng M, Chen R, Cheng H. Proper selection of contemporary dental cements. *Oral Health Dent Manag* 2014;13:54-9.

### Author Help: Online submission of the manuscripts

Articles can be submitted online from <http://www.journalonweb.com>. For online submission, the articles should be prepared in two files (first page file and article file). Images should be submitted separately.

1) **First Page File:**

Prepare the title page, covering letter, acknowledgement etc. using a word processor program. All information related to your identity should be included here. Use text/rtf/doc/pdf files. Do not zip the files.

2) **Article File:**

The main text of the article, beginning with the Abstract to References (including tables) should be in this file. Do not include any information (such as acknowledgement, your names in page headers etc.) in this file. Use text/rtf/doc/pdf files. Do not zip the files. Limit the file size to 1 MB. Do not incorporate images in the file. If file size is large, graphs can be submitted separately as images, without their being incorporated in the article file. This will reduce the size of the file.

3) **Images:**

Submit good quality color images. Each image should be less than 4096 kb (4 MB) in size. The size of the image can be reduced by decreasing the actual height and width of the images (keep up to about 6 inches and up to about 1800 x 1200 pixels). JPEG is the most suitable file format. The image quality should be good enough to judge the scientific value of the image. For the purpose of printing, always retain a good quality, high resolution image. This high resolution image should be sent to the editorial office at the time of sending a revised article.

4) **Legends:**

Legends for the figures/images should be included at the end of the article file.