




ORIGINAL ARTICLE

Cross-linked hyaluronic acid gel with or without a collagen matrix in the treatment of class III furcation defects: A histologic and histomorphometric study in dogs

Yoshinori Shirakata¹  | Takatomo Imafuji¹ | Toshiaki Nakamura¹  |
Yukiya Shinohara¹ | Masayuki Iwata¹ | Fumiaki Setoguchi¹ | Kazuyuki Noguchi¹ |
Anton Sculean² 

¹Department of Periodontology, Kagoshima University Graduate School of Medical and Dental Sciences, Kagoshima, Japan

²Department of Periodontology, School of Dental Medicine, University of Bern, Bern, Switzerland

Correspondence

Yoshinori Shirakata, 8-35-1 Sakuragaoka,
Kagoshima 890-8544, Japan.
Email: syoshi@dent.kagoshima-u.ac.jp

Funding information

Grants-in-Aid for Scientific Research C, Grant/
Award Number: 20K10011; REGEDENT AG

Abstract

Aim: To histologically evaluate the effects of cross-linked hyaluronic acid (xHyA) with or without a collagen matrix (CM) on periodontal wound healing/regeneration in class III furcation defects in dogs.

Materials and Methods: Class III furcation defects were surgically created in the mandibular premolars in six beagle dogs. The defects were randomly treated as follows: open flap debridement (OFD) + CM (CM), OFD + xHyA (xHyA), OFD + xHyA + CM (xHyA/CM) and OFD alone (OFD). At 10 weeks, the animals were euthanized for histological evaluation.

Results: The newly formed bone areas in the xHyA ($4.04 \pm 1.51 \text{ mm}^2$) and xHyA/CM ($4.32 \pm 1.14 \text{ mm}^2$) groups were larger than those in the OFD ($3.25 \pm 0.81 \text{ mm}^2$) and CM ($3.31 \pm 2.26 \text{ mm}^2$) groups. The xHyA ($6.25 \pm 1.45 \text{ mm}$) and xHyA/CM ($6.40 \pm 1.35 \text{ mm}$) groups yielded statistically significantly ($p < .05$) greater formation of new connective tissue attachment (i.e., new cementum, with inserting connective tissue fibres) compared with the OFD ($1.47 \pm 0.85 \text{ mm}$) group. No significant differences were observed in any of the histomorphometric parameters between the xHyA and xHyA/CM groups. Complete furcation closure was not observed in any of the four treatment modalities.

Conclusions: Within their limits, the present results suggest that the use of xHyA with or without CM positively influences periodontal wound healing in surgically created, acute-type class III furcation defects.

KEYWORDS

biomaterials, collagen matrix, furcation defect, hyaluronic acid, periodontal wound healing/regeneration

This is an open access article under the terms of the [Creative Commons Attribution-NonCommercial](https://creativecommons.org/licenses/by-nc/4.0/) License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited and is not used for commercial purposes.

© 2022 The Authors. *Journal of Clinical Periodontology* published by John Wiley & Sons Ltd.

Clinical Relevance

Scientific rationale for study: The potential effect of xHyA with or without volume-stable collagen matrix (CM) on periodontal wound healing/regeneration in class III furcation defects is currently unknown.

Principal findings: The application of xHyA with or without CM promoted periodontal healing in class III furcation defects, although complete furcation closure was not achieved.

Practical implications: The present findings indicate that xHyA is an effective biomodulator for facilitating periodontal wound healing/regeneration in class III furcation defects. Further studies are needed to determine the optimal scaffold/carrier for xHyA to further improve the outcomes of regenerative surgery.

1 | INTRODUCTION

Periodontal regeneration is one of the ultimate goals of periodontal therapy because of the potential to change the prognosis of questionable or even hopeless teeth to one of retention and long-term maintenance (Cortellini et al., 2017, 2020; Stavropoulos et al., 2021), thus preventing tooth loss and saving dental care costs (Fardal & Grytten, 2013; Cortellini et al., 2017, 2020). In recent decades, various periodontal reconstructive/regenerative procedures such as the use of bone substitutes, barrier membranes, various biologics/growth factors (e.g., enamel matrix derivative [EMD], platelet-derived growth factor [PDGF] and basic fibroblast growth factor [FGF-2]) have been used alone or in various combinations. Positive clinical (including clinical attachment level [CAL] gain and probing pocket depth [PPD] reduction) and radiographical outcomes have been reported, together with high levels of patient satisfaction (Camelo et al., 1998; Kitamura et al., 2016; Miron et al., 2016; Li et al., 2017). Human histological evidence for true regeneration of root cementum, alveolar bone and periodontal ligament (PDL) has also been reported, especially for decalcified freeze-dried bone allograft, demineralized bovine bone mineral, EMD and PDGF (Sculean et al., 2015; Nibali et al., 2020). Despite the successful results, several studies have demonstrated inconsistent and/or unfavourable results following various periodontal reconstructive/regenerative approaches, possibly due to factors such as the different nature of the biomaterials/biologics employed, the combinations used (Tu et al., 2010; Miron et al., 2016; J. Y. Lee et al., 2017) and post-operative complications (Sanz et al., 2004; Yoshinuma et al., 2012). Therefore, new biologics with excellent biocompatibility, easy handling and lower initial cost need to be developed to further enhance periodontal wound healing/regeneration and to increase the predictability of clinical outcomes.

Hyaluronic acid (HyA), an anionic, non-sulphated glycosaminoglycan structured biomolecule, is a major natural component of the extracellular matrix in many tissues including the skin, joints, eyes and periodontium (Eliezer et al., 2019; Pilloni et al., 2019). Physiochemically and biologically, HyA is hygroscopic (Dahiya & Kamal, 2013; Pilloni et al., 2019), viscoelastic (Dahiya & Kamal, 2013), bacteriostatic (Dahiya & Kamal, 2013; Eliezer et al., 2019; Pirnazar et al., 1999), antibacterial (Eick et al., 2013), anti-inflammatory (Sasaki & Watanabe, 1995; Moseley et al., 2002; Dahiya & Kamal, 2013; Eliezer et al., 2019) and anti-oedematous (Dahiya & Kamal, 2013; Eliezer et al., 2019). Extensive in vitro studies have

demonstrated that HyA significantly stimulates clot formation (Scully et al., 1995; Pilloni et al., 2019), induces angiogenesis (West et al., 1985; Pilloni et al., 2019) and increases osteogenesis (Pilloni & Bernard, 1998; Pilloni et al., 2019). HyA is currently also available in cross-linked form (cross-linked HyA: xHyA) for various tissue engineering applications, serving as biologics/scaffolds to further improve the overall mechanical properties and provide a longer degradation period compared with non-cross-linked HyA (Takeda et al., 2011; Choi et al., 2015; Fujioka-Kobayashi et al., 2016). Very recent studies have shown that the application of xHyA yielded statistically significant improvements characterized by PPD reduction and CAL gain in human intra-bony defects at 24 months (Pilloni et al., 2021) and effectively induced periodontal tissue regeneration in recession and two-wall-intra-bony defects in dogs (Shirakata, Imafuji, et al., 2021; Shirakata, Nakamura, et al., 2021).

It has been repeatedly demonstrated that the management of furcation involved molars is still one of the most challenging endeavours for the clinician. Due to their complicated anatomical characteristics (i.e., horizontal and vertical bone loss, presence of multiple roots with or without concavities and furrows, long trunks, etc.), furcation areas are hardly accessible for adequate instrumentation. Additionally, due to the wide avascular surfaces, coupled with the horizontal and vertical attachment and bone loss, it is extremely difficult to establish a biologic environment that facilitates periodontal wound healing/regeneration, which, in turn, may clinically lead to furcation closure (Bower, 1979; Waerhaug, 1980; Laugisch et al., 2019; Jepsen et al., 2020). These anatomical and biological considerations may explain the more unpredictable and heterogeneous outcomes obtained following various regenerative approaches obtained in furcations compared with those in recession and intra-bony defects (Sculean et al., 2008, 2015; Miron et al., 2016; Laugisch et al., 2019; Dommisch et al., 2020; Jepsen et al., 2020; Nibali et al., 2020). Apparently, novel treatment strategies leading to periodontal regeneration in furcation defects are stringently needed.

No data are, however, currently available on the potential effects of xHyA on periodontal wound healing/regeneration in furcation defects. In particular, class III furcation defects in experimental animals are considered appropriate for evaluating the potential regenerative effects of biologics/biomaterials, although human class III furcation lesions represent challenging defects that generally preclude periodontal regenerative therapy because of their unfavourable anatomical characteristics for clot and flap stabilization without sufficient surrounding




FIGURE 1 Clinical illustration of the treatment procedure. (a) Prior to reconstructive surgery. (b) Surgically created class III furcation defects. (c) The defects received cross-linked hyaluronic acid gel (xHyA) with collagen matrix (CM) (xHyA/CM), xHyA and CM (left to right). (d) Flap repositioning and suturing

periodontal tissues (Rossa et al., 2000; Roriz et al., 2006; Suiad et al., 2010; Laugisch et al., 2019). Therefore, the aim of this study was to histologically evaluate the effects of xHyA alone or in combination with a volume-stable collagen matrix (CM) on periodontal wound healing/regeneration in class III furcation defects in dogs.

2 | MATERIALS AND METHODS

2.1 | Animals

Six healthy male beagle dogs, 14–17 months of age and weighing 9.5–12.9 kg, were used in this study. The animals were housed and monitored daily for the duration of the study in the Animal Experimentation Facility, Shin Nippon Biomedical Laboratories, Ltd, Kagoshima, Japan. They were kept in individual cages at 20–26°C, with relative humidity of 30%–70%, and a 12-h light/dark cycle. Approximately 300 g of solid food (NVE-10, Nippon Pet Food, Co. Ltd, Tokyo, Japan) was provided to each animal daily and water was available ad libitum. All procedures during the in-life phase were approved by the ethical committee of the Animal Research Center of Kagoshima University, Japan (approval no. D20010; conducted from 28 May 2020 through 18 October 2021). This study conformed to the ARRIVE guidelines for pre-clinical animal experiments.

2.2 | Surgical protocol

All surgeries were performed by one experienced surgeon (Yo.S.) under general and local anaesthesia using aseptic routines. Before the surgical interventions, antibiotics (dihydrostreptomycin sulphate aqueous suspension for injection, 0.05 ml/kg; Mycillin Sol Meiji for veterinary use, Meiji Seika Pharma Co. Ltd, Tokyo, Japan) were administered intramuscularly. General anaesthesia was induced with intra-muscular injection using medetomidine hydrochloride (Domitor®, 0.08 ml/kg IM; Orion Corporation, Espoo, Finland), 0.08 ml/kg of midazolam (Dormicum®, IM; Maruichi Pharmaceutical, Osaka, Japan) and 0.02 ml/kg of butorphanol tartrate (Vetorphale® 5 mg, Meiji Seika Pharma). After sedation, the anaesthesia was maintained by inhalation of sevoflurane (0.5%–5.0%, Mylan Pharma Co., Ltd. Osaka, Japan) and a nitrogen/oxygen (2:1) mixture using an intra-circuit vaporizer for spontaneous breathing. Local anaesthesia (lidocaine HCl/epinephrine 2%, 1:80,000; Xylocaine; Fujisawa Inc., Osaka, Japan) was

administered to reduce peri-operative pain and bleeding. The mandibular second, third and fourth premolars (P2, P3 and P4) (six sites per dog) were employed for experiments (Figure 1a). After sulcular incisions and elevation of the mucoperiosteal flap, class III furcation defects were created surgically with the use of round burs and bone chisels with a sterile saline coolant (Figure 1b). The furcation defects were standardized with a millimetre probe and measured 5.0 mm in the occluso-apical direction and 5.0 mm in the mesio-distal direction. The bone between the mesial and distal roots was removed from the buccal and lingual sides. The exposed root surfaces were planed with Gracey curettes to remove the PDL and root cementum. Reference notches were made with a #1 round bur on the root surface at the base of the defects and on the crown surface, to indicate the precise centre plane/extension of the class III furcation defects and to allow for optimal histomorphometric analysis. The 36 bilateral mandibular class III furcation defects randomly received one of the following treatments: cross-linked porcine CM (Fibro-Gide®, Geistlich Pharma AG, Wolhusen, Switzerland) alone (CM); cross-linked hyaluronic acid gel (Hyadent BG®, REGEDENT AG, Zurich, Switzerland) alone (xHyA); HA + CM (xHyA/CM); and open flap debridement (OFD) as a surgical control (Figure 1c). In the CM group, CM (5 × 5 × 6 mm/defect) was soaked with sterile saline (0.2 ml/CM) before being applied to the defects (Figure 1c). The xHyA gel (0.2 ml/defect) was applied to the root surfaces, and the defects were filled up to the adjacent alveolar crest in the xHyA group (Figure 1c). In the xHyA/CM group, the CM was fully saturated with xHyA (0.2 ml/CM) instead of sterile saline and the constructs were allowed to rest for 10 min. The constructs were then placed in the defects with moderate pressure (Figure 1c). Maximum care was taken during surgery to prevent spilling of xHyA to the other site on the same side of the mandible. A periosteal releasing incision was made to allow coronal displacement of the flap, followed by suturing (Gore-Tex CV-6 Suture; W. L. Gore and Associates Inc., Flagstaff, AZ) slightly coronal to the cemento-enamel junction (Figure 1d) to obtain a complete tension-free coverage of the furcation defects and the regenerative materials. Sutures were removed after 2 weeks.

2.3 | Post-surgical protocol

The animals were fed a soft diet for 2 weeks post-operatively. Ketoprofen for analgesia (Capisten IM 50 mg, 2 mg/kg, 0.1 ml/kg; Kissei Pharmaceutical Co. Ltd, Matsumoto, Japan) and an antibiotic (Mycillin




FIGURE 2 Landmarks/parameters used in histomorphometric analysis. CTA, connective tissue area; CTL, connective tissue adhesion length; DH, defect height; DW, defect width; ETA, epithelial tissue area; JEL, junctional epithelial length; LRS, length of the root surface (TFL + JEL + CTL + NCL); N (N_1 , N_2), apical notch; NAL, new connective tissue attachment length; NBA, new bone area; NCL, new cementum formation length; NFA, non-filled area; TFL, tissue-free defect length

Sol) were administered daily for 2 days. Plaque control was maintained with routine (three times a week) flushing of the oral cavity with 2% chlorhexidine gluconate solution for 10 weeks after surgery.

2.4 | Histologic preparation

Ten weeks after surgery, the animals were euthanized with an overdose of sodium thiopental. All defects were then resected, together with the surrounding soft and hard tissues. The tissue blocks were fixed in 10% buffered formalin, trimmed according to intra-oral radiographs and the reference notch on the crown, and rinsed in phosphate-buffered saline. The samples were decalcified in Kalkitox™ (Wako Pure Chemical Industries, Ltd, Osaka, Japan), dehydrated and embedded in paraffin. Serial 6- μ m-thick sections were then prepared along the mesiodistal plane and were stained with haematoxylin and eosin or with azan.

2.5 | Histomorphometric analysis

All specimens were analysed under a light microscope (BX51; Olympus Corp., Tokyo, Japan) equipped with a computerized image system (WinROOF2015; Mitani Corporation, Tokyo, Japan). For histomorphometric analysis, three sections approximately 90 μ m apart were selected from the most central area of each class III furcation defect, identified by the length of the root canal and the reference notches. The mean

value of each histomorphometric parameter was then calculated for each site. The following parameters (Figure 2) were measured by a single experienced blinded examiner (T.I.). The following area measurements were taken (in square millimetre): (1) bone defect area (BDA)—area limited by the apical line (N_1 - N_2) and the root surface in the furcation region; (2) non-filled area (NFA)—portion of the BDA not filled with any tissue; (3) epithelial tissue area (ETA)—portion of the BDA filled with epithelial tissue; (4) connective tissue area (CTA)—portion of the BDA filled with connective tissue and (5) new bone area (NBA)—portion of the BDA filled with new bone. The following linear measurements were taken (in millimetre): (1) defect height (DH)—vertical length between the apical end of the root notches (N; N_1 , N_2) and the coronal end of the furcation (fornix); (2) defect width (DW)—horizontal length between the apical end of the root notches (N; N_1 , N_2); (3) length of the root surface (LRS)—length of the root surface from the mesial notch to the distal notch; (4) tissue-free defect length (TFL)—portion of the LRS with the absence of any new tissue formation; (5) junctional epithelial length (JEL)—total linear extensions of the root surface covered by epithelial tissue ($JEL_1 + JEL_2$); (6) connective tissue adhesion length (CTL)—total linear extensions of the root surface covered by connective tissue without cementum ($CTL_1 + CTL_2$); (7) new cementum formation length (NCL)—total linear extensions of the root surface covered by new cementum ($NCL_1 + NCL_2$) and (8) new connective tissue attachment formation length (NAL)—total linear extensions of the root surface covered by new connective tissue (NC) adjacent to newly formed bone, with functionally oriented collagen fibres ($NAL_1 + NAL_2$).

2.6 | Statistical analysis

The primary outcome of this study was the histomorphometric outcome in terms of NAL, measured for the four treatment groups at 10 weeks. However, due to the limited number of pre-clinical studies in dogs with a comparable design and primary outcome, no power analysis for sample size calculation could be performed. The animal was used as the statistical unit ($N = 6$) for histomorphometric analysis. Histomorphometric recordings from the selected step serial sections from each defect were used to calculate the mean scores for each animal. A non-parametrical analysis of variance (Kruskal–Wallis test) was used to detect statistically significant differences between the different treatment groups. When the Kruskal–Wallis test was significant, Steel–Dwass post hoc test was performed for multiple comparisons. The p -values less than .05 were considered statistically significant. These analyses were performed using statistical software (BellCurve for Excel, Social Survey Research Information Co. Ltd, Tokyo, Japan).

3 | RESULTS

3.1 | Clinical observations

All animals tolerated the surgical procedures well, and healing after the reconstructive surgeries occurred uneventfully. No severe




FIGURE 3 Representative photomicrographs of class III furcation defects in different groups. Open flap debridement (OFD) group. (a) Histologic overview of mandibular right fourth premolar. Collagen matrix (CM) group. (b) Histologic overview of mandibular left third premolar. Cross-linked hyaluronic acid (xHyA) group. (c) Histologic overview of mandibular left fourth premolar. Cross-linked hyaluronic acid with collagen matrix (xHyA/CM) group. (d) Histologic overview of mandibular right second premolar (scale bar, 1 mm; haematoxylin and eosin staining). Arrowhead: Notch (apical extension of root planing). NB, new bone




FIGURE 4 Representative photomicrographs of class III furcation defects in different groups. Open flap debridement (OFD) group. (a) Histologic overview of mandibular right second premolar (scale bar, 1 mm; azan staining). Arrowhead: Notch (apical extension of root planing). (b) Higher magnification of the framed area (left) in (a) (scale bar, 200 μ m; azan staining). (c) Higher magnification of the framed area (right) in (a) (scale bar, 200 μ m; azan staining). Collagen matrix (CM) group. (d) Histologic overview of mandibular right second premolar (scale bar, 1 mm; azan staining). Arrowhead: Notch (apical extension of root planing). (e) Higher magnification of the framed area (left) in (d) (scale bar, 200 μ m; azan staining). (f) Higher magnification of the framed area (right) in (d) (scale bar, 200 μ m; azan staining). Cross-linked hyaluronic acid (xHyA) group. (g) Histologic overview of mandibular left second premolar (scale bar, 1 mm; azan staining). (h) Higher magnification of the framed area (left) in (g) (scale bar, 200 μ m; azan staining). (i) Higher magnification of the framed area (right) in (g) (scale bar, 200 μ m; azan staining). Cross-linked hyaluronic acid with collagen matrix (xHyA/CM) group. (j) Histologic overview of mandibular left third premolar (scale bar, 1 mm; azan staining). (k) Higher magnification of the framed area (left) in (j) (scale bar, 200 μ m; azan staining). (l) Higher magnification of the framed area (right) in (j) (scale bar, 200 μ m; azan staining). D, root dentin; JE, apical end of junctional epithelium; NB, new bone; NC, new cementum; NPL, new periodontal ligament

inflammation or swelling and dehiscence of the flaps were observed throughout the entire experimental period.

3.2 | Descriptive histology

In the OFD group, down-growth of gingival epithelium was more evident (Figures 3a and 4a,b) than in the xHyA (Figures 3c and 4g) and xHyA/CM (Figures 3d and 4j) groups. However, spontaneous bone formation including large bone marrow spaces occurred to some extent (Figures 3a and 4a). Cementum formation was restricted below the bone crest in most sites. In addition, new connective tissue attachment formation was minimal at the level of the apical notch (Figures 3a and 4a,c). In the CM group, the CM was considerably resorbed; however, bone formation occurred to varying degrees in the furcation defects (Figures 3b and 4d). In four defects, bone formation was observed extending along the distal space onto the mesial root surface and along the mesial space onto the distal root surface with a dimple in the centre (Figure 3b). In the remaining five sites of the CM group, bone formation extended from the host bone towards the coronal region of the defects (Figure 4d). New cellular/acellular cementum was seen, with or without collagen fibres oriented parallel to or detached from the root surfaces (Figure 4e,f). The formation of bone and cementum was apparent and comparable in the xHyA and xHyA/CM groups (Figures 3 and 4). New bone was observed extending close to the fornix of the furcation in these groups, although two defects in the HA/CM group presented an incomplete or comparable bone filling similar to some sites observed in the CM group (Figure 3b, d). In most of the xHyA-applied (xHyA and xHyA/CM) sites, newly formed bone was characterized by cancellous bone, which consists of a network of bony trabeculae containing bone marrow, blood vessels, osteoblast-like cells and osteocyte-like cells (Figures 3 and 4). New cellular/acellular cementum, with inserting collagen fibres running perpendicular to the root surfaces, was observed covering approximately 60% of the denuded root surface (Figures 3c,d and 4g,i). The highly vascularized and dense new PDL-like tissue that formed between the NC and new bone maintained its width up to the coronal portion in the xHyA and xHyA/CM groups (Figure 4h-l). Complete defect resolution was not achieved in any of the defects and treatment modalities. Neither root resorption nor ankylosis was observed in any of the defects.

3.3 | Histomorphometric analysis

The results of the histomorphometric analysis are shown in Tables 1 and 2. No statistically significant differences were detected among the groups in regard to the measurements for BDA, NFA, ETA, CTA, NBA, DH, DW, LRS and TFL. The JEL on the denuded root surface was statistically significantly longer in the OFD group than in the xHyA and xHyA/CM groups. The length of connective tissue (without cementum formation) was statistically significantly greater in the OFD group than in the xHyA and xHyA/CM groups. The amount of NC in

the xHyA and xHyA/CM groups was statistically significantly greater than that in the OFD group. The xHyA and xHyA/CM groups yielded statistically significantly greater formation of new attachment (i.e., linear length of NC adjacent to newly formed bone, with functionally oriented collagen fibres) when compared with the OFD group. No significant differences in any of the histometric parameters were observed between the xHyA and xHyA/CM groups.

4 | DISCUSSION

To the best of our knowledge, the present study has for the first time histologically evaluated the potential effects on periodontal wound healing/regeneration of xHyA with or without CM in class III furcation defects in a larger animal model (i.e., in dogs). The most notable finding of this study was that sites treated with xHyA (i.e., either with xHyA alone or xHyA/CM) demonstrated statistically significantly greater amounts of new connective tissue attachment formation (i.e., NAL) than sites treated with OFD. Specifically, in the xHyA-treated sites, dense functionally oriented collagen fibres with many blood vessels were observed between the newly formed cementum and the newly formed bone. In addition, more new bone was observed in the xHyA ($40.70 \pm 12.80\%$) and xHyA/CM ($44.70 \pm 8.7\%$) groups than in the OFD ($35.10 \pm 14.10\%$) and CM ($30.10 \pm 15.40\%$) groups, although there were no statistically significant differences among the treatment groups. The rates of bone formation in the xHyA-treated groups were equal to or greater than those obtained in previous animal studies evaluating the histomorphometric analysis following the application of β -tricalcium phosphate (TCP) (Jiang et al., 2010), bovine bone mineral matrix (Suiad et al., 2010) and EMD (Fernandes et al., 2005) with or without barrier membranes in chronic class III furcation defects in dogs. Although these comparisons should be interpreted with caution due to the differences in acute versus chronic defects, species (beagle or mongrel dog) and length of healing period (10 weeks vs. 12 weeks), the use of the synthetic product xHyA shows promise as a safe, simple and cost-effective alternative approach for supporting periodontal wound regeneration. Moreover, the present outcomes are in accordance with previous studies that show favourable periodontal regeneration or clinical improvements in PPD reduction and CAL gain following the same xHyA application in intra-bony and gingival recession defects (Pilloni et al., 2021; Shirakata, Imafuji, et al., 2021; Shirakata, Nakamura, et al., 2021). These positive results may be explained by the numerous *in vitro* studies that have demonstrated that xHyA strongly sustains blood clot stability, attracts growth factors (Shimabukuro et al., 2005; Asparuhova et al., 2019; Pilloni et al., 2021) and increases angiogenesis (West et al., 1985; Pilloni et al., 2019) and osteogenesis (Pilloni & Bernard, 1998; Pilloni et al., 2019), while maintaining the fundamental physiochemical and biological properties of HyA (Dahiya & Kamal, 2013). In particular, studies have reported that the interaction between CD44, a cell surface molecule with HyA in PDL cells, is pivotal for the proliferation and migration of PDL cells (Shimabukuro et al., 2011; Al-Rekabi et al., 2019). HyA also induces early osteogenic

TABLE 1 Histomorphometric area measurements for each treatment modality (mean ± SD in square millimetre; N = 6 animals)

Parameters	Treatment group				Statistically significant differences
	(1) OFD	(2) CM	(3) xHyA	(4) xHyA/CM	
BDA	10.26 ± 4.37	10.66 ± 4.32	10.39 ± 3.54	10.19 ± 4.27	NS
NFA	0.31 ± 0.27	0.50 ± 0.58	0.49 ± 0.83	0.56 ± 0.71	NS
ETA	0.73 ± 0.84	0.57 ± 0.47	0.45 ± 0.71	0.36 ± 0.50	NS
CTA	2.88 ± 3.25	3.91 ± 2.61	1.72 ± 1.23	1.84 ± 1.77	NS
NBA	3.25 ± 0.81	3.31 ± 2.26	4.04 ± 1.51	4.32 ± 1.14	NS

Abbreviations: BDA, bone defect area; CM, collagen matrix; CTA, connective tissue area; ETA, epithelial tissue area; NBA, new bone area; NFA, non-filled area; NS, non-significant; OFD, open flap debridement; xHyA, cross-linked hyaluronic acid gel.

TABLE 2 Histomorphometric linear measurements for each treatment modality (mean ± SD in millimetre; N = 6 animals)

Parameters	Treatment group				Statistically significant differences
	(1) OFD	(2) CM	(3) xHyA	(4) xHyA/CM	
DH	4.65 ± 0.99	4.90 ± 1.08	4.90 ± 0.98	4.83 ± 1.15	NS
DW	2.90 ± 0.75	2.97 ± 0.66	2.80 ± 0.64	2.81 ± 0.78	NS
LRS	11.37 ± 1.93	11.62 ± 2.46	11.61 ± 2.16	11.37 ± 2.71	NS
TFL	1.13 ± 1.03	1.21 ± 1.40	1.00 ± 0.57	1.23 ± 0.68	NS
JEL	3.07 ± 1.28	3.72 ± 2.44	0.90 ± 0.64	0.76 ± 0.53	1 vs. 3* 1 vs. 4*
CTL	4.63 ± 1.61	1.85 ± 1.53	1.13 ± 0.76	1.33 ± 1.03	1 vs. 3* 1 vs. 4*
NCL	2.54 ± 1.35	4.45 ± 2.65	7.47 ± 1.85	6.86 ± 1.48	1 vs. 3* 1 vs. 4*
NAL	1.47 ± 0.85	3.40 ± 2.46	6.25 ± 1.45	6.40 ± 1.35	1 vs. 3* 1 vs. 4*

Abbreviations: CM, collagen matrix; CTL, connective tissue adhesion (without cementum) length; DH, defect height; DW, defect width; JEL, junctional epithelium length; LRS, length of the root surface; NAL, new connective tissue attachment length; NCL, new cementum formation length; NS, non-significant; OFD, open flap debridement; TFL, tissue-free defect length; xHyA, cross-linked hyaluronic acid gel.

*Statistically significant differences ($p < .05$).

differentiation of PDL cells (Fujioka-Kobayashi et al., 2017), increases the migratory and proliferative properties of gingival fibroblasts (Asparuhova et al., 2019) and maintains the stemness of mesenchymal stromal cells and pre-osteoblasts (Asparuhova et al., 2020) for accelerating the early phase of periodontal wound healing/regeneration.

The rationale for using a volume-stable CM as a scaffold or carrier for xHyA was based on very recent data from in vitro experiments demonstrating that PDL and endothelial cells exhibited increased migration towards this matrix, while, at the same time, the matrix facilitated the adsorption and long-term release (up to 12 days) of a number of key growth factors such as transforming growth factor (TGF)- β 1, PDGF-BB, FGF-2 and growth differentiation factor (GDF)-5 responsible for periodontal regeneration (Asparuhova et al., 2021). Moreover, the stimulatory effect of the CM on the expression of anti-fibrinolytic genes was synergistically enhanced by TGF- β 1, PDGF-BB or FGF-2, whereas the strong inhibitory effect of the CM on the expression of profibrinolytic genes was reversed by PDGF-BB, FGF-2 or GDF-5 (Asparuhova et al., 2021). These in vitro findings were corroborated by the results of an animal study that histologically evaluated the effect of this CM on periodontal regeneration in two-wall-intra-bony defects (Imber, Bosshardt, et al., 2021; Imber, Rocuzzo, et al., 2021). The histological analysis demonstrated statistically significantly higher formation of PDL, root cementum and bone

in defects treated with OFD + CM compared with those treated with OFD alone, thus providing evidence for the potential of the CM to facilitate periodontal regeneration (Imber, Bosshardt, et al., 2021). Moreover, the immunohistochemical analysis revealed that the regenerated PDL demonstrated statistically significantly more blood vessels compared with the pristine PDL, thus suggesting a positive effect of the CM on angiogenesis (Imber, Rocuzzo, et al., 2021).

However, no statistically significant differences in any of the histomorphometric parameters were found between the groups treated with either xHyA and xHyA/CM groups. In addition, no statistically significant differences were detected between the OFD and CM groups in any of the evaluated histomorphometric parameters, while the CM group demonstrated a large variation in healing pattern with or without periodontal regeneration. The findings indicate that the biologic effects triggered by xHyA might have masked the additional influence of CM on the regeneration process, and the CM seemed to inhibit periodontal wound healing/regeneration in this experimental model. In this study, the CM was used in a commercially available standardized size (5 × 5 × 6 mm) and tightly placed into the relatively narrow (approximately 3 mm) mesiodistal defect space between the mesial and distal roots to prevent the collapse of the mucoperiosteal flap. However, the use of condensed CM with a relatively longer degradation period in this particular class III furcation defects might

jeopardize the invasion of cells, nutrients and vascular supply desirable for periodontal wound regeneration (Shirakata et al., 2002; J. S. Lee et al., 2012; Yoshinuma et al., 2012), and thus it cannot be ruled out the possibility that the used CM was not the optimal carrier/scaffold. At this point, it is important to mention that at present no data are available on the binding and release kinetics data for the CM/xHyA construct. Therefore, further investigations are required to clarify the binding and release kinetics of xHyA when used in combination with CM. In addition, the CM might not play a role in cell occlusive barrier membrane for ensuring marginal sealing and preventing migration of junctional epithelium and gingival connective tissue and/or plaque accumulation (Pontoriero et al., 1992; Hovey et al., 2006; Roriz et al., 2006; Jiang et al., 2010) in the furcation defects with extremely short length of root trunk and concavities (Lu, 1992; Novaes et al., 2001) in dogs. Consequently, xHyA alone appears to possess the biological potential to positively influence periodontal wound healing compared with xHyA/CM without any additional effects of using CM in this study.

When interpreting the present findings, it should be kept in mind that, on the one hand, the positive outcomes following the use of xHyA were obtained in a relatively small number of animals and acute-type defects showed favourable spontaneous healing without strong bacterial challenges and inflammatory reactions (Sculean et al., 2008; Struillou et al., 2010; Donos et al., 2018), which may have limited the statistical power of the study. On the other hand, the inclusion of a higher number of animals and defects is limited by obvious ethical and practical reasons.

The fact that complete closure of class III furcation defects was not observed in any of the four treatment modalities is consistent with previous findings from pre-clinical and clinical studies that have clearly shown that these types of defects (regardless of an acute or chronic type) represent extremely challenging scenarios for periodontal regeneration (Rossa et al., 2000; Fernandes et al., 2005; Roriz et al., 2006; Jiang et al., 2010; Suiad et al., 2010; Laugisch et al., 2019). Further research should aim to develop novel strategies involving the use of xHyA or other biologics and their combinations with various types of carriers prior to clinical application in human class III furcation defects.

5 | CONCLUSION

Within their limits, the present results suggest that the use of xHyA with or without CM positively influences periodontal wound healing in surgically created, acute-type class III furcation defects.

AUTHOR CONTRIBUTIONS

Conceptualization: Yoshinori Shirakata and Anton Sculean. *Methodology:* Yoshinori Shirakata and Anton Sculean. *Validation:* Yoshinori Shirakata. *Formal analysis:* Toshiaki Nakamura. *Investigation:* Yoshinori Shirakata, Takatomo Imafuji, Toshiaki Nakamura, Yukiya Shinohara, Masayuki Iwata and Fumiaki Setoguchi. *Data curation:* Toshiaki Nakamura and Takatomo Imafuji. *Writing—original draft preparation:*

Yoshinori Shirakata and Anton Sculean. *Writing—review and editing:* All authors. *Visualization:* Yukiya Shinohara. *Supervision:* Kazuyuki Noguchi. *Project administration:* Yoshinori Shirakata. *Funding acquisition:* Yoshinori Shirakata. All authors have read and agreed to the published version of the manuscript.

ACKNOWLEDGEMENTS

The authors acknowledge Mr. Shinya Maeda (Shin Nippon, Biomedical Laboratories Ltd, Kagoshima, Japan) for his valuable assistance in preparing the histological sections. The authors report no conflicts of interest related to this study. REGEDENT AG (Zurich, Switzerland) kindly provided the hyaluronic acid gel used in this study. The 3-D cross-linked CM was provided free of charge by Geistlich Pharma AG, Wolhusen, Switzerland. The authors thank Edanz Group (<https://jp.edanz.com/ac>) for editing a draft of this manuscript.

FUNDING INFORMATION

This study was partly funded by REGEDENT AG (Zurich, Switzerland) and by Grants-in-Aid for Scientific Research C (No. 20K10011) from the Japan Society for the Promotion of Science (JSPS) KAKENHI.

CONFLICT OF INTEREST

The authors declare that they have no conflict of interest.

DATA AVAILABILITY STATEMENT

The data that support the findings of this study are available from the corresponding author upon reasonable request.

ETHICS STATEMENT

All applicable international, national and/or institutional guidelines for the care and use of animals were followed, and all procedures performed in studies involving animals were in accordance with the ethical standards of the ethical committee of the Animal Research Center of Kagoshima University, Japan (approval no. D20010).

ORCID

Yoshinori Shirakata  <https://orcid.org/0000-0003-0663-0524>

Toshiaki Nakamura  <https://orcid.org/0000-0003-2675-484X>

Anton Sculean  <https://orcid.org/0000-0003-2836-5477>

REFERENCES

- Al-Rekabi, Z., Fura, A. M., Juhlin, I., Yassin, A., Popowics, T. E., & Sniadecki, N. J. (2019). Hyaluronan-CD44 interactions mediate contractility and migration in periodontal ligament cells. *Cell Adhesion & Migration*, 13(1), 138–150. <https://doi.org/10.1080/19336918.2019.1568140>
- Asparuhova, M. B., Chappuis, V., Stähli, A., Buser, D., & Sculean, A. (2020). Role of hyaluronan in regulating self-renewal and osteogenic differentiation of mesenchymal stromal cells and pre-osteoblasts. *Clinical Oral Investigations*, 24(11), 3923–3937. <https://doi.org/10.1007/s00784-020-03259-8>
- Asparuhova, M. B., Kiryak, D., Eliezer, M., Mihov, D., & Sculean, A. (2019). Activity of two hyaluronan preparations on primary human oral fibroblasts. *Journal of Periodontal Research*, 54(1), 33–45. <https://doi.org/10.1111/jre.12602>

- Asparuhova, M. B., Stähli, A., Guldener, K., & Sculean, A. (2021). A novel volume-stable collagen matrix induces changes in the behavior of primary human oral fibroblasts, periodontal ligament, and endothelial cells. *International Journal of Molecular Sciences*, 22(8), 4051. <https://doi.org/10.3390/ijms22084051>
- Bower, R. C. (1979). Furcation morphology relative to periodontal treatment. Furcation root surface anatomy. *Journal of Periodontology*, 50(7), 366–374. <https://doi.org/10.1902/jop.1979.50.7.366>
- Camelo, M., Nevins, M. L., Schenk, R. K., Simion, M., Rasperini, G., Lynch, S. E., & Nevins, M. (1998). Clinical, radiographic, and histologic evaluation of human periodontal defects treated with Bio-Oss and Bio-Gide. *International Journal of Periodontics and Restorative Dentistry*, 18(4), 321–331. <https://doi.org/10.1007/s00784-004-0254-7>
- Choi, S. C., Yoo, M. A., Lee, S. Y., Lee, H. J., Son, D. H., Jung, J., Noh, I., & Kim, C. W. (2015). Modulation of biomechanical properties of hyaluronic acid hydrogels by crosslinking agents. *Journal of Biomedical Materials Research Part A*, 103(9), 3072–3080. <https://doi.org/10.1002/jbm.a.35437>
- Cortellini, P., Buti, J., Pini Prato, G., & Tonetti, S. (2017). Periodontal regeneration compared with access flap surgery in human intra-bony defects 20-year follow-up of a randomized clinical trial: Tooth retention, periodontitis recurrence and costs. *Journal of Clinical Periodontology*, 44(1), 58–66.
- Cortellini, P., Stalpers, G., Mollo, A., & Tonetti, M. S. (2020). Periodontal regeneration versus extraction and dental implant or prosthetic replacement of teeth severely compromised by attachment loss to the apex: A randomized controlled clinical trial reporting 10-year outcomes, survival analysis and mean cumulative cost of recurrence. *Journal of Clinical Periodontology*, 47(6), 768–776. <https://doi.org/10.1111/jcpe.13289>
- Dahiya, P., & Kamal, R. (2013). Hyaluronic acid: A boon in periodontal therapy. *North American Journal of Medicine and Science*, 5(5), 309–315. <https://doi.org/10.4103/1947-2714.112473>
- Domisch, H., Walter, C., Dannewitz, B., & Eickholz, P. (2020). Resective surgery for the treatments of furcation involvement: A systematic review. *Journal of Clinical Periodontology*, 47(Suppl. 22), 375–391. <https://doi.org/10.1111/jcpe.13241>
- Donos, N., Park, J. C., Vajgel, A., de Carvalho Farias, B., Nikou, G., & Dereka, X. (2018). Description of the periodontal pocket in preclinical models: Limitations and considerations. *Periodontology 2000*, 76(1), 16–34. <https://doi.org/10.1111/prd.12155>
- Eick, S., Renus, A., Heinicke, M., Pfister, W., Stratul, S. I., & Jentsch, H. (2013). Hyaluronic acid as an adjunct after scaling and root planing: A prospective randomized clinical trial. *Journal of Periodontology*, 84(7), 941–949. <https://doi.org/10.1902/jop.2012.120269>
- Eliezer, M., Imber, J. C., Sculean, A., Pandis, N., & Teich, S. (2019). Hyaluronic acid as adjunctive to non-surgical and surgical periodontal therapy: A systematic review and meta-analysis. *Clinical Oral Investigations*, 23(9), 3423–3435. <https://doi.org/10.1007/s00784-019-03012-w>
- Fardal, Ø., & Grytten, J. (2013). A comparison of teeth and implants during maintenance therapy in terms of the number of disease-free years and costs—An in vivo internal control study. *Journal of Clinical Periodontology*, 40(6), 645–651. <https://doi.org/10.1111/jcpe.12101>
- Fernandes, J. M., Rego, R. O., Spolidoric, L. C., Marcantonio, R. A., Marcantonio Júnior, E., & Cirelli, J. A. (2005). Enamel matrix proteins associated with GTR and bioactive glass in the treatment of class III furcation in dogs. *Brazilian Oral Research*, 19(3), 169–175. <https://doi.org/10.1590/s1806-83242005000300003>
- Fujioka-Kobayashi, M., Müller, H. D., Mueller, A., Lussi, A., Sculean, A., Schmidlin, P. R., & Miron, R. J. (2017). In vitro effects of hyaluronic acid on human periodontal ligament cells. *BMC Oral Health*, 17(1), 44. <https://doi.org/10.1186/s12903-017-0341-1>
- Fujioka-Kobayashi, M., Schaller, B., Kobayashi, E., Hernandez, M., Zhang, Y., & Miron, R. J. (2016). Hyaluronic acid gel-based scaffolds as potential carrier for growth factors: An in vitro bioassay on its osteogenic potential. *Journal of Clinical Medicine*, 5(12), 112. <https://doi.org/10.3390/jcm5120112>
- Hovey, L. R., Jones, A. A., McGuire, M., Mellonig, J. T., Schoolfield, J., & Cochran, D. L. (2006). Application of periodontal tissue engineering using enamel matrix derivative and a human fibroblast-derived dermal substitute to stimulate periodontal wound healing in class III furcation defects. *Journal of Periodontology*, 77(5), 790–799. <https://doi.org/10.1902/jop.2006.030264>
- Imber, J. C., Bosshardt, D. D., Stähli, A., Saulacic, N., Deschner, J., & Sculean, A. (2021). Pre-clinical evaluation of the effect of a volume-stable collagen matrix on periodontal regeneration in two-wall intrabony defects. *Journal of Clinical Periodontology*, 48(4), 560–569. <https://doi.org/10.1111/jcpe.13426>
- Imber, J. C., Rocuzzo, A., Stähli, A., Saulacic, N., Deschner, J., Sculean, A., & Bosshardt, D. D. (2021). Immunohistochemical evaluation of periodontal regeneration using a porous collagen scaffold. *International Journal of Molecular Sciences*, 22(20), 10915. <https://doi.org/10.3390/ijms222010915>
- Jepsen, S., Gennai, S., Hirschfeld, J., Kalemaj, Z., Buti, J., & Graziani, F. (2020). Regenerative surgical treatment of furcation defects: A systematic review and Bayesian network meta-analysis of randomized clinical trials. *Journal of Clinical Periodontology*, 47(Suppl. 22), 352–374. <https://doi.org/10.1111/jcpe.13238>
- Jiang, J., Wu, X., Lin, M., Doan, N., Xiao, Y., & Yan, F. (2010). Application of autologous periosteal cells for the regeneration of class III furcation defects in beagle dogs. *Cytotechnology*, 62(3), 235–243. <https://doi.org/10.1007/s10616-010-9284-y>
- Kitamura, M., Akamatsu, M., Kawanami, M., Furuichi, Y., Fujii, T., Mori, M., Kunimatsu, K., Shimauchi, H., Ogata, Y., Yamamoto, M., Nakagawa, T., Sato, S., Ito, K., Ogasawara, T., Izumi, Y., Gomi, K., Yamazaki, K., Yoshie, H., Fukuda, M., ... Murakami, S. (2016). Randomized placebo-controlled and controlled non-inferiority phase III trials comparing trafermin, a recombinant human fibroblast growth factor 2, and enamel matrix derivative in periodontal regeneration in intrabony defects. *Journal of Bone and Mineral Research*, 31(4), 806–814. <https://doi.org/10.1002/jbmr.2738>
- Laugisch, O., Cosgarea, R., Nikou, G., Nikolidakis, D., Donos, N., Salvi, G. E., Stavropoulos, A., Jepsen, S., & Sculean, A. (2019). Histologic evidence of periodontal regeneration in furcation defects: A systematic review. *Clinical Oral Investigations*, 23(7), 2861–2906. <https://doi.org/10.1007/s00784-019-02964-3>
- Lee, J. S., Park, W. Y., Cha, J. K., Jung, U. W., Kim, C. S., Lee, Y. K., & Choi, S. H. (2012). Periodontal tissue reaction to customized nano-hydroxyapatite block scaffold in one-wall intrabony defect: A histologic study in dogs. *Journal of Periodontal & Implant Science*, 42(2), 50–58. <https://doi.org/10.5051/jpis.2012.42.2.50>
- Lee, J. Y., Na, H. J., Kim, H. M., Lee, S. C., Lee, J. Y., Chung, C. P., Seol, Y. J., & Park, Y. J. (2017). Comparative study of rhPDGF-BB plus equine-derived bone matrix versus rhPDGF-BB plus beta-TCP in the treatment of periodontal defects. *International Journal of Periodontics and Restorative Dentistry*, 37(6), 825–832. <https://doi.org/10.11607/prd.3401>
- Li, F., Yu, F., Xu, X., Li, C., Huang, D., Zhou, X., Ye, L., & Zheng, L. (2017). Evaluation of recombinant human FGF-2 and PDGF-BB in periodontal regeneration: A systematic review and meta-analysis. *Scientific Reports*, 7(1), 65. <https://doi.org/10.1038/s41598-017-00113-y>
- Lu, H. K. (1992). Topographical characteristics of root trunk length related to guided tissue regeneration. *Journal of Periodontology*, 63(3), 215–219. <https://doi.org/10.1902/jop.1992.63.3.215>
- Miron, R. J., Sculean, A., Cochran, D. L., Froum, S., Zucchelli, G., Nemcovsky, C., Donos, N., Lyngstadaas, S. P., Deschner, J., Dard, M., Stavropoulos, A., Zhang, Y., Trombelli, L., Kasaj, A., Shirakata, Y., Cortellini, P., Tonetti, M., Rasperini, G., Jepsen, S., & Bosshardt, D. D. (2016). Twenty years of enamel matrix derivative: The past, the

- present and the future. *Journal of Clinical Periodontology*, 43(8), 668–683. <https://doi.org/10.1111/jcpe.12546>
- Moseley, R., Waddington, R. J., & Embery, G. (2002). Hyaluronan and its potential role in periodontal healing. *Dental Update*, 29(3), 144–148. <https://doi.org/10.12968/denu.2002.29.3.144>
- Nibali, L., Koldou, V. P., Nieri, M., Barbato, L., Pagliaro, U., & Cairo, F. (2020). Regenerative surgery versus access flap for the treatment of intrabony periodontal defects. A systematic review and meta-analysis. *Journal of Clinical Periodontology*, 47(Suppl. 22), 320–351. <https://doi.org/10.1111/jcpe.13237>
- Novaes, A. B., Jr., Tamani, J. P., Oliveira, P. T., Palioto, D. B., & Almeida, A. L. (2001). Root trunk concavities as a risk factor for regenerative procedures of class II furcation lesions in dogs. *Journal of Periodontology*, 72(5), 612–619. <https://doi.org/10.1902/jop.2001.72.5.612>
- Pilloni, A., & Bernard, G. W. (1998). The effect of hyaluronan on mouse intramembranous osteogenesis in vitro. *Cell and Tissue Research*, 294(2), 323–333. <https://doi.org/10.1007/s004410051182>
- Pilloni, A., Rojas, M. A., Marini, L., Russo, P., Shirakata, Y., Sculean, A., & Iacono, R. (2021). Healing of intrabony defects following regenerative surgery by means of single-flap approach in conjunction with either hyaluronic acid or an enamel matrix derivative: A 24-month randomized controlled clinical trial. *Clinical Oral Investigations*, 25(8), 5095–5107. <https://doi.org/10.1007/s00784-021-03822-x>
- Pilloni, A., Schmidlin, P. R., Sahrman, P., Sculean, A., & Rojas, M. A. (2019). Effectiveness of adjunctive hyaluronic acid application in coronally advanced flap in Miller class I single gingival recession sites: A randomized controlled clinical trial. *Clinical Oral Investigations*, 23(3), 1133–1141. <https://doi.org/10.1007/s00784-018-2537-4>
- Pirnazar, P., Wolinsky, L., Nachnani, S., Haake, S., Pilloni, A., & Bernard, G. W. (1999). Bacteriostatic effects of hyaluronic acid. *Journal of Periodontology*, 70(4), 370–374. <https://doi.org/10.1902/jop.1999.70.4.370>
- Pontoriero, R., Nyman, S., Ericsson, I., & Lindhe, J. (1992). Guided tissue regeneration in surgically-produced furcation defects. An experimental study in the beagle dog. *Journal of Clinical Periodontology*, 19(3), 159–163. <https://doi.org/10.1111/j.1600-051x.1992.tb00632.x>
- Roriz, V. M., Souza, S. L., Taba, M., Jr., Palloto, D. B., & Grisi, M. F. (2006). Treatment of class III furcation defects with expanded polytetrafluoroethylene membrane associated or not with anorganic bone matrix/synthetic cell-binding peptide: A histologic and histomorphometric study in dogs. *Journal of Periodontology*, 77(3), 490–497. <https://doi.org/10.1902/jop.2006.050081>
- Rossa, C., Jr., Marcantonio, E., Jr., Cirelli, J. A., Marcantonio, R. A., Spolidorio, L. C., & Fogo, J. C. (2000). Regeneration of class III furcation defects with basic fibroblast growth factor (b-FGF) associated with GTR. A descriptive and histometric study in dogs. *Journal of Periodontology*, 71(5), 775–784. <https://doi.org/10.1902/jop.2000.71.5.775>
- Sanz, M., Tonetti, M. S., Zabalegui, I., Sicilia, A., Blanco, J., Rebelo, H., Rasperini, G., Merli, M., Cortellini, P., & Suvan, J. E. (2004). Treatment of intrabony defects with enamel matrix proteins or barrier membranes: Results from a multicenter practice-based clinical trial. *Journal of Periodontology*, 75(5), 726–733. <https://doi.org/10.1902/jop.2004.75.5.726>
- Sasaki, T., & Watanabe, C. (1995). Stimulation of osteoinduction in bone wound healing by high-molecular hyaluronic acid. *Bone*, 16(1), 9–15. [https://doi.org/10.1016/s8756-3282\(94\)00001-8](https://doi.org/10.1016/s8756-3282(94)00001-8)
- Sculean, A., Nikolidakis, D., Nikou, G., Ivanovic, A., Chapple, I. L., & Stavropoulos, A. (2015). Biomaterials for promoting periodontal regeneration in human intrabony defects: A systematic review. *Periodontology 2000*, 68(1), 182–216. <https://doi.org/10.1111/prd.12086>
- Sculean, A., Nikolidakis, D., & Schwarz, F. (2008). Regeneration of periodontal tissues: Combinations of barrier membranes and grafting materials – biological foundation and preclinical evidence: A systematic review. *Journal of Clinical Periodontology*, 35(8 suppl), 106–116. <https://doi.org/10.1111/j.1600-051X.2008.01263.x>
- Scully, M. F., Kakkar, V. V., Goodwin, C. A., & O'Regan, M. (1995). Inhibition of fibrinolytic activity by hyaluronan and its alcohol ester derivatives. *Thrombosis Research*, 78(3), 255–258. [https://doi.org/10.1016/0049-3848\(95\)90876-h](https://doi.org/10.1016/0049-3848(95)90876-h)
- Shimabukuro, Y., Ichikawa, T., Takayama, S., Yamada, S., Takedachi, M., Hashikawa, T., & Murakami, S. (2005). Fibroblast growth factor-2 regulates the synthesis of hyaluronan by human periodontal ligament cells. *Journal of Cellular Physiology*, 203(3), 557–563. <https://doi.org/10.1002/jcp.20256>
- Shimabukuro, Y., Terashima, H., Takedachi, M., Maeda, K., Nakamura, T., Sawada, K., Kobashi, M., Awata, T., Oohara, H., Kawahara, T., Iwayama, T., Hashikawa, T., Yanagita, M., Yamada, S., & Murakami, S. (2011). Fibroblast growth factor-2 stimulates directed migration of periodontal ligament cells via PI3K/AKT signaling and CD44/hyaluronan interaction. *Journal of Cellular Physiology*, 226(3), 809–821. <https://doi.org/10.1002/jcp.22406>
- Shirakata, Y., Imafujii, T., Nakamura, T., Kawakami, Y., Shinohara, Y., Noguchi, K., Pilloni, A., & Sculean, A. (2021). Periodontal wound healing/regeneration of two-wall intrabony defects following reconstructive surgery with cross-linked hyaluronic acid-gel with or without a collagen matrix: A preclinical study in dogs. *Quintessence International*, 308–316. <https://doi.org/10.3290/j.qi.b987003>
- Shirakata, Y., Nakamura, T., Kawakami, Y., Imafujii, T., Shinohara, Y., Noguchi, K., & Sculean, A. (2021). Healing of buccal gingival recessions following treatment with coronally advanced flap alone or combined with a cross-linked hyaluronic acid gel. An experimental study in dogs. *Journal of Clinical Periodontology*, 48(4), 570–580. <https://doi.org/10.1111/jcpe.13433>
- Shirakata, Y., Oda, S., Kinoshita, A., Kikuchi, S., Tsuchioka, H., & Ishikawa, I. (2002). Histocompatible healing of periodontal defects after application of an injectable calcium phosphate bone cement. A preliminary study in dogs. *Journal of Periodontology*, 73(9), 1043–1053. <https://doi.org/10.1902/jop.2002.73.9.1043>
- Stavropoulos, A., Berti, K., Spinelli, L. M., Sculean, A., Cortellini, P., & Tonetti, M. (2021). Medium- and long-term clinical benefits of periodontal regenerative/reconstructive procedures in intrabony defects: Systematic review and network meta-analysis of randomized controlled clinical studies. *Journal of Clinical Periodontology*, 48(3), 410–430. <https://doi.org/10.1111/jcp.13409>
- Struillou, X., Boutigny, H., Soueidan, A., & Layrolle, P. (2010). Experimental animal models in periodontology: A review. *The Open Dentistry Journal*, 4, 37–47. <https://doi.org/10.2174/1874210601004010037>
- Suiad, F. A., Macedo, G. O., Novaes, A. B., Borges, G. J., Souza, S. L., Taba, M., Palioto, D. B., & Grisi, M. F. (2010). The bone formation capabilities of the anorganic bone matrix-synthetic cell-binding peptide 15 grafts in an animal periodontal model: A histologic and histomorphometric study in dogs. *Journal of Periodontology*, 81(4), 594–603. <https://doi.org/10.1902/jop.2010.090486>
- Takeda, K., Sakai, N., Shiba, H., Nagahara, T., Fujita, T., Kajiji, M., Iwata, T., Matsuda, S., Kawahara, K., Kawaguchi, H., & Kurihara, H. (2011). Characteristics of high-molecular-weight hyaluronic acid as a brain-derived neurotrophic factor scaffold in periodontal tissue regeneration. *Tissue Engineering Part A*, 17(7–8), 955–967. <https://doi.org/10.1089/ten.TEA.2010.0070>
- Tu, Y. K., Woolston, A., & Faggion, C. M., Jr. (2010). Do bone grafts or barrier membranes provide additional treatment effects for intrabony lesions treated with enamel matrix derivatives? A network meta-analysis of randomized-controlled trials. *Journal of Clinical Periodontology*, 37(1), 59–79. <https://doi.org/10.1111/j.1600-051X.2009.01499.x>

- Waerhaug, J. (1980). The furcation problem. Etiology, pathogenesis, diagnosis, therapy and prognosis. *Journal of Clinical Periodontology*, 72(2), 73–95. <https://doi.org/10.1111/j.1600-051x.1980.tb01951.x>
- West, D. C., Hampson, I. N., Arnold, F., & Kuma, S. (1985). Angiogenesis induced by degradation products of hyaluronic acid. *Science*, 228(4705), 1324–1326. <https://doi.org/10.1126/science.2408340>
- Yoshinuma, N., Sato, S., Fukuyama, T., Murai, M., & Ito, K. (2012). Ankylosis of nonresorbable. Hydroxyapatite graft material as a contributing factor in recurrent periodontitis. *International Journal of Periodontics and Restorative Dentistry*, 32(3), 331–336.

How to cite this article: Shirakata, Y., Imafuji, T., Nakamura, T., Shinohara, Y., Iwata, M., Setoguchi, F., Noguchi, K., & Sculean, A. (2022). Cross-linked hyaluronic acid gel with or without a collagen matrix in the treatment of class III furcation defects: A histologic and histomorphometric study in dogs. *Journal of Clinical Periodontology*, 49(10), 1079–1089. <https://doi.org/10.1111/jcpe.13694>