

Research Article

Quasi-Static and Harmonic Indentation of Osteonal Bone

S. S. Huja,¹ J. L. Hay,² A. M. Rummel,³ and F. M. Beck¹

¹ College of Dentistry, The Ohio State University, Columbus, OH 43210, USA

² Agilent Technologies, Nano Mechanical Operations, 105 Meco Lane, Oak Ridge, TN 37830, USA

³ Orthodontics, Marquette University, Milwaukee, WI 53201, USA

Correspondence should be addressed to S. S. Huja, huja.1@osu.edu

Received 19 March 2009; Revised 4 August 2009; Accepted 17 November 2009

Academic Editor: Paolo Cattaneo

Copyright © 2010 S. S. Huja et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The purpose of the study was to compare Quasi-Static (QS) and harmonic (CSM) methods of indentation testing. Bone sections were obtained from mid-femoral diaphyses of dogs which received a pair of calcein labels. Labeled ($n = 35$) and unlabeled ($n = 112$) osteons were identified. Indentation modulus (IM) and hardness (H) for the CSM method were collected during the entire loading cycle to peak depth, while IM and H for QS method were calculated at a peak depth of 500 nm. Results: The mean (SD) of the IM and H for labeled osteons were as follows: QS IM = 15.3 GPa (3.85) versus CSM IM = 14.7 GPa (3.58); $P = .52$ and QS H = .39 GPa (.171) versus CSM H = .42 GPa (.146); $P = .32$. The mean (SD) of the IM and H for unlabeled osteons were as follows: QS IM = 21.5 GPa (2.80) versus CSM IM = 20.6 GPa (2.53); $P = .054$ and QS H = .64 GPa (.117) versus CSM H = .70 GPa (.120); $P = .017$. There was no difference in IM and H for the two methods, except for H of the unlabeled osteons. In addition, for the CSM method, IM at 100 nm, 200 nm, 300 nm, 400 nm and 500 nm were not statistically significant different ($P = .06$). Bone is viscoelastic at an organ level. However, this component of its behavior was not detected at the length scale examined.

1. Introduction

Instrumented-indentation testing (also known as nanoin-indentation) has been used to investigate the mechanical properties of biological tissues such as bone [1–3], dentin [4] and enamel [5]. In the literature, there is no single protocol to measure the material properties of mineralized tissues by instrumented indentation [6, 7]. Results cited in the literature have been achieved using a variety of control mechanisms, force application rates, termination criteria, and analyses [2, 5, 8, 9]. To what extent are results from such disparate methods comparable? Are there sound reasons for preferring one method over another? While such questions remain unanswered, our ability to compare and interpret results from different studies is hindered. Therefore, the primary purpose of this work was to determine the sensitivity of indentation results to test method in order to increase the value of results reported by us and others.

Rather than examining every permutation of indentation method and bone type, we examined two identifiable extremes in indentation method (quasi-static and harmonic) for each of two extremes in bone mineralization (young and old osteons). We hypothesized no significant differences in

properties as a function of indentation method but significant difference in properties as a function of mineralization. If this hypothesis is upheld, we may conclude that it is valid to compare micron scale properties measured by most indentation methods that are commonly used today.

The *organ level* material properties of bone are heterogeneous and depend upon age [10] anatomical location [11], species and bone activity [12]. To span the identifiable extremes of variation in mineralization that can be apparent in bone we examined bone sections that were administered intravital bone labels. This allowed us to distinguish newly forming, younger, incompletely mineralized labeled osteons with older, more completely mineralized unlabeled osteons, a strategy we have used successfully in the past [12].

Indentation test methods may be broadly classified as quasi-static (QS) or harmonic (CSM), the primary difference being the means by which *contact stiffness*, S , is determined. A QS method involves monotonically pressing the indenter into the test surface, holding for a dwell time, and then withdrawing the indenter. (Note: This cycle may be controlled based on either force or displacement.) Pressing the indenter *into* the test surface causes both elastic and plastic deformation but as the indenter is withdrawn, the

material recovers elastically. For time-independent materials the contact stiffness is determined as the relationship between force reduction and recovered displacement at the onset of withdrawal. A CSM method also involves pressing the indenter into the test surface, dwelling, and withdrawal, but superimposed upon the pressing part of the test cycle is a small oscillation in force of amplitude F_o . A frequency-specific amplifier is used to sense the resulting displacement oscillation. The amplitude of the force oscillation is controlled so that the amplitude of the resulting displacement oscillation, z_o , maintains a constant value of just a few nanometers. (As the size of the contact increases the amplitude of the force oscillation must increase in order to maintain constant amplitude for the displacement oscillation.) Generally, oscillation frequencies from 1–300 Hz may be used, but when testing biological materials, frequencies above 45 Hz are rarely used. With a CSM method, contact stiffness is determined continuously during the “pressing” part of the test cycle from the amplitude ratio, F_o/z_o . This technique is described in detail elsewhere [13]. To summarize, with a QS method, the contact stiffness is determined as the slope of the unloading curve; with a CSM method, the contact stiffness is determined continuously during loading from the amplitude ratio of a superimposed oscillation. The acronym “CSM” stands for “continuous stiffness measurement”. It should be noted that both the QS and CSM methods may be implemented in a single indentation test, because the oscillation required for the CSM method is so small that it does not interfere with the quasi-static cycle. When both methods are implemented in a single test, the CSM method is used to continuously measure contact stiffness during loading, and the QS method is used to determine a single value of contact stiffness from the unloading force-displacement data. For materials which do not manifest time-dependent elasticity (viscoelasticity), these two different techniques for measuring contact stiffness yield the same measure of indentation modulus. This is true for most ceramic and glassy materials, but the extent to which this is true for bone has yet to be demonstrated.

Once the contact stiffness, S , has been determined by either method, the analyses for calculating indentation modulus (IM) and indentation hardness (H) are the same. However, because the QS method yields only one value of S , it can yield only one value of IM and H at the maximum penetration depth, whereas the CSM method yields a continuous measure of IM and H as a function of surface penetration (or applied force). Regardless of how S is determined, calculations of IM and H proceed as follows [13].

The depth over which the test material makes contact with the indenter, h_c , is calculated as:

$$h_c = h - \frac{0.75P}{S}, \quad (1)$$

where h is the indenter displacement as measured from the point of initial contact, P is the applied force, and S is the contact stiffness. The contact depth, h_c , is less than the total depth, h , because the material around the indenter deflects

downward elastically. For a Berkovich indenter, the contact area, A , is calculated as

$$A \sim 24.56h_c^2. \quad (2)$$

This expression for A is approximate because the real expression is slightly different for every physical diamond. The exact form of the expression for A is determined by indenting a material with known modulus. The reduced modulus, E_r , includes bidirectional displacements in both the indenter and the test sample, and is calculated as [14]

$$E_r = \frac{\sqrt{\pi}}{2} \frac{S}{\sqrt{A}}. \quad (3)$$

And the indentation elastic modulus (IM) of the sample is calculated from the reduced modulus as

$$\text{IM} \equiv E = (1 - \nu^2) \left[\frac{1}{E_r} - \frac{1 - \nu_i^2}{E_i} \right]^{-1}, \quad (4)$$

where ν is the Poisson’s ratio of the test sample, and ν_i and E_i are the Poisson’s ratio and elastic modulus of the indenter, respectively. If the indenter is diamond, then ν_i and E_i are 0.07 and 1140 GPa, respectively. Although the calculation of IM requires knowing the Poisson’s ratio of the sample (ν), the sensitivity is weak. Sensitivity analysis reveals that a generous uncertainty of 40% in the Poisson’s ratio manifests as only a 5% uncertainty in IM. For all the results reported in this work, a value of 0.3 was used for ν . Finally, indentation hardness (H) is calculated as

$$H = \frac{P}{A}. \quad (5)$$

2. Materials and Methods

2.1. Materials. Tissue specimens were obtained from another study which had Institutional Animal Care Committee approval. Calcein (Sigma St. Louis, MO) bone labels (5 mg/kg body weight) were administered intravenously to five skeletally mature (1-2 years) male Beagle dogs. The labels were given two weeks apart, that is, 17 days and 3 days prior to euthanasia. The femurs were harvested immediately after euthanasia and frozen in saline soaked gauze at -20°C for a brief storage period [15]. Two ~ 3 mm mid femoral bone slices were obtained from each dog.

2.2. Specimen Preparation. The method for sample preparation and osteon identification and localization have been described in detail in a recent publication [12]. Briefly, just prior to mechanical testing, the femurs were thawed and approximately 3 mm thick bone slices were obtained from the mid-diaphyseal region of the femur on a band saw. The femoral cross sections were examined under an epifluorescent microscope (Olympus BX 51, Tokyo, Japan) to confirm the presence of labeled osteons in that bone slice being examined. Among the labeled osteons we chose those that were approximately half way or greater in their bone formation cycle [12]. This allowed us adequate bone tissue to place the indents.

The selected femoral bone surfaces were then lightly polished [2, 8], and care was taken to prevent overpolishing of the specimens [16, 17]. This is very important in this study and thus we describe the standard polishing procedure used in our laboratory. The bone block was glued into a well of a custom-made polycarbonate specimen holder. The mounting was verified on a certified level stage to ensure parallelism. The sectioned specimens were wet-polished on a rotary wheel (Ecomet, Buehler, Lake Bluff, IL) at 120 rpm with 2,400 grit SiC papers. Additional polishing was done on a napless cloth (OP-Chem, Struers A/S, Rodovre, Denmark) with diluted $0.3\ \mu\text{m}$ and $0.05\ \mu\text{m}$ alumina oxide pastes (Micropolish C alpha Alumina, Buehler, Lake Bluff, IL). The specimens were sonicated for 2 minutes. The polishing was restricted to the minimum time to allow for examination of the detailed morphological features (e.g., lamellae, cement lines) of the cortical bone; after polishing, surface roughness was less than 30 nm.

Next, we identified and mapped the coordinates of the labeled and unlabeled osteons under an epifluorescent microscope. This was essential as labeled osteons cannot be identified under the optics of the indenter system. Multiple perpendicular lines (Figure 1) were scribed into the surface of the polished bone specimen with a surgical blade [12]. The exact location (x, y coordinates) of the central Haversian canal of the labeled osteon relative to two orthogonal scribe lines was measured in microns using a linear microscope eyepiece of the epifluorescent microscope. In addition, photomicrographs aided in documenting the unique cross sectional morphology of each labeled osteon site and its neighboring osteons and other structures such as blood vessels.

After the bone slice was mounted in the indenter (Nano Indenter XP, Agilent Technologies, Inc., Oak Ridge, TN), the photographic map produced from the epifluorescent microscope was referenced. A specific labeled osteon was located using the intersection of nearest two perpendicular lines from the osteon (Figure 1). The indenter optics were moved to the intersection of the two perpendicular lines and x, y coordinates to the center of the labeled osteon in microns were entered into the software. The sample was then translated to present the desired test location to the indenter optics. The photographic map confirmed the specific osteon of interest and a neighboring unlabeled osteon (Figure 2).

The above described procedure was repeated to locate additional labeled and unlabeled osteons on the bone slice (Figure 2). Each location was flagged into the computer with one set of coordinates for each labeled osteon. After all osteons that we desired to examine were located, we then programmed the software to place indents on the bone of the osteons. The indents were located approximately half the distance between the reversal cement line and the central canal for all the osteons. This is because each osteon does not have the same dimension in each cross section and osteons were sampled at different times during their formation phase. We made 5-6 indents on each labeled and unlabeled osteon.

After identification of all the labeled and unlabeled osteons the hydration system was turned on. A hydra-




FIGURE 1: Schematic of method to locate osteons. Multiple orthogonal scribe lines (only one shown) were cut into the polished bone surface. A labeled osteon was identified under the epifluorescent microscope and the perpendicular distances (a, b) from the axes to the center of the Haversian canal were measured. These distances were recorded and once the specimen was placed under the optics of the indenter microscope, the coordinates to the center of the osteon measured from the intersection of the scribe lines were entered into the indenter software. This procedure verified the previously identified labeled osteon. A neighboring unlabeled osteon was identified based on its morphology and proximity to the labeled osteon.

tion fluid containing a mixture [8] of distilled water and 0.5 mg/mL of gentamicin sulphate (Sigma Chemical Company, St. Louis, MO). The specimens were kept moist for the entire test. A total of 147 osteons (labeled = 35; unlabeled = 112) were measured.

All indentation testing was performed using a Berkovich indenter at room temperature. Proper functioning of the indentation tester was verified by testing fused silica prior to testing bone. Some tests (<5%) did not commence due to inability of the machine to detect contact, and occasionally, the target depth was exceeded (e.g., greater than 530 nm) and such tests were eliminated [12]. A total of 610 indents were made on the 35 labeled osteons and 112 nonlabeled osteons.

Quasi-Static Method (QS). Each indentation test comprised the following segments [18].

- (0) The indenter approaches the test surface until contact is sensed.
- (1) The indenter is pressed into contact with the test material at a rate of 10 nm/sec to a peak depth of 500 nm.
- (2) The force on the indenter is held constant for a dwell time of 30 seconds.
- (3) The indenter is withdrawn from the sample completely, and the sample is moved into position for the next test.




FIGURE 2: Pair of images (a) Brightfield and (b) Epifluorescent of cortical bone from a dog femur. Osteonal architecture of bone is evident. In addition labeled and unlabeled osteons can be clearly distinguished. The reversal lines and bone labels clearly demarcated the labeled and unlabeled osteons.

A single value of contact stiffness is calculated from the slope of the unloading curve as explained in the introduction. IM and H are calculated from this single value of S .

Harmonic Method (CSM). Superimposed upon the quasi-static loading segment (1) was a small oscillating force at 45 Hz. The amplitude of the oscillating force, F_o , was continuously adjusted in order to maintain the amplitude of the resulting displacement oscillation at $z_o = 2$ nm. Contact stiffness was determined continuously during loading from the amplitude ratio F_o/z_o . IM and H were calculated using this continuous measure of S . For the purpose of comparing with QS results, CSM results for IM and H were taken at the maximum displacement of 500 nm.

2.3. Statistical Analyses. The data were analyzed using multiple, repeated measures ANOVA. The independent variables were osteonal type (labeled, unlabeled) or the method (QS, CSM). The repeated factor was dog. Data for depth analyses for the CSM method were analyzed by a repeated measures, factorial analyses of variance with depth and type of osteon (labeled, unlabeled) as two factors and dog as the repeated factor.

3. Results

The mean (SD) of IM (Figure 3) and H (Figure 4) for labeled osteons obtained by the two indentation methods were as follows:

- (i) QS IM = 15.3 GPa (3.85) versus CSM IM = 14.7 GPa (3.58); $P = .52$, and
- (ii) QS H = .387 GPa (.171) versus CSM H = .422 GPa (.146); $P = .32$.

The mean (SD) of IM (Figure 3) and H (Figure 4) for unlabeled osteons were as follows:

- (i) QS IM = 21.5 GPa (2.80) versus CSM IM = 20.6 GPa (2.53); $P = .054$, and
- (ii) QS H = .639 GPa (.117) versus CSM H = .700 GPa (.120); $P = .017$.




FIGURE 3: Mean (SD) of indentation modulus (GPa) for labeled and unlabeled osteons derived by the two methods, quasi-static (QS) and continuous stiffness measurement (CSM). There are no difference in the IM between the two methods for the labeled ($P = .519$) and unlabeled ($P = .054$) osteons.

No difference in IM existed between the two methods for either type of bone, but statistically significant differences were found for H between methods for unlabeled osteons. CSM hardness values were 9% and 8% higher than QS hardness values for unlabeled and labeled osteons, respectively.

ANOVA showed significant ($P < .001$) differences between labeled and unlabeled osteons. The CSM method allows the determination of properties as a function of depth. However, there was no statistically significant difference for the IM with depth ($P = .06$) and there was no ($P = .21$) depth/type of osteon interaction (Figure 5). With the CSM method, IM (SD) for the labeled osteons increased from 13.2 (3.9) GPa at 100 nm to 14.76 (4.12) GPa at 500 nm depth (Figure 5). However, IM (SD) for the unlabeled osteons only increased from 20.51 (5.5) GPa at 100 nm to 20.57 (3.5) GPa at 500 nm.




FIGURE 4: Mean (SD) of indentation modulus (GPa) for labeled and unlabeled osteons derived by the two methods, quasi-static (QS) and continuous stiffness measurement (CSM). The hardness was not significantly different for the two methods for the labeled ($P = .32$) but different for the unlabeled osteons ($P = .017$).

4. Discussion

Although the primary focus of this study was test method, we have confirmed previous data [12] which showed IM and H of unlabeled osteons to be greater than labeled osteons by approximately 30%.

Since the primary focus of this study was determining the sensitivity of measured properties to test method, it was critical that the QS and CSM methods be implemented together in a single test. Implementing the methods simultaneously eliminated variables of test condition that can influence results, including tip wear, temperature, test site, and degree of tissue degradation. For example, if all the QS tests were performed in one batch, and all the CSM tests were performed in a later batch, and different results were obtained (for like materials) from the two batches, questions would remain as to whether the differences were due to variations in test method (QS or CSM) or test condition. By eliminating variables of test condition, we are able to attribute any observed property differences (for like materials) to test method and fundamental material behavior.

Although we found statistically significant differences in the properties of labeled and unlabeled bone, we found no significant difference in the IM *by method*. From this observation, we deduce that at the resolution of testing, bone tissue does not exhibit significant viscoelastic behavior, that is, the elastic strain response to stress occurs instantaneously. This conclusion, though far-reaching, is warranted by the breadth of this study. The labeled and unlabeled osteons represent identifiable low and high degrees of mineralization in bone, respectively. The fact that the QS and CSM methods yielded statistically equal measures of IM for osteons at opposite ends of the identifiable spectrum of mineralization causes us to include various levels of physiologic mineralization of bone




FIGURE 5: Indentation modulus (Least square means) for each depth (100 nm, 200 nm, 300 nm, 400 nm, 500 nm). While the labeled osteons have a significantly lower indentation modulus than the unlabeled osteons there is no significant ($P = .06$) difference in the IM with depth.

in this conclusion. Furthermore, the QS and CSM test methods represent extremes of physiological frequencies. The QS method quantifies long-time (10 seconds) response, and the CSM method quantifies short-time (0.022 second) response. The fact that these two methods yielded no statistically significant difference in IM causes us to include all physiologically interesting frequencies in this conclusion. Bone may well be viscoelastic at an organ level [19–21]. At an organ level, blood vessels, lacunae, fluid-filled channels/canaliculi, and the larger volume of collagen matrix may all contribute to a viscoelastic nature. However, dynamic testing of a whole femur from a 65-year-old female subject revealed only slight viscoelasticity; the loss modulus was about 5% of the Young's modulus, and the Young's modulus was nearly independent of frequency [22]. We should expect even less viscoelasticity at the scale of the test within the individual osteons. Thus, our conclusion is not so surprising, as the imprint diameter of a 500-nm indentation test is approximately 4-5 microns. The conclusion that bone tissue does not demonstrate significant viscoelasticity at this scale is relevant, because a frequent critique to testing bone by indentation is that analytic models for interpreting indentation data might not properly account for viscoelastic behavior. Whether or not such a critique is generally valid, the present study reveals that it is irrelevant for bone tissue at the scale of testing undertaken in this study. At this point, it is important to note that our tests were conducted under moist conditions for the entire test period, by means of a custom hydration system [12, 23]. We believed that it was important to conduct tests in this way so as not to artificially mitigate viscoelasticity.

Although the two test methods yielded no significant difference in IM, the two test methods did yield slightly but significantly different measures of H for the unlabeled (old) osteons. For the unlabeled osteons, the H obtained by the CSM method was 9% greater than that obtained by the QS method. (Although the same trend was observed for the labeled osteons, the difference was not quite large enough to be considered statistically significant.) Logistically,

this can be explained by the fact that during the 30-second hold segment (2), the indenter penetration continued to increase, even while the force on the indenter was held constant. Hardness (H) is calculated as load divided by area (P/A). The CSM value of H was obtained immediately prior to the hold segment, while the QS value of H was obtained after the hold segment. Over the course of the hold segment, applied load (P) remained constant, but the contact area increased, so the QS method returned a lower value of hardness. But what is the underlying cause of this relaxation? Because we provide evidence suggesting the lack of significant viscoelasticity, we must conclude that it is due to viscoplasticity. The plastic (or nonrecoverable) strain response to stress does not occur instantaneously, but rather, over a period of time. In other words, bone tissue does creep, and this tendency is potentially greater in older bone. Our findings are in agreement with another indentation study of osteonal bone, in which authors found that the dominant time-dependent deformation mechanism for bone was viscoplasticity [24]. Future work should focus on achieving a better understanding of this tendency.

Our protocol has been to make indents to a maximum depth of 500 nm, as this mitigates the consequences of surfaces roughness, which is 30 nm or less. However, the CSM method returns properties as a continuous function of indentation depth. For the labeled osteons, the value of IM at 500 nm was 6% higher than the value measured at 100 nm; however, this difference is not large enough to be statistically significant and may have biologic implications. For the unlabeled osteons, there was no perceptible trend in IM with depth; values measured at 100 nm were equal to those measured at 500 nm. This lack of depth dependence causes us to conclude that architectural features of bone as small as ~ 1 micron wide could be tested with indentations as small as 100 nm.

This study revealed that IM is largely independent of test method. Therefore, we may conclude that virtually any indentation method commonly used today will return the same value for IM for the same material under the same test conditions. However, because bone tissue at this scale does exhibit viscoplasticity, hardness measurements will be sensitive to test method. Hardness measurements should be compared only if they have been determined by the same method.

5. Conclusion

This study confirms that new and old osteons have significantly different indentation properties. In addition, we conclude the following.

- (i) Bone at the scale of testing described in this study, does not exhibit significant viscoelastic behavior.
- (ii) At this scale of testing, bone is viscoplastic; older bone is more so.
- (iii) IM values determined by different test methods are comparable, so long as test conditions are similar.
- (iv) H values should not be directly compared unless they have been measured by the same method.

Determining the material properties of biologic tissues such as bone, enamel, dentin and cementum is challenging. In this paper we present data and compare two techniques for testing the material properties at the scale of individual osteons. The techniques presented could be applied to other biologic tissues. Such spatially resolved testing may eventually allow us to understand the relationship between structure and function of organic and inorganic phases of mineralized tissues.

References

- [1] C. E. Hoffer, X. E. Guo, P. K. Zysset, K. E. Moore, and S. A. Goldstein, "Evaluation of bone microstructural properties: effect of testing conditions, depth, repetition, time delay and displacement rate," in *Proceeding of the ASME Bioengineering Conference (ASME '97)*, pp. 567–568, New York, NY, USA, 1997.
- [2] J.-Y. Rho, T. Y. Tsui, and G. M. Pharr, "Elastic properties of human cortical and trabecular lamellar bone measured by nanoindentation," *Biomaterials*, vol. 18, no. 20, pp. 1325–1330, 1997.
- [3] J.-Y. Rho, J. D. Currey, P. Zioupos, and G. M. Pharr, "The anisotropic Young's modulus of equine secondary osteons and interstitial bone determined by nanoindentation," *Journal of Experimental Biology*, vol. 204, no. 10, pp. 1775–1781, 2001.
- [4] W. Tesch, N. Eidelman, P. Roschger, F. Goldenberg, K. Klaushofer, and P. Fratzl, "Graded microstructure and mechanical properties of human crown dentin," *Calcified Tissue International*, vol. 69, no. 3, pp. 147–157, 2001.
- [5] J. L. Cuy, A. B. Mann, K. J. Livi, M. F. Teaford, and T. P. Weihs, "Nanoindentation mapping of the mechanical properties of human molar tooth enamel," *Archives of Oral Biology*, vol. 47, no. 4, pp. 281–291, 2002.
- [6] E. Ozcivici, S. Ferreri, Y.-X. Qin, and S. Judex, "Determination of bone's mechanical matrix properties by nanoindentation," *Methods in Molecular Biology*, vol. 455, pp. 323–334, 2008.
- [7] G. Lewis and J. S. Nyman, "The use of nanoindentation for characterizing the properties of mineralized hard tissues: state-of-the art review," *Journal of Biomedical Materials Research B*, vol. 87, no. 1, pp. 286–301, 2008.
- [8] C. E. Hoffer, K. E. Moore, K. Kozloff, P. K. Zysset, and S. A. Goldstein, "Age, gender, and bone lamellae elastic moduli," *Journal of Orthopaedic Research*, vol. 18, no. 3, pp. 432–437, 2000.
- [9] J. Y. Rho, S. R. Mishra, K. Chung, J. Bai, and G. M. Pharr, "Relationship between ultrastructure and the nanoindentation properties of intramuscular herring bones," *Annals of Biomedical Engineering*, vol. 29, no. 12, pp. 1082–1088, 2001.
- [10] U. Jonsson, P. Netz, and L. Stromberg, "Solid mechanics and strength of bone in young dogs," *Acta Orthopaedica Scandinavica*, vol. 55, no. 4, pp. 446–451, 1984.
- [11] I. F. Meta, S. A. Fernandez, P. Gulati, and S. S. Huja, "Adaptations in the mandible and appendicular skeleton of high and low bone density inbred mice," *Calcified Tissue International*, vol. 81, no. 2, pp. 107–113, 2007.
- [12] S. S. Huja, F. M. Beck, and D. T. Thurman, "Indentation properties of young and old osteons," *Calcified Tissue International*, vol. 78, no. 6, pp. 392–397, 2006.
- [13] W. C. Oliver and G. M. Pharr, "Improved technique for determining hardness and elastic modulus using load and

- displacement sensing indentation experiments,” *Journal of Materials Research*, vol. 7, no. 6, pp. 1564–1580, 1992.
- [14] I. N. Sneddon, “The relation between load and penetration in the axisymmetric boussinesq problem for a punch of arbitrary profile,” *International Journal of Engineering Science*, vol. 3, no. 1, pp. 47–57, 1965.
- [15] C. H. Turner and D. B. Burr, “Basic biomechanical measurements of bone: a tutorial,” *Bone*, vol. 14, no. 4, pp. 595–608, 1993.
- [16] J. Xu, J. Y. Rho, S. R. Mishra, and Z. Fan, “Atomic force microscopy and nanoindentation characterization of human lamellar bone prepared by microtome sectioning and mechanical polishing technique,” *Journal of Biomedical Materials Research A*, vol. 67, no. 3, pp. 719–726, 2003.
- [17] M. S. Bobji and S. K. Biswas, “Estimation of hardness by nanoindentation of rough surfaces,” *Journal of Materials Research*, vol. 13, no. 11, pp. 3227–3233, 1998.
- [18] J. L. Hay and G. M. Pharr, “Instrumented indentation testing,” in *ASM Handbook Mechanical Testing and Evaluation*, H. Kuhn and D. Medlin, Eds., pp. 232–243, ASM International, Materials Park, Ohio, USA, 2000.
- [19] R. S. Lakes, J. L. Katz, and S. S. Sterstein, “Viscoelastic properties of wet cortical bone. I. Torsional and biaxial studies,” *Journal of Biomechanics*, vol. 12, no. 9, pp. 657–678, 1979.
- [20] R. S. Lakes and J. L. Katz, “Viscoelastic properties of wet cortical bone. II. Relaxation mechanisms,” *Journal of Biomechanics*, vol. 12, no. 9, pp. 679–687, 1979.
- [21] R. S. Lakes and J. L. Katz, “Viscoelastic properties of wet cortical bone. III. A non-linear constitutive equation,” *Journal of Biomechanics*, vol. 12, no. 9, pp. 689–698, 1979.
- [22] C. Cherraf-Schweyer, G. Maurice, M. Taghite, and K. Taous, “An experimental and theoretical approach of elasticity and viscoelasticity of compact and spongy bone with periodic homogenization,” *Computer Methods in Biomechanics and Biomedical Engineering*, vol. 10, no. 3, pp. 195–207, 2007.
- [23] S. S. Huja, S. A. Fernandez, K. J. Hill, and P. Gulati, “Indentation modulus of the alveolar process in dogs,” *Journal of Dental Research*, vol. 86, no. 3, pp. 237–241, 2007.
- [24] Z. Fan and J.-Y. Rho, “Effects of viscoelasticity and time-dependent plasticity on nanoindentation measurements of human cortical bone,” *Journal of Biomedical Materials Research A*, vol. 67, no. 1, pp. 208–214, 2003.