

Cartilage Tissue Engineering Via Icariin and Adipose-derived Stem Cells in Fibrin Scaffold

Abstract

Background: Nowadays, cartilage tissue engineering is the best candidate for regeneration of cartilage defects. This study evaluates the function of herbal extracts icariin (ICA), the major pharmacological constituent of herba *Epimedium*, compared with transforming growth factor $\beta 3$ (TGF $\beta 3$) to prove its potential effect for cartilage tissue engineering. **Materials and Methods:** ICA, TGF $\beta 3$, and TGF $\beta 3$ + ICA were added fibrin-cell constructions derived from adipose tissue stem cells. After 14 days, cell viability analyzed by 3-(4,5-dimethyl-2-thiazolyl)-2,5-diphenyl-2H-tetrazolium bromide assay and the expression of cartilage genes was evaluated with real-time polymerase chain reaction (RT-PCR). **Results:** The results showed ICA, TGF $\beta 3$, and TGF $\beta 3$ + ICA increased the rate of proliferation and viability of cells; but there were no significant differences between them ($P > 0.05$). Furthermore, quantitative RT-PCR analysis demonstrated that cooperation of ICA with TGF $\beta 3$ showed a better effect in expression of cartilaginous specific genes and increased Sox9, type II collagen, and aggrecan expression significantly. Furthermore, the results of the expression of type I and X collagens revealed that TGF $\beta 3$ increased the expression of them ($P < 0.01$); However, treatment with ICA + TGF $\beta 3$ down regulated the expression of these genes significantly. **Conclusion:** The results indicated ICA could be a potential factor for chondrogenesis and in cooperation with TGF $\beta 3$ could reduce its hypertrophic effects and it is a promising factor for cartilage tissue engineering.

Keywords: Adipose-derived stem cells, chondrocytes, chondrogenesis, icariin

Introduction

Osteoarthritis is a prevalent and chronic form of joint disease and one of the major causes of disability among old people.^[1] The disease affects whole joint and destructs articular cartilage.^[2] Due to the absence of nutritional vessels in articular cartilage and lack of self-healing capacity in this tissue,^[3,4] its damages improve generally through scar tissue formation that is mostly fibrocartilage.^[5] Fibrocartilage tissue in compared with normal cartilage has substandard biomechanical properties and progressively degrades with time, and finally leading to inability of the joint.^[5,6]

Using stem cells in tissue engineering is a promising approach for the treatment of cartilage defects after injury^[7,8] and is based on the fact that stem cells have the potential to differentiate into multilineage cells.^[9,10] Growth factors play an important role for regulating stem cells differentiation and are considered as a powerful tool for tissue engineering.^[11,12] Among these, transforming growth factor- β (TGF β) superfamily widely

used in cartilage tissue engineering. Different studies have demonstrated the effects of these factors on chondrogenic differentiation and formation of cartilage-like tissue *in vivo* and *in vitro*.^[13,14] However, along with chondrogenic induction, they lead to hypertrophy of chondrocytes;^[15-17] Hence, it is necessary to develop low cost and effective compounds without hypertrophic effects as a replacement for growth factors.^[18,19]

Herba *Epimedium* (HEP) is one of 52 species of flowering herbaceous plants.^[20] It has been broadly used as an anti-rheumatoid, tonic, and aphrodisiac for more than 2000 years in Japan, Korea, and China.^[21-23] More than 260 different combinations have been identified from different *Epimedium* species. Among them, flavonoids and their derivatives are as the most important component.^[24,25] Icariin (ICA; C₃₃H₄₀O₁₅; molecular weight, 676.65), as a common flavonoid glycoside, is the most important pharmacologically component of HEP. This factor is selected as a medical marker for quality control of HEP in Chinese Pharmacopoeia.^[26] Different studies showed ICA is a safe anabolic

This is an open access article distributed under the terms of the Creative Commons Attribution-NonCommercial-ShareAlike 3.0 License, which allows others to remix, tweak, and build upon the work non-commercially, as long as the author is credited and the new creations are licensed under the identical terms.

For reprints contact: reprints@medknow.com

How to cite this article: Bahrami M, Valiani A, Amirpour N, Ra Rani MZ, Hashemibeni B. Cartilage Tissue Engineering Via Icariin and Adipose-derived Stem Cells in Fibrin Scaffold. *Adv Biomed Res* 2018;7:36.

Received: August, 2016. **Accepted:** September, 2016.

Maryam Bahrami¹,
Ali Valiani¹,
Noushin Amirpour¹,
Mohammad Zamani
Ra Rani²,
Batool
Hashemibeni^{1,3}

From the ¹Department of Anatomical Sciences, Faculty of Medicine, ³Torabinejad Dental Research Center, Dental School, Isfahan University of Medical Sciences, Isfahan, ²Department of Anatomical Sciences, Faculty of Medicine, Hormozgan University of Medical Sciences, Hormozgan, Iran

Address for correspondence:

Dr. Batool Hashemibeni,
Department of Anatomical Sciences, Faculty of Medicine, Isfahan University of Medical Sciences, Isfahan, Iran,
E-mail: hashemibeni@med.mui.ac.ir

Access this article online

Website: www.advbiores.net

DOI: 10.4103/2277-9175.225925

Quick Response Code:



agent for chondrogenesis.^[9,18,19,27] However, previous studies were based on the use of bone marrow mesenchymal stem cells (BM-MSCs) and chondrocytes and there is no study to investigate the chondrogenic effect of ICA on adipose-derived stem cells (ADSCs). In the current research, for the first time, we investigated the effect of ICA on chondrogenic differentiation of adipose-derived stem cells in fibrin scaffold.

Materials and Methods

Reagents

ICA (purity $\geq 94\%$) was purchased from Sigma-Aldrich Co., Stock solutions of ICA were dissolved in dimethylsulfoxide (DMSO; Sigma-Aldrich Co., USA) and stored at -20°C . Fetal bovine serum (FBS) was obtained from Bioidea (Iran). Penicillin/streptomycin and high glucose Dulbecco's modified Eagle medium (DMEM) were purchased from Gibco Co (USA). Majority of compounds including TGF β 3, phosphate-buffered saline (PBS), DMEM-low glucose, collagenase A, trypsin– ethylenediaminetetraacetic acid, dexamethasone, bovine serum albumin (BSA), insulin-transferrin-selenium (ITS), ascorbate-2-phosphate (ASP), 3-(4,5-dimethyl-2-thiazolyl)-2,5-diphenyl-2H-tetrazolium bromide (MTT), and linoleic acid, were purchased from Sigma-Aldrich Co (USA).

Isolation and culture of adipose-derived stem cells

Human subcutaneous adipose tissue was obtained from three healthy persons undergoing liposuction surgery. All procedures were carried out according to the Isfahan University of Medical Sciences, Medical Faculty Ethics Committee Approval. Fat tissue was cut into small pieces and washed thoroughly with PBS. Small pieces of fat were combined with 0.1% collagenase A and were incubated for 45 min at 37°C . Then, enzyme activity was neutralized with the same volume medium containing DMEM-low glucose, 10% FBS, and 1% penicillin/streptomycin. Following, the suspension was centrifuged for 10 min at 1400 rpm. The cell pellets were cultured in flasks containing fresh medium with DMEM-low glucose, 1% penicillin/streptomycin, and 10% FBS. The flasks were incubated at 37°C and 5% CO_2 conditions.

Fibrin scaffold preparation and adipose-derived stem cells encapsulation

Fibrin formed cryoprecipitate, which is enriched in fibrinogen. Thrombin as a main component is required to convert fibrinogen to fibrin. For thrombin preparation, 16 ml fresh frozen plasma transferred to conical tubes. Then, 10 ml of calcium gluconate added to each tube and the suspension incubated at 37°C for 70–90 min. Following, the suspension centrifuged for 10 min at 2200 rpm. Finally, transparent supernatant obtained from centrifugation contains thrombin stored at -80°C .^[28]

For preparation of cell-fibrin constructs, 10^6 cells at the third passage were resuspended in 500 μl fibrinogen in each well of 24-well plate. Then, 500 μl of thrombin was added to form the fibrin clot. After encapsulation, cell-fibrin constructs were classified into four groups: The first group was cultured with TGF β 3 (10 ng/ml); the second group was used with ICA (1×10^{-5} M);^[18] the third group cultured with TGF β 3 and ICA together; and the fourth group without TGF β 3 and ICA as control group. In all groups, chondrogenic medium containing high glucose DMEM, 100 nM dexamethasone, 1% ITS, 1% BSA, 5 ng/ml linoleic acid, 50 $\mu\text{g/ml}$ ASP, 1% penicillin-streptomycin was used. All groups were incubated for 14 days. The half of media refreshed every 3 days.

Cell viability evaluation

The effects of various agents on cell viability were analyzed by MTT assay. After 14 days, the cell-fibrin constructs were washed twice with PBS. The combination of 400 μl medium and 40 μl MTT solutions (5 mg/ml) was added to each well and incubated for 4 h. After the removal of the medium, the purple-blue formazan precipitates dissolved in 400 μl DMSO and plates placed for 2 h in the dark room. Then, 100 μl of each well solution was transferred to 96-well plate. The absorbance was measured at 540 nm by an ELISA reader (Spectra Max 340, Molecular Device Inc., CA, USA).

Real-time polymerase chain reaction analysis

To investigate the expression of chondrocyte-specific genes including type I, type II, type X collagens, aggrecan, and Sox9, the real-time polymerase chain reaction (RT-PCR) was performed. Total cellular RNA was extracted using RNA Extraction kit (Yekta Tajhiz Azma, Iran), according to the manufacturer's protocol. Using the RNA samples, cDNAs were synthesized by the PrimeScript™ RT reagent Kit (Fermentas, Canada). The RT-PCR reactions were performed using StepOnePlus™ RT-PCR System (Applied Biosystems, USA) with SYBR Green PCR Master Mix (Yekta Tajhiz Azma, Iran) under the implication condition including initial denaturation at 95°C followed by thirty cycles of denaturation at 95°C for 30 s, annealing at 56°C for 45 s and extension at 72°C for 45 s, and a final polymerization at 72°C for 10 min. RT-PCR was performed in triplicate. The primer sequences used for RT-PCR are summarized in Table 1. Relative cartilage gene expression was analyzed using the comparative Ct method ($2^{-\Delta\Delta\text{Ct}}$).^[29] All samples normalized to level of GAPDH, which used as the loading control.

Results

Adipose-derived stem cells morphology

Phase contrast microscopic morphology of ADSCs revealed homogenous fibroblast-like cells in the third passage in compared with multiform cells in primary culture (P0) [Figure 1].

Table 1: Primer sequences used in real-time polymerase chain reaction technique

Gene name	Forward primer	Reverse primer
Collagen II	5'-GCCACCGTGCCCAAGAAGAACT-3'	5'ACAGCAGGCGCAGGAAGGTCAT-3'
Collagen I	5'-AGAGGACCACGTGGAGAAAG-3'	5'-CCATCAAACCTGAGCAGCAAA-3'
Collagen X	5'-GGAAAACAAGGGGAGAGAGG-3'	5'-CCAGGAGCACCATATCCTGT-3'
Aggrecan	5'-CCTACCAGGACAAGGTCTCG-3'	5'-ACACCTTTCACCACGACCTC-3'
Sox9	5'-GGAAGCTCTGGAGACTGCTG-3'	5'-CGTTCTTACCAGACTTCCTC-3'
GAPDH	5'-ATCACTGCCACCCAGAAGAC-3'	5'-GTGAGTTTCCCGTTCAGCTC-3'




Figure 1: (a) Human subcutaneous adipose-derived stem cells in P0 passage after 3 days ($\times 40$); (b) Adipose-derived stem cells in third passage: cells reach 80% confluence and show spindle shape ($\times 40$)

Cell viability and proliferation

Our results indicated that the viability and proliferation of treatment groups increased in compared with the control group ($P < 0.05$) [Figure 2]. No significant difference was seen between treatment groups.

Gene expression in different groups

The results of RT-PCR were revealed the expression of the cartilaginous-specific genes including type II collagen, aggrecan, and Sox9 in all groups.

As shown in Figure 3a and b, ICA and TGF β 3 increased the expression of type II collagen and Sox9 in compared with the control group although the difference was not significant. In the ICA + TGF β 3 group, expression of Sox9 and type II collagen increased in compared with the control group ($P < 0.05$). RT-PCR analysis of differentiated cells at day 14 showed that expression of aggrecan gene in ICA + TGF β 3 group was the highest. In this group, expression of aggrecan increased 2.25-fold in comparison of TGF β 3 group ($P < 0.01$) [Figure 3c].

Quantitative RT-PCR results demonstrated that type I collagen (fibrocartilage marker) and type X collagen (hypertrophic marker) significantly upregulated in TGF β 3 group ($P < 0.01$). However, expression of these two markers downregulated in ICA group significantly. In addition, ICA alone decreased expression of type I and type X collagens 1.88- and 2.34-fold, respectively, in compared with TGF β 3 [Figure 3d and e].

Discussion

Due to cartilage's poor potential for natural repair, regeneration of cartilage defects is challenging to




Figure 2: Cell-fibrin constructs in 24-well microplate. Cell viability was analyzed using 3-(4,5-dimethyl-2-thiazolyl)-2,5-diphenyl-2H-tetrazolium bromide assay after 14 days (a). Dissolved purple-blue formazan precipitate in dimethylsulfoxide (b). Comparison of 3-(4,5-dimethyl-2-thiazolyl)-2,5-diphenyl-2H-tetrazolium bromide assay results in different groups. There are no significant differences between groups treated with icariin, TGF β 3, and TGF β 3-icariin together; but compared with the control group the rate of proliferation and viability are increased in all of three groups (c) ($P > 0.05$). ICA, icariin; TGF β 3, transforming growth factor β 3

orthopedic surgeons. Using autologous adult stem cells such as BM-MSCs and ADSCs to repair defective cartilage may become a viable clinical option. Nowadays, two cell sources were widely used in cartilage tissue engineering: BM-MSCs and adipose-derived stem cells. Huang *et al.* in their study compared these two cells and showed that the chondrogenesis potential of bone marrow stem cells is higher than adipose-derived stem cells.^[30] However, Zhu *et al.* reported that adipose-derived stem cells are better than them.^[31] Other studies revealed that the similar differentiation potential for these two sources.^[32-34] Adipose-derived stem cells in contrast with BM-MSCs obtained in large amounts and achieved easily with noninvasive techniques.^[35-37] These advantages for adipose-derived stem cells were considered them for cartilage defects repair; hence, in this study, these cells were used.

Many investigators indicated that the cartilage harvested during chondrogenic differentiation of stem cells with TGF β s are not the same as normal hyaline cartilage because of having many type I and X collagens and not enough type II collagen.^[38] Therefore, it is necessary to develop safe compounds that can substitute growth factors or cooperate with them. Therefore, it is necessary to develop a safe combination that can substitute growth factors or cooperate with them.




Figure 3: Effects of Icarin, TGFβ3, and TGFβ3 + icariin on gene expression of cartilage markers. Real-time polymerase chain reaction analysis was performed at day 14. Real-time polymerase chain reaction demonstrated that Sox9, type II collagen, and aggrecan significantly increased in icariin + TGFβ3 (a-c). Type I and X collagens decreased in icariin group (d and e). * $P < 0.05$; ** $P < 0.01$; *** $P < 0.001$. ICA, icariin; TGFβ3, transforming growth factor β3

It has been revealed that ICA is an effective compound in the treatment of osteoporosis, the restoration of bone defects, and the bone tissue engineering.^[9,19,39,40] Therefore, it is possible that ICA to be a potential promoting compound for cartilage tissue engineering. The present study investigated the effects of ICA, TGFβ3, and ICA + TGFβ3 on the ADSCs viability, proliferation, and expression some of cartilage-specific genes, *in vitro*. It proved that in treatment group cell viability and proliferation increased in compared with the control group. Furthermore, our findings indicated that ICA significantly downregulated the expression of type I and type X collagens in compared with TGFβ3. Although the expression of type II collagen, aggrecan, and Sox9 was superior in ICA + TGFβ3 group.

Zhang *et al.* reported that ICA affected on proliferation of chondrocytes in dose-dependent manner.^[18] In contrast with Zhang' study, we indicated that ICA in 10-5 M increased cell proliferation which might be related to the different kind of cell.

Some researchers have proven that ICA is an anabolic agent, which can enhance chondrocyte proliferation and reduce extracellular matrix degradation.^[27,41] It was reported that ICA promotes the secretion of various growth factors, including BMP2 and TGFβ1 in osteoblasts, *in vitro*.^[42,43] Different studies have shown that BMP signals upregulated the expression of Sox9.^[44] Sox9, a key gene in chondrogenesis and differentiation, promotes the expression of type II collagen and aggrecan.^[45] Li has demonstrated that the expression of Sox9 significantly increased by ICA.^[19] Similarly, our results indicated that ICA with TGFβ3 enhances the expression of Sox9 considerable.

Furthermore, in contrast with other studies, our finding indicate that ICA in combination with TGFβ3 upregulated cartilage-specific gene.^[18,19]

Type X and type I collagen are hypertrophic and fibrocartilage markers, respectively. Different reports have shown use of TGFβ3 lead to cell hypertrophy and fibrocartilage formation.^[15-17] In the current study, it was revealed that TGFβ3 increased expression of type I and type X collagens. However, ICA reduced these two genes.

Conclusion

All of these findings suggest that ICA may be a potential promoting factor for cartilage tissue engineering and it could reduce cell hypertrophy

Acknowledgment

We want to thanks the vice chancellor of Isfahan university of medical sciences and Mrs.Aliakbari who helps us to collect the samples.

Financial support and sponsorship

This study was founded by the research council of Isfahan University of Medical Sciences, Isfahan, Iran (No. 394590).

Conflicts of interest

There are no conflicts of interest.

References

- Lutz W, Sanderson W, Scherbov S. The coming acceleration of global population ageing. *Nature* 2008;451:716-9.
- Sellam J, Berenbaum F. The role of synovitis in pathophysiology and clinical symptoms of osteoarthritis. *Nat Rev Rheumatol* 2010;6:625-35.
- Ansar MM, Esfandiariy E, Mardani M, Hashemibeni B, Zarkesh-Esfahani SH, Hatef M, *et al.* A comparative study of aggrecan synthesis between natural articular chondrocytes and differentiated chondrocytes from adipose derived stem cells in 3D culture. *Adv Biomed Res* 2012;1:24.
- Sadeghi F, Esfandiari E, Hashemibeni B, Atef F, Salehi H, Shabani F. The effect of estrogen on the expression of cartilage-specific genes in the chondrogenesis process of adipose-derived stem cells. *Adv Biomed Res* 2015;4:43.
- Ahmed TA, Hincke MT. Strategies for articular cartilage lesion repair and functional restoration. *Tissue Eng Part B Rev* 2010;16:305-29.
- Aigner T, Stöve J. Collagens – Major component of the physiological cartilage matrix, major target of cartilage degeneration, major tool in cartilage repair. *Adv Drug Deliv Rev* 2003;55:1569-93.
- Ahmed TA, Hincke MT. Fibrin for encapsulation of human mesenchymal stem cells for chondrogenic differentiation. *Stem Cells and Cancer Stem Cells*. Vol. 10. New York: Springer; 2013. p. 59-69.
- Mardani M, Kabiri A, Esfandiari E, Esmaeili A, Pourazar A, Ansar M, *et al.* The effect of platelet rich plasma on chondrogenic differentiation of human adipose derived stem cells in transwell culture. *Iran J Basic Med Sci* 2013;16:1163-9.
- Wang ZC, Sun HJ, Li KH, Fu C, Liu MZ. Icarin promotes directed chondrogenic differentiation of bone marrow mesenchymal stem cells but not hypertrophy *in vitro*. *Exp Ther Med* 2014;8:1528-34.
- Diekman BO, Rowland CR, Lennon DP, Caplan AI, Guilak F. Chondrogenesis of adult stem cells from adipose tissue and

- bone marrow: Induction by growth factors and cartilage-derived matrix. *Tissue Eng Part A* 2010;16:523-33.
11. Vacanti JP, Langer R. Tissue engineering: The design and fabrication of living replacement devices for surgical reconstruction and transplantation. *Lancet* 1999;354 Suppl 1:S132-4.
 12. Reddi AH. Symbiosis of biotechnology and biomaterials: Applications in tissue engineering of bone and cartilage. *J Cell Biochem* 1994;56:192-5.
 13. Zamani S, Hashemibeni B, Esfandiari E, Kabiri A, Rabbani H, Abutorabi R. Assessment of TGF- β 3 on production of aggrecan by human articular chondrocytes in pellet culture system. *Adv Biomed Res* 2014;3:54.
 14. Jung MR, Shim IK, Chung HJ, Lee HR, Park YJ, Lee MC, *et al.* Local BMP-7 release from a PLGA scaffolding-matrix for the repair of osteochondral defects in rabbits. *J Control Release* 2012;162:485-91.
 15. Giovannini S, Diaz-Romero J, Aigner T, Heini P, Mainil-Varlet P, Nestic D. Micromass co-culture of human articular chondrocytes and human bone marrow mesenchymal stem cells to investigate stable neocartilage tissue formation *in vitro*. *Eur Cell Mater* 2010;20:245-59.
 16. Aung A, Gupta G, Majid G, Varghese S. Osteoarthritic chondrocyte-secreted morphogens induce chondrogenic differentiation of human mesenchymal stem cells. *Arthritis Rheum* 2011;63:148-58.
 17. Mueller MB, Fischer M, Zellner J, Berner A, Dienstknecht T, Kujat R, *et al.* Effect of parathyroid hormone-related protein in an *in vitro* hypertrophy model for mesenchymal stem cell chondrogenesis. *Int Orthop* 2013;37:945-51.
 18. Zhang L, Zhang X, Li KF, Li DX, Xiao YM, Fan YJ, *et al.* Icariin promotes extracellular matrix synthesis and gene expression of chondrocytes *in vitro*. *Phytother Res* 2012;26:1385-92.
 19. Li D, Yuan T, Zhang X, Xiao Y, Wang R, Fan Y, *et al.* Icariin: A potential promoting compound for cartilage tissue engineering. *Osteoarthritis Cartilage* 2012;20:1647-56.
 20. Stearn WT, Shaw J, Green PS, Mathew B. Genus *Epimedium* and other Herbaceous *Berberidaceae*. Timber Press, Inc., Portland, OR, USA; 2002.
 21. Li S, Ying Y. Ben Cao Gang Mu. Beijing, China: Xue Yuan Publishing House; 1991.
 22. Meng FH, Li YB, Xiong ZL, Jiang ZM, Li FM. Osteoblastic proliferative activity of *Epimedium brevicornum* Maxim. *Phytomedicine* 2005;12:189-93.
 23. Xie F, Wu CF, Lai WP, Yang XJ, Cheung PY, Yao XS, *et al.* The osteoprotective effect of herba epimedii (HEP) extract *in vivo* and *in vitro*. *Evid Based Complement Alternat Med* 2005;2:353-61.
 24. Wu H, Lien EJ, Lien LL. Chemical and pharmacological investigations of *Epimedium* species: A survey. *Prog Drug Res* 2003;60:1-57.
 25. Ma H, He X, Yang Y, Li M, Hao D, Jia Z. The genus *Epimedium*: An ethnopharmacological and phytochemical review. *J Ethnopharmacol* 2011;134:519-41.
 26. Li C, Li Q, Mei Q, Lu T. Pharmacological effects and pharmacokinetic properties of icariin, the major bioactive component in herba epimedii. *Life Sci* 2015;126:57-68.
 27. Liu MH, Sun JS, Tsai SW, Sheu SY, Chen MH. Icariin protects murine chondrocytes from lipopolysaccharide-induced inflammatory responses and extracellular matrix degradation. *Nutr Res* 2010;30:57-65.
 28. Yang SH, Wu CC, Shih TT, Chen PQ, Lin FH. Three-dimensional culture of human nucleus pulposus cells in fibrin clot: Comparisons on cellular proliferation and matrix synthesis with cells in alginate. *Artif Organs* 2008;32:70-3.
 29. Livak KJ, Schmittgen TD. Analysis of relative gene expression data using real-time quantitative PCR and the 2-Delta Delta CT method. *Methods* 2001;25:402-8.
 30. Huang JI, Kazmi N, Durbhakula MM, Hering TM, Yoo JU, Johnstone B. Chondrogenic potential of progenitor cells derived from human bone marrow and adipose tissue: A patient-matched comparison. *J Orthop Res* 2005;23:1383-9.
 31. Zhu Y, Liu T, Song K, Fan X, Ma X, Cui Z. Adipose-derived stem cell: A better stem cell than BMSC. *Cell Biochem Funct* 2008;26:664-75.
 32. Gimble JM, Katz AJ, Bunnell BA. Adipose-derived stem cells for regenerative medicine. *Circ Res* 2007;100:1249-60.
 33. Helder MN, Knippenberg M, Klein-Nulend J, Wuisman PI. Stem cells from adipose tissue allow challenging new concepts for regenerative medicine. *Tissue Eng* 2007;13:1799-808.
 34. Schäßfler A, Büchler C. Concise review: Adipose tissue-derived stromal cells – Basic and clinical implications for novel cell-based therapies. *Stem Cells* 2007;25:818-27.
 35. Zuk PA, Zhu M, Mizuno H, Huang J, Futrell JW, Katz AJ, *et al.* Multilineage cells from human adipose tissue: Implications for cell-based therapies. *Tissue Eng* 2001;7:211-28.
 36. Cowan CM, Shi YY, Aalami OO, Chou YF, Mari C, Thomas R, *et al.* Adipose-derived adult stromal cells heal critical-size mouse calvarial defects. *Nat Biotechnol* 2004;22:560-7.
 37. Kim HJ, Im GI. Chondrogenic differentiation of adipose tissue-derived mesenchymal stem cells: Greater doses of growth factor are necessary. *J Orthop Res* 2009;27:612-9.
 38. Chung C, Burdick JA. Engineering cartilage tissue. *Adv Drug Deliv Rev* 2008;60:243-62.
 39. Chen KM, Ge BF, Ma HP, Liu XY, Bai MH, Wang Y. Icariin, a flavonoid from the herb *Epimedium* enhances the osteogenic differentiation of rat primary bone marrow stromal cells. *Pharmazie* 2005;60:939-42.
 40. Zheng D, Peng S, Yang SH, Shao ZW, Yang C, Feng Y, *et al.* The beneficial effect of icariin on bone is diminished in osteoprotegerin-deficient mice. *Bone* 2012;51:85-92.
 41. Sun P, Liu Y, Deng X, Yu C, Dai N, Yuan X, *et al.* An inhibitor of Cathepsin K, icariin suppresses cartilage and bone degradation in mice of collagen-induced arthritis. *Phytomedicine* 2013;20:975-9.
 42. Hsieh TP, Sheu SY, Sun JS, Chen MH, Liu MH. Icariin isolated from *Epimedium pubescens* regulates osteoblasts anabolism through BMP-2, SMAD4, and Cbfa1 expression. *Phytomedicine* 2010;17:414-23.
 43. Liang W, Lin M, Li X, Li C, Gao B, Gan H, *et al.* Icariin promotes bone formation via the BMP-2/Smad4 signal transduction pathway in the hFOB 1.19 human osteoblastic cell line. *Int J Mol Med* 2012;30:889-95.
 44. Majumdar MK, Wang E, Morris EA. BMP-2 and BMP-9 promotes chondrogenic differentiation of human multipotential mesenchymal cells and overcomes the inhibitory effect of IL-1. *J Cell Physiol* 2001;189:275-84.
 45. Tew SR, Li Y, Pothacharoen P, Tweats LM, Hawkins RE, Hardingham TE. Retroviral transduction with SOX9 enhances re-expression of the chondrocyte phenotype in passaged osteoarthritic human articular chondrocytes. *Osteoarthritis Cartilage* 2005;13:80-9.