



# The effect of a desensitizer and CO<sub>2</sub> laser irradiation on bond performance between eroded dentin and resin composite

Meng Ding<sup>1</sup>, Sang-Wan Shin<sup>2</sup>, Min-Soo Kim<sup>2</sup>, Jae-Jun Ryu<sup>1\*</sup>, Jeong-Yol Lee<sup>2\*</sup>

<sup>1</sup>Department of Esthetic Restorative Dentistry, Graduate School of Clinical Dentistry, Korea University, Seoul, Republic of Korea

<sup>2</sup>Department of Advanced Prosthodontics, Institute for Clinical Dental Research, Korea University Medical Center, Korea University, Seoul, Republic of Korea

**PURPOSE.** This study was aimed to evaluate effect of the desensitizing pretreatments on the micro-tensile bond strengths ( $\mu$ TBS) to eroded dentin and sound dentin. **MATERIALS AND METHODS.** Forty-two extracted molars were prepared to form a flat dentin surface, and then they were divided into two groups. Group I was stored in distilled water while group II was subjected to a pH cycling. Each group was then subdivided into three subgroups according to desensitizing pretreatment used: a) pretreatment with desensitizer (Gluma); b) pretreatment with CO<sub>2</sub> Laser (Ultra Dream Pluse); c) without any pretreatment. All prepared surfaces were bonded with Single Bond 2 and built up with resin composite (Filtek Z250). The micro-tensile bond test was performed. Fracture modes were evaluated by stereomicroscopy. Pretreated surfaces and bonded interfaces were characterized by scanning electron microscope (SEM). The data obtained was analyzed by two-way ANOVA ( $\alpha = 0.05$ ). **RESULTS.** For both sound and eroded dentin, samples treated with desensitizer showed the greatest  $\mu$ TBS, followed by samples without any treatment. And samples treated with CO<sub>2</sub> laser showed the lowest  $\mu$ TBS. SEM study indicated that teeth with eroded dentin appeared prone to debonding, as demonstrated by existence of large gaps between adhesive layers and dentin. **CONCLUSION.** Pretreatment with Gluma increased the  $\mu$ TBS of Single Bond 2 for eroded and sound teeth. CO<sub>2</sub> laser irradiation weakened bond performance for sound teeth but had no effect on eroded teeth. [*J Adv Prosthodont* 2014;6:165-70]

**KEY WORDS:** Tooth erosion; Adhesives; Tensile strength; Lasers; Gluma dentin desensitizer

## INTRODUCTION

Dentin hypersensitivity (DH) is a painful and chronic dental

condition, and it occurs when dentinal tubules on the dentin surface are open and patent to vital pulp, which is probably related to erosion.<sup>1</sup> Although most erosive lesions are limited in enamel, deep lesions extending into dentin can occur if the erosive challenge persists.<sup>2</sup> Such lesions require a restorative treatment and it is important to be aware of the bonding performance on this type of substrate.

Resin composite (RC) is a popular material for the restoration of abrasion, abfraction, or erosive (AAE) lesions and all other non-carious tooth defects.<sup>3</sup> Although RC revealed good retention bonded to eroded dentin according to a 12-month-long clinical study,<sup>4</sup> other investigations have shown that failure rates are high.<sup>5,6</sup> Because of the poor outcomes of the restoration on AAE lesions, researchers have attempted to find a method to improve the bonding performance. Previous studies have evaluated the influence of different treatments involving roughing of dentin surface<sup>7</sup> and the application of a fluoride mouth rinse<sup>8</sup> on to

Corresponding author:

<sup>1</sup>Jae-Jun Ryu  
Korea University Anam Hospital, 73, Incheon-ro, Seongbuk-gu, Seoul, 136-705, Republic of Korea  
Tel. 82114040830, e-mail, koprosth@unitel.co.kr  
<sup>2</sup>Jeong-Yol Lee  
Korea University Guro Hospital, 148, Gurodong-ro, Guro-gu, Seoul, 152-703, Republic of Korea  
Tel. 821063349331: e-mail, wddc@korea.ac.kr  
Received August 13, 2013 / Last Revision March 12, 2014 / Accepted March 14, 2014

© 2014 The Korean Academy of Prosthodontics  
This is an Open Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/3.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

bonding performance, however, it has not been determined whether desensitization procedures such as sealant application and laser irradiation affect micro-tensile bond strengths.

Therefore, the aim of this study was to investigate whether desensitization pretreatment influence the micro-tensile bond strengths of RC to eroded and normal dentin.

The null hypotheses were;

1. There were no differences of micro-tensile bond strengths to eroded and sound dentin surfaces.
2. Pretreatment of dentin with desensitizer or a CO<sub>2</sub> laser has no influence on micro-tensile bond strengths.

## MATERIALS AND METHODS

This experiment was performed with an IRB approval of the Korea University Guro Hospital (NO. MD13024-001). Forty-two fresh human third molars without caries and restorations were extracted and restored in a 0.5% chloramine solution at 5°C until use. The teeth were ground down to form a flat dentin surface from the occlusal side using 320-grit silicon carbide paper on a polishing machine (Kyung Do Precision Industrial, Korea), and the teeth were randomly subjected to an immersion in distilled water during the experimental period (sound dentin, n = 21) and an erosion pH-cycling challenge (eroded dentin, n = 21). Six cycles per day involving 5-minute demineralization and 60-minute remineralization per cycle were applied for pH cycling for 9 days. For erosive demineralization,<sup>8</sup> a 0.05 M citric acid solution (pH 2.3, citric acid monohydrate) was used. After each erosion procedure, the teeth were thoroughly rinsed with tap water for at least 1 minute and kept in remineralization solution for 1 hour. The remineralization solution (pH 6.7)<sup>9</sup> consisted of 4.08 mmol/l H<sub>3</sub>PO<sub>4</sub>, 20.10 mmol/l KCl, 11.90 mmol/l Na<sub>2</sub>CO<sub>3</sub>, and 1.98 mmol/l CaCl<sub>2</sub>. All chemicals were obtained from Sigma Aldrich (St. Louis, MO, USA). The pH values of solutions were checked with a pH meter (pH/ION Meter DP-880, Dong-Woo Medical System, Seoul, Korea) at the beginning and end of each experimental day.

Afterward, teeth with sound dentin (I) or eroded dentin (II) were pretreated in three different ways (Table 1): a) application of Gluma<sup>®</sup> Desensitizer; b) irradiation with a CO<sub>2</sub> laser; c) left untreated. Two dentin substrate types and

3 desensitizing pretreatments produced 6 groups with 7 teeth in each (Table 2).

After surface pretreatment, one molar from each of the 6 groups (Ia, Ib, Ic, IIa, IIb, IIc) was prepared for SEM to evaluate morphological surface changes.

Teeth from each group was treated with Scotchbond<sup>™</sup> Etchant (LOT. 9AL, 3M<sup>™</sup> ESPE<sup>™</sup>, St. Paul, MN, USA) for 15 seconds and rinsed. The total-etch adhesive Adper<sup>™</sup> Single Bond 2 (LOT. N341785, 3M<sup>™</sup> ESPE<sup>™</sup>, St. Paul, MN, USA) was applied according to manufacturer's instructions.

After bonding procedure, molars were built up in two layers of 2 mm each with a RC- Filtek Z250 (Lot. N453720, 3M<sup>™</sup> ESPE<sup>™</sup>, St. Paul, MN, USA). Each layer of resin composite was light-cured for 20s, and all light-curing was performed with an LED light curing unit (LED curing light, Dong Yang Linuo Medical Apparatus Co., Ltd., China). And then, all specimens were stored in a water bath with distilled water (Water Bath, Chang Shin Scientific Co., Ltd., Korea) for 24 hours at 37°C.

Teeth were vertically serially sectioned (Minisaw, GLP Korea, Korea) perpendicularly to the bonded interface to produce several sections with 1 mm thickness. These sections were further sectioned perpendicularly to the adhesive interface to produce sticks with adhesive area approximately 1 mm<sup>2</sup> according to the non-trimming version of micro-tensile technique.<sup>10</sup> Six to seven sticks from each molar were obtained and four of them were randomly selected for

**Table 2.** Identification of specimen groups by dentin type and pretreatment

Dentin type	Pretreatment	Number of specimens	Group designation
Sound dentin (I)	Gluma (a)	7	Ia
	CO <sub>2</sub> laser (b)	7	Ib
	No treatment (c)	7	Ic
Eroded dentin (II)	Gluma (a)	7	IIa
	CO <sub>2</sub> laser (b)	7	IIb
	No treatment (c)	7	IIc

**Table 1.** Materials, composition and mode of application of the pretreatment methods

Method	Material(instrument)	Composition	Application mode
Gluma	Gluma <sup>®</sup> Desensitizer (Lot. 010207, Heraeus Kulzer GmbH, Hanau, Germany )	HEMA Glutaraldehyde	1. Apply Gluma Desensitizer with a cotton pellet, using gentle but firm mechanical pressure. 2. Wait 60 seconds and dry thoroughly.
CO <sub>2</sub> Laser	ULTRA DREAM PLUSE (Daeshin enterprise, Korea)	/	Irradiate dentin surface with laser, in an UP/90us mode, 28 mJ per pulse at 2000 pulses per min for 1 min.
No treatment	/	/	/

HEMA = Hydroxyethyl Methacrylate.

the measurement of micro-tensile bond strengths ( $\mu$ TBS). In cases of pre-test failure, another stick from the same tooth was used as a replacement. The exact dimensions of each stick's bonding surface areas (BS (mm<sup>2</sup>)) were measured using a digital caliper (Mitutoyo, Kawasaki, Japan). The sticks were fixed by their ends to a test jaw mounted in micro-tensile tester (Microtensile Tester, Bisco Inc., Schaumburg, IL, USA) using cyanoacrylate glue (Zapit, Bisco Inc., Schaumburg, IL, USA). Then they were stressed in tension at a crosshead speed of 1.0 mm/min until fracture occurred, and the maximum force (Fmax (N)) was recorded. The  $\mu$ TBS values (MPa) were calculated using the formula,  $\mu$ TBS = Fmax/ BS.

In addition, failure modes of debonded specimens were evaluated at 30 $\times$  under a stereoscopic microscope (Model CX31, Olympus, Tokyo, Japan). Failure modes were classified as: (1) adhesive failures (failure at interface between adhesive resin and dentin), (2) cohesive failures (cohesive failure of dentin or resin), or (3) mixed failures (exhibits some cohesive failure and some adhesive failure).

After pretreatment, one molar per group was mounted on aluminium stubs, dehydrated in a desiccator (Freeze Dryer ES-2030, Hitachi Co., Tokyo, Japan) for 24 hours, and then sputter-coated with gold using a sputtering device (ION SPUTTER E-1045, Hitachi Co., Tokyo, Japan). Dentin surfaces were evaluated under an SEM (SEM S-4700, Hitachi Co., Tokyo, Japan), and photographs were taken at 1,000 $\times$  and 5,000 $\times$ .

To analyze adhesive interfaces, one additional tooth from each group was prepared in a similar way as described for  $\mu$ TBS measurements. Samples were prepared for SEM and evaluated at 1,000 $\times$  and 5,000 $\times$ .

Micro-tensile bond strengths data were analyzed using two-way ANOVA, and Tukey's test was used as a post-hoc test to analyze difference between groups at a significance level of 0.05. The analysis was conducted using IBM SPSS Statistics (Version 19, IBM SPSS, Armonk, NY, USA).

## RESULTS

Table 3 shows the  $\mu$ TBS means and standard deviations for all groups. Two-way ANOVA revealed that both the factors tested (dentin type and desensitizing pretreatment) and their interaction had significant influences on  $\mu$ TBS. Tukey's test further showed that for all three pretreatments, the mean  $\mu$ TBS to sound dentin were significantly higher

than those to eroded dentin.

For sound dentin, the group of pretreatment with Gluma (Ia) exhibited the highest mean  $\mu$ TBS while the group of pretreatment with CO<sub>2</sub> Laser (Ib) showed the lowest mean  $\mu$ TBS. There are significant differences ( $P < .05$ ) between these two groups and the group without any pretreatment (Ic) in mean  $\mu$ TBS (Table 3).


For eroded dentin, the group of pretreatment with Gluma (IIa) presented significant higher ( $P < .05$ )  $\mu$ TBS than the other two groups (IIb and IIc), neither of which were different from each other (Table 3).

The failure mode percentages of the debonded specimens are shown in Fig. 1.

The overall failure types for specimens were "adhesive" and "mixed". However, more cohesive failures were observed in sound dentin groups (Group I) than in eroded dentin groups (Group II).

Fig. 2 shows the microstructure of the dentin (sound/eroded) surface after desensitizing pretreatment.

Fig. 3 shows adhesive interface between RC and dentin. Fig. 3 (B, E, F) reveal that adhesive layers were not consistently bonded to dentin; gaps and debonded regions were observed in Group Ib, IIb and IIc, which concurred with the low micro-tensile bond strengths observed.



**Fig. 1.** Graphical presentation of the incidence (%) of failure modes for each group.


Group Ia: sound dentin treated with Gluma, Group Ib: sound dentin treated with CO<sub>2</sub> laser, Group Ic: sound dentin without any treatment, Group IIa: eroded dentin treated with Gluma, Group IIb: eroded dentin treated with CO<sub>2</sub> laser, Group IIc: eroded dentin without any treatment.

**Table 3.** Micro-tensile bond strengths in MPa (mean  $\pm$  SD) for each group


Substrate	Pretreatment		
	a (Gluma)	b (CO <sub>2</sub> laser)	C (control)
I (Sound dentin)	38.41 $\pm$ 4.47 <sup>a</sup>	20.54 $\pm$ 2.91 <sup>b</sup>	30.25 $\pm$ 3.88 <sup>c</sup>
II (Eroded dentin)	12.32 $\pm$ 3.94 <sup>d</sup>	8.56 $\pm$ 2.33 <sup>e</sup>	9.02 $\pm$ 2.26 <sup>e</sup>

Different superscript letters indicate a statistically significant difference ( $P < .05$ ).





**Fig. 2.** Morphology of dentin surfaces under different pretreatment. (A) Group Ia: Dentinal tubules were completely or partially closed. (B) Group Ib: The irregular protrusions (asterisk) may be smear layer affected by laser irradiation. (C) Group Ic: Typical smear layer was observed. (D) Group IIa: Smear layer was entirely removed and dentin was demineralized, some tubules orifices were partially plugged (arrows). (E) Group IIb: Abnormal inter-tubular dentin was seen in laser affected spot (asterisk). (F) Group IIc: The smear layer is completely removed and dentinal tubules were opened. (Original magnification x1,000.)



**Fig. 3.** Adhesive interface between resin composite and dentin. (A) Group Ia: A typical hybrid layer was hardly seen. (B) Group Ib: Debond area was apparently observed. (C) Group Ic: Adhesive layer bonded to dentin firmly, no debond area was observed. (D) Group IIa: Small cracks due to dehydration process were observed (arrow). (E) Group IIb: A big gap was observed and some resin tags (arrow) were remaining after debonding. (F) Group IIc: A small gap was observed between dentin and resin composite (Original magnification x1,000). R: Resin composite, D: Dentin.

## DISCUSSION

The prevalence of both DH and dental erosion has increased over the last few decades and their causalities appear to be linked.<sup>11-14</sup> Increasing soft drink consumption contributes to the development of erosion.<sup>15,16</sup> Initially, acid softens enamel and dissolves enamel crystals, however, the lesions formed can extend to dentin if etiological factors are not controlled, and then oral rehabilitation becomes necessary. The present experiment was designed to simulate the clinical symptoms of dental erosion and DH, and to investigate the effect of desensitizing pretreatments on micro-tensile bond strengths of RC to sound and eroded dentin.

The pH cycling performed in present study simulated erosion challenges, in terms of severity and time, that occur in patients at high risk of dental erosion, e.g., people who frequently consume acidic soft drinks.<sup>16,17</sup> Such exposure can result in loss of minerals (around 90  $\mu\text{m}$ ),<sup>18</sup> a broad zone of exposed collagen matrix, and increased tubule

diameter.<sup>14</sup> In the present study, SEM revealed that the smear layer was entirely removed and dentinal tubules were totally opened. After demineralization, peritubular dentin was apparent as some hydroxyapatite crystals only remain around dentinal tubules (Fig. 2D, Fig. 2E, and Fig. 2F). These surface changes induced by the artificial erosion process are in accordance with a previous report.<sup>8</sup>

The micro-tensile test was used to evaluate micro-tensile bond strengths, because it is believed to provide an accurate means of verifying bond performance. As compared with “macro” tests, micro-tensile bond strengths test share some advantage, that is, the conservation of teeth, fewer cohesive failures in substrate, and uniform distribution of stress to the material, all of which justify its choice. However, there are also limitations of  $\mu\text{TBS}$  testing, including the following: labor intensive; technically demanding; specimens easily dehydrate and easily damaged; post-fracture specimens adhere to the test jaw with glue can be lost or damaged during removal.<sup>3,19,20</sup> To prepare the samples for

micro-tensile test, we utilized the 'non-trimming technique' instead of the former 'trimming version' in which fabrication of dumbbell or hourglass specimens is needed. The resulting modified technique provides a uniform cross-sectional area and allows tensile stress to be applied to a beam uniformly.<sup>20</sup>

The adhesive system used in the present study (Adper™ Single Bond 2) is an etch-and rinse adhesive system and has been well investigated and well documented.<sup>7,21</sup> Normally, this adhesive system is applied on sound dentin with presence of a smear layer. However, in the present study, we evaluated its bonding performance on demineralized dentin with an organic matrix.

It is well known that for etch-and rinse adhesive systems, bonding relies on the formation of a hybrid layer composed of residual hydroxyapatite, exposed collagen and infiltrated resin. After etching, resin monomers penetrate the spaces of the porous dentin collagen previously occupied by hydroxyapatite crystals. This etch-and rinse adhesive system has excellent bonding performance onto sound dentin surfaces, but its performance on erode dentin surfaces is much worse. This is in accordance with the findings of other studies regarding the lower micro-tensile bond strengths of etch-and rinse adhesives to demineralized dentin.<sup>7,8,22,23</sup> Regarding the thick layer of exposed collagen on eroded dentin surfaces and its higher water content, it is conceivable that Single Bond 2 could neither infiltrate completely nor polymerize properly. Thus, the micro-tensile bond strengths values observed represent the strengths of an adhesive system that penetrated demineralized dentin incompletely. Accordingly, it is understandable that the micro-tensile bond strengths values were significantly lower than for non-erosively demineralized teeth, regardless of the pretreatment used.

The artificial erosion process did not only negatively influence micro-tensile bond strengths, but also changed the failure pattern. Higher percentages of cohesive failures (Fig. 1) were observed in the eroded dentin groups. This type of failure has often been interpreted as evidence that bond strength of adhesive to dentin is stronger than the cohesive strength of dentin/RC. However, the nature of fracture is far more complex than that. It has been suggested that failure mode is affected by the material properties of all components of bonded joints, that is, the RC, hybrid layer, and dentin.<sup>24</sup> Thus, the presence of air bubbles can act as stress points in eroded dentin, which is softer and more porous than sound dentin, which would increase the likelihood of dentin cohesive fracture, especially in non-penetrated demineralized regions.

Moritz *et al.*<sup>25</sup> reported the use of the CO<sub>2</sub> laser for the treatment of DH for the first time, and demonstrated that its effects are related to its ability to occlude dentinal tubules. In the present study, micro-tensile bond strengths to sound dentin after irradiation were significantly lower ( $P < .05$ ). The reasons for this are related to the existence of an acid resistant smear layer and the deficient diffusion of adhesive monomers within denatured fibrils.<sup>26</sup> Laser irradiation

can form different organic and inorganic compounds, such as, melted collagen fibrils, calcium pyrophosphate, calcium meta phosphate, and  $\alpha$ - and  $\beta$ -tricalcium phosphates, which present different levels of acid solubility.<sup>27</sup> Thus, it is likely that laser-modified dentin is not etched completely, and this could partially obstruct the micromechanical attachment of adhesives, and make it difficult for the bonding agent to penetrate dentin.<sup>28</sup> The cohesive dentin failures, observed in the Ib and Iib groups, may suggest that the denatured surface of dentin is a fragile substrate that is not adequately infiltrated by resin monomer.

Gluma® Desensitizer contains 2-hydroxyl ethyl methacrylate (HEMA) and glutaraldehyde and causes coagulation of dentin fluid protein in dentinal tubule, and thus, plugs tubules, which contributes to its desensitizing effect. In the present study, Gluma® Desensitizer had a positive effect on the micro-tensile bond strengths of etch-and rinse adhesive to sound dentin, which corresponds to the findings of other investigations.<sup>29-31</sup> However, the new discovery was that bonding performance for eroded dentin was also developed after pretreatment with Gluma® Desensitizer. Since eroded dentin is characterized by exposed collagen fibrils, the etching process before bonding to eroded dentin can result in a wide, deep completely demineralized dentin zone.<sup>7</sup> We supposed that the way of Gluma® Desensitizer to improve the bonding performance is related to the use of glutaraldehyde and HEMA. Application of glutaraldehyde can fix completely exposed collagen fibrils, binding and reinforcing it to the underlying structure.<sup>32</sup> HEMA, on the other hand, can help resin monomer infiltrating into the collagen and blending hydrophobic and hydrophilic components.<sup>33</sup> However, the durability of it is unreliable because of the hydrolytic instability of HEMA.<sup>34</sup>

Therefore, water ageing is needed to measure the long-term bonding performance to eroded dentin. It would add much more useful information regarding the clinical lifetimes of adhesive restorations.

## CONCLUSION

Within the limitations of the study, the following conclusions were drawn;

Micro-tensile bond strength of resin adhesive to teeth was affected by dentin type and the surface treatments applied to dentin.

Erosion results in a significant decrease of bond strength compared to non-erosive demineralized teeth.

The application of Gluma® Desensitizer before bonding procedure is likely to promote the performance of the adhesive.

Irradiation with CO<sub>2</sub> laser on sound dentin surface may reduce the bonding performance of adhesive.

## REFERENCES

1. Murakami C, Oliveira LB, Sheiham A, Nahás Pires Corrêa MS, Haddad AE, Bönecker M. Risk indicators for erosive tooth wear in Brazilian preschool children. *Caries Res* 2011;

- 45:121-9.
2. Kazoullis S, Seow WK, Holcombe T, Newman B, Ford D. Common dental conditions associated with dental erosion in schoolchildren in Australia. *Pediatr Dent* 2007;29:33-9.
  3. Braga RR, Meira JB, Boaro LC, Xavier TA. Adhesion to tooth structure: a critical review of "macro" test methods. *Dent Mater* 2010;26:e38-49.
  4. Federlin M, Thonemann B, Schmalz G, Urlinger T. Clinical evaluation of different adhesive systems for restoring teeth with erosion lesions. *Clin Oral Investig* 1998;2:58-66.
  5. Brackett WW, Brackett MG, Dib A, Franco G, Estudillo H. Eighteen-month clinical performance of a self-etching primer in unprepared class V resin restorations. *Oper Dent* 2005; 30:424-9.
  6. Bartlett D, Sundaram G. An up to 3-year randomized clinical study comparing indirect and direct resin composites used to restore worn posterior teeth. *Int J Prosthodont* 2006;19:613-7.
  7. Zimmerli B, De Munck J, Lussi A, Lambrechts P, Van Meerbeek B. Long-term bonding to eroded dentin requires superficial bur preparation. *Clin Oral Investig* 2012;16:1451-61.
  8. Flury S, Koch T, Peutzfeldt A, Lussi A, Ganss C. The effect of a tin-containing fluoride mouth rinse on the bond between resin composite and erosively demineralised dentin. *Clin Oral Investig* 2013;17:217-25.
  9. Gerrard WA, Winter PJ. Evaluation of toothpastes by their ability to assist rehardening of enamel in vitro. *Caries Res* 1986;20:209-16.
  10. Shono Y, Ogawa T, Terashita M, Carvalho RM, Pashley EL, Pashley DH. Regional measurement of resin-dentin bonding as an array. *J Dent Res* 1999;78:699-705.
  11. Rees JS, Jin LJ, Lam S, Kudanowska I, Vowles R. The prevalence of dentine hypersensitivity in a hospital clinic population in Hong Kong. *J Dent* 2003;31:453-61.
  12. Udoye CI. Pattern and distribution of cervical dentine hypersensitivity in a Nigerian tertiary hospital. *Odontostomatol Trop* 2006;29:19-22.
  13. Scheutzel P. Etiology of dental erosion-intrinsic factors. *Eur J Oral Sci* 1996;104:178-90.
  14. Lussi A, Schlueter N, Rakhmatullina E, Ganss C. Dental erosion-an overview with emphasis on chemical and histopathological aspects. *Caries Res* 2011;45:2-12.
  15. Waterhouse PJ, Auad SM, Nunn JH, Steen IN, Moynihan PJ. Diet and dental erosion in young people in south-east Brazil. *Int J Paediatr Dent* 2008;18:353-60.
  16. Lussi A, Jaeggi T. Erosion-diagnosis and risk factors. *Clin Oral Investig* 2008;12:S5-13.
  17. Ganss C, Schleichriemen M, Klimek J. Dental erosions in subjects living on a raw food diet. *Caries Res* 1999;33:74-80.
  18. Schlueter N, Neutard L, von Hinckeldey J, Klimek J, Ganss C. Tin and fluoride as anti-erosive agents in enamel and dentine in vitro. *Acta Odontol Scand* 2010;68:180-4.
  19. Schreiner RF, Chappell RP, Glaros AG, Eick JD. Microtensile testing of dentin adhesives. *Dent Mater* 1998;14:194-201.
  20. Armstrong S, Geraldeli S, Maia R, Raposo LH, Soares CJ, Yamagawa J. Adhesion to tooth structure: a critical review of "micro" bond strength test methods. *Dent Mater* 2010;26:e50-62.
  21. Neelima L, Sathish ES, Kandaswamy D; Bupesh. Evaluation of microtensile bond strength of total-etch, self-etch, and glass ionomer adhesive to human dentin: an in vitro study. *Indian J Dent Res* 2008;19:129-33.
  22. Schmidlin PR, Siebenmann J, Kocher P, Seemann R, Attin T, Bindl A. Effects of de- and remineralization of dentin on bond strengths yielded by one-, three-, and four-step adhesives. *J Adhes Dent* 2008;10:119-26.
  23. Sattabanasuk V, Vachiramon V, Qian F, Armstrong SR. Resin-dentin bond strength as related to different surface preparation methods. *J Dent* 2007;35:467-75.
  24. Armstrong SR, Boyer DB, Keller JC. Microtensile bond strength testing and failure analysis of two dentin adhesives. *Dent Mater* 1998;14:44-50.
  25. Moritz A, Gutknecht N, Schoop U, Goharkhay K, Ebrahim D, Wernisch J, Sperr W. The advantage of CO<sub>2</sub>-treated dental necks, in comparison with a standard method: results of an in vivo study. *J Clin Laser Med Surg* 1996;14:27-32.
  26. Cakar G, Kuru B, Ipci SD, Aksoy ZM, Okar I, Yilmaz S. Effect of Er:YAG and CO<sub>2</sub> lasers with and without sodium fluoride gel on dentinal tubules: a scanning electron microscope examination. *Photomed Laser Surg* 2008;26:565-71.
  27. Apel C, Meister J, Götz H, Duschner H, Gutknecht N. Structural changes in human dental enamel after subablative erbium laser irradiation and its potential use for caries prevention. *Caries Res* 2005;39:65-70.
  28. Omae M, Inoue M, Itota T, Finger WJ, Inoue M, Tanaka K, Yamamoto K, Yoshiyama M. Effect of a desensitizing agent containing glutaraldehyde and HEMA on bond strength to Er:YAG laser-irradiated dentine. *J Dent* 2007;35:398-402.
  29. Sengun A, Koyuturk AE, Sener Y, Ozer F. Effect of desensitizers on the bond strength of a self-etching adhesive system to caries-affected dentin on the gingival wall. *Oper Dent* 2005;30:430-5.
  30. Ravikumar N, Shankar P, Indira R. Shear bond strengths of two dentin bonding agents with two desensitizers: An in vitro study. *J Conserv Dent* 2011;14:247-51.
  31. Stawarczyk B, Hartmann R, Hartmann L, Roos M, Ozcan M, Sailer I, Hämmerle CH. The effect of dentin desensitizer on shear bond strength of conventional and self-adhesive resin luting cements after aging. *Oper Dent* 2011;36:492-501.
  32. Munksgaard EC, Asmussen E. Bond strength between dentin and restorative resins mediated by mixtures of HEMA and glutaraldehyde. *J Dent Res* 1984;63:1087-9.
  33. Van Landuyt KL, Snauwaert J, De Munck J, Peumans M, Yoshida Y, Poitevin A, Coutinho E, Suzuki K, Lambrechts P, Van Meerbeek B. Systematic review of the chemical composition of contemporary dental adhesives. *Biomaterials* 2007; 28:3757-85.
  34. Van Landuyt KL, De Munck J, Snauwaert J, Coutinho E, Poitevin A, Yoshida Y, Inoue S, Peumans M, Suzuki K, Lambrechts P, Van Meerbeek B. Monomer-solvent phase separation in one-step self-etch adhesives. *J Dent Res* 2005; 84:183-8.